TEST REPORT

Document ID: DOC-0000718
Project: PRJ-009
Uploaded on: 2023-10-14
Uploaded by: user049
Export class: EAR99

Report No: TR-148650
Laboratory: Central Test
Test Date: 2023-10-14

Part P-100484 rev A.1

Test	Requirement	Measured	Result
Salt spray	48 - 500 hours	126.221	PASS
Thermal cycle	50 - 500 cycles	437.474	PASS
Dimensional check	0.05 - 0.5 mm	0.195	PASS
Flatness	0.01 - 0.2 mm	0.169	PASS

Overall result for P-100484: PASS

Part P-100605 rev A.1

Test	Requirement	Measured	Result
Dimensional check	0.05 - 0.5 mm	0.328	PASS
Flatness	0.01 - 0.2 mm	0.031	PASS
Thermal cycle	50 - 500 cycles	359.751	PASS
Salt spray	48 - 500 hours	159.532	PASS

Overall result for P-100605: PASS

Part P-100570 rev A.1

Test	Requirement	Measured	Result
Thermal cycle	50 - 500 cycles	314.299	PASS
Dimensional check	0.05 - 0.5 mm	0.287	PASS
Salt spray	48 - 500 hours	320.956	PASS
Flatness	0.01 - 0.2 mm	0.132	PASS

Overall result for P-100570: PASS