

Pipe Insulation - Micro-Lok HP vs Poly Pipe Insulation

Property	J9 (Specified) - JM Micro-Lok HP	J9 (Proposed) - Poly Pipe Insulation
Manufacturer	Johns Manville	Jones Stephens
Product	Micro-Lok HP	Poly Pipe Insulation
Material	Fiberglass (biosoluble glass fiber, thermoset resin)	Polyethylene closed-cell flexible foam
Form	Rigid pre-formed pipe sections	Flexible tubular foam
Service temperature	0 to 850 F (-18 to 454 C)	-200 to 200 F (-129 to 93 C)
Thermal conductivity k, 75 F mean	0.23 Btu-in/hr-ft ² -F (0.034 W/m-K)	0.270 Btu-in/hr-ft ² -F (0.039 W/m-K)
Water vapor permeance	0.02 perm max (ASJ jacket)	< 0.05 perm
Water absorption	< 5% by weight (moisture sorption)	< 0.20% by volume
Fire - flame/smoke	25/50 (ASTM E84); limited combustibility NFPA 90A/90B	25/50 up to 1-1/2 in (ASTM E84); UL94 HF-1
Jacket / vapor barrier	Factory ASJ vapor-retarder jacket, self-seal lap	None needed (closed-cell); paint for outdoor use
Wall thickness range	1/2 to 5 in	3/8, 1/2, 3/4, 1 in
Pipe size range	1/2 to 24 in IPS	3/8 to 4-1/2 in ID
Section length	3 ft (0.92 m)	6 ft (1.83 m)
Standards	ASTM C547 Type I; C585; C1136 (jacket)	ASTM C1427 Type I; E84; UL94 HF-1
Certifications	GREENGUARD Gold	GREENGUARD Gold; contains no halogens
Best suited for	Hot / high-temperature piping; code-driven vapor-jacketed systems	Cold / condensation control; flexible, fast install (to 200 F)

Highlighted rows show the main differences. Micro-Lok HP is a rigid fiberglass insulation with a factory vapor-barrier (ASJ) jacket, rated to 850 F for hot and high-temperature lines. Poly Pipe Insulation is a flexible closed-cell polyethylene foam with very low water absorption and inherent moisture resistance (no separate vapor jacket), best for cold-line condensation control and fast installation, limited to 200 F.