March 23, 2026

Abstract

Continuum robots are a type of soft robot heavily inspired by the motion of elephant trunks. They are able to navigate complex environments through their innate actuation methods and material properties. To achieve fully soft devices, pneumatic actuators are often used, however, the materials used in these actuators are typically delicate and are prone to failure. Recently, an approach to mitigate this is the use of self-healing polymers. This report covers the investigation of a new material based on a polyimide to achieve self-healing capabilities and its use in a soft continuum robot.

Contents

List of Figures

Chapter 1

Introduction

1.1 Importance and Applications of Soft Robotics

Soft robots are a type of robot known for their use of soft materials, compliant nature and near infinite degrees of freedom . Degrees of freedom (DOF) is a term related to the number of independent movements a robot can make in 3D space.[?] Soft robots are usually nature inspired such as "vine-like" tip growing robots,[?,?] "snake like" continuum robots[?,?] and "hand-like" soft grippers.[?,?] The advantages of using a body that is highly deformable and with near-infinite DOF means these devices can navigate tortuous environments with ease.

This report focuses on continuum robots, often characterised by their long flexible bodies, commonly used for navigation and delivery or retrieval of objects in constrained environments.[?] Continuum robots can be classified into "continuous backbone" and "segmented back-bone" designs.[?] Continuous backbone devices are made from a soft and compliant material, in this report we will call these "soft-bodied", whereas, a segmented backbone refers to those that are made from hard, inflexible segments that are flexibly attached to achieve high curvatures, referred to here as "hard-bodied".

Hard-bodied continuum robots benefit from stiffer materials allowing a greater ease of control[?] which can improve dexterity. However, they cannot deform and are more likely to impart a greater force on the surrounding environment.[?] Hard continuum robots are often tendon driven, whereby the segments are joined by wires that can be pulled to give specific movements. Whereas soft bodied continuum robots can achieve high curvatures and low forces on surroundings,[?] but are often harder to control due to their methods of actuation[?] and can suffer from material failure.[?] Soft continuum robots commonly take the form of an inflated body, these can be controlled in many ways such as varying pressure,[?] strain limiting a specific region[?,?] or magnetic actuation.[?,?] Pressurised systems that rely on fluids need a constant seal to maintain function as opposed to a segmented tendon driven approach that can be partially damaged and still actuatable. This leads the development of resilient materials such as self-healing polymers that can be applied to soft robotics.

1.2 Types of Self-Healing Polymers

Polymers are a type of molecule that consists of several repeating sub-units, these form chains that are combined many times over to form materials. Self-healing (S-H) polymers are a type of polymer that can heal damage.[?] This occurs through reactions and interac-




Figure 1.1: A continuum device sustaining damage before self-healing and regaining full functionality using a modified image from[?]




Figure 1.2: a) The polymer chain with a repeating chemical sub-unit. b) The mechanism of damage and repair for a self-healing polymer

tions between multiple polymer chains to reconnect chains that have been shifted apart through damage. The process of damaging or cutting a polymer does not break bonds in the polymer backbone but instead can break interchain interactions called cross-linking, allowing the chains to drift apart, reforming the cross-linking interactions will "heal" the material.[?]

S-H polymers can be classified into intrinsic or extrinsic healing, and autonomous or non-autonomous.[?] Materials with an intrinsic healing capacity involve a healing mechanism through chemical bonds or interactions that are continuously present in the polymer, rather than extrinsic healing, such as capsules of "healing" material that are broken through damage and causing the material to reform.[?] Autonomy refers to the healing process occurring without external input. For example, capsules that burst upon damage of the material and release a healing agent are classified as autonomous, whereas a photochemical reaction that needs UV light to activate[?,?] is a non-autonomous mechanism.

1.3 Comparison of Different Self-Healing Pathways

There are a variety of different pathways that can be taken to create a S-H polymer depending on the chemistry of the initial polymer. The pathways that will be focused on are intrinsically self-healed types, however, both autonomous and non-autonomous types will be considered.

The three pathways below rely on a property of some electrons called conjugation. Conjugation occurs when specific electron orbitals overlap in such as way that allows the electrons to move around the molecule. This is often exploited with a property of some atoms called electronegativity, having a highly electronegative atom in a molecule will attract conjugated electrons to create a local high density region of electrons and therefore a polarisation in a molecule.

Dynamic covalent bonds can form and break based on the conditions applied to them[?] and they are ideal for use as mechanisms for S-H due to their intrinsic nature and reliability in production of high yields.[?] This report investigates the use of two types of dynamic covalent bonding, Diels-Alder and Michael additions, and an example of a supramolecular interaction. Supramolecular chemistry is based on interactions that are non-covalent and may be more suited to a soft material.[?] This is due to the S-H mechanism of the cross-links that forms interactions therefore the polymer chains can move semi-independently.[?,?] Whereas, a dynamic covalent bond has a much higher bond energy[?] and can therefore get closer to the original physical properties of a polymer.

1.3.1 Using a Diels-Alder Addition as a Self-Healing Pathway

Diels-Alder (DA) reactions require a diene, a class of molecule characterised by having two sets of double bonds, and an alkene ("dieneophile").[?,?] The reaction occurs when conjugated electrons from the diene are free to move to form new bonds with the carbons either side of the alkene double bond, this creates a new ring structure. A faster reaction is generally observed with an electron rich diene and an electron poor dienophile.[?] The electronic character of the reagents can be altered by changing their local substituents. This class of reactions can have lots of different conditions depending on the molecules involved. Some variations can occur at room temperature,[?] which may make them an ideal choice for an autonomously healed medical device as the healing can occur whilst deployed in the body. However, many DA reactions are light[?,?] or heat activated.[?]




Figure 1.3: a) A Diels-Alder reaction between two molecules of cylopentadiene. b) A Diels-Alder reaction between a furan and maleimide. c) A Thiol-Michael Addition between a thiol and a conjugated alkene.

Some molecules such as cyclopentadiene can perform a DA reaction with itself, this has the potential to be an ideal choice for a S-H polymer as the molecule will never be in close proximity to a molecule that it cannot react with. However, some evidence has shown that the bonds formed are not very strong and therefore high tensile strength materials may not be possible.[?]

One of the most common types of DA reaction is a heat activated reaction between a derivative of both furan and maleimide.[?] They react extremely accurately and require mild conditions,[?] therefore they are very suitable for application as a robotics material. One of the reasons that this reaction is so effective is that the maleimide has electron withdrawing carbonyl groups which make the dieneophile electron poor and therefore reacting faster. However, this mechanism has a disadvantage compared to cyclopentadiene as there are two halves of the end product. Therefore, there must be a two different processes occurring to create both the furan substituted and maleimide substituted chains. This increases the number of total steps in the reaction which increases the risk of low reaction yields and wasted material.

1.3.2 Using a Thiol-Michael Addition as a Self-Healing Pathway

Thiol Michael additions are a type of reaction that relies on a thiol, a molecule characterised by a sulfur containing group and a conjugated alkene.[?] The conjugated alkene used in a Michael addition is with a carbonyl group that will attract the electrons from the alkene to allow the thiol group to react. This has a similar advantage to the Diels-Alder reaction that it is not totally dependant on specific reactants merely groups of reactants. Therefore slight changes can be made to the adjoining groups to tweak the reaction conditions. This has been previously shown to have been successful with a heat

activated reaction that could heal scratches after 15 to 30 minutes at 60 °C.[?]

1.3.3 Using a Pi-Stacking Approach as a Self-Healing Pathway

Pi-Stacking is a type of intermolecular interaction whereby conjugated systems interact based on the neighbouring substituents determining if a region is electron rich or poor. These electron disparities cause an electrostatic interaction. This method commonly uses pyrenyl groups, these are polycyclic aromatic compounds, a very pi-electron rich species. These can be interacted with a napthalene diimide complex, an electron poor pi-system to give four pi-stacking interactions. A method has shown the creation of a polymer chain end group which can sandwich a napthalene group within two pyrenyl groups.[?] This method can be combined with other intermolecular interactions like hydrogen bonding[?] or mettalosupramolecular interactions to give a stronger interaction.[?]

1.4 Applications of Self-Healing Polymers in Soft Robotics

Continuing the theme of biological inspiration of soft robotics, S-H polymers can be used to extend the lifespan of components. In soft continuum robots, the goal is usually to make the robot softer than the environment surrounding it.[?] This presents a challenge that the environment can often be abrasive and can damage the device. It is therefore evident that a damage resilient material would be useful. Damage resilient materials can take multiple forms: Damage isolation, material elasticity, physical self healing such as low melting temperature materials and chemical self healing.[?]

1.4.1 State of the Art Self-Healing Soft Robots

State-of-the-art approaches using intrinsic S-H mechanisms are commonly based on DA chemistry.[?] These have been successfully implemented in tendon-driven[?] and pneumatically controlled soft robotic devices.[?,?] Such devices are capable of recovering from macroscopic damage, including punctures and cuts. Additionally, there are non-covalent approaches that utilize hydrogen bonding in the development of soft self-healing actuators, such as in McKibben muscle designs.[?]

1.4.2 Requirements for Self-Healing Polymers in Soft Robotics

Terryn *et al.*[?] states that there are 5 main criteria for a S-H polymer; macroscopic damage must be healed completely; healing can take place multiple times at the same location; there are minimal material property changes after healing; elastomeric behaviour is achieved; the reprocessing and recycling of a material is possible. Here we propose that elastomeric behaviours are non-essential and a more useful requirement would involve a timely S-H reaction.

1.5 Limitations with Current Materials for Soft Robotics

Damage control whilst a device is active can be a challenge,[?] this shows a need for autonomous S-H.[?] Non-autonomous S-H can be made "functionally autonomous" through

the use of stimuli responsive mechanisms, however, the current options are slow in operation.[?] Currently recovery timescales of applied S-H polymers are around 25 hours.[?,?] By altering the polymer used or S-H pathway this could be improved. There is also a lack of an easy synthesis route for many of the current polymer options,[?] thereby increasing the cost and reducing widespread use. Also the number of damage-repair cycles in these devices are low, such as 3 or less.[?] Most devices do not achieve all 5 criteria laid out in the Terryn *et al.* review,[?] such as the McKibben design of A. Lopez Diaz *et al.*[?] only reports a healing efficiency of 65%.

Chapter 2

Project Aims and Objectives

Chapter 3

Synthesis of a Self-Healing Polymer

3.1 Results

3.1.1 Hydrolysis of the Polyimide

The hydrolysis of the polyimide follows a standard mechanism for hydrolysis of an amide to a carboxylic acid using sodium hydroxide (NaOH). These show the hydroxy group attacking the carbonyl which then breaks the C-N bond and gives the carboxylic acid free.

Structural Analysis

Structural determination was conducted via Infrared spectroscopy. A comparison was made between the attempted hydrolysis of the sheets and a purchased form (polyamic acid).

The infrared spectrum of the hydrolysis attempts indicate that the crosslinking was not a successful reaction as the peaks in the spectrum are extremely similar to the unreacted form of the polymer. Also, in a comparison to the purchased PAA, which should be the hydrolysed product that we were hoping for, the region around 3000 cm^{-1} is much busier and has the characteristic wide OH region. This would indicate that the hydrolysis hasn't occurred. This maybe due to the imide ring breaking and reforming as the temperature of the reaction is likely higher than the imide formation temperature meaning that the amide bond may get broken but in fact reforms at the high temperature. This seems a little unlikely though as I think there would be a suspension of material along with the main polymer.

The amount of NaOH was chosen to be in the ratio of 1:4 NaOH: monomer as there was a concern that we may fully hydrolyse the polymer (at all 4 amide bonds in the two imide rings) and give a tetrasubsituted benzene ring.

3.1.2 Cross-linking of the Polyimide

Cross-linking attempts follow a mechanism as proposed by (put reference here), where ethylene carbonate is used to form an ester with the carboxylic acids on neighbouring polymer chains, thereby joining them together with a "cross-link". This was performed with three different salts (TEAB, $ZnCl_2$, $FeCl_3$) as catalysts.

During the cross-linking reaction with TEAB, an orange-brown suspension was formed that when washed, filtered and freeze dried gave a pale orange powder. With $ZnCl_2$, the

liquid was a dark orange clear liquid that, when water was added, gave a single clump of grey polymeric residue. This was freeze dried to remove the excess water and then analysed. The cross-linking reaction with the $FeCl_3$, gave a dark orange/brown gel, which gave a grey gum-like texture in small pieces when water was added. This was also frozen and analysed.

During a cross-linking with ethylene carbonate, CO2 is released. This was a concern as the monowave reactor has a pressure limit of 20 bar. To ensure there was a reliable safety buffer, we set an artificial limit of 5 bar. The calculation to ensure this limit was kept used PV = nRT. (insert calculations).

From the IR data, the crosslinking with TEAB was unsuccessful as the product didnt have the key peaks of the C-O bond in the ester or any alcohol peak. The alcohol peaks would be likely as the crosslinking was unlikely to be 100% successful and there would likely be the single ester product formed. However, neither of these were present and since the product was insoluble, no NMR could be obtained. This IR specturm was compared with the spectrum of Kapton (i.e. the ring closed form of the polyamic acid) and the similarities confirmed that the imide ring reformation had occured. The absorbance of the synthsised form from the PAA has much stronger absorbances. THis is likely due to the fact that the clamping force on the kapton film is not as strong as in the powder and the powdered material is thicker so will absorb more just due to the material.

From the IR data of the ZnCl2 and the FeCl3, there are two new peaks at around 1800 which are not in either the kapton or the polyamic acid. These are likely the C-O bonds in the ehtylene carbonate starting material. There is also a new peak at 4.43ppm in the NMR spectrum, however, when adding 2 L of EC in a "spike test", the peak increased in size, confirming that the new peak was just starting material. This

3.1.3 Catalytic cyclisation of Kapton® imide rings

During the attempted crosslinking reactions, we observed the imide ring formation at a lower temperature than in the literature. We attempted to recreate this with the

3.2 Experimental

3.2.1 The Hydrolysis of a Polyimide

Poly..... (Kapton) film (0.2g, thickness of x) was cut into pieces of approx. $3mm^2$, these were mixed with a solution of NaOH () in a reaction tube. This tube was placed into a monowave reactor that was set to ramp for 20 minutes and hold for 20 minutes at 100 °C. A sample was taken and the remaining mixture was reacted again on the monowave for ramp 20 mins and hold 20 minutes at 100°C. There was no observable difference in the Kapton film. Then this was thoroughly washed with water and IR was collected.

3.2.2 Crosslinking of Polyamic acid

This procedure outlines the crosslinking procedure of Polyamic acid via ethylene carbonate using a catalytic salt as outlined in previously published procedures.

3.2.3 Cross-linking with TEAB and Ethylene carbonate

A mixture of polyamic acid (0.51mL, conc) was mixed with ethylene carbonate (0.08g) and tetraethylammonium bromide (). This was mixed in a monowave reactor set to ramp for 20 minutes and hold for 1 hour at 150°C. This gave an orange suspension that was dried to give a pale orange powder as the final product (grams, yield).

3.2.4 Cross-linking with other salts

The crosslinking with ZnCl2 and FeCl3 was performed at 100°C for 1 hour. With ZnCl2 a clear dark brown viscous liquid was obtained and with the FeCl3, a clear dark brown gelatinous liquid was obtained. A solid was extracted from each of these liquids and spectroscopic analyses were performed.

3.2.5 Spectral Data

tetraethylammonium bromide Crosslinking

A orange powder (grams,moles,yield) was isolated, ν max/cm^{-1}(solid);

Iron chloride Crosslinking

A white gum (grams,moles,yield) was isolated, δ H(400MHz, DMSO); , δ C(100MHz, DMSO); , ν max/cm^{-1}(solid);

Zinc chloride Crosslinking

Brittle brown pieces (grams,moles,yield) were isolated, δ H(400MHz, DMSO); , δ C(100MHz, DMSO); , ν max/cm^{-1}(solid);

Chapter 4

Construction of a Bellows Based Actuator

4.1 Design

Actuators were constructed using a combination of a folded polyimide sleeve and a internal silicon tube with nitinol wires for actuation.

4.1.1 Construction of a Folded Protective Sleeve

The polyimide film was folded into a []-style design as based on the previously published work. For the proposed design, the film selected was Kapton® (Supplier, thickness).

Manual folding versus using a plotter

A commercially available Cricut® was used with a scribe tool and a cutter to achieve a rapid manufacturing of a folded sleeve. This was attempted with paper initally for cheap prototyping and then transferring to the polymer film.

The paper was easy however the polyimide did not take up the scores so easily.

4.1.2 Complete Assembly

The complete assembly was formed with the polyimide sleeve, the silicon continuum device and 3D printed parts. The construction method is as follows: a sheet of polyimide is marked with the desired folding pattern (as shown in figure), the sheet is folded by hand before being shaped into a tube and glued along an overlapping edge. The folds are encouraged into place and one end is sealed. This is the assembled with 3D printed parts to form the actuator.

The silicon actuator contains 7 holes where three lengths of nitinol wire were threaded through and fastened with two grub screws each in 3D printed handles. This leaves a separate tube through the centre of the silicon tube that could be used in future work for targeted delivery of liquid or components such as naneye cameras for observation.

4.2 Methodology

Our methodology is inspired by similar "bellows-style" approaches to construct continuum devices (references) with the key difference in the use of Polyimide sheets (Kapton) forming the main body of the device.

This work focuses on the use of Kapton (thickness =) due to its good robustness and high temperature capabilities.

4.2.1 Stiffness Characterisation

4.2.2 Temperature Stability of the Bellows

4.2.3 Workspace Characterisation

4.3 Results

4.3.1 Stiffness Characterisation

4.3.2 Temperature Stability of the Bellows

4.3.3 Workspace Characterisation

Bibliography

[1] Matteo Cianchetti, Tommaso Ranzani, Giada Gerboni, Thrishantha Nanayakkara, Kaspar Althoefer, Prokar Dasgupta, and Arianna Menciassi. Soft robotics technologies to address shortcomings in today's minimally invasive surgery: the stiff-flop approach. *Soft Robotics*, **1**(2):122–131, 2014. [17/10/2025]. Available from: 10.1089/soro.2014.0001.

[2] Kevin M Lynch and Frank C Park. *Modern robotics*. Cambridge University Press, 2017. [01/10/2025]. Available from: 10.1017/9781316661239.

[3] Elliot W Hawkes, Laura H Blumenschein, Joseph D Greer, and Allison M Okamura. A soft robot that navigates its environment through growth. *Science Robotics*, **2**(8):eaan3028, 2017. [16/10/2025]. Available from: 10.1126/scirobotics.aan3028.

[4] Joshua Davy, Thomas P Dean, Nikita J Greenidge, Benjamin Calmé, Peter Lloyd, James H Chandler, and Pietro Valdastri. Magnetic fluid-driven vine robots for minimally invasive tissue biopsy sampling. *Advanced Intelligent Systems*, **7**:2400827, 2025. [16/10/2025]. Available from: 10.1002/aisy.202400827.

[5] VV Anderson. Tenser arm manipulator design. *ASME Trans.*, 67:1–12, 1967. [10/10/2025].

[6] Peter Lloyd, Ali Kafash Hoshiar, Tomas Da Veiga, Aleks Attanasio, Nils Marahrens, James Henry Chandler, and Pietro Valdastri. A learnt approach for the design of magnetically actuated shape forming soft tentacle robots. *IEEE Robotics and Automation Letters*, **5**(3):3937–3944, 2020. [16/10/2025]. Available from: 10.1109/LRA.2020.2983704.

[7] Filip Ilievski, Aaron D Mazzeo, Robert F Shepherd, Xin Chen, and George M Whitesides. Soft robotics for chemists. *Angewandte Chemie International Edition*, **50**(8):1890–1895, 2011. [01/10/2025]. Available from: 10.1002/ange.201006464.

[8] Jianglong Guo, Khaled Elgeneidy, Chaoqun Xiang, Niels Lohse, Laura Justham, and Jonathan Rossiter. Soft pneumatic grippers embedded with stretchable electroadhesion. *Smart Materials and Structures*, **27**(5):055006, 2018. [17/10/2025]. Available from: 10.1088/1361-665X/aab579.

[9] Matteo Russo, Seyed Mohammad Hadi Sadati, Xin Dong, Abdelkhalick Mohammad, Ian D Walker, Christos Bergeles, Kai Xu, and Dragos A Axinte. Continuum robots: An overview. *Advanced Intelligent Systems*, **5**(5):2200367, 2023. [02/10/2025]. Available from: 10.1002/aisy.202200367.

[10] Joshua Davy, Nikita J Greenidge, Sukjun Kim, Luke J Tinsley, Peter Lloyd, James H Chandler, Russell A Harris, Tania K Morimoto, and Pietro Valdastri. Vine robots with magnetic skin for surgical navigations. *IEEE Robotics and Automation Letters*, **9**(8):6888–6895, 2024. [16/10/2025]. Available from: 10.1109/LRA.2024.3412637.

[11] Daniela Rus and Michael T Tolley. Design, fabrication and control of soft robots, 2015. [02/10/2025]. Available from: 10.1038/nature14543.

[12] Haider Abidi and Matteo Cianchetti. On intrinsic safety of soft robots. *Frontiers in Robotics and AI*, **4**:5, 2017. [10/10/2025]. Available from: 10.3389/frobt.2017.00005.

[13] Xinyu Guo, Wenbo Li, Fuyi Fang, Huyue Chen, Linchuan Zhao, Xiaoyong Fang, Zhiran Yi, Lei Shao, Guang Meng, and Wenming Zhang. Encoded sewing soft textile robots. *Science Advances*, **10**(1):eadk3855, 2024. [17/10/2025]. Available from: 10.1126/sciadv.adk3855.

[14] Thomas P Dean, Joshua Davy, Jane Scott, Pietro Valdastri, and James H Chandler. Anisotropic 3d-knitted sleeves as inverse pneumatic artificial muscles for soft and wearable robotics. In *2025 IEEE 8th International Conference on Soft Robotics (RoboSoft)*, pages 1–6. IEEE, 2025. [17/10/2025]. Available from: 10.1109/RoboSoft63089.2025.11020963.

[15] Ruchir Shanker Srivastav and Aarti P More. A comprehensive review of self-healing polymers: Mechanisms, types, and industry implications. *Polymers for Advanced Technologies*, **36**(2):e70092, 2025. [10/10/2025]. Available from: 10.1002/pat.70092.

[16] Wolfgang H Binder. *Self-healing polymers: from principles to applications*. John Wiley & Sons, 2013.

[17] Seppe Terryn, Jakob Langenbach, Ellen Roels, Joost Brancart, Camille Bakkali-Hassani, Quentin-Arthur Poutrel, Antonia Georgopoulou, Thomas George Thuruthel, Ali Safaei, Pasquale Ferrentino, et al. A review on self-healing polymers for soft robotics. *Materials Today*, **47**:pp.187–205, 2021. [01/10/2025]. Available from: 10.1016/j.mattod.2021.01.009.

[18] Scott R White, Nancy R Sottos, Philippe H Geubelle, Jeffrey S Moore, Michael R Kessler, SR Sriram, Eric N Brown, and S Viswanathan. Autonomic healing of polymer composites. *Nature*, 409(6822):794–797, 2001.

[19] Scott R Trenor, Allan R Shultz, Brian J Love, and Timothy E Long. Coumarins in polymers: from light harvesting to photo-cross-linkable tissue scaffolds. *Chemical reviews*, 104(6):3059–3078, 2004.

[20] Pablo Froimowicz, Daniel Klinger, and Katharina Landfester. Photoreactive nanoparticles as nanometric building blocks for the generation of self-healing hydrogel thin films. *Chemistry–A European Journal*, 17(44):12465–12475, 2011.

[21] Jie Guo. *Diels-Alder chemistry: An old workhorse for new self-healing nanocomposites and adhesives*. PhD thesis, 2025. [12/10/2025]. Available from: 10.33612/diss.1198671697.

[22] Kyriacos Costa Nicolaou, Scott A Snyder, Tamsyn Montagnon, and Georgios Vassilikogiannakis. The diels–alder reaction in total synthesis. *Angewandte Chemie International Edition*, 41(10):1668–1698, 2002.

[23] Ying Yang and Marek W Urban. Self-healing of polymers via supramolecular chemistry. *Advanced Materials Interfaces*, **5**(17):1800384, 2018. [12/10/2025]. Available from: 10.1002/admi.201800384.

[24] Shiwanka V Wanasinghe, Obed J Dodo, and Dominik Konkolewicz. Dynamic bonds: adaptable timescales for responsive materials. *Angewandte Chemie*, 134(50):e202206938, 2022.

[25] Chirag R Ratwani, Ali Reza Kamali, and Amr M Abdelkader. Self-healing by diels-alder cycloaddition in advanced functional polymers: A review. *Progress in Materials Science*, **131**:101001, 2023. [02/10/2025]. Available from: 10.1016/j.pmatsci.2022.101001.

[26] Benoit Briou, Bruno Améduri, and Bernard Boutevin. Trends in the diels–alder reaction in polymer chemistry. *Chemical Society Reviews*, **50**(19):11055–11097, 2021. [01/10/2025]. Available from: 10.1039/D0CS01382J.

[27] David Huertas, Melinda Florscher, and Veljko Dragojlovic. Solvent-free diels–alder reactions of in situ generated cyclopentadiene. *Green Chemistry*, 11(1):91–95, 2009.

[28] Jinhui Li, Guoping Zhang, Libo Deng, Songfang Zhao, Yongju Gao, Kun Jiang, Rong Sun, and Chingping Wong. In situ polymerization of mechanically reinforced, thermally healable graphene oxide/polyurethane composites based on diels–alder chemistry. *Journal of Materials Chemistry A*, 2(48):20642–20649, 2014.

[29] Bryan Ingoglia. Microencapsulation of diels-alder monomers in self-healing materials. *Kaleidoscope*, 11(1):43, 2014.

[30] Devatha P Nair, Maciej Podgorski, Shunsuke Chatani, Tao Gong, Weixian Xi, Christopher R Fenoli, and Christopher N Bowman. The thiol-michael addition click reaction: a powerful and widely used tool in materials chemistry. *Chemistry of Materials*, **26**(1):724–744, 2014. [06/10/2025]. Available from: 10.1021/cm402180t.

[31] Natascha Kuhl, Robert Geitner, Ranjita K Bose, Stefan Bode, Benjamin Dietzek, Michael Schmitt, Jürgen Popp, Santiago J Garcia, Sybrand van der Zwaag, Ulrich S Schubert, et al. Self-healing polymer networks based on reversible michael addition reactions. *Macromolecular Chemistry and Physics*, **217**(22):2541–2550, 2016. [10/10/2025].
Available from: 10.1002/macp.201600353.

[32] Stefano Burattini, Barnaby W Greenland, Wayne Hayes, Michael E Mackay, Stuart J Rowan, and Howard M Colquhoun. A supramolecular polymer based on tweezer-type π–π stacking interactions: Molecular design for healability and enhanced toughness. *Chemistry of Materials*, **23**(1):6–8, 2011. [15/10/2025]. Available from: 10.1021/cm102963k.

[33] Xin Yuan, Xiangyu Lin, Fuhao Dong, Xujuan Huang, He Liu, and Xu Xu. Self-healed, tough, and highly resilient elastomer facilitated by cooperative hydrogen-bonding interaction and π–π stacking interaction. *ACS Applied Polymer Materials*, **7**(3):1328–1337, 2025. [16/10/2025]. Available from: 10.1021/acsapm.4c03053.

[34] Jin-Feng Mei, Xiao-Yong Jia, Jian-Cheng Lai, Yang Sun, Cheng-Hui Li, Jun-Hua Wu, Yi Cao, Xiao-Zeng You, and Zhenan Bao. A highly stretchable and autonomous self-healing polymer based on combination of pt···pt and π–π interactions. *Macromolecular Rapid Communications*, **37**(20):1667–1675, 2016. [15/10/2025]. Available from: 10.1002/marc.201600428.

[35] R Adam Bilodeau and Rebecca K Kramer. Self-healing and damage resilience for soft robotics: A review. *Frontiers in Robotics and AI*, **4**:48, 2017. [01/10/2025]. Available from: 10.3389/frobt.2017.00048.

[36] Ellen Roels, Seppe Terryn, Joost Brancart, Guy Van Assche, and Bram Vanderborght. A multi-material self-healing soft gripper. In *2019 2nd IEEE International Conference on Soft Robotics (RoboSoft)*, pages 316–321. IEEE, 2019. [16/10/2025]. Available from: 10.1109/ROBOSOFT.2019.8722781.

[37] Seppe Terryn, Joost Brancart, Ellen Roels, Guy Van Assche, and Bram Vanderborght. Room temperature self-healing in soft pneumatic robotics: Autonomous self-healing in a diels–alder polymer network. *IEEE Robotics & Automation Magazine*, **27**(4):44–55, 2020. [16/10/2025].
Available from: 10.1109/MRA.2020.3024275.

[38] Seppe Terryn, Joost Brancart, Dirk Lefeber, Guy Van Assche, and Bram Vanderborght. A pneumatic artificial muscle manufactured out of self-healing polymers that can repair macroscopic damages. *IEEE Robotics and Automation Letters*, **3**(1):16–21, 2017. [17/10/2025].
Available from: 10.1109/LRA.2017.2724140.

[39] Antonio López-Díaz, Ana Martín-Pacheco, Alicia Naranjo, Cristina Martín, M Antonia Herrero, Ester Vázquez, and Andrés S Vázquez. Autonomous self-healing pneumatic mckibben muscle based on a new hydrogel material. In *2020 3rd IEEE International Conference on Soft Robotics (RoboSoft)*, pages 13–18. IEEE,
2020. [16/10/2025]. Available from: 10.1109/RoboSoft48309.2020.9115992.

[40] Seyedreza Kashef Tabrizian, Seppe Terryn, and Bram Vanderborght. Toward autonomous self-healing in soft robotics: A review and perspective for future research. *Advanced Intelligent Systems*, **7**(8):2400790, 2025. [16/10/2025]. Available from: 10.1002/aisy.202400790.