

UNIVERSITY OF LEEDS

Title Subtitle

Thomas P. Dean

Masters Thesis

The University of Leeds

Faculty of Engineering and Physical Sciences

School of Chemistry

School of Electronic and Electrical Engineering

March 2026

Acknowledgements.

Stick some more acknowledgments here.

Abstract

Acknowledgements

Professor Bao N. Nguyen, Professor James H. Chandler

Dr Ben, Dr Ben, Dr Josh, Dr Pete (STORM People)

Chem people

Sam Wilson, Alfred Alexander

Priestley + Porter techs

Intellectual Property

The candidate confirms that the work submitted is his/her own and that appropriate credit has been given where reference has been made to the work of others.

This copy has been supplied on the understanding that it is copyright material and that no quotation from the thesis may be published without proper acknowledgment.

© 2026 The University of Leeds, Thomas P. Dean

Contents

1 Introduction **1**

1.1 Importance and Applications of Soft Robotics 1

1.2 Types of Self-Healing Polymers 3

1.3 Comparison of Different Self-Healing Pathways 5

1.3.1 Using a Diels-Alder Addition as a Self-Healing Pathway 6

1.3.2 Using a Thiol-Michael Addition as a Self-Healing Pathway 7

1.3.3 Using a Pi-Stacking Approach as a Self-Healing Pathway 7

1.4 Applications of Self-Healing Polymers in Soft Robotics 8

1.4.1 State of the Art Self-Healing Soft Robots 8

1.4.2 Requirements for Self-Healing Polymers in Soft Robotics 9

1.5 Limitations with Current Materials for Soft Robotics 9

2 Project Aims and Objectives **10**

2.1 Aims and Objectives of this Project 10

3 Synthesis of a Self-Healing Polymer **12**

3.1 Results 12

3.1.1 Hydrolysis of the Polyimide 12

3.1.2 Spectrophotometry 15

3.1.3 Cross-linking of the Polyimide 18

3.1.4 Catalytic Imidisation of polyimide 21

3.2 Experimental 23

3.2.1 Equipment 23

3.2.2 The Hydrolysis of a Polyimide 23

3.2.3 Spectrophotometry as a Determination Method for Hydrolysis . . 24

3.2.4 Crosslinking of Polyamic acid 25

3.2.5 Catalytic Imidisation of Polyamic Acid 26

4 Construction of a Bellows Based Actuator 28

4.1 Design 28

4.1.1 Construction of a Folded Protective Sleeve 28

4.1.2 Complete Assembly 33

4.2 Results 34

4.2.1 Stiffness Characterisation 34

4.2.2 Temperature Stability of the Bellows 36

4.2.3 Workspace Characterisation 38

4.2.4 Navigation 42

4.2.5 Clinical Case Study: Drug Delivery in Stomach 44

4.3 Methodology 45

4.3.1 Stiffness Characterisation 45

4.3.2 Temperature Stability of the Polyimide Sleeve 45

4.3.3 Workspace Characterisation 45

4.3.4 Moulding of polyamic acid 46

4.3.5 Moulding of Polyamic Acid 46

5 Conclusion **47**

List of Figures

1.1 A continuum device sustaining damage before self-healing and regaining full functionality using a modified image from[1] 2

1.2 a) The polymer chain with a repeating chemical sub-unit. b) The mechanism of damage and repair for a self-healing polymer 4

1.3 a) A Diels-Alder reaction between two molecules of cylopentadiene. b) A Diels-Alder reaction between a furan and maleimide. c) A Thiol-Michael Addition between a thiol and a conjugated alkene. 6

3.1 Structure of polyoxydiphenylene mellitimide (Kapton) with higlighted pthalamide region at A 12

3.2 Structure of polyamic acid 13

3.3 Hyrolysis of polyimide to polyamic acid 14

3.4 15

3.5 17

3.6 20

3.7 22

4.1 caption 34

4.2 A) The Kapton sleeve is placed into an oven for an hour and then placed onto the stiffness characterisation experimental setup. B) The initial profile of the actuator before heating. C) The profile after 3 cycles in the oven. D) A plot comparing the average force vs. displacement across all cycles 37

4.3 cap 38

4.4 caption 39

4.5 cap 41

4.6 caption 43

List of Tables

3.1 ATR-FTIR absorbance ratios and relative imide surface content for various samples in comparison to Wu (2017)[2] 16

3.2 ATR-FTIR peak positions, absorbances, and relative imide surface content 22

3.3 Dye mixtures for examination in a spectrophotometer with dilution by number of parts water. Here a "part" is defined as 1.5mL. 24

3.4 Samples for testing in a spectrophotometer using dye mixture summarised in Table 3.3. 24

3.5 Catalysts, reaction temperatures and analytical methods used in crosslinking attempts of polyamic acid with ethylene carbonate. 25

4.1 Design parameters for the contruction of the folded polyimide sleeve . . . 30

Chapter 1

Introduction

1.1 Importance and Applications of Soft Robotics

Soft robots are a type of robot known for their use of soft materials, compliant nature and near infinite degrees of freedom . Degrees of freedom (DOF) is a term related to the number of independent movements a robot can make in 3D space.[3] Soft robots are usually nature inspired such as "vine-like" tip growing robots,[4,5] "snake like" continuum robots[6,7] and "hand-like" soft grippers.[8,9] The advantages of using a body that is highly deformable and with near-infinite DOF means these devices can navigate tortuous environments with ease.

This report focuses on continuum robots, often characterised by their long flexible bodies, commonly used for navigation and delivery or retrieval of objects in constrained environments.[10] Continuum robots can be classified into "continuous backbone" and "segmented back-bone" designs.[10] Continuous backbone devices are made from a soft and compliant material, in this report we will call these "soft-bodied", whereas, a segmented backbone refers to those that are made from hard, inflexible segments that are flexibly attached to achieve high curvatures, referred to here as "hard-bodied".

Hard-bodied continuum robots benefit from stiffer materials allowing a greater ease of




Figure 1.1: A continuum device sustaining damage before self-healing and regaining full functionality using a modified image from[1]

control[10] which can improve dexterity. However, they cannot deform and are more likely to impart a greater force on the surrounding environment.[11] Hard continuum robots are often tendon driven, whereby the segments are joined by wires that can be pulled to give specific movements. Whereas soft bodied continuum robots can achieve high curvatures and low forces on surroundings,[12] but are often harder to control due to their methods of actuation[10] and can suffer from material failure.[13] Soft continuum robots commonly take the form of an inflated body, these can be controlled in many ways such as varying pressure,[4] strain limiting a specific region[14,15] or magnetic actuation.[5,11] Pressurised systems that rely on fluids need a constant seal to maintain function as opposed to a segmented tendon driven approach that can be partially damaged and still actuatable. This leads the development of resilient materials such as self-healing polymers that can be applied to soft robotics.

1.2 Types of Self-Healing Polymers

Polymers are a type of molecule that consists of several repeating sub-units, these form chains that are combined many times over to form materials. Self-healing (S-H) polymers are a type of polymer that can heal damage.[16] This occurs through reactions and interactions between multiple polymer chains to reconnect chains that have been shifted apart through damage. The process of damaging or cutting a polymer does not break bonds in the polymer backbone but instead can break interchain interactions called cross-linking, allowing the chains to drift apart, reforming the cross-linking interactions will "heal" the material.[17]

S-H polymers can be classified into intrinsic or extrinsic healing, and autonomous or non-autonomous.[18] Materials with an intrinsic healing capacity involve a healing mechanism through chemical bonds or interactions that are continuously present in the polymer, rather than extrinsic healing, such as capsules of "healing" material that are broken through damage and causing the material to reform.[19] Autonomy refers to the healing




Figure 1.2: a) The polymer chain with a repeating chemical sub-unit. b) The mechanism of damage and repair for a self-healing polymer

process occurring without external input. For example, capsules that burst upon damage of the material and release a healing agent are classified as autonomous, whereas a photochemical reaction that needs UV light to activate[20,21] is a non-autonomous mechanism.

1.3 Comparison of Different Self-Healing Pathways

There are a variety of different pathways that can be taken to create a S-H polymer depending on the chemistry of the initial polymer. The pathways that will be focused on are intrinsically self-healed types, however, both autonomous and non-autonomous types will be considered.

The three pathways below rely on a property of some electrons called conjugation. Conjugation occurs when specific electron orbitals overlap in such as way that allows the electrons to move around the molecule. This is often exploited with a property of some atoms called electronegativity, having a highly electronegative atom in a molecule will attract conjugated electrons to create a local high density region of electrons and therefore a polarisation in a molecule.

Dynamic covalent bonds can form and break based on the conditions applied to them[22] and they are ideal for use as mechanisms for S-H due to their intrinsic nature and reliability in production of high yields.[23] This report investigates the use of two types of dynamic covalent bonding, Diels-Alder and Michael additions, and an example of a supramolecular interaction. Supramolecular chemistry is based on interactions that are non-covalent and may be more suited to a soft material.[24] This is due to the S-H mechanism of the cross-links that forms interactions therefore the polymer chains can move semi-independently.[24,25] Whereas, a dynamic covalent bond has a much higher bond energy[22] and can therefore get closer to the original physical properties of a polymer.




Figure 1.3: a) A Diels-Alder reaction between two molecules of cylopentadiene. b) A Diels-Alder reaction between a furan and maleimide. c) A Thiol-Michael Addition between a thiol and a conjugated alkene.

1.3.1 Using a Diels-Alder Addition as a Self-Healing Pathway

Diels-Alder (DA) reactions require a diene, a class of molecule characterised by having two sets of double bonds, and an alkene ("dieneophile").[22,26] The reaction occurs when conjugated electrons from the diene are free to move to form new bonds with the carbons either side of the alkene double bond, this creates a new ring structure. A faster reaction is generally observed with an electron rich diene and an electron poor dienophile.[27] The electronic character of the reagents can be altered by changing their local substituents. This class of reactions can have lots of different conditions depending on the molecules involved. Some variations can occur at room temperature,[28] which may make them an ideal choice for an autonomously healed medical device as the healing can occur whilst deployed in the body. However, many DA reactions are light[20,21] or heat activated.[29]

Some molecules such as cyclopentadiene can perform a DA reaction with itself, this has the potential to be an ideal choice for a S-H polymer as the molecule will never be in close proximity to a molecule that it cannot react with. However, some evidence has shown

that the bonds formed are not very strong and therefore high tensile strength materials may not be possible.[26]

One of the most common types of DA reaction is a heat activated reaction between a derivative of both furan and maleimide.[30] They react extremely accurately and require mild conditions,[26] therefore they are very suitable for application as a robotics material. One of the reasons that this reaction is so effective is that the maleimide has electron withdrawing carbonyl groups which make the dieneophile electron poor and therefore reacting faster. However, this mechanism has a disadvantage compared to cyclopentadiene as there are two halves of the end product. Therefore, there must be a two different processes occurring to create both the furan substituted and maleimide substituted chains. This increases the number of total steps in the reaction which increases the risk of low reaction yields and wasted material.

1.3.2 Using a Thiol-Michael Addition as a Self-Healing Pathway

Thiol Michael additions are a type of reaction that relies on a thiol, a molecule characterised by a sulfur containing group and a conjugated alkene.[31] The conjugated alkene used in a Michael addition is with a carbonyl group that will attract the electrons from the alkene to allow the thiol group to react. This has a similar advantage to the Diels-Alder reaction that it is not totally dependant on specific reactants merely groups of reactants. Therefore slight changes can be made to the adjoining groups to tweak the reaction conditions. This has been previously shown to have been successful with a heat activated reaction that could heal scratches after 15 to 30 minutes at 60 °C.[32]

1.3.3 Using a Pi-Stacking Approach as a Self-Healing Pathway

Pi-Stacking is a type of intermolecular interaction whereby conjugated systems interact based on the neighbouring substituents determining if a region is electron rich or poor.

These electron disparities cause an electrostatic interaction. This method commonly uses pyrenyl groups, these are polycyclic aromatic compounds, a very pi-electron rich species. These can be interacted with a napthalene diimide complex, an electron poor pi-system to give four pi-stacking interactions. A method has shown the creation of a polymer chain end group which can sandwich a napthalene group within two pyrenyl groups.[33] This method can be combined with other intermolecular interactions like hydrogen bonding[34] or mettalosupramolecular interactions to give a stronger interaction.[35]

1.4 Applications of Self-Healing Polymers in Soft Robotics

Continuing the theme of biological inspiration of soft robotics, S-H polymers can be used to extend the lifespan of components. In soft continuum robots, the goal is usually to make the robot softer than the environment surrounding it.[12] This presents a challenge that the environment can often be abrasive and can damage the device. It is therefore evident that a damage resilient material would be useful. Damage resilient materials can take multiple forms: Damage isolation, material elasticity, physical self healing such as low melting temperature materials and chemical self healing.[36]

1.4.1 State of the Art Self-Healing Soft Robots

State-of-the-art approaches using intrinsic S-H mechanisms are commonly based on DA chemistry.[18] These have been successfully implemented in tendon-driven[37] and pneumatically controlled soft robotic devices.[38,39] Such devices are capable of recovering from macroscopic damage, including punctures and cuts. Additionally, there are non-covalent approaches that utilize hydrogen bonding in the development of soft self-healing actuators, such as in McKibben muscle designs.[40]

1.4.2 Requirements for Self-Healing Polymers in Soft Robotics

Terryn *et al.*[18] states that there are 5 main criteria for a S-H polymer; macroscopic damage must be healed completely; healing can take place multiple times at the same location; there are minimal material property changes after healing; elastomeric behaviour is achieved; the reprocessing and recycling of a material is possible. Here we propose that elastomeric behaviours are non-essential and a more useful requirement would involve a timely S-H reaction.

1.5 Limitations with Current Materials for Soft Robotics

Damage control whilst a device is active can be a challenge,[41] this shows a need for autonomous S-H.[18] Non-autonomous S-H can be made "functionally autonomous" through the use of stimuli responsive mechanisms, however, the current options are slow in operation.[41] Currently recovery timescales of applied S-H polymers are around 25 hours.[36,39] By altering the polymer used or S-H pathway this could be improved. There is also a lack of an easy synthesis route for many of the current polymer options,[36] thereby increasing the cost and reducing widespread use. Also the number of damage-repair cycles in these devices are low, such as 3 or less.[39] Most devices do not achieve all 5 criteria laid out in the Terryn *et al.* review,[18] such as the McKibben design of A. Lopez Diaz *et al.*[40] only reports a healing efficiency of 65%.

Chapter 2

Project Aims and Objectives

2.1 Aims and Objectives of this Project

The aim of this project is to understand the use of a self-healing polyimide in a soft robotics context.

We hypothesise that the incorporation of a S-H polyimide into soft robotic components will enhance their lifespan.

The objectives of this project are to:

- Investigate the alteration of a polyimide through a Diels-Alder pathway to achieve a self-healing polymer
- Investigate the processability of the modified polymer through material tests such as melting point analysis.
- Based on the processability, apply the polymer to either a sheet film material or a moulded component suitable for use as a soft robotics component
- Based upon the form of the modified polymer construct and use as an inflatable soft continuum robot or for use in other hard or soft bodied components

- Test component/robot through different techniques such as tensile testing and force characterisation.
- If time allows, design and construct a system that can autonomously self heal components. For example, using a UV controlled self healing reaction, the flow rate of air into an inflatable device could be measured so that if the flow changed a UV light could be activated thereby autonomously self-healing the components.

Chapter 3

Synthesis of a Self-Healing Polymer

3.1 Results

3.1.1 Hydrolysis of the Polyimide

$$C_{22}N_2O_5H_{10} + NaOH \longrightarrow C_{22}N_2O_6H_{11}Na \tag{3.1}$$

The method for hydrolysis used was based on previous literature publications[2,42–48] where an alkaline solution is used to hydrolyse polyimide to form a salt intermediate and then an acidification to form carboxlyic acid groups. A NaOH solution (0.2M)[42–44] was initially trialled for the alkaline hydrolysis step at room temperature for 90 mins, however when there was minimal change under Infrared spectrometry (IR), the temperature of the




Figure 3.1: Structure of polyoxydiphenylene mellitimide (Kapton) with higlighted pthalamide region at A




Figure 3.2: Structure of polyamic acid

reaction was increased to 120°C. Also, the NaOH concentration was adapted similar to that used in Xue (1986).[47] This comprised of the use of 1 equiv. OH^- for every 1 monomer of the polyimide. This was chosen to ensure a partial hydrolysis, to only expose one carboxylic acid group rather than the total hydrolysis to form a tetrasubstituted benzene ring. However during analysis of this reactio we also observed minimal hydrolysis via IR.

A widely accepted base-catalysed amide hydrolysis route is through a second order pathway, where a hydroxy group (OH^-), from the base, nucleophillically adds to the carbonyl group (C=O) to form a tetrahedral intermediate.[49] This cleaves into two and the amine is eliminated. In pthalamide structures (Fig 3.1A), a molecule close in character to the polyimide monomer, has been shown to exhibit similar behaviour when in solution.[50]

However, mechanistic changes occur when the reaction contains macromolecules, it has been shown in previous literature that there is a third order dependence on the concentration of OH^-($[OH^-]$) and follows a mechanism that starts with the nucleophillic addition of the OH^- to form a charged intermediate before undergoing rate-determining cleavage of the C-N bond to form the associated polyamic acid.[42] Moens (1957) proposed that, due the hydrostatic repulsion, the rate of hydrolysis is lowered when a polymeric chain has increasing numbers of negative charges,[51] this would imply that the formation of the monanion intermediate could hinder the reaction.

While multiple literature sources opt to use KOH,[2,45,47,48] hydrolysis has been shown to occur in the presence of NaOH.[42–44] In retrospect, hydrolysis attempts using KOH should have also been approached due to the success of many KOH hydrolysis attempts.

However, we attribute most of the failure in this experiment to the low concentration




Figure 3.3: Hyrolysis of polyimide to polyamic acid

of NaOH, as sources have stated that a concentration below 0.5M was ineffective.[2] This explains why the testing with 0.04M was also ineffective. Additionally, some of the failure may be caused by the lack of addition of a reagent to maintain constant ionic strength, which has been shown to assist hydrolysis with NaOH.[42]

Spectral Analysis

Structural determination was conducted via Infrared spectroscopy (IR). A comparison was made between the attempted hydrolysis of the sheets and a purchased form (polyamic acid).

Characteristic peaks of both the hydrolysed and the control forms are observed around 1500cm^{-1} , corresponding to the C=C bond in the central benzene ring[2,45] along with the 1235 cm^{-1} aromatic ether stretch[45] both which do not change throughout the hydrolysis.

Also observed is the C=O asymmetric stretching mode at around 1710 cm^{-1},[2,43,45–47] the peak around 1775 cm^{-1} as the symmetric C=O stretch[45–47] and the C-N-C imide ring stretch at 1370 cm^{-1},[45,46] all of which decrease in magnitude during hydrolysis.[2,46]

One literature source[52] states that the symmetric C=O stretch is at 1775 cm^{-1} and the asymmetric is at 1720 cm^{-1} however, due to the disparity between this and the other sources, we disregarded this result.




Figure 3.4: .

Some sources estimate their degree of hydrolysis with a comparison of the ratio of intensities of the C=O : C=C (1720:1500 cm^{-1}) peaks,[2,47] these are summarised in the table 3.1. In this report, the symmetric C=O peak was observed slightly lower at around 1710 cm^{-1}.

As in the Wu 2017 paper,[2] this report assumes the Kapton sample to have 100% imide content on the surface, hence finding that the polyamic acid sample contains 18.71% surface imide content. Also observed was the decrease in imide content relative to both an increase in NaOH concentration and time. This work found that the best hydrolysis attempt was the 90 minute, 0.2M hydrolysis at room temperature, giving a total imide surface content of 94.24%, meaning that 5.76% of the imide rings were cleaved.

3.1.2 Spectrophotometry

Due to the limitations of only using one method of analysis of the degree of hydrolysis of Kapton, an additional method was sought out. Other traditional methods of determi-

Sample	Base	Conc. /M	A_{1500}	A_{1720}	A_{1720}/A_{1500}	Rel. imide content
90 min, 25°C	NaOH	0.2	0.2243	0.2304	1.0273	0.9424
20 min, 120°C	NaOH	0.03	0.1062	0.1167	1.0990	1.0082
40 min, 120°C	NaOH	0.03	0.1608	0.1735	1.0789	0.9898
Kapton	—	—	0.1125	0.1226	1.0900	1.0000
PAA	—	—	0.8508	0.1735	0.2040	0.1871
Wu (2017)	KOH	0	0.0513	0.0587	1.1440	1.0000
Wu (2017)	KOH	0.1	0.0504	0.0573	1.1375	0.9943
Wu (2017)	KOH	0.5	0.0511	0.0568	1.1096	0.9699
Wu (2017)	KOH	1	0.0587	0.0617	1.0519	0.9194
Wu (2017)	KOH	5	0.0763	0.0072	0.0946	0.0827

Table 3.1: ATR-FTIR absorbance ratios and relative imide surface content for various samples in comparison to Wu (2017)[2]

nation such as nuclear magnetic resonance (NMR) rely on solubilty of samples, this is a property which, by design, Kapton does not have. Therefore, a spectrophotometric test was proposed.

Other spectrophotometric methods of detection of carboxylic acids involve fluorescent tagging. These involve the attachment of a fluorescent label to the carboxylic acid group, producing a distinct peak in a UV-vis spectrum. Attachment reagents involved are varied, including halogenoalkyl, hydrazine, amine, alcohols and sulfonate groups. However, most of these options require activation of the COOH group before binding of the fluorescent marker. We aimed to avoid any pre-activation reagents as this would lower the activation of the unwanted intramolecular amide formation, thereby reforming an imide ring.[53]

Therefore, a method proposed by Johar (1972) involving the use of Eosin Y (EY) and Methylene blue (MB) for determination of carboxylic acids was used.[54]

Dyes were mixed as according to the concentrations stated by Johar (1972). However, is was apparent that ther concentration was too high, therefore additional dilutions of the dye mixtures were made. Initally tested were the interactions between the dyes and water, we observed a peak at (515 ish) confirmed to be corresponding to EY[55–57] and a peak at (650 ish) correspoding to MB.[58–61] The shoulder on the EY peak is formed




Figure 3.5: .

through the dimerisation of the molecule due to the high concentration.[56]

An example of a postive test would occur with acetic acid, a simple carboxylic acid. In the spectophotometer, the peak corresponding to the EY was destroyed. This report proposes that this destruction is due to the use of glacial (the most concentrated an acid can be) acetic acid. In high concentrations, acetic acid can to convert the EY into a precursor (dihydrofluoran)[62] which causes the observed blue shift in the peak[63] along with the reduction in magnitude.

Next assessed was the interaction between dye mixture and polyamic acid (PAA) dissolved in dimethyl sulfoxide (DMSO). This gave two peaks, one in the EY region at (515ish) and one in the MB region at (650ish). The interaction with the MB was very similar to that of the acetic acid which was a promising result. However, in the EY region, the large peak was not similar to that of acetic acid. We propose this effect was caused by EY catalysing amide formation, hence forming imide rings and removing the carboxylic acids. This implies that the peak at (515ish) corresponds to the solvent (DMSO) rather than an interaction with the PAA.

To test this hypothesis, DMSO was mixed with the dyes and a peak at (515ish) and

(650ish) was observed, which we confirm to be EY[56] (maybe aslo cite aroteinvestigating) and MB[58,60](maybe also cite tchaikovskaya2023solvent). As a final validation, we checked that the interaction was not simply pH based by testing HCl, this was chosen as an acid that does not contain carboxyl groups and therefore should react differently to the acetic acid. The absorbance spectrum showed one peak at (450), which we believe is due to the ....

Due to the difference in absorbance for the acetic acid and the PAA and the catalytic effects of EY on imide reformation, we determined that the GS Johar method is not appropriate for a determination of hydrolysis of Kapton.

3.1.3 Cross-linking of the Polyimide

$$2\,C_{21}N_2O_5H_{13}{-}CO_2H + C_3O_3H_4 \xrightarrow{\text{cat}\cdot\text{salt}} (C_{21}N_2O_5H_{13})_2C_4O_4H_4 + CO_2 + H_2O \quad (3.2)$$

Cross-linking attempts follow a route where ethylene carbonate (EC) is used to form an ester with the carboxylic acids on neighbouring polymer chains, thereby joining them together with a "cross-link". This was attempted with three different salts (Et_4NBr, $ZnCl_2$, $FeCl_3$) as catalysts.

During the cross-linking reaction with Et_4NBr, an orange-brown suspension was formed that when washed, filtered and freeze dried yielded a pale orange powder. With $ZnCl_2$, the liquid was a dark orange clear liquid that, when water was added, gave a single clump of grey polymeric residue. This was freeze dried to remove the excess water and then analysed. The cross-linking reaction with the $FeCl_3$, yielded a dark orange/brown gel, which formed a grey gum-like texture in small pieces when water was added. This was also frozen and analysed.

Safety Consideration

During a cross-linking with ethylene carbonate, CO_2 is released (Eq. 3.2). This was a concern as the monowave reactor has a pressure limit of 20 bar. To ensure there was a reliable safety buffer, an artificial limit of 5 bar was set. The Ideal Gas law was used to give the amount of EC to use to ensure this limit was held.

$$PV = nRT \rightarrow n = \frac{PV}{RT}$$

P = 500 kPa, V = 10 mL, R = 8.314 J K^{-}1 mol^{-}1, T = 423K

$$n = \frac{500 \times 10 \times 10^{-3}}{8.314 \times 423} = 0.00142mol$$

Since the CO_2 is generated from the EC, there are same number of moles for the CO_2 and for the EC. This motivates the use of $mass = Mr \times n$, where Mr = 88, n = 0.00142

$$Mr \times n = 88 \times 0.00142 = 0.12496g$$

Detailed mechanistic studies of the reaction between a carboxylic acid and ethylene carbonate in the presence of a quaternary ammonium salt, such as Et_4NBr, have been performed in other literature.[64–66] Yoshino (1977) states that the mechanism begins with a nucleophillic ativation by the anion of the catalytic salt on a methylene group of the EC, this cleaves the hydrogen from the alcohol group (OH) of the carboxylic acid which can now nucleophillically substitute the halide to form the ester. Fagerburg (1984) disagreed with this mechanism as they proposed that the rate of the reaction was be dependent on the anion of the catalytic salt. However they did not find this experimentally. They observed during a reaction of the catalytic salt and EC alone, the activation energy of the EC decomposition was much higher than any esterification attempts . They therefore




Figure 3.6: .

proposed a mechanism involving the attack of a carboxylate species on the methylene carbon of the EC to decompose the ring and form the ester product. Given the depth of Fagerburg's work, we consider this mechanism to be more robust than the one proposed by Yoshino.

The change of catalyst to a lewis acid ($ZnCl_2, FeCl_3$) was to encourage a direct activation of the carbonyl group on the EC, the mechanism for this proposed step was as follows: The lewis acid activates the carbonyl on the EC by forming a "complex". This allows the alkoxide to attack the methylene group of the EC and form the hydroxyethyl ester.[67] Von Seggern (2020) however reported, the use of zinc based catalysts was found to be ineffective in this reaction.[67]

Spectral analysis

Spectral analysis was performed mainly with IR, but also with ^{1}H NMR and DOSY.

From the IR data, the crosslinking with Et_4NBr was deemed to be unsuccessful as the product spectra the key peaks of the C-O bond corresponding to an ester or any alcohol formation were not observed. Alcohol peaks would be likely as crosslinking attempts are unlikely to be 100% successful, hence the single ester product would also be formed. However, neither of these were present and since the product was insoluble, no NMR could be obtained. This IR spectrum was compared with the spectrum of Kapton (i.e. the ring closed form of the polyamic acid) and the similarities confirmed that the imide ring reformation had occured. Key spectral peaks confirming the lack of crosslinking contain the C-N-C peak, commonly found at 1370 cm^{-1}, however in our sample we observed this peak at 1391 cm^{-1}. Other signs of imidisation include the increase in the magnitude of the C=O stretch at 1715 cm^{-1}. These peaks would indicate the imide ring reformation as opposed to the esterification product.

From the IR data of the $ZnCl_2$ and the $FeCl_3$ attempts, we observe two new peaks at around 1800 cm^{-1} which are not in either the Kapton or the PAA samples. This shows the presence of EC in the final sample as C=O bonds in liquid EC[68] are found in this regon. Since these samples were soluble, proton nuclear magnetic resonance (^{1}H NMR) was available. A new peak was observed at 4.43ppm in the ^{1}H NMR spectrum, however, when adding 2 μL of EC in a "spike test", the peak increased in size confirming that the new peak was starting material (EC). Other peaks in the $ZnCl_2$ and $FeCl_3$ samples are indicative of unreacted polyamic acid. After increasing the temperature of the $ZnCl_2$ catalysed sample, the peaks positions show the intramolecular cyclisation of the imide ring with the C-N-C stretch at 1370cm^{-1}.

DOSY data was collected for the $ZnCl_2$ sample ....

3.1.4 Catalytic Imidisation of polyimide

During the attempted crosslinking reactions, the imide ring formation was observed at a lower temperature than previously seen in the literature. This motivated attempts to




Figure 3.7: .

Sample	ν_{1500} /cm^{-1}	A_{1500}	ν_{1720} /cm^{-1}	A_{1720}	A_{1720}/A_{1500}	Rel. imide content
PAA	1495.02	0.8508	1709.18	0.1735	0.2040	0.1871
No_cat	1495.02	0.4209	1717.34	0.1375	0.3268	0.2998
With_cat	1497.06	0.0727	1721.42	0.0443	0.6084	0.5581
Kapton	1497.06	0.1125	1709.18	0.1226	1.0900	1.0000

Table 3.2: ATR-FTIR peak positions, absorbances, and relative imide surface content

recreate this with only polyamic acid (PAA) and $ZnCl_2$.

Without the catalyst, material got slightly darker after heating for an hour. This was attributed to some minor solvent evaporation and therefore, substrate becoming more concentrated. A similar colouration after heating the sample containing catalyst was observed, however, there was also material suspended. This was proposed as indicative of a partially successful attempt.

An assessment of the success of the imidisation can be made by comparing the A_{1720} to the A_{1500} in the same manner as previous analysis.[2] In table 3.2, again the Kapton sheet was assumed to have 100% surface imide content and others were calculated relative to this. This report finds that the imide content of the polyamic acid heated without the catalyst had 29.98% imide content as compared to the baseline value from the unheated PAA at 18.71%. However, the sample with $ZnCl_2$ catalyst presents as successful as 55.81% imide content is observed. Also observed was a shift in peak position in the 1500 peak when imide content is over 50%. To confirm the degree of imidisation in the future, a pure sample could be obtained through a recrystallisation from DMSO.

3.2 Experimental

3.2.1 Equipment

A MonoWave reactor (MonoWave 50 Closed Reaction Vessel; ANTON PAAR) was used for the majority of experiments covered in this report. This reaction vessel contains integrated temperature and pressure control and a magnetic stir element. This allowed the user to perform reactions more quickly as samples could be heated above their ambient pressure boiling points. The MonoWave reactor required a specific 10mL tube that was sealed with a rubber cap and a PTFE septum, to ensure agitation, an oval-shaped magnetic stir bar was included.

3.2.2 The Hydrolysis of a Polyimide

Polyoxydiphenylene mellitimide (Kapton) film (0.18g, thickness: x) was cut into pieces of approx. 3mm^2 and placed into a beaker. This was stirred at room temperature with a solution of NaOH in DMSO (0.2M, 22ml). There was no observable difference and an Infrared (IR) spectrum was taken.

Another sample of Kapton film was cut into approx. 3mm^2 pieces and placed into a MonoWave reaction tube along with a solution of NaOH (vol, 0.03M). This tube was placed into a MonoWave reactor that was set to ramp for 20 minutes and hold for 20 minutes at 100°C. There was no observable difference, so a sample was taken and the remaining mixture was placed onto the MonoWave under the same conditions. The mixture was filtered and thoroughly washed with water before IR was collected.

Dye Mix	Parts water	Parts Eosin Y (0.5%)	Parts Methylene Blue (0.1%)
Mix 1	10	2	1
Mix 2	5	2	1
Mix 3	0	2	1

Table 3.3: Dye mixtures for examination in a spectrophotometer with dilution by number of parts water. Here a "part" is defined as 1.5mL.

Sample number	Test compound	Dye mix
S01	Dimethyl Sulfoxide	Dye 1
S02	Polyamic Acid solution	Dye 1
S03	Water	Dye 1
S04	Acetic Acid	Dye 1
S05	Hydrochloric Acid	Dye 1
S06	Dimethyl Sulfoxide	Dye 2
S07	Polyamic Acid solution	Dye 2
S08	Water	Dye 2
S09	Acetic Acid	Dye 2
S10	Hydrochloric Acid	Dye 2
S11	Dimethyl Sulfoxide	Dye 3
S12	Polyamic Acid Solution	Dye 3
S13	Water	Dye 3
S14	Acetic Acid	Dye 3
S15	Hydrochloric Acid	Dye 3

Table 3.4: Samples for testing in a spectrophotometer using dye mixture summarised in Table 3.3.

3.2.3 Spectrophotometry as a Determination Method for Hydrolysis

The preparation of samples for the spectrophotometric analysis was as follows:

3 mL 0.5% Eosin Y solution was added to 1.5mL 0.1% Methylene Blue solution. This solution was diluted with 10 parts water and 5 parts water (where a "part" is 1.5mL) to give three dye mixes (summarised in 3.3)

Test compound (2.7mL) was added to a sample vial along with one of the dye mixes (0.3 mL) to form samples summarised in 3.4. These were inverted to ensure mixing before

Catalytic Salt	Mass Salt /g	Reaction Temp. /°C	Analytical Method
Et_4NBr	0.08	150	IR
$FeCl_3$	0.02	100	IR, NMR
$ZnCl_2$	0.03	100	IR, NMR, DOSY

Table 3.5: Catalysts, reaction temperatures and analytical methods used in crosslinking attempts of polyamic acid with ethylene carbonate.

being transferred to a plastic cuvette and placed in a spectrophotometer (DETAILS) to test between 250 and 750nm.

3.2.4 Crosslinking of Polyamic acid

This procedure outlines the crosslinking procedure of polyamic acid (PAA) via ethylene carbonate (EC) using a catalytic salt as outlined in previously published procedures.

A mixture of polyamic acid (0.51mL, conc) was placed into a MonoWave tube with ethylene carbonate (0.08g) and a catalytic salt. These were placed into the MonoWave to ramp for 20 minutes and hold at the reaction temperature for an hour. The products were washed with water and filtered before being freeze dried and examined on the spectrometers. The reagent amounts and processing methods are summarised in table 3.5.

Tetraethylammonium Bromide (Et_4NBr) Crosslinking Spectral Data

A orange powder (grams,moles,yield) was isolated, ν max/cm^{-1}(solid); 1715, 1601, 1501, 1391, 1307, 1252, 1167, 1116, 885, 815, 800, 724 634 606, 567, 516, 428

Iron Chloride ($FeCl_3$) Crosslinking Spectral Data

A white gum (grams,moles,yield) was isolated, δ H(400MHz, DMSO); , δ C(100MHz, DMSO); , ν max/cm^{-1}(solid); 2931, 1805, 1774, 1721, 1609, 1497, 1403, 1372, 1309,

1256, 1163, 1114, 1075, 987, 822, 759, 724, 679, 606, 563, 479

Zinc Chloride ($ZnCl_2$) Crosslinking at 100°C Spectral Data

A grey gum (g,mol,yield) was isolated, δ H(400MHz, DMSO); , δ C(100MHz, DMSO); , ν max/cm^{-1}(solid); 3263, 3112, 1679, 1603, 1583, 1530, 1493, 1403, 1367, 1316, 1263, 1187, 1163, 1081, 1036, 1008, 836, 722, 706, 630, 600, 559, 534, 502, 404

Zinc Chloride ($ZnCl_2$) Crosslinking at 110°C Spectral Data

Brittle brown pieces (g,mol,yield) were isolated, ν max/cm^{-1}(solid); 3043, 1776, 1715, 1606, 1538, 1497, 1371, 1307, 1238, 1165, 1114, 1012, 879, 820, 724, 632, 606, 565, 514, 430

3.2.5 Catalytic Imidisation of Polyamic Acid

Polyamic acid (0.51mL), $ZnCl_2$ (0.02g) and a magnetic stirbar were added to a MonoWave tube. This was placed in the MonoWave at 110°C to ramp for 20 minutes and hold at 150° for 60 minutes. A control experiment without the $ZnCl_2$ was also placed under the same conditions. The control experiment gave a clear dark brown viscous liquid which, when dried, gave a gum-like pale orange solid. The test with the $ZnCl_2$ gave a similar dark brown liquid, however this was slightly cloudy and, when processed, gave an orange powder.

Control Spectral Data

IR(solid): vals, vals cm^{-1}

Catalytic Imidisation Spectral Data

IR(solid): vals, vals cm^{-1}

Chapter 4

Construction of a Bellows Based Actuator

4.1 Design

Actuators were constructed using a combination of a folded polyimide sleeve and an internal multilumen silicon tube with nitinol wires for actuation. The design of this device was inspired by similar origami based approaches to construct continuum devices (references)

4.1.1 Construction of a Folded Protective Sleeve

Protective sleeves are a common addition to soft actuators in order to protect against harsh environments such as abrasive surfaces, high heat, strong chemicals and UV radiation. Nanomaterial based coatings are often at the forefront of resistance mechanisms with some focused on flame and heat resistance and others for chemical resistance through superomniphobia[69] (repellant to almost all liquids). However nanomaterials are only suitable as coatings rather than the main building material, therefore the use of high

performance resilient polymers has become more popular.

In this report, we use polyimide (Kapton, Details) to form the main body of the protective polymer sleeve. Polyimides have been used before in protective sleeves and have been shown to be resistant to harsh environments. Possibly the most famous example of a polyimide as a protective layer was on the surface of Eagle, the Apollo 11 lunar landing module. This was coated in Kapton film due to its thermal insulation properties.One of the harshest environments that robotics faces is space, the material chopse are lightweight, highly compressible, extremely temperature stabile and highly UV radiation resistant.[70] Other applications, such as in medical devices, require chemical resistance, particularly useful when presented with the low pHs of stomach acid (pH 2-3). Kapton film has been shown to be highly resilient to UV and heat,[70,71] highly compressible when folded into cylinders[70] and relatively resistant to acids. Fuming nitric acid (HNO_3) has been shown to degrade Kapton,[71] however this was due to the highly oxidising nature of HNO_3. This is unlike hydrochloric acid (the main component of gastric acid) which is not an oxidising agent. In addition to this, Kapton and other polyimides contain mellitimide ring structures allowing the partial break down of the polymer chain thereby motivating the addition of intrinsic functionality such as self-healing Diels-Alder groups without the complete conversion back to oligomer material.

There are three main designs of folded cylinders used in soft robotics: Kresling, Yoshimura and Accordion. Possibly the most popular design is Kresling, which was discovered through the twist buckling of paper cyclinders,[72] this was adapted to form consitent folds through the segmentation of a flat sheet into triangles to form a helical folding pattern.[73] Yoshimura patterns are formed through the segmentation of a sheet into parallelograms in a diamond configuration, these parallelograms are bisected with horizontal lines to form triangles.[74] Yoshimura designs can be modified through the inversion of specific protruding vertices to form a pattern known as Accordion. This transforms the parallelograms into hexagons and therefore the triangles into trapeziums.

An in depth analysis of the Accordion versus Kresling designs was performed by Butler

Symbol	Description	Value
L_1	10	2
Mix 2	5	2 1
Mix 3	0	2 1

Table 4.1: Design parameters for the contruction of the folded polyimide sleeve

(2016),[70] here it was found that the number of folds to make a functional device was approximately 10× less in the Kresling design than the Accordion. Often the initial failure of devices occured on the vertices, such failure was observed to occur less in Kresling designs than in Accordion. Also, when comparing compressibility (using Eq. 4.1) it was found that, while both designs have a compressibility over 90%, the Kresling design slightly outperforms the Accordion by 1.5%.

$$compressibility = \frac{h_{deployed} - h_{compressed}}{h_{deployed}} \tag{4.1}$$

Due to the configuration of the nitinol wires in the silicon actuation device, it was observed that the controllability was improved when the device had torsional stability. While there are methods of adapting a Kresling design to limit torsional movement through the reflection of alternating layers. These devices are inherently prone to torque due to the helical design. Accordion Yoshimura designs are significantly more torque resistant in comparison. This is one of the primary reasons for the use of the Accordion folding pattern in this work. The design parameters are summarised in figure and table 4.1.

Manufacturing of a Folded Polyimide Sleeve

To manufacture an Accordion patterned sleeve, a 2D drawing to map the fold lines was drawn in Fusion360 (Autodesk, details) and printed onto paper. This paper was taped to a table and a sheet of Kapton was taped over the top, the Kapton is clear so the printed lines were visible through. The lines were then traced onto the Kapton with a ruler and a ballpoint pen. The ballpoint pen marked the desired fold lines and also partially indented

on the lines. The sheet of kapton was removed from the table and the outer edge was cut with scissors. The Kapton sheet was then folded along the lines as shown in the figure [ref figure]. The folds on the sheet were inverted and the kapton was rolled into a cylinder. This was taped along the overlapped edge to form a temporary seal while maintaining care to line up the folds. The tape was removed in small sections and JBweld HighHeat was applied until the whole adhesion region. This was threaded onto a plastic tube with a diameter approx. 2mm smaller than the kapton sleeve. The sleeve was taped to the tube and the adhesion region was taped over the top to clamp the glued region. This was left for 24 hours to cure. The glueing and the curing process was performed in a Fume cupboard [brand/details] due to the risk of respiratory irritation through the curing process. After curing, the sleeve was removed from the plastic tube and a strip of Kapton tape was placed over the edge on the adhesion region. This improved the flexiblity of the region. One of the ends was folded over to make a cap and this was also glued. In this work, this assembly is known as the "Kapton sleeve" or "polyimide sleeve".

Manual folding versus using a plotter

A commercially available plotter (Cricut®) was used with a scribe tool and a cutter to achieve a rapid manufacturing of a folded sleeve. This was attempted with paper initally for cheap prototyping and then with the polymer film. This would avoid the time consuming folding steps

The Cricut was set up with the cricut design space software. This software allows the user to draw and communicate with the cricut either through bluetooth or via cable. The cricut has an adhesive cutting mat to hold the material in place whilst the tool interacts with it. For our testing, we drew a rectangle (10 x 5 cm) and set the cricut to cut on this line. Then a line (5cm) was drawn to split the long edge into two squares ($5cm^2$), this line was set to score. These two drawings were attached so as they would be performed in the same material loading cycle, the scoring was set to be first in the cricut's "job queue" to avoid there being potential for the score tool to catch the newly cut edge of the polymer

and cause the adhesion between the sheet and the polymer to fail. A piece of the desired material was adhered to the cutting mat and the cricut was started. This method was repeated for 2 thicknesses of Kapton (details) and 80gsm paper (roughly 0.25mm).

The three pieces of prepared material were taped by the top edge to the jaws of a vice. The vice had the jaws enlarged by 3D printed pieces to ensure that the clamping would occur across the whole of the material. The vice was manually controlled to compress the pieces of material into the crease to form a fold and then slowly decompress to evaluate the fold. The folding with the paper was highly effective, when the jaws were opened the paper was clearly separated into two sections by a fold in the centre. Both thicknesses of Kapton were not so effective, when they were decompressed there was no clear fold line and the material was left haning in a curve. The plotter can visible score the Kapton, however, the score lines do not define a crease as the scoring tool does with paper. This phenomenon is explored further in the [put paper here], where polyimide is shown to not form precise folds.

We determine here that the use of a plotter could be useful in the rapid production of folded sleeves, however when using this particular material, the cricut is not a viable route for creasing Kapton. A comprimise could be to use the cricut to draw the fold lines by using a pen in place of the scribe tool, this would allow the user to bypass the printing and tracing the pattern by hand.

Limitations with the design and manufacturing

The actuator exhibits self-deploying characteristics, which are present in other devices. This is a product of treating the material as having non-zero thickness.[75] Steps can be taken to avoiod thios by adjusting the location of the folds. however when flding by hand, there is so much imprecision that moving the folds by the thickness of the width of a sheet is not neccessary (there is a reference somewhere)

Previously, it has been shown to achieve an actuator with "wrinkle-free" compression, the

triangles in Yoshimura designs should be right angled isoceles[76] and hence, the hexagons in Accordion should have a horizontal short side length equal to $\sqrt{2}a$ and long side length to be $2\sqrt{2}a$ if the angled sides are of length a. The design in this work does not feature wholly right angle triangles as the hexagonal segments can be split into four right angled isoceles triangles and two squares. However, the slight deviations from perfect compressibility in this device have been attributed to the variability in the folding pattern rather than the optimised design mentioned by Suh (2021).[76]

The polyimide was observed cracking on the vertices, although initally thought to be repairable with a patch of Kapton tape, the complexity of bending in that region meant constitent adhesion was not achieved. This meant the contructed sleeve was not air tight and therefore locomotion via changing air pressure was not successful with the current design.

4.1.2 Complete Assembly

The complete assembly was formed with the polyimide sleeve, the silicon continuum device and 3D printed parts.

The silicon continuum device contains a silicon 7-hole multilumen tube with a 3D printed cap, the lumen are arranged so that there are 6 equally spaced edge lumen and one central lumen. There are 3 nitinol wires that are approximately double the length of the silicon tube and these are threaded through one of the edge lumen, through the 3D printed cap and back through a neighbouring lumen. This is repeated another 2 times until all 6 outer lumen contain a niinol wire. We define the disatl end as the end with the 3D printed cap. At the proximal end, where the ends of the nitinol wires are, these are fed into 3 3D printed handles where the wires are held with 1.5mm grub screws. This assembly is threaded through a stiffer tube (approx. 15mm diameter) and a cable gland on the end of this stiff tube holds the silicon tube and the larger tube together. The device can be actuater by fixing the stiff tube in place and pulling on the 3D printed handles. In




Figure 4.1: caption

some instance, we increased the stiffness of the device to improve the controllability of the deivce by putting a nitinol wire through the centre lumen. This centre lumen can also be used for adding to the functionality of the device by presenting an opportunity for targeted drug delivery, a tool channel or for wires from tip-based components.

The construction method for the completed assembly is as follows: the silicon continuum device is threaded through the middle. The glued end of the kapton sleeve has a cable gland (size and details) and a 3D printed octagonal connecting piece glued to it. the silicon device is threaded through the middle of the sleeve and secured in place with the cable gland. The other end of the sleeve is clamped to the silicon continuum device with 3D printed parts to form the completed device.

4.2 Results

4.2.1 Stiffness Characterisation

During compression of the polyimide sleeve, it was observed that it acted as a non-linear spring with a maxium force (shown in figure 4.1) as 2.4N at a displacement from the relaxed state of 90mm displacement. This is consitent with literature expectations for a uniaxial loading of origami cylinders.[77] Reid (2017) compared the forces applied to different origami cyclinder designs using acetate (thickness: 0.1mm) that had been per-

forated with a laser to create folded regions. Reid (2017) observed that the compression of Accordion cylinders was non-linear and extremely unpredictable, however the design used was not optimally designed and therefore largely incompressible.

Extension was observed as linear with the maxium force of 2.6N with 60mm displacement relative to the relaxed length. The relaxed length of the sleeve was 120mm, the compressed length was 30mm which therefore meant that extension of the sleeve began at 90mm displacement. The extension of the device was measured to 150mm as this was the full travel of the linear stage. It was observed that around 145mm, some vertices on the sleeve inverted and therefore if compressed manual reversal of these vertices was needed. In future work, the linear stage should be configured to travel in both directions to allow a full hysteresis profile to be examined.

Due to the compression and extension of the sleeve being collected on the same experimental rig, the load cell was set tared at the relaxed length (120mm length, 90mm displacement) of the sleeve meaning that compression was measured as positive and extension as negative. However, when the data was collected it was observed that the force became zero at only 20mm displacement. This behaviour was attributed to the polyimide displaying an elastic characteristic where the folds settled into a more compressed form (cite kapton folding). This settlling behaviour may change through a full hysteresis characterisation.

Due to the time-consuming nature of the design process, a limited number of kapton sleeves were contructed. Combined with the fragility of the sleeves and susceptibility to failure at the corners, the device was not consistently air tight. This meant that the unpressurised stiffness was characterised. This is a relatively uncommon method and due to the number of parameters related to the design of the sleeve, a direct literature comparison was not available.

Deviations from a smooth curve observed in the extension of the device were attributed to the contraint method of the sleeve. Deformation was constrained to uniaxial compression

with a wooden rod inserted through the inside of the sleeve. The friction on the inside of the sleeve on the wooden rod caused moments of higher force. In the future, a new experimental rig would be designed where the securing cap attached to the distal end of the sleeve would contain longer supporting arms that could pass through the clamp at the proximal end and remove the need for an internal constraint rod.

In the future, a control platform will be developed. This would include linear actuators to control the nitinol tendons and a vaccum/pressure pump to control the locomotion. This platform would need to allow for the fact that when constrained to a length shorter than 120mm the force required for forwards locomotion has been shown here to have a non-linear relationship to the length of the device. The unpressurised characterisation shown in this experiment sets a low bound on the stiffness of the device, when pressurised the device will exert more force axially.

4.2.2 Temperature Stability of the Bellows

Temperature stability of the polyimide sleeve was evaluated through repeated exposure to high temperature (200°C, 1 hour) in an oven. This was completed on the same experimental rig as the room temperature stiffness characterisation. After 3 repetitions of heating the sleeve for an hour, it was determined that there was minimal characteristic change in the performance of the actuator after exposure to heat (Shown in 4.2). The variability in the stiffness of the unheated sleeve and the actuator that had been heated for 3 hours in total was x. Literature results are similar in their findings, with some examples showing a resistance to x °C for x cycles of x hours.[70] Therefore it was not a surprise that polyimide sleeve was unaffected. Kapton, the specific polyimide used here, has a thermal decomposition point at x °C, hence the behaviour in this constuction was as expected. The lack of behavioural change implies that the assembly would be well suited to a thermally harsh environment. In the future, the examination of heat treatment along with other degradation techniques should be examined. In the use case of space robotics, an analysis of the UV resistance whilst heating would confirm the suitability of the sleeve.




Figure 4.2: A) The Kapton sleeve is placed into an oven for an hour and then placed onto the stiffness characterisation experimental setup. B) The initial profile of the actuator before heating. C) The profile after 3 cycles in the oven. D) A plot comparing the average force vs. displacement across all cycles




Figure 4.3: cap

4.2.3 Workspace Characterisation

The workspace of a device is the set of all reachable tip positions that the device can achieve.[78]The resultant workspace reachable by the tip of this actuator is shown in figure 4.3. It was observed that the reachable workspace of the device in the XY plane was approximately circular, however there is slight asymmetry in the circle, with an area of high density (associated with the relaxed actuator) at a slight positive Y shift. This plot was centred on the lowest point in the Z plane which therefore indicates a slight tip bend during the actuators relaxed state. In the X-Z view, a roughly circular workspace was observed, with the actuator achieving greater than a hemisphere, which demonstrates the ability of the actuator to extend beyond the base of the device when fully actuated. The Y-Z view shows a more triangular shape, indicating that the device doesn't have a perfectly symmetrical workspace. This behaviour was attribute to the internal friction in the tendon channels causing the device to exhibit uneven behaviour.

Uniaxial Trajectory Characterisation

Primary evaluation of the actuator performance was conducted through independent actuation of each tendon and monitoring the tip location in 3D space. Rotation matrices and xyz shifts were applied to the data to rotate the plots and align the base of the actuator at the origin ($(x, y, z) = (0, 0, 0)$). This was tested through 4 different assemblies of increasing stiffness, labelled *Silicon* for just the silicon actuator, *Silicon with Nitinol* for




Figure 4.4: caption

the silicon actuator with NiTi (0.6mm) inserted through the central channel, *Kapton* for the silicon actuator with the Kapton sleeve and finally *Kapton with Nitinol* as a combination of the *Silicon with Nitinol* surrounded with the polyimide sleeve. These constuctions were chosen to gradually increase the stiffness of the device in an attempt to decrease the variation in the device and therefore improve the controllability. It was observed that the variation in paths was lowered through increasing the stiffness, with the polyimide sleeve constraining torsional movement. The occurence of dexterity improving with stiffness is a known phenomenon in the soft robotics community with efforts to created devices with variable stiffness to allow for ease of manouverability and high controllabilty for complex tasks.

Starting with the least stiff assembly, the *Silicon* actuator only, it was observed that through independent actuation of the device was difficult to control, this is presented in the plots in figure 4.4. After increasing the stiffness through the insertion of the nitinol wire in *Silicon with Nitinol*, a more manouverable device was observed. The polar insert plots 4.4 showed that the trajectories were 120° apart, however also observed was a twisting motion at the tip of the device, giving the plots a "hooked" shape. This deformation explained the reduction in vertical displacement of the actuator (see 3D plot 4.4). When adding the polyimide sleeve to constrain the torsional deformation of the actuator in the *Kapton* experiment, the "hooked" shape was minimised, however the device did not achieve trajectories with even 120° paths, instead the path exhibited a region of approxmately 170° with consistent path. There was a small region of tracking observed within this region, however this was not linked to the other tracking points due to the actuator body partially occluding the reflective ball from view of the cameras. Again the polar insert plots 4.4 revealed that the independent actuation of the *Kapton with Nitinol* also contained a wide region with no tip tracking data. This implied that the Kapton sleeve was providing unwanted asymmetry which was attributed to the glued seam in the polyimide sleeve.




Figure 4.5: cap

Multiaxial Trajectory Characterisation

Another characterisation method investigated a multiaxial trajectory, whereby the first handle was pulled fully, then another pulled fully before slowly releasing the original handle. This method was repeated with all three handles until the actuator had returned to the starting point. This method was inspired by the out-of-phase sinosoidal actuation by Chandler (2020) cite chandler. After examining the least stiff construction, *Silicon*, it was observed that there was minimal vertical movement and a polar plot indicative of tip-twisting as observed in the previous experiment. After adding the internal nitinol, *Silicon with Nitinol* was observed to be more controllable. It was observed that the XY plot was more circular than without the nitinol and had a radius of approximately 50mm. Adding the polyimide sleeve to give the *Kapton* construction resulted in an off-center oval-shaped XY plot that had a semi-major axis of approximately 100 mm and a semi-minor axis of 75mm. Finally, the stiffest construction, *Kapton with Nitinol*, was a more regular shape in the XY plot and the greatest vertical displacement of the four contsructions. The XY plot shape had a radius of approximately 100mm. As with the *Kapton* construction, the plot was not centered which was attributed to the asymmetric behaviour due to the seam in the polyimide sleeve.

Variable Length of the Actuator

Since this device has a variable length it is not limited in its workspace to the hollow hemisphere in Fig.4.3. This means that in comparison to other devices without this capability the workspace is a much greater proportion of the hemisphere than a device without length variability. In medical engineering, this is an improvement on traditional surgical catheters that need to be retracted through the patient causing large shear forces on the surrounding surfaces in the body. In this polyimide-sleeved device, the retraction occurs within the body of the device to "improve patient comfort".

Another workspace based experiment was conducted in which the same multiaxial actuation was used to manouver the tip of the device. This was conducted at three different lengths: 60 mm, 90mm and 120mm in the *Kapton with Nitinol* contruction. In the XY plane with an actuator length of 60mm, the trajectory was generally triangular with three distinct points roughly 120mm apart. As the length of the device was increased, the shape of the trajectory was observed to become more circular with a radius approximately equal to the device length. It can be observed that there was a rotation in the trajectory of the plots as the length changed. This occured as a cable gland clamped the silicon actuation device to the desired length and the tightening rotation also caused a slight rotation in the actuator. Data was also collected for the other stiffness constuctions, however the trends in the data were the same.

4.2.4 Navigation

Notes: tip tracking versus time

To demonstrate the robots ability to navigate an arbitrary path, a route was set up using 3D printed obstacles to simulate a path that a real world use case could need. The goal of the path was to show that fluid could be delivered through a channel in the silicon inner tube.




Figure 4.6: caption

This path started shorted than the relaxed length of the actuator and so required the operator to pull on the silicon tube to retract the device before steering the device using the tendons.

Extending the device further than the relaxed length was difficult due to the soft the silicon tube buckling under compression. This meant that the maximum path length was limited to around 120mm.

Practically the effects of the stiffness of the bellows are felt, when we use our device for naviagation we found that retracting the silicon and extending is by pushing it was easy until the relaxed point. After this, overcoming the force of the sleeve pushing back on the silicon actuation device causes buckling internally due to the lack of rigidity of the silicon tube.

The introduction of a pressurised approach to controlling the locomotion of the device is beyond the scope of this

The device successfully navigated the pre-planned path taking x seconds to complete the x cm journey achieving a tip angle of 30°.

4.2.5 Clinical Case Study: Drug Delivery in Stomach

Finally, we demonstrate the use of the bellows based actuator in a stomach training simulator for the application of targeted drug delivery. Here we use the same assembly as the previous navigations with the addition of water to simulate the drug delivery. We use an external camera (camera details) inserted through a separate entry into the stomach to give an approximate location for completing the navigations.

The device was inserted into the stomach phantom in its shortest state

4.3 Methodology

4.3.1 Stiffness Characterisation

To characterise the stiffness profile, a linear stage was used with a load cell (brand) held in a SmallRig Magic Arm. This was attached to the end of the polyimide sleeve which was clamped in a 3D printed stand. The whole experimental setup was attached to a ThorLabs Breadboard. The linear stage was set to 60mm (the resting length of the actuator was 120mm, the linear stage is in reverse so to get to 60mm, the linear displacement is 90) and the load cell was zeroed. The load cell was moved to 150mm (actuator length is 20mm compressed) and then the linear stage was set to go to 0mm at 0.5mm s^{-1}. This contained a compression force and a stretching force. The speed of the actuator was translated into the displacement using:

$$v = \frac{d}{t}$$

. The load cell data was collected using DSCUSB Toolkit and processed in python.

4.3.2 Temperature Stability of the Polyimide Sleeve

Using the same experimental set-up as the stiffness characterisation. The kapton® sleeve was placed in an oven at 200°C for 1 hour, left to cool and then compressed and stretched as before.

4.3.3 Workspace Characterisation

To characterise the usable workspace of the device, an experiment was set-up with the four camera Optitrack system and Motive 2.3 software to track the tip position of the device in 3D space with submillimeter accuracy (mean error: value). When assembled,

the device was not very predictably controllable partially due to the additional weight at the tip of the added cable gland. This meant that the actuator size exculsion filter

4.3.4 Moulding of polyamic acid

Polyamic acid undergoes an imidisation reaction at 150-200° to form Kapton. It shoudl, in theory be prossible to pour the polyamic acid into a mould and heat to form Kapton. This was attempted by pouring the PAA into a mould and heating to 150°C for 20 mins to cause imidisation. This was repeated after placing half the mould into the smartvap with a 3D printed adaptor. The smartvap heats the sample and blows a stream of air into a vortex over a sample to remove the solvent. This was performed for a week before then heating the sample to 150°C for 1 hour.

4.3.5 Moulding of Polyamic Acid

Polyamic acid in NMP (stats) was poured into a Cone-shaped mould. This was assembled with a 3D printed part to connect to the SmartVap (Supplier) for 1 week at 100°C. This reduced the volume and made the liquid a darker brown. This was heated to 150°C for 1 hour to cause imidisation before being extracted from the mould with a scalpel. This experiment was also repeated without drying off the solvent first. Undergoes thermal imidisation

Chapter 5

Conclusion

Hydrolysis was attempted with minimal success due to low concentration of basic reagent. Crosslinking was attempted but due to the competition of the intramolecular imidisation this was unsuccessful. A reduction in the temperature of the imidisation process was shown to occur with $ZnCl_2$ as a catalyst, this could have implications towards a greener production of Kapton due to a 40°C decrease in temperature.

An actuator constructed from Kapton was shown to withstand temperatures of 200°C with no loss in capability, it has a hemispherical workspace of radius x and it successfully navigated an arbitrary path of length x, achieving a tip angle of x. When in a stomach training simulator, the device navigated and deployed targeted liquid drug simulation via an internal channel in the actuator.

The combined contributions of the chemistry and the robotics has the potential to extend the capability of the device

This work demonstrates steps towards a novel high resistance material for use in soft robotic applications with broad applications in both medical and space fields.

Futture work would attempt functionalisation at a different place on the polyimide chain. The structure contains an oxydiphenyl ether structure that could provide locations for

additional functionalisation pre-polymerisation, when in the monomer stage. This would avoid the challenges presented with the thermal imidisation. Alterations of the folding pattern of the polyimide sleeve to adopt an accordion pattern based in right angle triangles to limit crease-based damage due to non-compressibility. Other manufacturing approaches such as spin casting on a preshaped mould would make a homogeneous surface and therefore there would be no anisotropic behaviour. Development of a control platform through modelling and the addition of hardware in order to navigate with greater precision. This would involve linearly actuated tendons and pressurised airsupply and vacuum chamber in order to control the devices locomotion and tip bending.

Bibliography

[1] Matteo Cianchetti, Tommaso Ranzani, Giada Gerboni, Thrishantha Nanayakkara, Kaspar Althoefer, Prokar Dasgupta, and Arianna Menciassi. Soft robotics technologies to address shortcomings in today's minimally invasive surgery: the stiff-flop approach. *Soft Robotics*, **1**(2):122–131, 2014. [17/10/2025]. Available from: 10.1089/soro.2014.0001.

[2] Pei-Yu Wu, Ching-Hsuan Lin, and Chih-Ming Chen. Study of surface metallization of polyimide film and interfacial characterization. *Metals*, 7(6):189, 2017.

[3] Kevin M Lynch and Frank C Park. *Modern robotics*. Cambridge University Press, 2017. [01/10/2025]. Available from: 10.1017/9781316661239.

[4] Elliot W Hawkes, Laura H Blumenschein, Joseph D Greer, and Allison M Okamura. A soft robot that navigates its environment through growth. *Science Robotics*, **2**(8):eaan3028, 2017. [16/10/2025]. Available from: 10.1126/scirobotics.aan3028.

[5] Joshua Davy, Thomas P Dean, Nikita J Greenidge, Benjamin Calmé, Peter Lloyd, James H Chandler, and Pietro Valdastri. Magnetic fluid-driven vine robots for minimally invasive tissue biopsy sampling. *Advanced Intelligent Systems*, **7**:2400827, 2025. [16/10/2025]. Available from: 10.1002/aisy.202400827.

[6] VV Anderson. Tenser arm manipulator design. *ASME Trans.*, 67:1–12, 1967. [10/10/2025].

[7] Peter Lloyd, Ali Kafash Hoshiar, Tomas Da Veiga, Aleks Attanasio, Nils Marahrens, James Henry Chandler, and Pietro Valdastri. A learnt approach for the de-

sign of magnetically actuated shape forming soft tentacle robots. *IEEE Robotics and Automation Letters*, **5**(3):3937–3944, 2020. [16/10/2025]. Available from: 10.1109/LRA.2020.2983704.

[8] Filip Ilievski, Aaron D Mazzeo, Robert F Shepherd, Xin Chen, and George M Whitesides. Soft robotics for chemists. *Angewandte Chemie International Edition*, **50**(8):1890–1895, 2011. [01/10/2025]. Available from: 10.1002/ange.201006464.

[9] Jianglong Guo, Khaled Elgeneidy, Chaoqun Xiang, Niels Lohse, Laura Justham, and Jonathan Rossiter. Soft pneumatic grippers embedded with stretchable electroadhesion. *Smart Materials and Structures*, **27**(5):055006, 2018. [17/10/2025]. Available from: 10.1088/1361-665X/aab579.

[10] Matteo Russo, Seyed Mohammad Hadi Sadati, Xin Dong, Abdelkhalick Mohammad, Ian D Walker, Christos Bergeles, Kai Xu, and Dragos A Axinte. Continuum robots: An overview. *Advanced Intelligent Systems*, **5**(5):2200367, 2023. [02/10/2025]. Available from: 10.1002/aisy.202200367.

[11] Joshua Davy, Nikita J Greenidge, Sukjun Kim, Luke J Tinsley, Peter Lloyd, James H Chandler, Russell A Harris, Tania K Morimoto, and Pietro Valdastri. Vine robots with magnetic skin for surgical navigations. *IEEE Robotics and Automation Letters*, **9**(8):6888–6895, 2024. [16/10/2025]. Available from: 10.1109/LRA.2024.3412637.

[12] Daniela Rus and Michael T Tolley. Design, fabrication and control of soft robots. *Nature*, **521**(7553):467–475, 2015. [02/10/2025]. Available from: 10.1038/nature14543.

[13] Haider Abidi and Matteo Cianchetti. On intrinsic safety of soft robots. *Frontiers in Robotics and AI*, **4**:5, 2017. [10/10/2025]. Available from: 10.3389/frobt.2017.00005.

[14] Xinyu Guo, Wenbo Li, Fuyi Fang, Huyue Chen, Linchuan Zhao, Xiaoyong Fang, Zhiran Yi, Lei Shao, Guang Meng, and Wenming Zhang. Encoded sewing soft textile robots. *Science Advances*, **10**(1):eadk3855, 2024. [17/10/2025]. Available from: 10.1126/sciadv.adk3855.

[15] Thomas P Dean, Joshua Davy, Jane Scott, Pietro Valdastri, and James H Chandler. Anisotropic 3d-knitted sleeves as inverse pneumatic artificial muscles for soft and wearable robotics. In *2025 IEEE 8th International Conference on Soft Robotics (RoboSoft)*, pages 1–6. IEEE, 2025. [17/10/2025]. Available from: 10.1109/RoboSoft63089.2025.11020963.

[16] Ruchir Shanker Srivastav and Aarti P More. A comprehensive review of self-healing polymers: Mechanisms, types, and industry implications. *Polymers for Advanced Technologies*, **36**(2):e70092, 2025. [10/10/2025]. Available from: 10.1002/pat.70092.

[17] Wolfgang H Binder. *Self-healing polymers: from principles to applications*. John Wiley & Sons, 2013.

[18] Seppe Terryn, Jakob Langenbach, Ellen Roels, Joost Brancart, Camille Bakkali-Hassani, Quentin-Arthur Poutrel, Antonia Georgopoulou, Thomas George Thuruthel, Ali Safaei, Pasquale Ferrentino, et al. A review on self-healing polymers for soft robotics. *Materials Today*, **47**:pp.187–205, 2021. [01/10/2025]. Available from: 10.1016/j.mattod.2021.01.009.

[19] Scott R White, Nancy R Sottos, Philippe H Geubelle, Jeffrey S Moore, Michael R Kessler, SR Sriram, Eric N Brown, and S Viswanathan. Autonomic healing of polymer composites. *Nature*, 409(6822):794–797, 2001.

[20] Scott R Trenor, Allan R Shultz, Brian J Love, and Timothy E Long. Coumarins in polymers: from light harvesting to photo-cross-linkable tissue scaffolds. *Chemical reviews*, 104(6):3059–3078, 2004.

[21] Pablo Froimowicz, Daniel Klinger, and Katharina Landfester. Photoreactive nanoparticles as nanometric building blocks for the generation of self-healing hydrogel thin films. *Chemistry–A European Journal*, 17(44):12465–12475, 2011.

[22] Jie Guo. *Diels-Alder chemistry: An old workhorse for new self-healing nanocomposites and adhesives*. PhD thesis, University of Groningen, 2025. [12/10/2025]. Available from: 10.33612/diss.1198671697.

[23] Kyriacos Costa Nicolaou, Scott A Snyder, Tamsyn Montagnon, and Georgios Vassilikogiannakis. The diels–alder reaction in total synthesis. *Angewandte Chemie International Edition*, 41(10):1668–1698, 2002.

[24] Ying Yang and Marek W Urban. Self-healing of polymers via supramolecular chemistry. *Advanced Materials Interfaces*, **5**(17):1800384, 2018. [12/10/2025]. Available from: 10.1002/admi.201800384.

[25] Shiwanka V Wanasinghe, Obed J Dodo, and Dominik Konkolewicz. Dynamic bonds: adaptable timescales for responsive materials. *Angewandte Chemie*, 134(50):e202206938, 2022.

[26] Chirag R Ratwani, Ali Reza Kamali, and Amr M Abdelkader. Self-healing by diels-alder cycloaddition in advanced functional polymers: A review. *Progress in Materials Science*, **131**:101001, 2023. [02/10/2025]. Available from: 10.1016/j.pmatsci.2022.101001.

[27] Benoit Briou, Bruno Améduri, and Bernard Boutevin. Trends in the diels–alder reaction in polymer chemistry. *Chemical Society Reviews*, **50**(19):11055–11097, 2021. [01/10/2025]. Available from: 10.1039/D0CS01382J.

[28] David Huertas, Melinda Florscher, and Veljko Dragojlovic. Solvent-free diels–alder reactions of in situ generated cyclopentadiene. *Green Chemistry*, 11(1):91–95, 2009.

[29] Jinhui Li, Guoping Zhang, Libo Deng, Songfang Zhao, Yongju Gao, Kun Jiang, Rong Sun, and Chingping Wong. In situ polymerization of mechanically reinforced, thermally healable graphene oxide/polyurethane composites based on diels–alder chemistry. *Journal of Materials Chemistry A*, 2(48):20642–20649, 2014.

[30] Bryan Ingoglia. Microencapsulation of diels-alder monomers in self-healing materials. *Kaleidoscope*, 11(1):43, 2014.

[31] Devatha P Nair, Maciej Podgorski, Shunsuke Chatani, Tao Gong, Weixian Xi, Christopher R Fenoli, and Christopher N Bowman. The thiol-michael addition click

reaction: a powerful and widely used tool in materials chemistry. *Chemistry of Materials*, **26**(1):724–744, 2014. [06/10/2025]. Available from: 10.1021/cm402180t.

[32] Natascha Kuhl, Robert Geitner, Ranjita K Bose, Stefan Bode, Benjamin Dietzek, Michael Schmitt, Jürgen Popp, Santiago J Garcia, Sybrand van der Zwaag, Ulrich S Schubert, et al. Self-healing polymer networks based on reversible michael addition reactions. *Macromolecular Chemistry and Physics*, **217**(22):2541–2550, 2016. [10/10/2025].
Available from: 10.1002/macp.201600353.

[33] Stefano Burattini, Barnaby W Greenland, Wayne Hayes, Michael E Mackay, Stuart J Rowan, and Howard M Colquhoun. A supramolecular polymer based on tweezer-type π–π stacking interactions: Molecular design for healability and enhanced toughness. *Chemistry of Materials*, **23**(1):6–8, 2011. [15/10/2025]. Available from: 10.1021/cm102963k.

[34] Xin Yuan, Xiangyu Lin, Fuhao Dong, Xujuan Huang, He Liu, and Xu Xu. Self-healed, tough, and highly resilient elastomer facilitated by cooperative hydrogen-bonding interaction and π–π stacking interaction. *ACS Applied Polymer Materials*, **7**(3):1328–1337, 2025. [16/10/2025]. Available from: 10.1021/acsapm.4c03053.

[35] Jin-Feng Mei, Xiao-Yong Jia, Jian-Cheng Lai, Yang Sun, Cheng-Hui Li, Jun-Hua Wu, Yi Cao, Xiao-Zeng You, and Zhenan Bao. A highly stretchable and autonomous self-healing polymer based on combination of pt···pt and π–π interactions. *Macromolecular Rapid Communications*, **37**(20):1667–1675, 2016. [15/10/2025]. Available from: 10.1002/marc.201600428.

[36] R Adam Bilodeau and Rebecca K Kramer. Self-healing and damage resilience for soft robotics: A review. *Frontiers in Robotics and AI*, **4**:48, 2017. [01/10/2025]. Available from: 10.3389/frobt.2017.00048.

[37] Ellen Roels, Seppe Terryn, Joost Brancart, Guy Van Assche, and Bram Vanderborght. A multi-material self-healing soft gripper. In *2019 2nd IEEE International*

Conference on Soft Robotics (RoboSoft), pages 316–321. IEEE, 2019. [16/10/2025]. Available from: 10.1109/ROBOSOFT.2019.8722781.

[38] Seppe Terryn, Joost Brancart, Ellen Roels, Guy Van Assche, and Bram Vanderborght. Room temperature self-healing in soft pneumatic robotics: Autonomous self-healing in a diels–alder polymer network. *IEEE Robotics & Automation Magazine*, **27**(4):44–55, 2020. [16/10/2025].
Available from: 10.1109/MRA.2020.3024275.

[39] Seppe Terryn, Joost Brancart, Dirk Lefeber, Guy Van Assche, and Bram Vanderborght. A pneumatic artificial muscle manufactured out of self-healing polymers that can repair macroscopic damages. *IEEE Robotics and Automation Letters*, **3**(1):16–21, 2017. [17/10/2025].
Available from: 10.1109/LRA.2017.2724140.

[40] Antonio López-Díaz, Ana Martín-Pacheco, Alicia Naranjo, Cristina Martín, M Antonia Herrero, Ester Vázquez, and Andrés S Vázquez. Autonomous self-healing pneumatic mckibben muscle based on a new hydrogel material. In *2020 3rd IEEE International Conference on Soft Robotics (RoboSoft)*, pages 13–18. IEEE, 2020. [16/10/2025]. Available from: 10.1109/RoboSoft48309.2020.9115992.

[41] Seyedreza Kashef Tabrizian, Seppe Terryn, and Bram Vanderborght. Toward autonomous self-healing in soft robotics: A review and perspective for future research. *Advanced Intelligent Systems*, **7**(8):2400790, 2025. [16/10/2025]. Available from: 10.1002/aisy.202400790.

[42] Lori E Stephans, Anthony Myles, and Richard R Thomas. Kinetics of alkaline hydrolysis of a polyimide surface. *Langmuir*, 16(10):4706–4710, 2000.

[43] Richard R Thomas, Stephen L Buchwalter, L Paivikki Buchwalter, and Taina H Chao. Organic chemistry on a polyimide surface. *Macromolecules*, 25(18):4559–4568, 1992.

[44] Miro M Plechaty and Richard R Thomas. Chemical surface-modification of a polyimide: Characterization and a kinetic study on the diffusion of ions in a modified polymer. *Journal of the Electrochemical Society*, 139(3):810–821, 1992.

[45] Wei-Ping Dow, Guo-Liang Liao, Shang-En Huang, and Sinn-Wen Chen. Modification of cu nanoparticles with a disulfide for polyimide metallization. *Journal of Materials Chemistry*, 20(18):3600–3609, 2010.

[46] Tzu-Jung Liu, Chien-Han Chen, Pei-Yu Wu, Ching-Hsuan Lin, and Chih-Ming Chen. Efficient and adhesiveless metallization of flexible polyimide by functional grafting of carboxylic acid groups. *Langmuir*, 35(22):7212–7221, 2019.

[47] G Xue. Studies of etching mechanism of polyimide films on silicon chips. *Die Angewandte Makromolekulare Chemie: Applied Macromolecular Chemistry and Physics*, 142(1):61–68, 1986.

[48] Nancy C Stoffel, Meng Hsieh, Sweta Chandra, and Edward J Kramer. Surface modification studies of polyimide films using rutherford backscattering and forward recoil spectrometry. *Chemistry of materials*, 8(5):1035–1041, 1996.

[49] Charmian O'Connor. Acidic and basic amide hydrolysis. *Quarterly Reviews, Chemical Society*, 24(4):553–564, 1970.

[50] M Niyaz Khan. Kinetics and mechanism of the alkaline hydrolysis of maleimide. *Journal of pharmaceutical sciences*, 73(12):1767–1771, 1984.

[51] J Moens and G Smets. Alkaline and acid hydrolysis of polyvinylamides. *Journal of Polymer Science*, 23(104):931–948, 1957.

[52] Jin-Hae Chang, Kwang Min Park, Soo-Min Lee, and Jae Buem Oh. Two-step thermal conversion from poly (amic acid) to polybenzoxazole via polyimide: Their thermal and mechanical properties. *Journal of Polymer Science Part B: Polymer Physics*, 38(19):2537–2545, 2000.

[53] So-Yeop Han and Young-Ah Kim. Recent development of peptide coupling reagents in organic synthesis. *Tetrahedron*, 60(11):2447–2467, 2004.

[54] GS Johar. Detection of carboxylic acid group in organic compounds with eosin, mercurochrome, and methylene blue. *Fresenius' Zeitschrift für analytische Chemie*, 260(2):122–123, 1972.

[55] Faiz Salih Abbas, Azhar S Alaboodi, and Ali Abid Abojassim. Studying the effect of the solvent on the spectral properties of the eosin-y dye that used as medical laser medium. *Cardiometry*, -(25):1463–1467, 2022.

[56] Moumita Chakraborty and Amiya Kumar Panda. Spectral behaviour of eosin y in different solvents and aqueous surfactant media. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 81(1):458–465, 2011.

[57] Lihong Yu, Zhongfang Liu, Shaopu Liu, Xiaoli Hu, and Linfeng Liu. Fading spectrophotometric method for the determination of polyvinylpyrrolidone with eosin y. *Chinese Journal of Chemistry*, 27(8):1505–1509, 2009.

[58] A Ghanadzadeh Gilani, M Salmanpour, and T Ghorbanpour. Solvatochromism, dichroism and excited state dipole moment of azure a and methylene blue. *Journal of Molecular Liquids*, 179:118–123, 2013.

[59] Leonardo Marmo Moreira, Juliana Pereira Lyon, Adriana Lima, Lúcia Codognoto, Divinomar Severino, Maurício da Silva Baptista, Andre Luiz Tessaro, Adriana Passarela Gerola, Noboru Hioka, Maira Regina Rodrigues, et al. The methylene blue self-aggregation in water/organic solvent mixtures: Relationship between solvatochromic properties and singlet oxygen production. *Orbital: The Electronic Journal of Chemistry*, pages 279–289, 2017.

[60] Sokaina Saad Hemdan. The shift in the behavior of methylene blue toward the sensitivity of medium: Solvatochromism, solvent parameters, regression analysis and investigation of cosolvent on the acidity constants. *Journal of Fluorescence*, 33(6):2489–2502, 2023.

[61] Olga Tchaikovskaya, Vlada Chaidonova, Elena Bocharnikova, Evgeny Telminov, Natalia Dmitrieva, and Dmitry Ezhov. Solvent effect on the spectra of methylene green and methylene blue. *Journal of Fluorescence*, 33(2):685–695, 2023.

[62] Fan Lin, Wei Fan, and Gary E Wise. Eosin y staining of proteins in polyacrylamide gels. *Analytical biochemistry*, 196(2):279–283, 1991.

[63] EA Slyusareva, FN Tomilin, AG Sizykh, E Yu Tankevich, AA Kuzubov, and SG Ovchinnikov. The effect of halogen substitution on the structure and electronic spectra of fluorone dyes. *Optics and Spectroscopy*, 112(5):671–678, 2012.

[64] Teruo Yoshino, Shigeru Inaba, Hajime Komura, and Yoshiharu Ishido. Synthetic studies with carbonates. part 6. syntheses of 2-hydroxyethyl derivatives by reactions of ethylene carbonate with carboxylic acids or heterocycles in the presence of tetraethylammonium halides or under autocatalytic conditions. *Journal of the Chemical Society, Perkin Transactions 1*, 1(11):1266–1272, 1977.

[65] David R Fagerburg. Reaction kinetics of the model reaction of benzoic acid with ethylene carbonate. *Journal of Macromolecular Science—Chemistry*, 21(2):141–154, 1984.

[66] David R Fagerburg. Reaction kinetics of the reaction of terephthalic acid and ethylene carbonates. *Journal of applied polymer science*, 30(9):3617–3623, 1985.

[67] Nils von Seggern, Tamara Schindler, and Stefan Naumann. Dual catalytic ring-opening polymerization of ethylene carbonate for the preparation of degradable peg. *Biomacromolecules*, 21(7):2661–2669, 2020.

[68] Bruno Fortunato, Paolo Mirone, and Glancaelo Fini. Infrared and raman spectra and vibrational assignment of ethylene carbonate. *Spectrochimica Acta Part A: Molecular Spectroscopy*, 27(9):1917–1927, 1971.

[69] Haitao Qing, Sravanthi Vallabhuneni, Yinding Chi, Mohammad Javad Zarei, Pouya Sharbati, Haoze Sun, Jie Yin, and Arun Kumar Kota. Enhancing soft robots with chemical shielding for harsh corrosive liquid environments. *Materials Horizons*, 2026.

[70] Jared Butler, Jessica Morgan, Nathan Pehrson, Kyler Tolman, Terri Bateman, Spencer P Magleby, and Larry L Howell. Highly compressible origami bellows for harsh environments. In *International design engineering technical conferences and computers and information in engineering conference*, volume 50169, page V05BT07A001. American Society of Mechanical Engineers, 2016.

[71] CE Sroog, AL Endrey, S Ve Abramo, CE Berr, WM Edwards, and KL Olivier. Aromatic polypyromellitimides from aromatic polyamic acids. *Journal of Polymer Science Part A: General Papers*, 3(4):1373–1390, 1965.

[72] Ravindra Masana, Ahmed S Dalaq, Shadi Khazaaleh, and Mohammed F Daqaq. The kresling origami spring: a review and assessment. *Smart Materials and Structures*, 33(4):043002, 2024.

[73] Ji Zhang, Jintong Chen, Xizi Zhang, Shuai Liu, and Changguo Wang. A review of kresling origami: Smart design, mechanics, and applications. *Engineering Structures*, 345:121499, 2025.

[74] Anastasia L Wickeler, Kyra McLellan, Yu-Chen Sun, and Hani E Naguib. 4d printed origami-inspired accordion, kresling and yoshimura tubes. *Journal of Intelligent Material Systems and Structures*, 34(20):2379–2392, 2023.

[75] Austin Reid, Frederic Lechenault, Sergio Rica, and Mokhtar Adda-Bedia. Geometry and design of origami bellows with tunable response. *Physical Review E*, 95(1):013002, 2017.

[76] Jong-Eun Suh, Tae-Hyun Kim, and Jae-Hung Han. New approach to folding a thin-walled yoshimura patterned cylinder. *Journal of Spacecraft and Rockets*, 58(2):516–530, 2021.

[77] Qianying Chen, Fan Feng, Pengyu Lv, and Huiling Duan. Origami spring-inspired shape morphing for flexible robotics. *Soft Robotics*, 9(4):798–806, 2022.

[78] Josephine Granna and Jessica Burgner. Characterizing the workspace of concentric tube continuum robots. In *ISR/Robotik 2014; 41st International Symposium on Robotics*, pages 1–7. VDE, 2014.