


Plasticizers & Raw Materials Portfolio

Asia Petrochemicals LLC



High Performance PVC & Polymer Solutions

About Asia Petrochemicals

Asia Petrochemicals LLC was established in 1989 in the UAE with a strong vision to expand its footprint in manufacturing, trading, distribution and storage of petrochemicals, petroleum products, fuels and polymers. Our operations support pharmaceuticals, lubricants, paints & coatings, adhesives, food packaging, plastics and foam manufacturing industries. Our state-of-the-art ester production facility in Ras Al Khaimah has an installed capacity of 36,000 MTPA of various acetates and integrates storage terminals for both feedstock and finished products. With consistent growth and strategic global partnerships, Asia Petrochemicals continues to deliver reliability, quality and performance.

Dioctyl Phthalate (DOP)

CAS No: 117-81-7

A colorless transparent oily liquid widely used in processing of PVC resins, chemical fiber resins, acetate resins, ABS resins and rubber. Suitable for lacquer, dyes, dispersants, wires and cables.

Characteristic	Standard
Appearance	Colourless, Clear Liquid
Ester Content	$\geq 99.5\%$
Specific Gravity @25°C	0.982 – 0.986
Moisture Content	$\leq 0.10\%$
Volatile Loss	$\leq 0.10\%$

Dioctyl Terephthalate (DOTP)

CAS No: 6422-86-2

Low volatility plasticizer used for cable materials and artificial leather films. Excellent compatibility with PVC and synthetic rubber. Preferred for high performance flexible applications.

Characteristic	Standard
Appearance	Colourless, Clear Liquid
Ester Content	≥ 99.5%
Specific Gravity @25°C	0.980 – 0.985
Moisture Content	≤ 0.10%
Volatile Loss	≤ 0.10%

2-Ethylhexanol

CAS No: 104-76-7

Primarily used as a raw material for PVC plasticizers and as a solvent and preservative. Widely used in production of phthalate esters and petroleum additives for plastics and coatings industries.

Characteristic	Standard
Purity (Assay)	≥ 99.5%
Specific Gravity @20°C	0.832 – 0.834
Moisture Content	≤ 0.10%
Distillation Range	183 – 186°C