

|                                 |                                            |
|---------------------------------|--------------------------------------------|
| <b>Product Name:</b>            | <b>BT-60</b>                               |
| <b>Product Type:</b>            | Integrally Formed Triaxial Geogrid         |
| <b>Polymer:</b>                 | Polypropylene                              |
| <b>Load Transfer Mechanism:</b> | Positive Mechanical Interlock              |
| <b>Primary Applications:</b>    | Base Reinforcement, Subgrade Stabilization |

**PRODUCT PROPERTIES<sup>1</sup>**

| Index Properties                              | Test Method | Units        | Values <sup>1</sup> |
|-----------------------------------------------|-------------|--------------|---------------------|
| » Aperture Shape                              |             |              | TRIANGULAR          |
| » Rib Shape                                   |             |              | RECTANGULAR         |
| » Rib Pitch <sup>2</sup>                      | MEASURED    | in (mm)      | 1.6 (40.0)          |
| » Mid Rib Thickness <sup>2</sup>              | MEASURED    | in (mm)      | 0.06 (1.52)         |
| » Mid Rib Width <sup>2</sup>                  | MEASURED    | in (mm)      | 0.08 (2.0)          |
| » Radial Stiffness @ 0.5% Strain <sup>3</sup> | ASTM D6637  | lb/ft (kN/m) | 21,500 (314)        |

**Structural Integrity**

|                       |                    |           |     |
|-----------------------|--------------------|-----------|-----|
| » Junction Efficiency | ASTM D6637 & D7737 | %         | 93  |
| » Aperture Stability  | ASTM D7864         | kg-cm/deg | 3.6 |

**Durability**

|                                       |            |   |     |
|---------------------------------------|------------|---|-----|
| » Resistance to Long Term Degradation | EPA 9090   | % | 100 |
| » Resistance to UV Degradation        | ASTM D4355 | % | 100 |

**Dimensions**

|                       | Length ft (m) | Width ft (m) |
|-----------------------|---------------|--------------|
| » Standard Roll Sizes | 246 (75)      | 12.5 (3.81)  |
|                       | 246 (75)      | 16 (4.88)    |

**Dimensions & Delivery**

The Triaxial geogrid shall be delivered to the job site in roll form with each roll individually identified. **Roll sizes depend on availability at time of order.**

**Notes:**

1. Unless indicated otherwise, values shown are Minimum Average Roll Values (MARV) in accordance with ASTM D4759.
2. Nominal Dimensions.
3. Determined in accordance with ASTM D6637 Method B



**Industrial Fabrics, Inc.**  
510 O'Neal Lane Ext  
Baton Rouge LA 70819  
800 848 4500  
[www.baselok.com](http://www.baselok.com)

Customer should verify with the product manufacturer that customer has the most current **BASELOK® GEOGRID** specifications for the product ordered or purchased. The **BASELOK® GEOGRID** system can be used in the application described in our literature and on our website, provided proper installation and engineering principles are followed. Professional engineering should be consulted before installation of **BASELOK® GEOGRID** units to assure appropriate design and use. ALL EXPRESSED OR IMPLIED WARRANTIES, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE DISCLAIMED. **BASELOK®** is a trademark of Industrial Fabrics, Inc.