



Product Name: BT-60
Product Type: Integrally Formed Triaxial Geogrid
Polymer: Polypropylene
Load Transfer Mechanism: Positive Mechanical Interlock
Primary Applications: Base Reinforcement, Subgrade Stabilization

PRODUCT PROPERTIES¹

Index Properties	Test Method	Units	Values ¹
» Aperture Shape			TRIANGULAR
» Rib Shape			RECTANGULAR
» Rib Pitch ²	MEASURED	in (mm)	1.6 (40.0)
» Mid Rib Thickness ²	MEASURED	in (mm)	0.06 (1.52)
» Mid Rib Width ²	MEASURED	in (mm)	0.08 (2.0)
» Radial Stiffness @ 0.5% Strain ³	ASTM D6637	lb/ft (kN/m)	21,500 (314)

Structural Integrity

» Junction Efficiency	ASTM D6637 & D7737	%	93
» Aperture Stability	ASTM D7864	kg-cm/deg	3.6

Durability

» Resistance to Long Term Degradation	EPA 9090	%	100
» Resistance to UV Degradation	ASTM D4355	%	100

Dimensions

	Length ft (m)	Width ft (m)
» Standard Roll Sizes	246 (75)	12.5 (3.81)
	246 (75)	16 (4.88)

Dimensions & Delivery

The Triaxial geogrid shall be delivered to the job site in roll form with each roll individually identified. **Roll sizes depend on availability at time of order.**

Notes:

1. Unless indicated otherwise, values shown are Minimum Average Roll Values (MARV) in accordance with ASTM D4759.
2. Nominal Dimensions.
3. Determined in accordance with ASTM D6637 Method B



Industrial Fabrics, Inc.
 510 O'Neal Lane Ext.
 Baton Rouge, LA 70819
 800 848 4500
 baselok.com

Customer should verify with the product manufacturer that customer has the most current **BASELOK® GEOGRID** specifications for the product ordered or purchased. The **BASELOK® GEOGRID** system can be used in the application described in our literature and on our website, provided proper installation and engineering principles are followed. Professional engineering should be consulted before installation of **BASELOK® GEOGRID** units to assure appropriate design and use. ALL EXPRESSED OR IMPLIED WARRANTIES, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE DISCLAIMED. **BASELOK®** is a trademark of Industrial Fabrics, Inc.