


Product Name: BX2020
Product Type: Integrally Formed Biaxial Geogrid
Polymer: Polypropylene
Load Transfer Mechanism: Positive Mechanical Interlock
Primary Applications: Base Reinforcement, Subgrade Stabilization



PRODUCT PROPERTIES¹

Index Properties	Test Method	Units	MD Values ¹	XMD Values ¹
» Aperture Dimensions ²		in (mm)	1.5 (38)	1.5 (38)
» Minimum Rib Thickness ²		in (mm)	0.04 (1.1)	0.03 (0.8)
» Tensile Strength @ 2% Strain ³	ASTM D6637	lb/ft (kN/m)	450 (6.5)	450 (6.5)
» Tensile Strength @ 5% Strain ³	ASTM D6637	lb/ft (kN/m)	890 (13)	890 (13)
» Ultimate Tensile Strength ³	ASTM D6637	lb/ft (kN/m)	1,370 (20)	1,370 (20)
» Radial Stiffness @ 0.5% Strain ³	ASTM D6637	lb/ft (kN/m)		24,000 (350)

Structural Integrity

» Junction Efficiency	ASTM D6637 & D7737	%	93
» Overall Flexural Stiffness	ASTM D7748	mg-cm	700,000
» Aperture Stability	ASTM D7864	m-N/deg	0.45

Durability

» Resistance to Installation Damage	ASTM D6637 & D5818	%SC / %SW / %GP	95 / 93 / 90
» Resistance to Long Term Degradation	EPA 9090	%	100
» Resistance to UV Degradation	ASTM D4355	%	100

Dimensions

	Length ft (m)	Width ft (m)
» Standard Roll Sizes	328 (100)	12.5 (3.81)
	328 (100)	16 (4.88)

Dimensions & Delivery

The biaxial geogrid shall be delivered to the job site in roll form with each roll individually identified. **Roll sizes depend on availability at time of order.**

Notes:

1. Unless indicated otherwise, values shown are Minimum Average Roll Values (MARV) in accordance with ASTM D4759.
2. Nominal Dimensions.
3. Determined in accordance with ASTM D6637 Method B



Industrial Fabrics, Inc.
 510 O'Neal Lane Ext.
 Baton Rouge, LA 70819
 800 848 4500
 baselok.com