



id	authors	geometry_type	geometry_label	geometry_data_type	geometry_data	constituent_material_1	constituent_material_2	materials_label	constituent_material_1_poissons_ratio	constituent_material_2_poissons_ratio	constituent_material_1_youngs_modulus_value	constituent_material_1_youngs_modulus_unit	constituent_material_2_youngs_modulus_value	constituent_material_2_youngs_modulus_unit	effective_poissons_ratio	effective_youngs_modulus	effective_youngs_modulus_unit
i_s_00000001	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,0,0,0	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.33	2.00E+09	Pa
i_s_00000002	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,0,0,0	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.306472	1.80E+09	Pa
i_s_00000003	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,0,0,1	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.317484	1.82E+09	Pa
i_s_00000004	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,0,0,1	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.314845	1.43E+09	Pa
i_s_00000005	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,0,1,0	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.312472	1.59E+09	Pa
i_s_00000006	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,0,1,0	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.292545	1.54E+09	Pa
i_s_00000007	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,0,1,1	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.312935	1.53E+09	Pa
i_s_00000008	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,0,1,1	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.276555	1.05E+09	Pa
i_s_00000009	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,1,0,0	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.308478	1.65E+09	Pa
i_s_00000010	Caltech	C4v	geometry type 2c	embedded	0,0,0,0,0,0,0,0,0,1,0,0	vero_white	tango_black	first material is m	0.33	0.49	2.00E+09	Pa	2.00E+06	Pa	0.288084	1.55E+09	Pa



metamine .kg.setl.ttl

```
@prefix materialsmine: <http://materialsmine.org/> .
@prefix prov: <http://www.w3.org/ns/prov#> .
@prefix rdfs: <http://www.w3.org/2000/01/rdf-schema#> .
@prefix sio: <http://semanticscience.org/resource/> .

materialsmine:i_s_00000001 a materialsmine:Metamaterial ;
    sio:hasAttribute <http://materialsmine.org/i_s_00000001/effective_poissons_ratio>,
        <http://materialsmine.org/i_s_00000001/effective_youngs_modulus> ;
    sio:hasPart <http://materialsmine.org/i_s_00000001/tango_black>,
        <http://materialsmine.org/i_s_00000001/vero_white> ;
    sio:isDescribedBy <http://materialsmine.org/i_s_00000001/C4v> .
```

Metamine Knowledge Graph