

INFINITE MATERIAL & TECHNOLOGY CO., LTD.

Neocoat Intumescent Paint - Technical Data Sheet (TDS)

Fire-protective intumescent coating for structural steel

STANDARDS

- Fire resistance test: ISO 834 Part 1:1999
- ASTM E119 / UL-equivalent fire test
- Test report: FSRG 2019/035 (Fire Science Research Group)
- Certified by professional civil engineer

PRODUCT VARIANTS

- Neocoat Intumescent Paint-S (Solvent base)
- Neocoat Intumescent Paint-W (Water base)

TECHNICAL DATA

- Type: Intumescent (expands to insulating char on heating)
- Fire rating: 1 - 3 hours (depending on film thickness / Hp/A)
- Dry film thickness (DFT): up to 500 microns
- Coverage: approx. 23 - 25 sq.m. per 22 kg unit
- Colour: white / grey (topcoat optional)
- Packaging: 22 kg pail; QC checked, ISO 9001 factory

APPLICATION

- Substrate: blast-cleaned steel + Neocoat Primer Grey Oxide
- Method: airless spray, brush or roller
- Topcoat: Neogloss enamel for weathering / colour finish

CONTACT

Tel: 02-041-0119, 086-339-4682, 061-421-5422

Email: sales@infinitematerialtech.com LINE: imat999 / blue999

Khlong Sam Wa, Bangkok 10510, Thailand

This document is a summary data sheet. Contact our engineers for the full specification, method statement and project-specific fire calculation.