

835M30/EN30B

BS970: 1955	BS970: 1991	COLOUR CODE	DESCRIPTION
EN30B	835M30		Black 4.1/4% nickel chromium (with/without) molybenum steel

CHEMICAL ANALYSIS		
Car	0.26 / 0.34	
Sil	0.10 / 0.35	
Mang	0.45 / 0.70	
Phos	0.025 max	
Sul	0.025 max	
Chr	1.10 / 1.40	
Moly	0.20 / 0.35	
Nick	3.90 / 4.30	

INTERNATIONAL SPECIFICATION COMPARISON		
BRITISH BS 970:1991	835M30	
BRITISH BS 970:1955	EN30B	
GERMAN DIN		
FRENCH AFNOR		
SWEDISH SS		
AMERICAN SAE		
EUROPEAN STEEL NO.	1.6773	
EUROPEAN STEEL NAME	36CrNiMo16	
EUROPEAN STANDARD	EN10083-1	

QUICK VIEW SYSTEM		
MACHINEABILITY	40	
WELDABILITY	Seek advice	
HARDENABILITY	Air hardening up to 60mm dia	
SELECTION GUIDE AND USAGE EXAMPLES	Chisels and hammers	

Sectors

The company specifically concentrates on supplying Precision Engineering Companies covering the automotive, defence, food, marine, medical, pharmaceutical and other manufacturing industries with their exact needs, whether it be a bar or thousands of cut pieces.



Our Service

Our service and commitment to supplying customers with high quality steels or non ferrous metals, competitively priced and backed up by a service second to none is the basis upon which the business has successfully developed since its foundation.



Whilst every effort has been taken to ensure the accuracy of this publication, Acton Bright Steel Ltd cannot accept responsibility for any errors, omissions or mis-statements. Acton Bright Steel Ltd also reserves the right to change all or any part of the information contained within this data sheet without notice.