Description

Image

Caption

1. Cast iron pan. © Evan-Amos at en.wikipedia - Public domain 2. The fluidity of the material allows intricate castings. © John Fernandez

The material

The foundations of modern industrial society are set, so to speak, in cast iron: it is the material that made the industrial revolution possible. Today it holds a second honor: that of being the cheapest of all engineering metals. Cast iron contains at least 2% carbon -- most have 3 to 4% -- and from 1-3% silicon. The carbon makes the iron very fluid when molten, allowing it to be cast to intricate shapes. There are five classes of cast iron: gray, white, ductile (or nodular), malleable and alloy; details are given under Design Guidelines, below. The two that are most used are gray and ductile. This record is for gray cast iron.

Compositional summary

Fe/3.2-4.1%C/1.8-2.8%Si/<0.8%Mn/<0.1%P/<0.03%S

General properties

Density	440	-	453	lb/ft^3
Price	* 0.186	-	0.2	USD/lb
Date first used	-513			

Mechanical properties

Young's modulus	11.6	-	20	10^6 psi
Shear modulus	4.5	-	8.27	10^6 psi
Bulk modulus	18.9	-	20.3	10^6 psi
Poisson's ratio	0.26	-	0.28	
Yield strength (elastic limit)	20.3	-	60.9	ksi
Tensile strength	20.3	-	65	ksi
Compressive strength	72.5	-	160	ksi
Elongation	0.17	-	0.7	% strain

Hardness - Vickers		90	-	310	HV
Fatigue strength at 10^7 cycles		5.8	-	24.7	ksi
Fracture toughness		9.1	-	21.8	ksi.in^0.5
Mechanical loss coefficient (tan delta)	*	0.01	-	0.04	

Thermal properties

Melting point		2.07e3	-	2.51e3	°F
Maximum service temperature		662	-	842	°F
Minimum service temperature		-238	-	-58	°F
Thermal conductor or insulator?		Good conductor			
Thermal conductivity		23.1	-	41.6	BTU.ft/h.ft^2.F
Specific heat capacity		0.103	-	0.118	BTU/lb.°F
Thermal expansion coefficient		6.11	-	6.94	µstrain/°F

Electrical properties

Electrical conductor or insulator?		Good conductor			
Electrical resistivity		62	-	86	µohm.cm

Optical properties

Transparency		Opaque			

Processability

Castability		5			
Formability		1	-	2	
Machinability		4			
Weldability		1			
Solder/brazability		1	-	2	

Durability: water and aqueous solutions

Water (fresh)	Acceptable
Water (salt)	Limited use
Soils, acidic (peat)	Acceptable
Soils, alkaline (clay)	Acceptable
Wine	Unacceptable

Durability: acids

Acetic acid (10%)	Limited use
Acetic acid (glacial)	Limited use
Citric acid (10%)	Limited use
Hydrochloric acid (10%)	Unacceptable
Hydrochloric acid (36%)	Unacceptable
Hydrofluoric acid (40%)	

	Unacceptable
Nitric acid (10%)	Unacceptable
Nitric acid (70%)	Unacceptable
Phosphoric acid (10%)	Unacceptable
Phosphoric acid (85%)	Unacceptable
Sulfuric acid (10%)	Unacceptable
Sulfuric acid (70%)	Excellent

Durability: alkalis

Sodium hydroxide (10%)	Excellent
Sodium hydroxide (60%)	Acceptable

Durability: fuels, oils and solvents

Amyl acetate	Excellent
Benzene	Excellent
Carbon tetrachloride	Excellent
Chloroform	Excellent
Crude oil	Acceptable
Diesel oil	Excellent
Lubricating oil	Excellent
Paraffin oil (kerosene)	Excellent
Petrol (gasoline)	Excellent
Silicone fluids	Excellent
Toluene	Excellent
Turpentine	Excellent
Vegetable oils (general)	Excellent
White spirit	Excellent

Durability: alcohols, aldehydes, ketones

Acetaldehyde	Limited use
Acetone	Excellent
Ethyl alcohol (ethanol)	Acceptable
Ethylene glycol	Acceptable
Formaldehyde (40%)	Limited use
Glycerol	Excellent
Methyl alcohol (methanol)	Acceptable

Durability: halogens and gases

Chlorine gas (dry)	Excellent
Fluorine (gas)	Limited use
O2 (oxygen gas)	Limited use

Sulfur dioxide (gas)	Acceptable

Durability: built environments

Industrial atmosphere	Acceptable
Rural atmosphere	Acceptable
Marine atmosphere	Limited use
UV radiation (sunlight)	Excellent

Durability: flammability

Flammability	Non-flammable

Durability: thermal environments

Tolerance to cryogenic temperatures	Unacceptable
Tolerance up to 150 C (302 F)	Excellent
Tolerance up to 250 C (482 F)	Excellent
Tolerance up to 450 C (842 F)	Excellent
Tolerance up to 850 C (1562 F)	Unacceptable
Tolerance above 850 C (1562 F)	Unacceptable

Geo-economic data for principal component

Annual world production, principal component	2.26e9	ton/yr
Reserves, principal component	1.57e11	l. ton

Primary material production: energy, CO2 and water

Embodied energy, primary production	* 1.84e3	-	2.28e3	kcal/lb
CO2 footprint, primary production	* 1.65	-	1.75	lb/lb
Water usage	* 5.03	-	5.56	gal(US)/lb
Eco-indicator 95	40			millipoints/kg
Eco-indicator 99	112			millipoints/kg

Material processing: energy

Casting energy	* 1.08e3	-	1.2e3	kcal/lb
Metal powder forming energy	* 3.26e3	-	3.95e3	kcal/lb
Vaporization energy	* 1.18e6	-	1.3e6	kcal/lb
Coarse machining energy (per unit wt removed)	* 91.1	-	101	kcal/lb
Fine machining energy (per unit wt removed)	* 449	-	495	kcal/lb
Grinding energy (per unit wt removed)	* 845	-	934	kcal/lb
Non-conventional machining energy (per unit wt removed)	1.18e4	-	1.3e4	kcal/lb

Material processing: CO2 footprint

Casting CO2	* 0.751	-	0.83	lb/lb
Metal powder forming CO2	* 2.41	-	2.92	lb/lb

Vaporization CO2	* 815	-	901	lb/lb
Coarse machining CO2 (per unit wt removed)	* 0.0631	-	0.0697	lb/lb
Fine machining CO2 (per unit wt removed)	* 0.31	-	0.343	lb/lb
Grinding CO2 (per unit wt removed)	* 0.585	-	0.646	lb/lb
Non-conventional machining CO2 (per unit wt removed)	8.15	-	9.01	lb/lb

Material recycling: energy, CO2 and recycle fraction

Recycle	✓			
Embodied energy, recycling	* 829	-	915	kcal/lb
CO2 footprint, recycling	* 0.601	-	0.664	lb/lb
Recycle fraction in current supply	60	-	80	%
Downcycle	✓			
Combust for energy recovery	✗			
Landfill	✓			
Biodegrade	✗			
Toxicity rating	Non-toxic			
A renewable resource?	✗			

Environmental notes

As metals go, it takes relatively little energy to make cast iron; it's exceptionally durable, and easily recycled. The pollution caused by blast furnaces in which it is made was at one time a major problem; but modern technology has totally overcome this.

Supporting information

Design guidelines

There are five kinds of cast iron. Gray cast iron machines easily, damps vibration well, is relatively brittle and has low tensile strength; it is the material of automotive cylinder blocks, exhaust manifolds, break disks and drums, gears and flywheels. White cast iron, made by chill casting to give a high cooling rate at the surface, is much harder than gray; it is used when wear resistance is wanted, as in rolls for rolling mills, blades for crushers and mixers. Nodular (ductile) cast iron contains additions that cause the flakes of graphite that are present in gray iron to spherodize, giving higher toughness and strength but at the loss of damping-ability; it is used for crank shafts and heavy duty gears. Malleable cast iron, made by heat-treating white cast iron, is ductile and easily machined; it is used for heavy-duty parts of cars, trucks, and railway rolling stock. Finally, alloy cast irons contain up to 35% of chromium or nickel; they are corrosion resistant and have high strength, but are much more expensive.

Technical notes

There is no single systematic numbering system for cast irons. The UNS and the AISI systems are widely used, particularly in the US. More information on designations and equivalent grades can be found on the Granta Design website at www.grantadesign.com/designations

Phase diagram



Phase diagram description

Grey cast irons are based on iron (Fe) with 3 - 4.1% carbon (C), for which this is the phase diagram. Some have additions of silicon and manganese.

Typical uses

Brake discs and drums; bearings; camshafts; cylinder liners; piston rings; machine tool structural parts; engine blocks, gears, crankshafts; heavy-duty gear cases; pipe joints; pump casings; components in rock crushers.

Links

Reference

ProcessUniverse

Producers