

## Description

### Image



### Caption

1. Rigid polystyrene foam covered in foil, used for wall insulation to reduce heat loss. © Leyo at en.wikipedia - (CC BY-SA 2.0) 2. Rigid polystyrene foam boards. © John Fernandez

### The material

Polymer foams are made by the controlled expansion and solidification of a liquid or melt through a blowing agent; physical, chemical or mechanical blowing agents are possible. The resulting cellular material has a lower density, stiffness and strength than the parent material, by an amount that depends on its relative density - the volume-fraction of solid in the foam. Rigid foams are made from polystyrene, phenolic, polyethylene, polypropylene or derivatives of polymethylmethacrylate. They are light and stiff, and have mechanical properties that make them attractive for energy management and packaging, and for lightweight structural use. Open-cell foams can be used as filters, closed cell foams as flotation. Self-skinning foams, called 'structural' or 'syntactic', have a dense surface skin made by foaming in a cold mold. Rigid polymer foams are widely used as cores of sandwich panels.

### Compositional summary

Hydrocarbon

### General properties

Density	36	-	70	kg/m <sup>3</sup>
Price	* 15.3	-	16.9	USD/kg
Date first used	1931			

### Mechanical properties

Young's modulus	0.023	-	0.08	GPa
Shear modulus	0.008	-	0.035	GPa
Bulk modulus	0.023	-	0.08	GPa
Poisson's ratio	0.25	-	0.33	
Yield strength (elastic limit)	0.3	-	1.7	MPa
Tensile strength	0.45	-	2.25	MPa
Compressive strength	0.37	-	1.7	MPa
Elongation	2	-	5	% strain

Hardness - Vickers	0.037	-	0.17	HV
Fatigue strength at 10 <sup>7</sup> cycles	* 0.296	-	1.36	MPa
Fracture toughness	0.0021	-	0.02	MPa.m <sup>0.5</sup>
Mechanical loss coefficient (tan delta)	* 0.005	-	0.3	

### Thermal properties

Glass temperature	66.9	-	171	°C
Maximum service temperature	66.9	-	147	°C
Minimum service temperature	-113	-	-73.2	°C
Thermal conductor or insulator?	Good insulator			
Thermal conductivity	0.023	-	0.04	W/m.°C
Specific heat capacity	1.12e3	-	1.91e3	J/kg.°C
Thermal expansion coefficient	20	-	80	µstrain/°C

### Electrical properties

Electrical conductor or insulator?	Good insulator			
Electrical resistivity	1e17	-	1e21	µohm.cm
Dielectric constant (relative permittivity)	1.04	-	1.1	
Dissipation factor (dielectric loss tangent)	8e-4	-	0.008	
Dielectric strength (dielectric breakdown)	1.9	-	6.04	1000000 V/m

### Optical properties

Transparency	Opaque			
--------------	--------	--	--	--

### Processability

Castability	1	-	3	
Moldability	3	-	4	
Machinability	3	-	4	
Weldability	1	-	2	

### Durability: water and aqueous solutions

Water (fresh)	Excellent
Water (salt)	Excellent
Soils, acidic (peat)	Excellent
Soils, alkaline (clay)	Excellent
Wine	Excellent

### Durability: acids

Acetic acid (10%)	Excellent
Acetic acid (glacial)	Limited use
Citric acid (10%)	Excellent
Hydrochloric acid (10%)	

	Excellent
Hydrochloric acid (36%)	Limited use
Hydrofluoric acid (40%)	Unacceptable
Nitric acid (10%)	Acceptable
Nitric acid (70%)	Limited use
Phosphoric acid (85%)	Acceptable
Sulfuric acid (10%)	Excellent
Sulfuric acid (70%)	Unacceptable

### **Durability: alkalis**

Sodium hydroxide (10%)	Excellent
Sodium hydroxide (60%)	Excellent

### **Durability: fuels, oils and solvents**

Amyl acetate	Unacceptable
Benzene	Unacceptable
Carbon tetrachloride	Excellent
Chloroform	Unacceptable
Crude oil	Limited use
Diesel oil	Limited use
Lubricating oil	Limited use
Paraffin oil (kerosene)	Acceptable
Petrol (gasoline)	Acceptable
Silicone fluids	Excellent
Toluene	Unacceptable
Turpentine	Unacceptable
Vegetable oils (general)	Limited use
White spirit	Limited use

### **Durability: alcohols, aldehydes, ketones**

Acetaldehyde	Unacceptable
Acetone	Unacceptable
Ethyl alcohol (ethanol)	Excellent
Ethylene glycol	Excellent
Formaldehyde (40%)	Limited use
Glycerol	Excellent
Methyl alcohol (methanol)	Acceptable

### **Durability: halogens and gases**

Chlorine gas (dry)	Unacceptable
Fluorine (gas)	Unacceptable

O2 (oxygen gas)	Unacceptable
Sulfur dioxide (gas)	Excellent

### **Durability: built environments**

Industrial atmosphere	Acceptable
Rural atmosphere	Excellent
Marine atmosphere	Excellent
UV radiation (sunlight)	Good

### **Durability: flammability**

Flammability	Self-extinguishing
--------------	--------------------

### **Durability: thermal environments**

Tolerance to cryogenic temperatures	Unacceptable
Tolerance up to 150 C (302 F)	Acceptable
Tolerance up to 250 C (482 F)	Unacceptable
Tolerance up to 450 C (842 F)	Unacceptable
Tolerance up to 850 C (1562 F)	Unacceptable
Tolerance above 850 C (1562 F)	Unacceptable

### **Primary material production: energy, CO2 and water**

Embodied energy, primary production	* 96.6	-	107	MJ/kg
CO2 footprint, primary production	* 3.68	-	4.07	kg/kg
Water usage	* 436	-	482	l/kg
Eco-indicator 95	420			millipoints/kg
Eco-indicator 99	368			millipoints/kg

### **Material processing: energy**

Polymer extrusion energy	* 7.51	-	8.28	MJ/kg
Polymer molding energy	* 19.3	-	21.3	MJ/kg
Coarse machining energy (per unit wt removed)	* 0.61	-	0.674	MJ/kg
Fine machining energy (per unit wt removed)	* 1.82	-	2.01	MJ/kg
Grinding energy (per unit wt removed)	* 3.17	-	3.5	MJ/kg

### **Material processing: CO2 footprint**

Polymer extrusion CO2	* 0.601	-	0.662	kg/kg
Polymer molding CO2	* 1.55	-	1.71	kg/kg
Coarse machining CO2 (per unit wt removed)	* 0.0457	-	0.0505	kg/kg
Fine machining CO2 (per unit wt removed)	* 0.137	-	0.151	kg/kg
Grinding CO2 (per unit wt removed)	* 0.238	-	0.263	kg/kg

### **Material recycling: energy, CO2 and recycle fraction**

Recycle	✗			
Recycle fraction in current supply	0.1		%	
Downcycle	✓			
Combust for energy recovery	✓			
Heat of combustion (net)	* 17.3	-	18.2	MJ/kg
Combustion CO2	* 1.37	-	1.44	kg/kg
Landfill	✓			
Biodegrade	✗			
Toxicity rating	Non-toxic			
A renewable resource?	✗			

#### Environmental notes

Foaming of insulation with CFCs has a damaging effect on the ozone layer - it is now abandoned. Monomers and foaming agents pose hazards; good practice overcomes these.

## Supporting information

### Design guidelines

Energy management and packaging requires the ability to absorb energy at a constant, controlled crushing stress; here polyurethane, polypropylene and polystyrene foams are used. Acoustic control requires the ability to absorb sound and damp vibration; polyurethane, polystyrene and polyethylene foams are all used. Thermal insulation requires long life; polyurethane foams were common but are now replaced by phenolics and polystyrenes. When fire-protection is needed phenolic foams are used. Foams are usually shaped by injecting or pouring a mix of polymer and foaming agent into a mold where the agent evolves gas, expanding the foam. The mix can be palletized, and the mold part-filled with solid pellets before foaming (see "Expanded foam molding" in this database). Expanding in a cold mold gives a solid surface skin, creating a sandwich-like structure with attractive mechanical properties.

### Technical notes

The properties of foams depend, most directly, on the material of which they are made and on the relative density (the fraction of the foam that is solid). Most commercial foams have a relative density between 1% and 30%. To a lesser extent, the properties depend on the size and the shape of the cells. Low density, closed cell, foams have exceptional low thermal conductivity. Skinned rigid foams have good bending stiffness and strength of low weight.

### Typical uses

Thermal insulation, Cores for sandwich structures, Panels, Partitions, Refrigeration, Energy Absorption, Packaging, Buoyancy, Floatation.

## Links

Reference

ProcessUniverse

Producers