

**General information****Designation**

Diospyros spp. (L)

**Typical uses**

Fancy articles; inlays; shuttles; turnery; piano keys; finger boards of stringed instruments; bowls.

**Composition overview****Compositional summary**Cellulose/Hemicellulose/Lignin/12%H<sub>2</sub>O

Material family	Natural		
Base material	Wood (tropical)		
Renewable content	100		%

**Composition detail (polymers and natural materials)**

Wood	100		%
------	-----	--	---

**Price**

Price	* 3.04	- 4.88	USD/lb
-------	--------	--------	--------

**Physical properties**

Density	0.034	- 0.0412	lb/in <sup>3</sup>
---------	-------	----------	--------------------

**Mechanical properties**

Young's modulus	1.41	- 1.73	10 <sup>6</sup> psi
Yield strength (elastic limit)	3.77	- 4.61	ksi
Tensile strength	* 16.6	- 20.3	ksi
Elongation	* 4.77	- 5.83	% strain
Compressive strength	10.2	- 12.4	ksi
Flexural modulus	1.81	- 2.22	10 <sup>6</sup> psi
Flexural strength (modulus of rupture)	17.9	- 21.9	ksi
Shear modulus	* 0.104	- 0.128	10 <sup>6</sup> psi
Shear strength	1.68	- 2.06	ksi
Bulk modulus	* 0.467	- 0.526	10 <sup>6</sup> psi
Poisson's ratio	* 0.35	- 0.4	
Shape factor	5.5		
Hardness - Vickers	* 16.2	- 19.8	HV
Hardness - Brinell	18	- 22	ksi
Hardness - Janka	* 3.65e3	- 4.46e3	lbf
Fatigue strength at 10 <sup>7</sup> cycles	* 5.37	- 6.56	ksi
Mechanical loss coefficient (tan delta)	* 0.0064	- 0.0078	
Differential shrinkage (radial)	0.24	- 0.3	%
Differential shrinkage (tangential)	* 0.44	- 0.54	%
Radial shrinkage (green to oven-dry)	* 3.2	- 7	%
Tangential shrinkage (green to oven-dry)	9.6	- 11.7	%
Volumetric shrinkage (green to oven-dry)	20.8	- 23.1	%
Work to maximum strength	* 2.01	- 2.45	ft.lbf/in <sup>3</sup>

**Impact & fracture properties**

Fracture toughness	* 9.46	- 11.6	ksi.in <sup>0.5</sup>
--------------------	--------	--------	-----------------------

**Thermal properties**

Glass temperature	171	- 216	°F
-------------------	-----	-------	----

Maximum service temperature	248	-	284	°F
Minimum service temperature	* -99.4	-	-9.4	°F
Thermal conductivity	* 0.26	-	0.324	BTU.ft/hr.ft^2. °F
Specific heat capacity	0.396	-	0.408	BTU/lb. °F
Thermal expansion coefficient	* 1.11	-	6.11	µstrain/°F

### Electrical properties

Electrical resistivity	* 6e13	-	2e14	µohm.cm
Dielectric constant (relative permittivity)	* 10.1	-	12.4	
Dissipation factor (dielectric loss tangent)	* 0.124	-	0.152	
Dielectric strength (dielectric breakdown)	* 10.2	-	15.2	V/mil

### Optical properties

Transparency	Opaque
--------------	--------

### Magnetic properties

Magnetic type	Non-magnetic
---------------	--------------

### Bio-data

RoHS (EU) compliant grades?	✓
Food contact	No

### Durability

Water (fresh)	Limited use
Water (salt)	Limited use
Weak acids	Limited use
Strong acids	Unacceptable
Weak alkalis	Acceptable
Strong alkalis	Unacceptable
Organic solvents	Acceptable
Oxidation at 500C	Unacceptable
UV radiation (sunlight)	Good
Flammability	Highly flammable

### Primary production energy, CO2 and water

Embodied energy, primary production	* 4.99e3	-	5.5e3	BTU/lb
CO2 footprint, primary production	* 0.574	-	0.633	lb/lb
NOx creation	0.00257	-	0.00284	lb/lb
SOx creation	0.00656	-	0.00725	lb/lb
Water usage	* 1.84e4	-	2.03e4	in^3/lb

### Processing energy, CO2 footprint & water

Coarse machining energy (per unit wt removed)	* 510	-	564	BTU/lb
Coarse machining CO2 (per unit wt removed)	* 0.089	-	0.0984	lb/lb
Fine machining energy (per unit wt removed)	* 3.27e3	-	3.61e3	BTU/lb
Fine machining CO2 (per unit wt removed)	* 0.57	-	0.63	lb/lb
Grinding energy (per unit wt removed)	* 6.33e3	-	6.99e3	BTU/lb
Grinding CO2 (per unit wt removed)	* 1.1	-	1.22	lb/lb

### Recycling and end of life

Recycle	✗			
Recycle fraction in current supply	8.55	-	9.45	%
Downcycle	✓			
Combust for energy recovery	✓			

---

Heat of combustion (net)	* 8.49e3	-	9.16e3	BTU/lb
Combustion CO2	* 1.69	-	1.78	lb/lb
Landfill	✓			
Biodegrade	✓			
<b>Eco-indicators for principal component</b>				
Eco-indicator 95	2.99			millipoints/lb
EPS value	62.7	-	69.3	

## Notes

### Warning

All woods have properties which show variation; they depend principally on growth conditions and moisture content.

## Links

ProcessUniverse

Reference

Shape