

## Description

### Image



### Caption

Cellulose acetate used for a tool handle. ©

### The material

Cellulose is one of the main structural polymers in plants (specifically that of wood or cotton). These natural fibers are treated with acids to produce a resin, a process called 'esterification'. Cellulose acetate (CA), cellulose acetate butyrate (CAB) and cellulose acetate propionate (CAP) are three common cellulose materials. CA combines toughness, transparency and a natural surface texture. Some cellulose resins are biodegradable allowing their use for envelopes with transparent windows that can be disposed of as if they were paper alone.

## General properties

Density	61.2	-	81.2	lb/ft <sup>3</sup>
Price	* 2.3	-	2.72	USD/lb
Date first used	1894			

## Mechanical properties

Young's modulus	0.232	-	0.29	10 <sup>6</sup> psi
Shear modulus	0.0211	-	0.214	10 <sup>6</sup> psi
Bulk modulus	0.435	-	0.464	10 <sup>6</sup> psi
Poisson's ratio	0.383	-	0.438	
Yield strength (elastic limit)	3.63	-	6.53	ksi
Tensile strength	3.63	-	7.25	ksi
Compressive strength	3.99	-	7.18	ksi
Elongation	5	-	50	% strain
Hardness - Vickers	10	-	15	HV
Fatigue strength at 10 <sup>7</sup> cycles	1.45	-	2.9	ksi
Fracture toughness	0.91	-	2.28	ksi.in <sup>0.5</sup>
Mechanical loss coefficient (tan delta)	0.00976	-	0.0966	

### Thermal properties

Glass temperature	15.5	-	224	°F
Maximum service temperature	127	-	194	°F
Minimum service temperature	-190	-	-99.7	°F
Thermal conductor or insulator?	Good insulator			
Thermal conductivity	0.0751	-	0.173	BTU.ft/h.ft <sup>2</sup> .F
Specific heat capacity	0.331	-	0.398	BTU/lb.°F
Thermal expansion coefficient	83.3	-	167	μstrain/°F

### Electrical properties

Electrical conductor or insulator?	Good insulator			
Electrical resistivity	1e17	-	4.5e20	μohm.cm
Dielectric constant (relative permittivity)	3	-	5	
Dissipation factor (dielectric loss tangent)	0.005	-	0.01	
Dielectric strength (dielectric breakdown)	305	-	457	V/mil

### Optical properties

Transparency	Optical Quality			
Refractive index	1.46	-	1.5	

### Processability

Castability	4	-	5	
Moldability	3	-	4	
Machinability	4	-	5	
Weldability	4			

### Durability: water and aqueous solutions

Water (fresh)	Acceptable
Water (salt)	Acceptable
Soils, acidic (peat)	Unacceptable
Soils, alkaline (clay)	Unacceptable
Wine	Excellent

### Durability: acids

Acetic acid (10%)	Unacceptable
Acetic acid (glacial)	Unacceptable
Citric acid (10%)	Excellent
Hydrochloric acid (10%)	Excellent
Hydrochloric acid (36%)	Unacceptable
Hydrofluoric acid (40%)	Unacceptable
Nitric acid (10%)	Unacceptable

Nitric acid (70%)	Unacceptable
Phosphoric acid (10%)	Unacceptable
Phosphoric acid (85%)	Unacceptable
Sulfuric acid (10%)	Unacceptable
Sulfuric acid (70%)	Unacceptable

### **Durability: alkalis**

Sodium hydroxide (10%)	Unacceptable
Sodium hydroxide (60%)	Unacceptable

### **Durability: fuels, oils and solvents**

Amyl acetate	Unacceptable
Benzene	Excellent
Carbon tetrachloride	Excellent
Chloroform	Unacceptable
Crude oil	Acceptable
Diesel oil	Excellent
Lubricating oil	Excellent
Paraffin oil (kerosene)	Excellent
Petrol (gasoline)	Excellent
Silicone fluids	Excellent
Toluene	Unacceptable
Turpentine	Excellent
Vegetable oils (general)	Acceptable
White spirit	Excellent

### **Durability: alcohols, aldehydes, ketones**

Acetaldehyde	Unacceptable
Acetone	Unacceptable
Ethyl alcohol (ethanol)	Limited use
Ethylene glycol	Limited use
Formaldehyde (40%)	Unacceptable
Glycerol	Limited use
Methyl alcohol (methanol)	Unacceptable

### **Durability: halogens and gases**

Chlorine gas (dry)	Unacceptable
Fluorine (gas)	Unacceptable
O2 (oxygen gas)	Unacceptable
Sulfur dioxide (gas)	Unacceptable

### Durability: built environments

Industrial atmosphere	Acceptable
Rural atmosphere	Acceptable
Marine atmosphere	Acceptable
UV radiation (sunlight)	Fair

### Durability: flammability

Flammability	Highly flammable
--------------	------------------

### Durability: thermal environments

Tolerance to cryogenic temperatures	Unacceptable
Tolerance up to 150 C (302 F)	Acceptable
Tolerance up to 250 C (482 F)	Unacceptable
Tolerance up to 450 C (842 F)	Unacceptable
Tolerance up to 850 C (1562 F)	Unacceptable
Tolerance above 850 C (1562 F)	Unacceptable

### Primary material production: energy, CO2 and water

Embodied energy, primary production	* 9.25e3	-	1.02e4	kcal/lb
CO2 footprint, primary production	* 3.62	-	4	lb/lb
Water usage	* 27.3	-	30.2	gal(US)/lb

### Material processing: energy

Polymer extrusion energy	* 625	-	690	kcal/lb
Polymer molding energy	* 1.85e3	-	2.05e3	kcal/lb
Coarse machining energy (per unit wt removed)	* 93.6	-	103	kcal/lb
Fine machining energy (per unit wt removed)	* 473	-	523	kcal/lb
Grinding energy (per unit wt removed)	* 895	-	989	kcal/lb

### Material processing: CO2 footprint

Polymer extrusion CO2	* 0.432	-	0.478	lb/lb
Polymer molding CO2	* 1.28	-	1.42	lb/lb
Coarse machining CO2 (per unit wt removed)	* 0.0648	-	0.0716	lb/lb
Fine machining CO2 (per unit wt removed)	* 0.328	-	0.362	lb/lb
Grinding CO2 (per unit wt removed)	* 0.619	-	0.685	lb/lb

### Material recycling: energy, CO2 and recycle fraction

Recycle				
Embodied energy, recycling	* 3.75e3	-	4.15e3	kcal/lb
CO2 footprint, recycling	* 2.72	-	3.01	lb/lb
Recycle fraction in current supply	* 0.5	-	1	%

Downcycle	✓			
Combust for energy recovery	✓			
Heat of combustion (net)	* 1.99e3	-	2.1e3	kcal/lb
Combustion CO2	* 1.79	-	1.89	lb/lb
Landfill	✓			
Biodegrade	✗			
Toxicity rating	Non-toxic			
A renewable resource?	✓			

#### Environmental notes

Cellulose - a natural, renewable material - forms one ingredient in cellulose-based polymers, which can therefore qualify as biopolymers. The processing, however, involves chemicals that create a problem of disposal. Most cellulose-based polymers burn easily, requiring protection from naked flame. Some are biodegradable.

#### Recycle mark



## Supporting information

#### Design guidelines

Cellulose materials have good optical transparency (up to 90%) and mechanical properties; they are often used in products where surface finish is important. They can be translucent, transparent or opaque and come in a range of colors including pearlescent, opaque or metallic. Cellulose materials are anti-static and so dust does not stick to the surface. They have glossy surfaces and a self-polishing effect that allows surface scratches to disappear with use. They can be formulated for outdoor use. Cellulose acetates have a high vapor permeability and limited heat resistance; their electrical insulation and dimensional stability are poor; water absorption is high compared with PVC. Compared with CA, CAB and CAP are slightly softer, of lower densities and heat distortion temperatures and they flow more easily. CAB and CAP have a wider operating temperature range (0 to 60 C). In bulk, cellulose acetate often has a light yellow-brown color but it can also attain water, white transparency. Cellulose is easily made into fibers, fabrics and films, known under the trade name of Rayon. It has excellent flow properties and so is well-suited to injection molding but the resin must be kept dry. Stiffer flow grades are available for extrusion to produce film and sheet. These polymers are also some of the best for cutting, turning and milling. CAB is well-suited for thermoforming.

#### Technical notes

Grades of cellulose materials are varied by increasing the level of acid-treatment or by adding plasticizers. Increasing the plasticizer increases flow and toughness but reduces the creep resistance. But this lack of creep resistance can be used to an advantage in molding where parts can be shot in without problems because the stresses will relax quite quickly.

#### Typical uses

Tool handles; panels for illuminated signs; steering wheels; bathroom fittings; decorative trim for cars and consumer durables; drawing stencils; pens; pneumatic system traps; blister packaging; laminating with aluminum foil; Spectacle frames; lenses; goggles; tool handles; covers for television screens; cutlery handles.

#### Tradenames

Dexel, Rotuba, Tenite, Xylonite, Cellidor

## Links

Reference

ProcessUniverse

Producers