

## General information

### Designation

Guaiacum spp.

### Typical uses

Bearing & bushing blocks; lining of stern tubes for steamship propeller shafts; underwater use; mallets; pulley sheaves; caster wheels; stencil; chisel block; turned articles; brush backs.

## Composition overview

### Compositional summary

Cellulose/Hemicellulose/Lignin/12%H2O

Material family	Natural		
Base material	Wood (tropical)		
Renewable content	100		%

### Composition detail (polymers and natural materials)

Wood	100		%
------	-----	--	---

### Price

Price	* 3.04	-	4.88	USD/lb
-------	--------	---	------	--------

### Physical properties

Density	0.0401	-	0.0488	lb/in^3
---------	--------	---	--------	---------

### Mechanical properties

Young's modulus	* 1.62	-	1.81	10^6 psi
Yield strength (elastic limit)	* 0.627	-	0.766	ksi
Tensile strength	* 1.04	-	1.28	ksi
Elongation	* 0.19	-	0.23	% strain
Compressive strength	* 3.16	-	3.86	ksi
Flexural modulus	1.46	-	1.64	10^6 psi
Flexural strength (modulus of rupture)	* 1.04	-	1.28	ksi
Shear modulus	* 0.167	-	0.23	10^6 psi
Shear strength	* 9.01	-	11	ksi
Rolling shear strength	* 0.334	-	1	ksi
Bulk modulus	* 0.753	-	0.848	10^6 psi
Poisson's ratio	* 0.02	-	0.04	
Shape factor	5.7			
Hardness - Vickers	18	-	22	HV
Hardness - Brinell	* 9.89	-	12.1	ksi
Hardness - Janka	4.05e3	-	4.95e3	lbf

Fatigue strength at 10 <sup>7</sup> cycles	* 0.313	-	0.383	ksi
Mechanical loss coefficient (tan delta)	* 0.007	-	0.009	
Differential shrinkage (radial)	* 0.32	-	0.39	%
Differential shrinkage (tangential)	* 0.53	-	0.65	%
Radial shrinkage (green to oven-dry)	* 3.2	-	7	%
Tangential shrinkage (green to oven-dry)	* 6.8	-	11.5	%
Volumetric shrinkage (green to oven-dry)	* 11	-	18	%
Work to maximum strength	* 0.259	-	0.315	ft.lbf/in <sup>3</sup>

### Impact & fracture properties

Fracture toughness	* 1.12	-	1.37	ksi.in <sup>0.5</sup>
--------------------	--------	---	------	-----------------------

### Thermal properties

Glass temperature	171	-	216	°F
Maximum service temperature	248	-	284	°F
Minimum service temperature	* -99.4	-	-9.4	°F
Thermal conductivity	0.127	-	0.156	BTU.ft/hr.ft <sup>2</sup> .°F
Specific heat capacity	0.396	-	0.408	BTU/lb.°F
Thermal expansion coefficient	* 25.6	-	32.8	µstrain/°F

### Electrical properties

Electrical resistivity	* 2.1e14	-	7e14	µohm.cm
Dielectric constant (relative permittivity)	* 6.45	-	7.89	
Dissipation factor (dielectric loss tangent)	* 0.1	-	0.122	
Dielectric strength (dielectric breakdown)	* 25.4	-	50.8	V/mil

### Magnetic properties

Magnetic type	Non-magnetic
---------------	--------------

### Optical properties

Transparency	Opaque
--------------	--------

### Durability

Water (fresh)	Limited use
Water (salt)	Limited use
Weak acids	Limited use
Strong acids	Unacceptable
Weak alkalis	Acceptable
Strong alkalis	Unacceptable
Organic solvents	Acceptable
Oxidation at 500C	Unacceptable
UV radiation (sunlight)	

	Good
Flammability	Highly flammable

### Primary production energy, CO2 and water

Embodied energy, primary production	* 4.99e3	-	5.5e3	BTU/lb
CO2 footprint, primary production	* 0.574	-	0.633	lb/lb
Water usage	* 1.84e4	-	2.03e4	in^3/lb

### Processing energy, CO2 footprint & water

Coarse machining energy (per unit wt removed)	* 285	-	315	BTU/lb
Coarse machining CO2 (per unit wt removed)	* 0.0496	-	0.0549	lb/lb
Fine machining energy (per unit wt removed)	* 1.01e3	-	1.11e3	BTU/lb
Fine machining CO2 (per unit wt removed)	* 0.176	-	0.194	lb/lb
Grinding energy (per unit wt removed)	* 1.81e3	-	2e3	BTU/lb
Grinding CO2 (per unit wt removed)	* 0.316	-	0.349	lb/lb

### Recycling and end of life

Recycle	✗			
Recycle fraction in current supply	8.55	-	9.45	%
Downcycle	✓			
Combust for energy recovery	✓			
Heat of combustion (net)	* 8.49e3	-	9.16e3	BTU/lb
Combustion CO2	* 1.69	-	1.78	lb/lb
Landfill	✓			
Biodegrade	✓			

### Notes

#### Warning

All woods have properties which show variation; they depend principally on growth conditions and moisture content.

### Links

ProcessUniverse

Reference

Shape