


Description

Process schematic



The process

FUSED DEPOSITION MODELLING (FDM) is an additive manufacturing technique suitable for use in an office environment. A fine stream of molten material (usually thermoplastic) is deposited by a two-axis heated extrusion head. Semi-liquid thermoplastic material is extruded and then deposited one layer at a time starting at the base. This builds the model vertically on a fixtureless base. Successive layers adhere together through thermal fusion. The FDM process requires no post-production UV curing, enabling multiple versions of a part to be created within a short time frame. This is the most widely used additive manufacturing method for home and office use due to the low machine and operating costs. As with other additive manufacturing processes, a CAD solid model of the part is required.

Material compatibility

Polymers - thermoplastics



Shape

Circular prismatic



Non-circular prismatic



Flat sheet



Dished sheet



Solid 3-D



Hollow 3-D



Economic compatibility

Relative tooling cost

low

Relative equipment cost

high

Labor intensity	medium		
Economic batch size (units)	1	-	10

Physical and quality attributes

Mass range	* 0.22	-	33.1	lb
Range of section thickness	19.7	-	3.94e3	mil
Tolerance	5	-	78.7	mil
Roughness	* 3.94	-	4.92	mil
Surface roughness (A=v. smooth)	C			


Process characteristics

Primary shaping processes	✓
Discrete	✓
Prototyping	✓

Cost model and defaults

Relative cost index (per unit)	* 173	-	1.27e3
--------------------------------	-------	---	--------

[Parameters:](#) Material Cost = 3.63USD/lb, Component Mass = 2.2lb, Batch Size = 1e3, Overhead Rate = 150USD/hr, Discount Rate = 5%, Capital Write-off Time = 5yrs, Load Factor = 0.5



Material Cost=3.63USD/lb, Component Mass=2.2lb, Overhead Rate=150USD/hr, Capital Write-off Time=5yrs, Load Factor=0.5, Discount Rate=5%

Capital cost	9.43e4	-	4e5	USD
Material utilization fraction	* 0.9	-	0.98	
Production rate (units)	0.13	-	1	/hr
Tooling cost	* 0	-	0.1	USD
Tool life (units)	1e5	-	1e6	

Supporting information

Design guidelines

Support structures (which can be removed later) are required in addition to the main body of the object for overhangs. Due to the rounded bead, sharp angles are not possible and small voids occur where the deposition direction changes so there is porosity in some areas. This porosity may be reduced at the expense of surface finish.

Technical notes

The build envelope (L x W x H) ranges from 127 x 127 x 127 mm to 914 x 610 x 914 mm.

Typical layer thickness is 78 - 330 μm .

A variety of materials and colors can be used for model building including ABS, wax-filled plastic adhesive material, proprietary nylon, investment casting wax and possibly metals with a low melting point.

Typical uses

Making prototypes and models quickly from CAD systems.

The economics

Prices range from around \$200 for DIY assembly machines, to \$1500 for ready-assembled, to \$15000 for industrial models. Objects cost around \$0.40 per cubic cm.

The environment

The materials are non-toxic. There is minimum material wastage in the

Links

MaterialUniverse

Reference