

General information**Designation**

Poly Vinyl Chloride (Chlorinated, Molding and Extrusion); CPVC

Tradenames

Corzan; Lucalor; ProTherm; TempRite; Boltaron; Kydex

Typical uses

Hot water piping; fibers; lacquers.

Composition overview**Compositional summary**Compound of chlorinated PVC: $(CH_2CHCl)_n$ with additional random substitution of H by Cl. 63-66% chlorine compared to 56.7% in standard PVC.

Material family

Plastic (thermoplastic, amorphous)

Base material

PVC-C (Polyvinyl chloride, chlorinated)

Polymer code

PVC-C

Composition detail (polymers and natural materials)

Polymer	100	%
---------	-----	---

Price

Price	* 1.32	- 1.46	USD/lb
-------	--------	--------	--------

Physical properties

Density	0.0524	- 0.0564	lb/in ³
---------	--------	----------	--------------------

Mechanical properties

Young's modulus	0.316	- 0.495	10 ⁶ psi
Yield strength (elastic limit)	7.69	- 8.41	ksi
Tensile strength	6.67	- 8.41	ksi
Elongation	20	- 50	% strain
Elongation at yield	4	- 7	% strain
Compressive modulus	* 0.316	- 0.495	10 ⁶ psi
Compressive strength	* 7.25	- 9.72	ksi
Flexural modulus	0.318	- 0.405	10 ⁶ psi
Flexural strength (modulus of rupture)	11.9	- 13.1	ksi
Shear modulus	* 0.113	- 0.177	10 ⁶ psi
Bulk modulus	* 0.621	- 0.652	10 ⁶ psi
Poisson's ratio	0.35	- 0.38	
Shape factor	5.8		
Hardness - Vickers	* 13.7	- 16.6	HV
Hardness - Rockwell M	* 71.9	- 90.4	
Hardness - Rockwell R	* 113	- 132	
Fatigue strength at 10 ⁷ cycles	* 2.64	- 3.2	ksi
Mechanical loss coefficient (tan delta)	* 0.0122	- 0.017	

Impact & fracture properties

Fracture toughness	* 3.22	- 3.52	ksi.in ^{0.5}
Impact strength, notched 23 °C	0.00581	- 0.00801	BTU/in ²
Impact strength, unnotched 23 °C	0.361	- 0.367	BTU/in ²

Thermal properties

Glass temperature	216	- 244	°F
-------------------	-----	-------	----

Heat deflection temperature 0.45MPa	216	-	246	°F
Heat deflection temperature 1.8MPa	201	-	234	°F
Vicat softening point	* 216	-	246	°F
Maximum service temperature	185	-	212	°F
Minimum service temperature	* -59.8	-	-23.8	°F
Thermal conductivity	0.0768	-	0.0832	BTU.ft/hr.ft^2.°F
Specific heat capacity	* 0.309	-	0.321	BTU/lb.°F
Thermal expansion coefficient	62	-	78	μstrain/°F

Electrical properties

Electrical resistivity	1e21	-	2e22	μohm.cm
Dielectric constant (relative permittivity)	3	-	3.2	
Dissipation factor (dielectric loss tangent)	0.0189	-	0.0208	
Dielectric strength (dielectric breakdown)	599	-	625	V/mil

Optical properties

Transparency	Opaque
--------------	--------

Magnetic properties

Magnetic type	Non-magnetic
---------------	--------------

Bio-data

RoHS (EU) compliant grades?	✓
Food contact	Yes

Absorption & permeability

Water absorption @ 24 hrs	0.02	-	0.15	%
Permeability (O2)	8.86	-	17.7	cc.mil/day.(100.in^2).atm

Processing properties

Polymer injection molding	Acceptable			
Polymer extrusion	Acceptable			
Polymer thermoforming	Acceptable			
Linear mold shrinkage	0.3	-	0.7	%
Melt temperature	360	-	441	°F
Mold temperature	104	-	158	°F
Molding pressure range	14.9	-	39.9	ksi

Durability

Water (fresh)	Excellent
Water (salt)	Excellent
Weak acids	Excellent
Strong acids	Excellent
Weak alkalis	Excellent
Strong alkalis	Excellent
Organic solvents	Limited use
Oxidation at 500C	Unacceptable
UV radiation (sunlight)	Good
Flammability	Self-extinguishing

Primary production energy, CO2 and water

Embodied energy, primary production	2.12e4	-	2.34e4	BTU/lb
Sources				
51.8 MJ/kg (Franklin Associates, 2008)				
CO2 footprint, primary production				

	* 1.78	- 1.97	lb/lb
NOx creation	* 0.00638	- 0.00706	lb/lb
SOx creation	* 0.0192	- 0.0212	lb/lb
Water usage	* 5.48e3	- 6.06e3	in^3/lb

Processing energy, CO2 footprint & water

Polymer extrusion energy	* 2.47e3	- 2.73e3	BTU/lb
Polymer extrusion CO2	* 0.431	- 0.476	lb/lb
Polymer extrusion water	* 133	- 199	in^3/lb
Polymer molding energy	* 7.07e3	- 7.81e3	BTU/lb
Polymer molding CO2	* 1.23	- 1.36	lb/lb
Polymer molding water	* 322	- 484	in^3/lb
Coarse machining energy (per unit wt removed)	* 361	- 399	BTU/lb
Coarse machining CO2 (per unit wt removed)	* 0.063	- 0.0697	lb/lb
Fine machining energy (per unit wt removed)	* 1.78e3	- 1.96e3	BTU/lb
Fine machining CO2 (per unit wt removed)	* 0.31	- 0.342	lb/lb
Grinding energy (per unit wt removed)	* 3.35e3	- 3.7e3	BTU/lb
Grinding CO2 (per unit wt removed)	* 0.584	- 0.645	lb/lb

Recycling and end of life

Recycle	✓		
Embodied energy, recycling	* 7.18e3	- 7.95e3	BTU/lb
CO2 footprint, recycling	* 0.605	- 0.669	lb/lb
Recycle fraction in current supply	1.43	- 1.58	%
Downcycle	✓		
Combust for energy recovery	✓		
Heat of combustion (net)	* 5.52e3	- 5.8e3	BTU/lb
Combustion CO2	* 1.08	- 1.13	lb/lb
Landfill	✓		
Biodegrade	✗		
Recycle mark			



Geo-economic data for principal component

Principal component	PVC (rigid)		
Annual world production	4.67e7	- 5.17e7	ton/yr
Reserves	6.46e8	- 7.14e8	l. ton

Eco-indicators for principal component

Eco-indicator 95	122		millipoints/lb
Eco-indicator 99	77.2		millipoints/lb
EPS value	564	- 624	

Links

ProcessUniverse

Producers

Reference

Shape