


Description

Process schematic



The process

In 3D CERAMIC MOLD PRINTING, a multi-jet print head, like that of a bubble-jet printer, deposits a binder on a bed of fine foundry sand. After each sweep of the print head, a new, thin, layer of sand is spread across the surface of the model, so that on the next sweep of the print head a new layer of bonded sand is created. The final model, after shaking it free of unbonded sand, now becomes the mold for a shell casting, allowing single metal parts with very complex shapes to be fabricated. As with other additive manufacturing processes, a CAD solid model of the part is required.

The data below refer to the casting itself, not the mold.

Material compatibility

| Metals - ferrous | ✓ |
|----------------------|---|
| Metals - non-ferrous | ✓ |

Shape

| <u>onapo</u> | |
|------------------------|---|
| Circular prismatic | ✓ |
| Non-circular prismatic | ✓ |
| Flat sheet | ✓ |
| Dished sheet | ✓ |
| Solid 3-D | ✓ |
| Hollow 3-D | ✓ |

Economic compatibility

| Economic batch size (units) | 1 | - 10 | |
|-----------------------------|---|------|--|
|-----------------------------|---|------|--|



Physical and quality attributes

| Mass range | 0.1 | - | 30 | kg |
|----------------------------|-----|---|-----|----|
| Range of section thickness | 0.8 | - | 100 | mm |
| Tolerance | 0.1 | - | 0.5 | mm |
| Roughness | 10 | - | 50 | μm |

Process characteristics

| Primary shaping processes | ✓ |
|---------------------------|---|
| Discrete | ✓ |
| Prototyping | ✓ |


Cost model and defaults

Relative cost index (per unit)

172 - 794

Resonant Mass - 1kg, Retch Size - 163 Overhead Rate - 150USD/kg Discount Rate - 59/, Conitro

Parameters: Material Cost = 8USD/kg, Component Mass = 1kg, Batch Size = 1e3, Overhead Rate = 150USD/hr, Discount Rate = 5%, Capital Write-off Time = 5yrs, Load Factor = 0.5



Capital Write-off Time=5yrs, Component Mass=1kg, Load Factor=0.5, Material Cost=8USD/kg, Overhead Rate=150USD/hr, Discount Rate=5%

| Capital cost | 5.66e4 | - | 1.32e5 | USD |
|-------------------------------|--------|---|--------|-----|
| Material utilization fraction | 0.4 | - | 0.6 | |
| Production rate (units) | 0.2 | - | 1 | /hr |
| Tooling cost | 0 | - | 0.1 | USD |
| Tool life (units) | 1e5 | - | 1e6 | |

Supporting information

Design guidelines

3D printing expands the techniques for rapid prototyping with metals. Printing with wax gives patterns for lost wax casting, and sand-mold printing creates a mold for shell castings. Both techniques are capable of almost unlimited freedom of shape and of complexity.

Technical notes



3D ceramic-mold prototyping

Rapid prototyping systems are evolving very rapidly, and are already an essential part of the model-building capability of designers. Their speed and precision will increase and their cost will decrease in the future.

Typical uses

Mold making for castings up to 30 kg in

The economics

The cost of making an object by 3-dimensional printing depends on size and process - \$300 to \$3000 gives an idea. This will decrease as faster systems become available.

The environment

No particular environmental

Links

MaterialUniverse

Reference