Anton Paar Kaomi for Nova

version 3.01

Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso

Analysis Data

Sample

ID	CNT	**Weight**	0.1322 g		
Name	CNT	**Description**	CNT		

Analysis

Data ID	{3d916f1c-fe01-40c0-b3f1-2ef8525a0c27}				
Analysis Profile	UJ N2 full isotherm(2)				
Operator	Solomon	**Date**	08/12/2026	**Duration**	811.90 min
Instrument	St 3 on NOVA 800 [s/n:1050040039]			**Firmware**	3.01
Comments:	""				
Void Volume Mode	He Measure	**Cold Zone**	25.2762 cm³	**Warm Zone**	3.08828 cm³
Cell Type	9 mm with filler rod				
Thermal Delay	180 sec	**p_0 Mode**	Monitor		

Adsorbate

Name	Nitrogen	**Molecular Weight**	28.0134 g/mol	**Cross Sectional Area**	16.2 Å²/molecule
Non-Ideality	6.580000e-05 1/Torr	**Bath Temperature**	77.35 K		

Degas information

Type	Vacuum Degassing
Operator	Solomon
Description	CNT
Degassed	Degas at 150 °C for 8 hours

Anton Paar Kaomi for Nova

version 3.01

Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso

BJH Adsorption Summary/Results

Surface Area 53.4164 m²/g **Pore Volume** 0.409953 cm³/g
Mode Pore Radius dV(r) 2.5872 nm


BJH Pore Size Distribution-Adsorption

Radius	Pore Volume	Pore Surface Area	dV(r)	dS(r)	dV(log r)	dS(log r)
nm	cm³/g	m²/g	cm³/nm/g	m²/nm/g	cm³/g	m²/g
1.60441	1.283612e-03	1.600108e+00	7.151523e-03	8.914849e+00	2.639218e-02	3.289960e+01
1.79512	2.704743e-03	3.183434e+00	7.037363e-03	7.840543e+00	2.905767e-02	3.237405e+01
2.01377	4.020588e-03	4.490281e+00	5.590884e-03	5.552655e+00	2.589469e-02	2.571764e+01
2.27292	5.778583e-03	6.037184e+00	6.213050e-03	5.467013e+00	3.247458e-02	2.857517e+01
2.58720	9.478633e-03	8.897458e+00	1.070614e-02	8.276236e+00	6.368415e-02	4.923018e+01
2.97210	1.233261e-02	1.081797e+01	6.727841e-03	4.527329e+00	4.596383e-02	3.093018e+01
3.46229	1.631046e-02	1.311578e+01	7.152153e-03	4.131457e+00	5.689571e-02	3.286593e+01
4.20436	2.580467e-02	1.763214e+01	1.023118e-02	4.866936e+00	9.864369e-02	4.692444e+01
5.28848	3.813949e-02	2.229694e+01	9.945370e-03	3.761148e+00	1.205493e-01	4.558943e+01
6.95205	5.850084e-02	2.815459e+01	9.756789e-03	2.806881e+00	1.550037e-01	4.459222e+01
10.1356	1.000182e-01	3.634698e+01	9.699866e-03	1.914019e+00	2.229711e-01	4.399761e+01
21.6487	2.320680e-01	4.854631e+01	7.044163e-03	6.507703e-01	3.279769e-01	3.029993e+01
73.0516	4.099527e-01	5.341643e+01	2.116170e-03	5.793633e-02	3.124403e-01	8.553965e+00

Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso


BJH-Adsorption-dV(d)



Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso


BJH-Adsorption-dV(logd)



Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso


BJH-Adsorption-dS(d)



Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso

BJH-Adsorption-dS(logd)



Anton Paar Kaomi for Nova

version 3.01

Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso

BJH Desorption Summary/Results

Surface Area 77.6597 m²/g **Pore Volume** 0.418254 cm³/g
Mode Pore Radius dV(r) 7.70851 nm


BJH Pore Size Distribution-Desorption

Radius	Pore Volume	Pore Surface Area	dV(r)	dS(r)	dV(log r)	dS(log r)
nm	cm³/g	m²/g	cm³/nm/g	m²/nm/g	cm³/g	m²/g
1.63860	4.876277e-04	5.951765e-01	2.677498e-03	3.268034e+00	1.009183e-02	1.231763e+01
1.83599	1.110509e-03	1.273700e+00	2.928978e-03	3.190625e+00	1.236846e-02	1.347335e+01
2.06970	2.369531e-03	2.490323e+00	4.942018e-03	4.775589e+00	2.352222e-02	2.273007e+01
2.34256	4.235144e-03	4.083120e+00	6.411803e-03	5.474179e+00	3.454042e-02	2.948944e+01
2.64774	6.662887e-03	5.916945e+00	7.601373e-03	5.741791e+00	4.628656e-02	3.496313e+01
3.06637	1.228432e-02	9.583453e+00	1.085449e-02	7.079697e+00	7.645653e-02	4.986774e+01
3.68066	2.249734e-02	1.513301e+01	1.437079e-02	7.808819e+00	1.214135e-01	6.597382e+01
4.47321	3.738957e-02	2.179143e+01	1.703096e-02	7.614656e+00	1.748579e-01	7.818009e+01
5.64097	6.645466e-02	3.209643e+01	1.989258e-02	7.052897e+00	2.569299e-01	9.109426e+01
7.70851	1.256808e-01	4.746287e+01	2.214911e-02	5.746668e+00	3.891612e-01	1.009693e+02
12.7284	2.541817e-01	6.765409e+01	1.744558e-02	2.741205e+00	4.966968e-01	7.804544e+01
32.4334	4.152466e-01	7.758613e+01	5.026341e-03	3.099485e-01	3.425458e-01	2.112303e+01
81.7685	4.182540e-01	7.765968e+01	4.513747e-05	1.104031e-03	8.005398e-03	1.958065e-01

Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso


BJH-Desorption-dV(d)



Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso


BJH-Desorption-dV(logd)



Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso


BJH-Desorption-dS(d)



Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso

BJH-Desorption-dS(logd)



Anton Paar Kaomi for Nova

version 3.01

Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso


HK Method Summary/Results

Mode(Half Pore Width) 0.21575 nm **Micropore Volume** 0.0359558 cm³/g

HK Method-Pore Size Distribution

Half Pore Width nm	dV(r) cm³/nm/g
0.188250	0.182006
0.213250	0.198257
0.238250	0.0487534
0.263250	0.063625
0.288250	0.0602702
0.313250	0.0472133
0.338250	0.0417946
0.363250	0.0390092
0.388250	0.0354525
0.413250	0.0343833
0.438250	0.0335001
0.463250	0.0320765
0.488250	0.031098
0.513250	0.0303786
0.538250	0.0295617
0.563250	0.0292186
0.588250	0.0287666
0.613250	0.0282855
0.638250	0.0279841
0.663250	0.0271422
0.688250	0.025772
0.713250	0.0247879
0.738250	0.0241863
0.763250	0.0235776
0.788250	0.0237263
0.813250	0.0238665
0.838250	0.0232628
0.863250	0.0226425
0.888250	0.0224677
0.913250	0.0223043
0.938250	0.0215808
0.963250	0.0208005
0.988250	0.020334
1.00075	0.0201154

HK Method Pore Volume



Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso


Kr(87K) Pore Size Distribution Summary/Results

Mode Pore Radius dV(r) 3.00305 nm

Kr(87K) Pore Size Distribution-Pore Size Distribution

Radius nm	Pore Volume cm³/g	dV(r) cm³/nm/g	dV(log r) cm³/g
0.487840	0.000000e+00	0.000000e+00	0.000000e+00
0.554949	0.000000e+00	0.000000e+00	0.000000e+00
0.635537	0.000000e+00	0.000000e+00	0.000000e+00
0.737806	0.000000e+00	0.000000e+00	0.000000e+00
0.834686	0.000000e+00	0.000000e+00	0.000000e+00
0.930323	0.000000e+00	0.000000e+00	0.000000e+00
1.00430	0.000000e+00	0.000000e+00	0.000000e+00
1.05536	0.000000e+00	0.000000e+00	0.000000e+00
1.12810	0.000000e+00	0.000000e+00	0.000000e+00
1.23058	0.000000e+00	0.000000e+00	0.000000e+00
1.34271	0.000000e+00	0.000000e+00	0.000000e+00
1.46132	0.000000e+00	0.000000e+00	0.000000e+00
1.58952	0.000000e+00	0.000000e+00	0.000000e+00
1.72916	8.568962e-04	5.886960e-03	2.342537e-02
1.87997	8.568962e-04	0.000000e+00	0.000000e+00
2.04490	2.688934e-03	1.053958e-02	4.959641e-02
2.24740	1.304513e-02	4.480008e-02	2.316282e-01
2.47761	3.037330e-02	7.558191e-02	4.308806e-01
2.72294	6.456228e-02	1.308002e-01	8.194601e-01
3.00305	1.438700e-01	2.653812e-01	1.833537e+00

Kr(87K) Pore Size Distribution-dV(d)



Copyright ©2025 Anton Paar GmbH

Report date: 08/13/2026 **Operator:** Solomon
File name: CNT.qcuPhysIso

Kr(87K) Pore Size Distribution-dV(logd)

