DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 25/10/2026 Shift: C

Color: CL12 Thickness: 2.00mm Batch: 40405

Mixer Operator: ALFRED CPW: 79 kg Line Speed: 40 Hz

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	1.96	1.98	0.10mm	Complies	No	Complies
22:50	1.98	1.96	0.06mm	Complies	Slight shade variation	Complies
23:15	1.90	1.95	0.08mm	Complies	No	Complies
23:40	1.92	1.97	0.00mm	Complies	No	Complies
00:05	1.94	1.96	0.06mm	Complies	No	Complies
00:30	1.95	1.97	0.03mm	Complies	No	Complies
00:55	1.92	1.95	0.06mm	Complies	No	Complies
01:20	1.95	1.98	0.10mm	Complies	No	Complies
01:45	1.90	1.98	0.06mm	Complies	No	Complies
02:10	1.95	1.96	0.02mm	Complies	No	Complies
02:35	1.90	1.95	0.02mm	Complies	No	Complies
03:00	1.95	1.96	0.06mm	Complies	No	Complies
03:25	1.94	1.98	0.00mm	Complies	No	Complies
03:50	1.90	1.95	0.06mm	Complies	No	Complies
04:15	1.91	1.98	0.10mm	Complies	No	Complies
04:40	1.94	1.97	0.08mm	Complies	No	Complies
05:05	1.91	1.96	0.04mm	Complies	No	Complies
05:30	1.95	1.97	0.10mm	Complies	No	Complies
05:55	CL12R	2.00	40415			

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 – 23:00	36	24	-12
23:00 – 00:00	36	28	-8
00:00 – 01:00	36	24	-12
01:00 – 02:00	36	20	-16
02:00 – 03:00	36	17	-19
03:00 – 04:00	36	24	-12
04:00 – 05:00	36	26	-10
05:00 – 06:00	36	6/4	changing colour
Total	288	173	-115

Remarks: 1. Colour Change. 2. No Thickness change
2. Slight shade variation observed on boxes 24–32 - separated to another pallet
3. Replaced 9 boxes with the balance (9 boxes)

Checked By QAI: SENTO Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 28/10/2026

Shift: B

Color: marbling

Thickness: 2.00mm

Batch: 9101

Mixer Operator: REFILWE

CPW: 48 kg

Line Speed: 38 Hz

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
16:25						
14:50						
15:15						
15:40						
16:05	PRODUCTION		STOPPED –	NO MARBLING		
16:30						
16:55						
17:20						
17:45						
18:10						
18:35						
19:00						
19:25						
19:50						
20:15						
20:40						
21:05						
21:30	CL 12	2.00	40405			
21:55	1.92	1.97	0.10mm	complies	NO	complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
21:35 22:00	36	12	-24
Total	36	12	-24

Remarks: * Colour change
* No thickness change

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 28/10/2026

Shift: A

Color: CL15

Thickness: 200mm

Batch: 40395

Mixer Operator: BOAGO

CPW: 79 kg

Line Speed: 40 Hz

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25	1.90	1.97	0.09mm	Complies	NO	Complies
06:50	1.96	1.97	0.08mm	Complies	NO	Complies
07:15	1.92	1.98	0.10 mm	Complies	NO	Complies
07:40	1.94	1.97	0.00 mm	Complies	NO	Complies
08:05	1.94	1.98	0.00mm	Complies	NO	Complies
08:30	1.92	1.97	0.05mm	Complies	NO	Complies
08:55	1.94	1.99	0.10mm	Complies	NO	Complies
09:20	1.93	1.95	0.08 mm	Complies	NO	Complies
09:45	1.91	1.97	0.02 mm	Complies	NO	Complies
10:10	1.94	1.97	0.00mm	Complies	NO	Complies
10:35	1.92	1.95	0.08 mm	Complies	NO	Complies
11:00	1.90	1.99	0.10 mm	Complies	NO	Complies
11:25	1.94	1.97	0.02 mm	Complies	NO	Complies
11:50	1.93	1.97	0.05 mm	Complies	NO	Complies
12:15	1.94	1.98	0.00 mm	Complies	NO	Complies
12:40	1.92	1.96	0.08mm	Complies	NO	Complies
13:05	MARBLING		2.00 9101			
13:30	↓		↓	↓	↓	↓
13:55	↓		↓	↓	↓	↓

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	36	26	-10
07:00 08:00	36	24	-12
08:00 09:00	36	30	-6
09:00 10:00	36	28	-8
10:00 11:00	36	24	Linecut -12
11:00 12:00	36	28	-18
12:00 13:00	36	9	Colour Change
13:00 14:00	marbling 2.00 9101 -	-	-
Total	288	167	-121

Remarks: *Colour change
*No thickness change
*Material fall from mixing mill causing several line cuts.

Checked By QAI: BETTY

Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 27/10/2026

Shift: C

Color: 207

Thickness: 250mm

Batch: 5265

Mixer Operator: ALFRED

CPW: 30.5 kg

Line Speed: 32/41 Hz

Time	Thickness Range: 237-263 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.45	2.46	0.10mm	Complies	No	Rough
22:50	2.42	2.45	0.106mm	Complies	No	"
23:15	2.40	2.45	0.108mm	Complies	No	Complies
23:40	2.45	2.45	0.10mm	Complies	No	Complies
00:05	2.44	2.45	0.108mm	Complies	No	Complies
00:30	2.46	2.52	0.106mm	Complies	No	Complies
00:55	2.45	2.50	0.102mm	Complies	No	Complies
01:20	2.43	2.48	0.10mm	Complies	No	Complies
01:45	2.45	2.50	0.103mm	Complies	No	Complies
02:10	2.43	2.47	0.106mm	Complies	No	Complies
02:35	2.45	2.50	0.10mm	Complies	No	Complies
03:00	2.43	2.48	0.13mm	Complies	No	Complies
03:25	2.45	2.47	0.106mm	Complies	No	Complies
03:50	2.42	2.45	0.10mm	Complies	No	Complies
04:15	2.45	2.45	0.108mm	Complies	No	Complies
04:40	2.43	2.46	0.106mm	Complies	No	Complies
05:05	2.41	2.45	0.108mm	Complies	No	Complies
05:30	CLIS	2.00	40393			
05:55	2.44	2.48	0.10mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00			
23:00	36	7	-29
23:00			
00:00	36	36	—
00:00			
01:00	36	22	-14
01:00			
02:00	36	26	-10
02:00			
03:00	36	28	-8
03:00			
04:00	36	26	-10
04:00			
05:00	36	18	-18
05:00			Changing thickness
06:00	36	13	
Total	288	186	-102

Remarks: No colour change
Thickness increase
Material felling at mixing mill causing low production

Checked By QAI: SETTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 27/01/2026

Shift: B

Color: 207

Thickness: 2.50mm

Batch: 5265

Mixer Operator: BOAGO

CPW: 80.5 kg

Line Speed: 34 Hz

	Thickness Range: 237-263						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
14:25	2.42	2.48	0.10 mm	Complies	NO	complies	14:00 15:00	36	18	Line cuts -18
14:50	2.44	248	0.02 mm	complies	NO	complies	15:00 16:00	36	24	-12
15:15	2.41	247	0.05 mm	complies	NO	complies	16:00 17:00	36	28	-8
15:40	2.43	2.47	0.00 mm	complies	NO	complies	17:00 18:00	36	24	-12
16:05	2.42	246	0.08 mm	complies	NO	complies	18:00 19:00	36	24	Line cuts -12
16:30	2.40	2.49	0.10 mm	complies	NO	complies	19:00 20:00	36	18	Line cuts -18
16:55	2.44	248	0.02 mm	complies	NO	complies	20:00 21:00	36	20	-16
17:20	2.45	248	0.05 mm	complies	NO	complies	21:00 22:00	36	21	-15
17:45	2.42	247	002 mm	complies	NO	complies				
18:10	2.44	247	000 mm	complies	NO	complies				
18:35	2.41	2.49	0.10 mm	complies	NO	complies				
19:00	2.43	2.48	0.08 mm	complies	NO	complies				
19:25	2.40	248	0.05 mm	complies	NO	complies				
19:50	2.44	2.46	0.02 mm	complies	NO	complies				
20:15	2.41	2.47	0.00 mm	complies	NO	complies				
20:40	2.44	2.47	0.10 mm	complies	NO	complies				
21:05	2.42	2.48	0.00 mm	complies	NO	complies				
21:30	2.41	2.49	0.02 mm	complies	NO	complies				
21:55	2.43	2.48	0.05 mm	complies	NO	complies	Total	288	177	-111

Remarks: * NO colour change
* NO thickness change slight shade variation (light) observed from box 128-180
* material fall from mixing mill causing several line cuts

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 27/10/2026 Shift: A

Color: 204 Thickness: 2.00mm Batch: 5255

Mixer Operator: BOAGO CPW: 79 kg Line Speed: 44 Hz

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25	1.90	1.98	0.00 mm	Complies	NO	Complies
06:50	1.94	1.98	0.02 mm	Complies	NO	Complies
07:15	1.93	1.96	0.05 mm	Complies	NO	Complies
07:40	1.94	1.97	0.00 mm	Complies	NO	Complies
08:05	1.92	1.95	0.08 mm	Complies	NO	Complies
08:30	1.94	1.96	0.05 mm	Complies	NO	Complies
08:55	1.94	1.97	0.00 mm	Complies	NO	Complies
09:20	1.92	1.97	0.08 mm	Complies	NO	Complies
09:45	1.94	1.98	0.00mm	Complies	NO	Complies
10:10	2.07	2.50	5265			
10:35	2.44	2.47	0.08 mm	Complies	NO	Complies
11:00	2.40	2.47	0.05mm	Complies	NO	Complies
11:25	CHANGING		KNIVES			
11:50	↓		↓		↓	↓
12:15	↓		↓		↓	↓
12:40	RESTART					
13:05	2.44	2.48	0.00 mm	Complies	NO	Complies
13:30	2.42	2.47	0.02 mm	Complies	NO	Complies
13:55	2.40	2.47	0.00 mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	36	20	in 30 mins
07:00 08:00	36	24	-12
08:00 09:00	36	16	No marbling
09:00 10:00	36	30	-6
10:00 11:00	36	18	Colour + Thickness Change
11:00 12:00	36	11	Changing Knives
12:00 13:00	36	20	in 25 mins
13:00 14:00	36	29	-7
Total	288	160	-128

Remarks: *Colour Change
#Thickness Change
*Several line cuts due to material fall from mixing mill.

Checked By QAI: BETTY Supervisor: MAKO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 26/10/2026

Shift: C

Color: 202

Thickness: 2.00mm

Batch: 5245

Mixer Operator: Alfred

CPW: 79 kg

Line Speed: 41 Hz

	Thickness Range: 1.87 – 2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
22:25	1.90	1.94	0.05 mm	Complies	NO	Complies	22:00 23:00	36	32	
22:50	1.93	1.96	0.00 mm	Complies	NO	Complies	23:00 00:00	36	31	
23:15	1.94	1.96	0.05 mm	Complies	NO	Complies	00:00 01:00	36	28	
23:40	1.95	1.99	0.02 mm	Complies	NO	Complies	01:00 02:00	36	36	
00:05	1.95	1.99	0.05 mm	Complies	NO	Complies	02:00 03:00	36	28	
00:30	1.94	1.98	0.04 mm	Complies	NO	Complies	03:00 04:00	36	32	
00:55	1.92	1.97	0.02 mm	Complies	NO	Complies	04:00 05:00	36	28	
01:20	1.92	1.97	0.02 mm	Complies	NO	Complies	05:00 06:00	36		
01:45	1.93	1.96	0.05 mm	Complies	NO	Complies				
02:10	1.94	1.98	0.03 mm	Complies	NO	Complies	Total	288	257	
02:35	1.93	1.98	0.04 mm	Complies	NO	Complies				
03:00	1.92	1.97	0.03 mm	Complies	NO	Complies				
03:25	1.92	1.97	0.04 mm	Complies	NO	Complies				
03:50	1.93	1.98	0.05 mm	Complies	NO	Complies				
04:15	1.94	1.98	0.05 mm	Complies	NO	Complies				
04:40	1.93	1.97	0.05 mm	Complies	NO	Complies				
05:05	1.92	1.97	0.03 mm	Complies	NO	Complies				
05:30	1.92	1.98	0.02 mm	Complies	NO	Complies				
05:55	1.92	1.97	0.02 mm	Complies	NO					

Remarks: No thickness change and colour change

Checked By QAI: Motshidiso

Supervisor: Daniel

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 26/10/2026 Shift: B

Color: 202 Thickness: 2.00mm Batch: 5245

Mixer Operator: REFILWE CPW: 79 kg Line Speed: 41 Hz

	Thickness Range: 1.87–2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
14:25	1.92	1.96	0.10 mm	complies	NO	complies	14:00 15:00	36	31	−5
14:50	1.94	1.98	0.05mm	complies	NO	complies	15:00 16:00	36	24	Line cut −12
15:15	1.90	1.97	0.02 mm	complies	NO	complies				
15:40	1.93	1.92	0.00 mm	complies	NO	complies	16:00 17:00	36	26	−10
16:05	1.96	1.98	0.10 mm	complies	NO	complies				
16:30	1.91	1.99	0.05 mm	complies	NO	complies	17:00 18:00	36	30	−6
16:55	1.94	1.97	0.08 mm	complies	NO	complies				
17:20	1.92	1.98	0.02 mm	complies	NO	complies	18:00 19:00	36	24	Line cuts −12
17:45	1.90	1.97	0.05 mm	complies	NO	complies				
18:10	1.94	1.99	0.10 mm	complies	NO	complies	19:00 20:00	36	32	−4
18:35	1.92	1.98	0.00 mm	complies	NO	complies				
19:00	1.90	1.96	0.05 mm	complies	NO	complies	20:00 21:00	36	24	Line cut −12
19:25	1.94	1.97	0.00 mm	complies	NO	complies				
19:50	1.92	1.97	0.02 mm	complies	NO	complies	21:00 22:00	36	32	−4
20:15	1.92	1.98	0.10 mm	complies	NO	complies				
20:40	1.91	1.98	0.05 mm	complies	NO	complies				
21:05	1.90	1.99	0.02 mm	complies	NO	complies				
21:30	1.94	1.97	0.00 mm	complies	NO	complies				
21:55	1.92	1.97	0.10 mm	complies	NO	complies	Total	288	223	−65

Remarks: * NO colour change
* NO thickness change

Checked By QAI: KARABO Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 26/10/2026 Shift: A

Color: VT38 Thickness: 2.50mm Batch: 5235

Mixer Operator: ..... CPW: 80 kg Line Speed: 35 Hz

	Thickness Range: 2.37-2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
06:25	2.40	2.48	0.05 mm	Complies	NO	Complies	06:00 07:00	36	10	in 25 mins
06:50	2.44	2.47	0.00 mm	Complies	NO	Complies	07:00 08:00	36	9	colour + thickness change
07:15	2.42	2.46	0.02 mm	Complies	NO	Complies	08:00 09:00	36	20	in 50 mins
07:40	2.44	2.47	0.00 mm	Complies	NO	Complies	09:00 10:00	36	28	line cut
08:05	202	2.00	5245				10:00 11:00	36	26	-10
08:30	1.94	1.97	0.05mm	Complies	NO	Complies	11:00 12:00	36	26	-10
08:55	1.92	1.97	0.00 mm	Complies	NO	Complies	12:00 13:00	36	22	-14
09:20	1.94	1.98	0.08 mm	Complies	NO	Complies	13:00 14:00	36	27	-9
09:45	1.92	1.96	0.10 mm	Complies	NO	Complies				
10:10	1.94	1.97	0.05mm	Complies	NO	Complies				
10:35	1.92	1.98	0.00 mm	Complies	NO	Complies				
11:00	1.94	1.95	0.05mm	Complies	NO	Complies				
11:25	1.92	1.98	0.08 mm	Complies	NO	Complies				
11:50	1.94	1.97	0.05 mm	Complies	NO	Complies				
12:15	1.90	1.95	0.10 mm	Complies	NO	Complies				
12:40	1.94	1.97	0.08 mm	Complies	NO	Complies				
13:05	1.94	1.99	0.05mm	Complies	NO	Complies				
13:30	1.92	1.97	0.08mm	Complies	NO	Complies				
13:55	1.94	1.97	0.02 mm	Complies	NO	Complies	Total	288	168	-120

Remarks: *Colour change
*Thickness change
*Material spill from mixing mill causing several line cuts.

Checked By QAI: BETTY Supervisor: MAILO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 23/01/2026

Shift: C

Color: VT 38

Thickness: 2.50mm

Batch: 5235

Mixer Operator: BOAGD

CPW: 79 kg

Line Speed: 34 Hz

	Thickness Range: 2.37 – 2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
22:25	2.40	2.47	0.10mm	complies	NO	complies	22:00 23:00	36	20	Uncounts -16
22:50	2.42	2.48	0.00 mm	complies	Slight shade variation	complies	23:00 00:00	36	24	-12
23:15	2.44	2.47	0.02mm	complies	NO	complies	00:00 01:00	36	28	-8
23:40	2.42	2.45	0.05 mm	complies	NO	complies	01:00 02:00	36	32	-4
00:05	2.43	2.48	0.08 mm	complies	NO	complies	02:00 03:00	36	32	-4
00:30	2.44	2.48	0.02 mm	complies	NO	complies	03:00 04:00	36	24	-12
00:55	2.42	2.47	0.00mm	complies	NO	complies	04:00 05:00	36	24	-12
01:20	2.41	2.48	0.10 mm	complies	NO	complies	05:00 06:00	36	26	-10
01:45	2.40	2.46	0.02mm	complies	NO	complies				
02:10	2.42	2.45	0.05 mm	complies	NO	complies	Total	288	210	-78
02:35	2.44	2.47	0.08mm	complies	NO	complies				
03:00	2.45	2.47	0.00 mm	complies	NO	complies				
03:25	2.40	2.48	0.05mm	complies	NO	complies				
03:50	2.42	2.48	0.10mm	complies	NO	complies				
04:15	2.44	2.47	0.02 mm	complies	NO	complies				
04:40	2.41	2.49	0.08 mm	complies	NO	complies				
05:05	2.42	2.47	0.05 mm	complies	NO	complies				
05:30	2.43	2.42	0.10 mm	complies	NO	complies				
05:55	2.46	2.48	0.02 mm	complies	NO	complies				

Remarks: * NO colour change
* NO thickness change

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 23/02/2026 Shift: B

Color: VT 38 Thickness: 20mm Batch: 5735

Mixer Operator: ALFRED CPW: 80 kg Line Speed: 35 Hz

Time	Thickness Range: 2.37-2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	CHANGING		KNIVES			
14:50	2.41	2.47	0.00 mm	Complies	No	Complies
15:15	2.44	2.47	0.02mm	Complies	No	Complies
15:40	2.41	2.46	0.00 mm	Complies	No	Complies
16:05	2.44	2.48	0.08mm	Complies	No	Complies
16:30	2.40	2.46	0.10 mm	Complies	No	Complies
16:55	2.44	2.47	0.08 mm	Complies	Slight shade variation	Complies
17:20	2.43	2.47	0.00mm	Complies	No	Complies
17:45	2.40	2.46	0.08 mm	Complies	No	Complies
18:10	2.44	2.48	0.05 mm	Complies	Slight shade variation	Complies
18:35	2.42	2.47	0.00mm	Complies	No	Complies
19:00	2.44	2.47	0.00 mm	Complies	No	Complies
19:25	2.43	2.46	0.02 mm	Complies	No	Complies
19:50	2.43	2.49	0.10 mm	Complies	No	Complies
20:15	2.40	2.47	0.00 mm	Complies	Slight shade variation	Complies
20:40	2.44	2.45	0.02 mm	Complies	No	Complies
21:05	2.44	2.47	0.00 mm	Complies	No	Complies
21:30	2.42	2.46	0.00 mm	Complies	No	Complies
21:55	2.44	2.47	0.05 mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 15:00	36	12	changing knives
15:00 16:00	36	30	-6
16:00 17:00	36	26	Line Cut
17:00 18:00	36	30	-6
18:00 19:00	36	32	-4
19:00 20:00	36	24	Linecut
20:00 21:00	36	30	-6
21:00 22:00	36	30	-6
Total	288	204	-84

Remarks: *No colour change
*No thickness change
*Material fell from mixing mill causing several line cuts. *Inconsistent shade

Checked By QAI: BETTY Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 23/10/2026 Shift: A

Color: 202 Thickness: 2.00mm Batch: 5225

Mixer Operator: Alfred CPW: 79 kg Line Speed: ..... Hz

Time	Thickness Range: 1.87 – 2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25	1.90	1.94	0.00mm	Complies	NO	Complies
06:50	1.94	1.97	0.02mm	Complies	NO	Complies
07:15	CL12	2.00	403~~7~~5			
07:40	1.93	1.96	0.00mm	Complies	NO	Complies
08:05	1.95	1.97	0.05 mm	Complies	NO	Complies
08:30	1.91	1.97	0.05 mm	Complies	NO	Complies
08:55	1.93	1.98	0.08 mm	Complies	NO	Complies
09:20	1.93	1.97	0.05 mm	Complies	NO	Complies
09:45	1.90	1.95	0.02 mm	Complies	NO	Complies
10:10	1.92	1.96	0.05mm	Complies	NO	Complies
10:35	CL149	2.00	40385			
11:00	1.93	1.98	0.00mm	Complies	NO	Complies
11:25	1.96	1.99	0.02mm	Complies	NO	Complies
11:50	1.95	1.98	0.02 mm	Complies	NO	Complies
12:15	1.94	1.97	0.07 mm	Complies	NO	Complies
12:40	1.93	1.96	0.10 mm	Complies	NO	Complies
13:05	1.94	1.97	0.10 mm	Complies	NO	Complies
13:30	1.90	1.97	0.08 mm	Complies	Slight shade	Complies
13:55	Changing Punching Press Knives					

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 – 07:00	36	32	
07:00 – 08:00	36	26	-10
08:00 – 09:00	36	26	-10
09:00 – 10:00	36	29	
10:00 – 11:00	36	19	Colour change
11:00 – 12:00	36	24	
12:00 – 13:00	36	24	
13:00 – 14:00	36		
Total			

Remarks: *Colour change *Slight shade variation observe from box 69 to 82. QC Manager to review shade for approval *Separated box 70 → 82 (reserved them for recycling) and repacked CL69 200 39245 (15 boxes) from dispatch to complete the order of 84 boxes.

Checked By QA: MATSHIDISO Supervisor: Daniel

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 22/01/2026

Shift: C

Color: 202

Thickness: 2.00mm

Batch: 5225

Mixer Operator: REFILWE

CPW: 79 kg

Line Speed: 41 Hz

	Thickness Range: 1.87–2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
23:25	1.92	1.97	0.05mm	complies	NO	complies	23:25 00:00	36	20	Line cut −16
23:50	1.94	1.98	0.02 mm	complies	NO	complies	00:00 01:00	36	20	Line cuts − 16
00:15	1.90	1.97	0.10 mm	complies	NO	complies	01:00 02:00	36	24	Line cuts −12
00:40	1.92	1.99	0.08mm	complies	NO	complies	02:00 03:00	36	30	−6
01:05	1.94	1.98	0.05mm	complies	NO	complies	03:00 04:00	36	26	−10
01:30	1.91	1.97	0.00 mm	complies	NO	complies	04:00 05:00	36	26	−10
01:55	1.93	1.97	0.10mm	complies	NO	complies	05:00 06:00	36	28	−8
02:20	1.92	1.99	0.05mm	complies	NO	complies				
02:45	1.94	1.96	0.02mm	complies	NO	complies				
03:10	1.90	1.98	0.10 mm	complies	NO	complies				
03:35	1.93	1.98	0.00mm	complies	NO	complies				
04:00	1.91	1.97	0.08 mm	complies	NO	complies				
04:25	1.92	1.99	0.05 mm	complies	NO	complies				
04:50	1.94	1.97	0.02 mm	complies	NO	complies				
05:15	1.92	1.98	0.00 mm	complies	NO	complies				
05:40	1.90	1.98	0.05 mm	complies	NO	complies	Total	237	174	−63

Remarks: * n/o colour change

* no thickness change

* Production started late because of the combi.

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 22/1/2026

Shift: B

Color: MARBLING

Thickness: 200mm

Batch: 9212

Mixer Operator: BOAGO

CPW: 50 kg

Line Speed: 34 Hz

Time	Thickness Range: 1.87-2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	↓		↓	↓	↓	↓
14:50	↓		↓	↓	↓	→
15:15	PRODUCTION STOPPED					
15:40	RESTART					
16:05	↓		↓	↓	↓	↓
16:30	2.02	2.00	5225	→	→	→
16:55	1.92	1.99	0.00 mm	Complies	NO	Complies
17:20	1.90	1.95	0.08 mm	Complies	NO	Complies
17:45	1.90	1.97	0.05 mm	Complies	NO	Complies
18:10	1.93	1.97	0.02 mm	Complies	NO	Complies
18:35	1.96	1.98	0.00 mm	Complies	NO	Complies
19:00	1.94	1.97	0.08mm	Complies	NO	Complies
19:25	1.93	1.96	0.00 mm	Complies	NO	Complies
19:50	1.94	1.97	0.08 mm	Complies	NO	Complies
20:15	1.94	1.95	0.05 mm	Complies	NO	Complies
20:40	1.90	1.98	0.10 mm	Complies	NO	Complies
21:05	1.92	1.97	0.00mm	Complies	NO	Complies
21:30	1.94	1.97	0.05 mm	Complies	NO	Complies
21:55	1.94	1.99	0.05 mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
16:00 17:00	36	12	In 30 mins
17:00 18:00	36	28	Linecut -8
18:00 19:00	36	26	-10
19:00 20:00	36	30	-6
20:00 21:00	36	24	Line Cuts
21:00 22:00	36	20	-16
Total	288	140	-148

Remarks: *NO Colour change
*No thickness change
*Material fall from mixing mill causing several line cuts.

Checked By QAI: BETTY

Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 22/10/2026

Shift: A

Color: Q14

Thickness: 2.50mm

Batch: 40365

Mixer Operator: Alfred

CPW: 80 kg

Line Speed: 31 Hz

Time	Thickness Range: 2.37–2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25	2.41	2.47	0.00 mm	Complies	NO	Complies
06:50	2.40	2.48	0.05 mm	Complies	NO	Complies
07:15	PRODUCTION		STOPPED	–		
07:40						
08:05	RESTART					
08:30	2.43	2.48	0.00mm	Complies	NO	Complies
08:55	2.42	2.48	0.05 mm	Complies	NO	Complies
09:20	2.42	2.47	0.05mm	Complies	NO	Complies
09:45	2.41	2.46	0.03mm	complies	No	Complies
10:10	2.43	2.45	0.07mm	Complies	No	Complies
10:35	2.45	2.49	0.05 mm	Complies	NO	Complies
11:00	2.44	2.49	0.06 mm	Complies	NO	Complies
11:25	2.43	2.48	0.00 mm	Complies	No	Complies
11:50	2.44	2.48	0.05 mm	Complies	NO	Complies
12:15	2.40	2.46	0.05 mm	Complies	NO	Complies
12:40	2.43	2.47	0.00 mm	Complies	NO	Complies
13:05	2.44	2.47	0.08 mm	Complies	NO	Complies
13:30	2.42	2.46	0.08 mm	Complies	NO	Complies
13:55	MARBLING	9212		2.00		

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	36	18	
07:00 08:00	—	—	—
08:00 09:00	36	20	-16
09:00 10:00	36	28 +3	-5
10:00 11:00	36	32	-4
11:00 12:00	36	29	
12:00 13:00	36	24	
13:00 14:00	36		
Total	252		

Remarks: * No colour change
* Thickness change

Checked By QAI: MATSHIDISO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 21/10/2026

Shift: C

Color: Q14

Thickness: 2.50 mm

Batch: 40365

Mixer Operator: REFILWE

CPW: 80 kg

Line Speed: 31 Hz

	Thickness Range: 2.37–2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
22:25	2.44	2.47	0.10 mm	complies	no	complies	22:00 23:00	36	19	-17 (4 x cuts)
22:50	2.40	2.48	0.05 mm	complies	no	complies	23:00 00:00	36	24	-12 (4 x cuts)
23:15	2.42	2.47	0.00 mm	complies	no	complies	60:00 61:00	36	19	-17
23:40	2.41	2.49	0.02 mm	complies	no	complies	01:00 02:00	36	30	-6
00:05	2.44	2.48	0.08 mm	complies	no	complies	02:00 03:00	36	24	-12
00:30	2.42	2.48	0.00 mm	complies	no	complies	03:00 04:00	36	24	-12
00:55	2.40	2.47	0.10 mm	complies	no	complies	04:00 05:00	36	24	-12
01:20	2.43	2.49	0.02 mm	complies	no	complies	05:00 06:00	36	26	-10
01:45	2.44	2.49	0.05 mm	complies	no	complies				
02:10	2.42	2.48	0.08 mm	complies	no	complies				
02:35	2.44	2.47	0.10 mm	complies	no	complies				
03:00	2.40	2.47	0.05 mm	complies	no	complies				
03:25	2.41	2.46	0.02 mm	complies	no	complies				
03:50	2.42	2.48	0.08 mm	complies	no	complies				
04:15	2.43	2.49	0.10 mm	complies	no	complies				
04:40	PRODUCTION STOPPED – breakdown at mixing mill									
05:05	RESTART									
05:30	2.44	2.49	0.10 mm	complies	no	complies	Total	288	190	-98
05:55	2.42	2.47	0.05 mm	complies	no	complies				

Remarks: * no colour change
* no thickness change
* material fall from mixing mill causing several line cuts.

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 21/10/2026

Shift: B

Color: 814

Thickness: 2.50mm

Batch: 40365

Mixer Operator: BOAGO

CPW: 80 kg

Line Speed: 33 Hz

Time	Thickness Range: 2.37–2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	2.42	2.47	0.00mm	Complies	NO	Complies
14:50	2.44	2.48	0.05 mm	Complies	NO	Complies
15:15	2.43	2.46	0.10 mm	Complies	NO	Complies
15:40	2.43	2.45	0.08 mm	Complies	NO	Complies
16:05	2.40	2.47	0.08 mm	Complies	NO	Complies
16:30	2.44	2.47	0.00 mm	Complies	NO	Complies
16:55	CHANGING		KNIVES			
17:20	↓		↓	↓	↓	↓
17:45	RESTART					
18:10	2.43	2.47	0.00 mm	Complies	NO	Complies
18:35	2.42	2.48	0.00 mm	Complies	NO	Complies
19:00	2.44	2.46	0.05 mm	Complies	NO	Complies
19:25	2.42	2.45	0.08 mm	Complies	NO	Complies
19:50	2.40	2.46	0.00 mm	Complies	NO	Complies
20:15	2.44	2.47	0.00 mm	Complies	NO	Complies
20:40	2.44	2.47	0.00 mm	Complies	NO	Complies
21:05	2.44	2.47	0.05 mm	Complies	NO	Complies
21:30	2.41	2.48	0.00 mm	Complies	NO	Complies
21:55	2.44	2.49	0.02 mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 15:00	36	32	-4
15:00 16:00	36	28	-8
16:00 17:00	CHANGING ↓	↓	KNIVES ↓
17:00 18:00	36	10	in 15 mins
18:00 19:00	36	32	-4
19:00 20:00	36	26	-10
20:00 21:00	36	30	-6
21:00 22:00	36	29	-7
Total	288	187	-65

Remarks: *No colour change
*No thickness Change
*1 in hole observed, knives were changed, then tiles were much better after that.

Checked By QAI: BETTY

Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 21/10/26

Shift: A

Color: Q14

Thickness: 2.50mm

Batch: 40365

	Thickness Range: 2.37 - 2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
06:25	2.43	2.48	0.00 mm	Complies	NO	Complies	06:00 07:00	36	27	
06:50	2.41	2.49	0.05mm	Complies	NO	Complies	09:00 08:00	36	20	Several line cuts
07:15	2.44	2.49	0.10 mm	Complies	NO	Complies	08:00 09:00	36	20	
07:40	2.44	2.48	0.08 mm	Complies	NO	Complies	09:00 10:00	36	24	line cuts
08:05	2.43	2.48	0.08 mm	Complies	NO	Complies	10:00 11:00	36	20	
08:30	2.45	2.48	0.00 mm	Complies	NO	Complies	11:00 12:00	36	28	
08:55	2.43	2.47	0.00mm	Complies	NO	Complies	12:00 13:00	36		
09:20	2.42	2.45	0.04mm	complies	NO	complies	13:00 14:00	36		
09:45	1.44	2.46	0.05mm	complies	NO	complies				
10:10	2.41	2.44	0.09mm	complies	NO	Complies				
10:35	2.43	2.46	0.07mm	Complies	No	Complies				
11:00	2.42	2.44	0.04mm	complies	No	complies				
11:25	2.40	2.45	0.00 mm	Complies	NO	Complies				
11:50	2.43	2.46	0.00 mm	Complies	NO	Complies				
12:15	2.41	2.46	0.05 mm	Complies	NO	Complies				
12:40	2.42	2.48	0.03mm	Complies	NO	Complies				
13:05	2.40	2.44	0.02 mm	Complies	NO	Complies				
13:30	2.41	2.45	0.00 mm	Complies	NO	Complies				
13:55	2.42	2.46	0.00mm	Complies	NO	Complies	Total	288		

Remarks: Q14 250mm 40365 136 boxes rejected and kept as stock due to incorrect marbling setting resulting in a marbling pattern that did not meet the required quality standard & specification

* No Colour and thickness change XKFC

Checked By QAI: Matshidiso

Supervisor: Daniel

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 20/10/2026

Shift: C

Color: marbling

Thickness: 2.00 mm

Batch: 9215

Mixer Operator: REFILOE

CPW: 50 kg

Line Speed: 34 Hz

	Thickness Range: 1.87–2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
22:25							23:05 00:00	36	12	Line cuts −24
22:50							00:00 01:00	36	17	Line cuts −19
23:15	1.14	2.50	40365				01:00 02:00	PRODUCTION STOPPED		
23:40	2.44	2.47	0.05mm	complies	NO	complies	02:00 03:00			
00:05	2.42	2.48	0.00 mm	complies	NO	complies	03:00 04:00			
00:30	2.40	2.47	0.10 mm	complies	NO	complies	04:00 05:00	36	27	−9
00:55	2.43	2.49	0.08 mm	complies	NO	complies	05:00 06:00	36	17	−19
01:20	PRODUCTION	STOPPED –	breakdown	at	punching	press				
01:45										
02:10										
02:35										
03:00										
03:25										
03:50	RESTART									
04:15	2.42	2.47	0.10mm	complies	NO	complies				
04:40	2.44	2.49	0.05mm	complies	NO	complies				
05:05	2.40	2.48	0.02 mm	complies	NO	complies				
05:30	2.44	2.46	0.00 mm	complies	NO	complies				
05:55	2.43	2.48	0.08 mm	complies	NO	complies	Total	144	73	−71

Remarks: * colour change – KRAFT MARBLING SPEC WAS USED

* Thickness change

* material fall from mixing mill causing several line cuts. 36 BOXES Rejected and KEPT AS STOCK

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 20/10/2026 Shift: B

Color: CL12 Thickness: 2.00mm Batch: 40335

Mixer Operator: BOAGO CPW: 79 kg Line Speed: 43 Hz

Time	Thickness Range: 1.87-2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	1.94	1.97	0.00mm	Complies	NO	Complies
14:50	1.92	1.97	0.05mm	Complies	NO	Complies
15:15	CL 15 2.00 40355					
15:40	1.92	1.98	0.05 mm	Complies	NO	Complies
16:05	1.94	1.96	0.00 mm	Complies	NO	Complies
16:30	1.94	1.97	0.10 mm	Complies	NO	Complies
16:55	1.94	1.97	0.08 mm	Complies	NO	Complies
17:20	1.93	1.98	0.10 mm	Complies	NO	Complies
17:45	1.92	1.97	0.05 mm	Complies	NO	Complies
18:10	1.94	1.96	0.08 mm	Complies	NO	Complies
18:35	1.91	1.97	0.00 mm	Complies	NO	Complies
19:00	MARBLING	2.00	9246			
19:25	CHANGING	KNIVES				
19:50						
20:15						
20:40	MARBLING	2.00	9215			
21:05						
21:30						
21:55						

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 – 15:00	36	18	in 50 mins
15:00 – 16:00	36	20	line cuts
16:00 – 17:00	36	32	-4
17:00 – 18:00	36	34	-2
18:00 – 19:00	marbling changing	2.00 knives	9246
19:00 – 20:00	MARBLING	2.00	9215
20:00 – 21:00			
21:00 – 22:00			
Total	158	104	-54

Remarks: *Colour change
*No thickness change
*Material fall from mixing mill causing several line cuts

Checked By QAI: BETTY Supervisor: MAIKO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 20/10/2026

Shift: A

Color: Q10

Thickness: 2.00mm

Batch: 40345

Mixer Operator: ALFRED

CPW: 79 kg

Line Speed: 43 Hz

	Thickness Range: 1.87 - 2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
06:25	1.94	1.98	0.05mm	Complies	NO	Complies	06:00 07:00	36	32	-4
06:50	1.90	1.98	0.00mm	Complies	NO	Complies	07:00 08:00	36	13	
07:15	1.92	1.97	0.02mm	Complies	NO	Complies	Breakdown at marbling mill			
07:40	PRODUCTION STOPPED - Breakdown at marbling -									
08:05	replacing the gasket.									
08:30		↓					11:00 12:00	36	30	-6
08:55							12:00 13:00	36	20	
09:20							13:00 14:06	36	27	
09:45		↓					—	—	—	—
10:10					↓					
10:35	CL12	2.00	40335	→		→				
11:00	1.90	1.99	0.00mm	Complies	NO	Complies				
11:25	1.94	2.02	0.05mm	Complies	NO	Complies				
11:50	1.96	2.05	0.00mm	Complies	NO	Rough				
12:15	1.94	2.00	0.00mm	Complies	NO	Complies				
12:40	1.90	1.99	0.00mm	Complies	NO	Complies				
13:05	1.93	1.98	0.00mm	Complies	NO	Complies				
13:30	1.91	1.98	0.00mm	Complies	NO	Complies	Total	180	123	
13:55										

Remarks: * No thickness change. Several line cuts observed.
* Colour change.

Checked By QAI: Matshidiso

Supervisor: Daniel Setwaba

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 19/10/2026

Shift: C

Color: 010

Thickness: 2.00mm

Batch: 40345

Mixer Operator: REFILOE

CPW: 59 kg

Line Speed: 40 Hz

	Thickness Range: 1.87 – 2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
22:25	1.92	1.97	0.10 mm	Complies	NO	Complies	22:30 23:00	36	16	1h 30 mins
22:50	1.94	1.98	0.05 mm	Complies	NO	Complies	23:00 00:00	36	28	-8
23:15	1.90	1.96	0.02 mm	Complies	NO	Complies	00:00 01:00	36	32	-4
23:40	1.94	1.97	0.08 mm	Rough	NO	Complies	01:00 02:00	36	28	-8
00:05	1.92	1.99	0.00 mm	Complies	NO	Complies	02:00 03:00	36	28	-8
00:30	1.91	1.98	0.10 mm	Complies	NO	Complies	03:00 04:00	36	28	-8
00:55	1.92	1.98	0.05 mm	Complies	Slight shade variation	Complies	04:00 05:00	36	32	-4
01:20	1.94	1.97	0.02 mm	Complies	NO	Complies	05:00 06:00	36	23	-13
01:45	1.91	1.97	0.00 mm	Complies	NO	Complies				
02:10	1.90	1.99	0.10 mm	Complies	NO	Complies				
02:35	1.93	1.99	0.00 mm	Complies	NO	Complies				
03:00	1.94	1.97	0.02 mm	Complies	NO	Complies				
03:25	1.92	1.96	0.10 mm	Complies	NO	Complies				
03:50	1.92	1.98	0.06 mm	Complies	NO	Complies				
04:15	1.90	1.98	0.05 mm	Complies	NO	Complies				
04:40	1.93	1.97	0.02 mm	Complies	NO	Complies				
05:05	1.91	1.99	0.10 mm	Complies	NO	Complies				
05:30	1.92	1.97	0.00 mm	Complies	NO	Complies	Total	288	215	-73
05:55	1.94	1.98	0.02 mm	Complies	NO	Complies				

Remarks: * no colour change

* no thickness change

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 19/10/2026 Shift: B

Color: MARBLING Thickness: 200mm Batch: 9272

Mixer Operator: BOAGO CPW: 50 kg Line Speed: 35 Hz

	Thickness						Number of Boxes Produced Per Hour			
	Range: 1.87 - 2.13						Time	Target	Actual	Difference
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface				
18:30										
18.55										
19:20										
19:45										
20:10										
20:35	MARBLING		2.00	9101						
21:00										
21:25										
21:50										
							Total	—	—	—

Remarks: *Colour change
*No thickness change

Checked By QAI: BETTY Supervisor: MACO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 19/10/2026

Shift: A

Color: .....

Thickness: .....

Batch: .....

Mixer Operator: .....

CPW: ..... kg

Line Speed: ..... Hz

Time	Thickness Range: Min (mm)	Thickness Range: Max (mm)	Squareness	Edges	Color	Surface
NO PRODUCTION						

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
Total			

Remarks: No production : Maintenance going on

Checked By QA: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 16/10/2026

Shift: C

Color: 814

Thickness: 2.00mm

Batch: 40325

Mixer Operator: BOAGO

CPW: 79 kg

Line Speed: 42 Hz

Time	Thickness Range: 1.87-2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	PRODUCTION STOPPED					
22:50	↓		↓	↓		↓
23:15	RESTART					
23:40	1.94	1.96	0.00mm	Complies	NO	Complies
00:05	1.94	1.97	0.08mm	Complies	NO	Complies
00:30	1.92	1.99	0.10mm	Complies	NO	Complies
00:55	1.94	1.98	0.10mm	Complies	NO	Complies
01:20	1.90	1.97	0.05mm	Complies	NO	Complies
01:45	1.93	1.96	0.10mm	Complies	NO	Complies
02:10	1.94	1.96	0.08mm	Complies	NO	Complies
02:35	1.91	1.97	0.00mm	Complies	NO	Complies
03:00	1.94	1.97	0.00mm	Complies	NO	Complies
03:25	CL 12	2.00	40335			
03:50	1.94	1.97	0.02mm	Complies	NO	Complies
04:15	1.94	1.95	0.05mm	Complies	NO	Complies
04:40	1.93	1.97	0.10mm	Complies	NO	Complies
05:05	1.92	1.97	0.08mm	Complies	NO	Complies
05:30	1.90	1.98	0.00mm	Complies	NO	Complies
05:55	PRODUCTION STOPS					

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
23:00 00:00	36	12	in 35 mins
00:00 01:00	36	24	Line cuts
01:00 02:00	36	30	-6
02:00 03:00	36	22	-14
03:00 04:00	36	20	colour change
04:00 05:00	36	32	-4
05:00 06:00	36	23	Line cuts
Total	288	161	-127

Remarks: * Colour * ~~Bridge~~ * No thickness change

*Production Stopped - Fixing auto switch of the punching press because it was loose

*Shortage of line operators *Several line cuts due to material fall from mixing mill

*Tile 2 of 872 2.00 40325 failed dimensional stability with a minimum of 299.06 (machine direction)

Checked By QA: BETTY

Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 16/10/2026

Shift: B

Color: G28

Thickness: 13mm

Batch: 40295

Mixer Operator: ALFRED

CPW: 71 kg

Line Speed: 50.00 Hz

Time	Thickness Range: 1.17-1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25			0.10mm	Complies		Complies
14:50			0.08mm	Complies		Complies
15:15	G27	1.30	L40305			
15:40			0.13mm	Complies		Complies
16:05			0.08mm	Complies		Complies
16:30			0.09mm	Complies		Complies
16:55			0.10mm	Complies		Complies
17:20			0.13mm	Complies		Complies
17:45			0.12mm	Complies		Complies
18:10			0.13mm	Complies		Complies
18:35			0.06mm	Complies		Complies
19:00	G72	2.00	L40315			
19:25	1.94	1.96	0.10mm	Complies	NO	Complies
19:50	1.93	1.96	0.13mm	Complies	slight shade	Complies
20:15	1.95	1.99	0.08mm	Complies	variation	Complies
20:40	1.95	1.98	0.10mm	Complies	NO	Complies
21:05	1.95	1.97	0.10mm	Complies	NO	Complies
21:30	1.96	1.97	0.09mm	Complies	NO	Complies
21:55	G14	2.00	L40025			

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00			
15:00	28	25	-3
15:00			Changing colour
16:00	28	15	
16:00			
17:00	28	23	-5
17:00			
18:00	28	26	-2
18:00			Changing colour
19:00	28	10	
19:00			
20:00	36	34	-2
20:00			
21:00	36	31	-5
21:00			
22:00	36	8/	
Total	248	182	-66

Remarks: *Colour change
*Thickness change
*Shade variation observed from boxes 31-44 light shade (separated to another pallet)

Checked By QAI: SEITO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 16/10/2026 Shift: A

Color: Q14 Thickness: 1.30mm Batch: 40285

Time	Thickness Range: 1.17 – 1.47 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25			0.13mm	Rough		Complies
06:50			0.13mm	Complies		Complies
07:15			0.15mm	Complies		Complies
07:40			0.10mm	Rough		Complies
08:05			0.13mm	"		Complies
08:30	Changing Punching Press Knives					
08:55	RESTART					
09:20			0.00mm	Complies		Complies
09:45			0.00mm	Complies		Complies
10:10			0.05mm	Complies		Complies
10:35			0.00mm	Complies		Complies
11:00			0.10mm	Complies		
11:25	Q28	1.30mm	40295			
11:50			0.04mm	Complies		Complies
12:15			0.06mm	Complies		Complies
12:40			0.08mm	Complies		Complies
13:05			0.04mm	Complies		Complies
13:30			0.05mm	Complies		Complies
13:55			0.05mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	28	10	-18
07:00 08:00	28	22	-6
08:00 09:00	28	19	Changing P.P Knives
09:15 10:00	28	20	-8
10:00 11:00	28	20	-8
11:00 12:00	28	6/9	
12:00 13:00	28	21	-7
13:00 14:00	28	21	-7
Total	224	138	-86

Remarks: *Colour change
*No thickness change

Checked By QAI: TSHIDI

Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 15/10/2026 Shift: C

Color: CL 49 Thickness: 2.00 mm Batch: 40275

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	1.94	1.97	0.00 mm	Complies	NO	Complies
22:50	1.92	1.96	0.05mm	Complies	No	Complies
23:15	1.94	1.97	0.10mm	Complies	No	Complies
23:40	1.92	1.98	0.00 mm	Complies	No	Complies
00:05	1.94	1.95	0.05mm	Complies	No	Complies
00:30	1.94	1.98	0.00mm	Complies	No	Complies
00:55	1.90	1.97	0.08mm	Complies	No	Complies
01:20	1.94	1.98	0.10mm	Complies	No	Complies
01:45	1.90	1.96	0.06mm	Complies	No	Complies
02:10	1.94	1.97	0.10 mm	Complies	No	Complies
02:35	1.92	1.97	0.08 mm	Complies	No	Complies
03:00	1.91	1.95	0.00 mm	Complies	No	Complies
03:25	1.94	1.97	0.05 mm	Complies	No	Complies
03:50	1.93	1.97	0.00mm	Complies	No	Complies
04:15	1.94	1.99	0.00 mm	Complies	No	Complies
04:40	1.92	1.97	0.08mm	Complies	No	Complies
05:05	KK 49	2.00	40275	→	→	→
05:30	1.94	1.97	0.08 mm	Complies	No	Complies
05:55	1.94	1.97	0.05mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 – 23:00	36	30	−6
23:00 – 00:00	36	30	−6
00:00 – 01:00	36	30	−6
01:00 – 02:00	36	28	line cut
02:00 – 03:00	36	30	−6
03:00 – 04:00	36	28	−8
04:00 – 05:00	36	13	line cuts
05:00 – 06:00	36	9	line cuts
Total	288	211	−77

Remarks: *No colour change
*No thickness change
*Material fall from mixing mill causing several line cuts

Checked By QAI: BETTY Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 15/10/2026

Shift: B

Color: Q49

Thickness: 2.00mm

Batch: 40265

Mixer Operator: ALFRED

CPW: 79 kg

Line Speed: 40 Hz

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	196	198	0.10mm	Complies	No	Complies
14:50	193	196	0.06mm	Complies	No	Complies
15:15	195	199	0.04mm	Complies	No	Complies
15:40	194	196	0.06mm	Complies	No	Complies
16:05	190	198	0.10mm	Complies	No	Complies
16:30	195	196	0.11mm	Complies	No	Complies
16:55	CL49	2.00	40	275		
17:20	194	199	0.10mm	Complies	No	Complies
17:45	196	198	0.08mm	Complies	No	Complies
18:10	192	197	0.06mm	Complies	No	Complies
18:35	194	198	0.10mm	Complies	No	Complies
19:00	192	198	0.10mm	Complies	No	Complies
19:25	191	196	0.06mm	Complies	No	Complies
19:50	195	196	0.08mm	Complies	No	Complies
20:15	192	199	0.10mm	Complies	No	Complies
20:40	195	196	0.08mm	Complies	No	Complies
21:05	194	198	0.06mm	Complies	No	Complies
21:30	191	196	0.02mm	Complies	No	Complies
21:55	195	198	0.00mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 – 15:00	36	25	-11
15:00 – 16:00	36	28	-8
16:00 – 17:00	36	169	Changing colour
17:00 – 18:00	36	28	-8
18:00 – 19:00	36	28	-8
19:00 – 20:00	36	28	-8
20:00 – 21:00	36	28	-8
21:00 – 22:00	36	28	-8
Total	288	216	-72

Remarks: * No colour change
* No thickness change
* Bluish marbling observed on the tiles

Checked By QA: SEFTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 15/10/2026

Shift: A

Color: Q49

Thickness: 2.50 mm

Batch: 40265

Mixer Operator: REFILWE

CPW: 79 kg

Line Speed: 40 Hz

Time	Thickness Range: 2.37 – 2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25	Q49	2-00	40265			
06:50	1.95	2-01	0.00mm	Complies	NO	Complies
07:15	1-94	1-99	0.00mm	Complies	NO	Complies
07:40	1.90	1-99	0.05mm	Complies	NO	Complies
08:05	1-93	1-99	0.08mm	Complies	NO	Complies
08:30	1-94	1-97	0.08mm	Complies	NO	Complies
08:55	1-93	1-96	0.05mm	Complies	NO	Complies
09:20	1-92	1-98	0.00mm	Complies	NO	Complies
09:45	1-93	1-99	0.05mm	Complies	NO	Complies
10:10	1-95	1-98	0.05mm	Complies	NO	Complies
10:35	1-94	1-99	0.00mm	Complies	NO	Complies
11:00	1-93	1-97	0.00mm	Complies	NO	Complies
11:25	1-92	1-96	0.00mm	Complies	NO	Complies
11:50	BRODUCTION	STOPPED				
12:15			RESTART			
12:40	1.93	1-97	0.00mm	Complies	NO	Complies
13:05	1-94	1-98	0.00mm	Complies	NO	Complies
13:30	1.90	1.96	0.00mm	Complies	NO	Complies
13:55	1-92	1-96	0.00mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 – 07:00	36	23	Thickness change
07:00 – 08:00	36	28	-8
08:00 – 09:00	36	28	-8
09:00 – 10:00	36	28	-8
10:00 – 11:00	36	28	-8
11:00 – 12:00	36	15	
12:00 – 13:00	36	17	
13:00 – 14:00	36	27	
Total	288	194	

Remarks: Q10 2.00 40255 Box 1-35 rejected because dark shade Pallet 1 dispatched box 36-119 Pallet 2 box 120-203. 35 boxes was replaced with the balance of KK10 2:00 40255

Checked By QAI: MATSHIDISO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 14/10/2026 Shift: C

Color: KK10 Thickness: 2.00mm Batch: 40255

Mixer Operator: BOAGO CPW: 79 kg Line Speed: 45 Hz

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	1.90	1.97	0.05 mm	Complies	NO	Complies
22:50	1.94	1.99	0.10mm	Complies	NO	Complies
23:15	1.94	1.96	0.05mm	Complies	NO	Complies
23:40	1.92	1.97	0.00mm	Complies	NO	Complies
00:05	@ 49	2.50	40265			
00:30	2.44	2.47	0.00 mm	Complies	NO	Complies
00:55	2.42	2.48	0.05 mm	Complies	NO	Complies
01:20	2.43	2.46	0.00 mm	Complies	NO	Complies
01:45	2.42	2.48	0.02 mm	Complies	NO	Complies
02:10	2.40	2.47	0.00 mm	Complies	NO	Complies
02:35	2.44	2.45	0.02 mm	Complies	NO	Complies
03:00	2.44	2.47	0.05 mm	Complies	NO	Complies
03:25	2.43	2.47	0.00 mm	Complies	NO	Complies
03:50	2.42	2.49	0.08 mm	Complies	NO	Complies
04:15	2.44	2.47	0.00 mm	Complies	NO	Complies
04:40	2.40	2.48	0.05 mm	Complies	NO	Complies
05:05	2.40	2.46	0.10 mm	Complies	NO	Complies
05:30	2.44	2.47	0.08 mm	Complies	NO	Complies
05:55	2.44	2.47	0.00mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	36	34	-2
23:00 00:00	36	26	-10
00:00 01:00	36	16	Colour/thickness change
01:00 02:00	36	32	-4
02:00 03:00	36	28	-8
03:00 04:00	36	30	-6
04:00 05:00	36	28	-8
05:00 06:00	36	23	Line cut -13
Total	288	217	-71

Remarks: *Colour change
*Thickness change

Checked By QA: BETTY Supervisor: MARCO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 14/10/2026

Shift: B

Color: Marbling

Thickness: 2.00mm

Batch: 9101

Mixer Operator: ALFRED

CPW: 79 kg

Line Speed: 44 Hz

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25						
14:50						
15:15						
15:40						
16:05	KK10	2.00	40255			
16:30	194	196	0.10mm	Complies	No	Rough
16:55	193	198	0.08mm	Complies	No	"
17:20	190	195	0.13mm	Complies	No	Complies
17:45	195	197	0.10mm	Complies	No	Complies
18:10	192	196	0.10mm	Complies	No	Complies
18:35	194	198	0.08mm	Complies	Slight shade variation	Complies
19:00	193	196	0.10mm	Complies		complies
19:25	195	2.00	0.13mm	Complies	No	Complies
19:50	195	198	0.10mm	Complies	slight shade variation	Complies
20:15	193	196	0.10mm	Complies	No	Complies
20:40	195	198	0.08mm	Complies	No	Complies
21:05	194	197	0.08mm	Complies	No	complies
21:30	KK10	2.00	40255			
21:53	195	198	0.10mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
16:00 – 19:00	36	28	-8
17:00 – 18:00	36	32	-4
18:00 – 19:00	36	36	—
19:00 – 20:00	36	33	-3
20:00 – 21:00	36	39	+3
21:00 – 22:00	36	31	-5
Total	216	199	-17

Remarks: Colour change & No thickness change

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 14/10/2026

Shift: A

Color: Q14

Thickness: 2.00mm

Batch: 40245

Mixer Operator: REFILWE

CPW: 80 kg

Line Speed: 39 Hz

Time	Thickness Range: Min (mm)	Thickness Range: Max (mm)	Squareness	Edges	Color	Surface
06:25	1.92	1.97	0.10 mm	complies	NO	complies
06:50	1.94	1.98	0.08 mm	complies	NO	complies
07:15	1.90	1.96	0.05 mm	complies	NO	complies
07:40	1.94	1.97	0.02 mm	complies	NO	complies
08:05	1.92	1.99	0.10 mm	complies	NO	complies
08:30	1.94	1.98	0.06 mm	complies	NO	complies
08:55	1.90	1.97	0.05 mm	complies	NO	complies
09:20	1.94	1.96	0.02 mm	complies	NO	complies
09:45	1.92	1.97	0.10 mm	complies	NO	complies
10:10	1.91	1.98	0.08 mm	complies	NO	complies
10:35	1.94	1.99	0.02 mm	complies	NO	complies
11:00	1.92	1.98	0.10 mm	complies	NO	complies
11:25	1.94	1.97	0.00 mm	complies	NO	complies
11:50	CHANGING		KNIVES / MARBLING		-.9244 -2.00	
12:15						
12:40						
13:05						
13:30						
13:55						

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	36	25	-11 (Line CHG)
07:00 08:00	36	22	-14
08:00 09:00	36	35	-1
09:00 10:00	36	37	+1
10:00 11:00	36	19	Colour change
11:00 12:00			
12:00 13:00			
13:00 14:00			
Total	180	138	-42

Remarks: * colour change
* NO thickness change

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 13/10/2026 Shift: C

Color: Q10 Thickness: 2.00mm Batch: 40235

Mixer Operator: BOAGO CPW: 79 kg Line Speed: 42 Hz

	Thickness Range: 1.87–2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
22:25	1.94	1.98	0.00 mm	Complies	No	Complies	22:00 23:00	36	32	-4
22:50	1.90	1.97	0.08 mm	Complies	No	Complies	23:00 00:00	36	28	-8
23:15	1.94	1.97	0.05 mm	Complies	Slight shade variation	Complies	00:00 01:00	36	32	-4
23:40	1.94	1.99	0.02mm	Complies	No	Complies	01:00 02:00	36	38	-6
00:05	1.94	1.95	0.08mm	Complies	No	Complies	02:00 03:00	36	33	-3
00:30	1.93	1.97	0.05mm	Complies	No	Complies	03:00 04:00	36	12	Colour change
00:55	1.90	1.97	0.10 mm	Complies	No	Complies	04:00 05:00	36	22	Line cuts
01:20	1.94	1.97	0.08 mm	Complies	No	Complies	05:00 06:00	36	21	-15
01:45	1.94	1.98	0.05mm	Complies	Slight shade variation	Complies				
02:10	1.91	1.98	0.00mm	Complies	No	Complies				
02:35	1.93	1.97	0.00 mm	Complies	No	Complies				
03:00	1.92	1.97	0.10mm	Complies	No	Complies				
03:25	Q 14	2.00	40235							
03:50	1.94	1.97	0.10 mm	Complies	No	Complies				
04:15	1.93	1.95	0.00 mm	Complies	No	Complies				
04:40	1.90	1.97	0.08 mm	Complies	No	Complies				
05:05	1.92	1.98	0.02 mm	Complies	No	Complies				
05:30	1.94	1.99	0.05 mm	Complies	No	Complies				
05:55	1.94	1.97	0.00 mm	Complies	No	Complies	Total	288	208	-80

Remarks: * Colour change

*No thickness change

*Inconsistent shade on Q10 2.00 40235 extra mix was done. did not label the pallet until final inspection on 14/10/2026 *Tile 20F Q10 2.00 40235 failed dimensional stability with a minimum of 298.30 (machine direction)

Checked By QAI: BETTY Supervisor: MALO

DO NOT REPRODUCED

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 13/10/2026

Shift: B

Color: KK05

Thickness: 2.50mm

Batch: 40225

Mixer Operator: ALFRED

CPW: 81/79 kg

Line Speed: 34/43 Hz

	Thickness Range: 2.37 - 2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
14:25	243	249	0:10mm	Complies	NO	Complies	14:00 15:00	36	26	13
14:50	2:44	2:52	0:13mm	Complies	NO	Complies	15:00 16:00	36	16	-20
15:15	240	245	0:13mm	Complies	NO	Complies	16:00 17:00	36	24	-12
15:40	243	248	0:10mm	Complies	NO	Complies	17:00 18:00	36	28	-8
16:05	244	252	0:08mm	Complies	NO	Complies	18:00 19:00	36	26	-10
16:30	245	250	0:10mm	Complies	NO	Complies	19:25 20:00	36	17	Changing colour
16:55	243	248	0:08mm	Complies	NO	Complies	20:00 21:00	36	28	-8
17:20	241	248	0:06mm	Complies	NO	Complies	21:00 22:00	36	30	-6
17:45	245	250	0:10mm	Complies	Slight black variation	Complies				
18:10	244	248	0:08mm	Complies	NO	Complies				
18:35	245	255	0:10mm	Complies	NO	Complies				
19:00	243	248	0:06mm	Complies	NO	Complies				
19:25	240	200	40234							
19:50	194	198	0:06mm	Complies	NO	Complies				
20:15	193	196	0:15mm	Complies	NO	Complies				
20:40	194	198	0:10mm	Complies	NO	Complies				
21:05	190	196	0:12mm	Complies	NO	Complies				
21:30	194	198	0:10mm	Complies	NO	Complies				
21:55	196	200	0:08mm	Complies	NO	Complies	Total	288	195	-93

Remarks: *Colour Change
*Thickness change
*On and off stepping of tiles

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 13/10/2026

Shift: A

Color: KK 15

Thickness: 2.50mm

Batch: 40215

Mixer Operator: REFILWE

CPW: 80 kg

Line Speed: 31 Hz

	Thickness Range: 2.37-2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
06:25	2.44	2.47	0.10 mm	complies	NO	complies	06:00 07:00	36	19	Line cuts -17
06:50	2.40	2.48	0.08 mm	complies	NO	complies				
07:15	2.42	2.49	0.05 mm	complies	NO	complies	07:00 08:00	36	32	-4
07:40	2.44	2.47	0.02 mm	complies	NO	complies				
08:05	2.41	2.47	0.00 mm	complies	NO	complies	08:00 09:00	36	26	-10
08:30	2.40	2.48	0.10 mm	complies	NO	complies				
08:55	2.42	2.46	0.08 mm	complies	NO	complies	09:00 10:00	36	10	Line cuts -26
09:20	2.44	2.47	0.05 mm	complies	NO	complies				
09:45	2.43	2.48	0.10 mm	complies	NO	complies	10:00 11:00	36	16	-20
10:10	2.41	2.48	0.06 mm	complies	NO	complies				
10:35	2.40	2.47	0.05 mm	complies	NO	complies	11:00 12:00	36	28	-8
11:00	2.44	2.47	0.10 mm	complies	NO	complies				
11:25	2.42	2.49	0.08 mm	complies	NO	complies	12:00 13:00	36	20	-16
11:50	2.42	2.48	0.02 mm	complies	NO	complies				
12:15	2.43	2.49	0.00 mm	complies	NO	complies	13:00 14:00	36	2/16	Colour change
12:40	2.44	2.47	0.05 mm	complies	NO	complies				
13:05	KK 05	2.50	40225							
13:30	2.42	2.47	0.08 mm	complies	NO	complies	Total	288	169	-119
13:55	2.40	2.49	0.02 mm	complies	NO	complies				

Remarks: * Colour change
* No thickness change

Checked By QA: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 12/10/2026

Shift: C

Color: KK 15

Thickness: 250 mm

Batch: 40215

Mixer Operator: BORGO

CPW: 80 kg

Line Speed: 32 Hz

Time	Thickness Range: 2.37-2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.44	2.47	0.08 mm	Complies	NO	Complies
22:50	2.40	2.47	0.05 mm	Complies	NO	Complies
23:15	2.42	2.48	0.00 mm	Complies	NO	Complies
23:40	2.44	2.49	0.02 mm	Complies	NO	Complies
00:05	2.44	2.46	0.00mm	Complies	NO	Complies
00:30	2.43	2.47	0.00 mm	Complies	NO	Complies
00:55	2.49	2.48	0.08 mm	Complies	NO	Complies
01:20	2.44	2.46	0.05 mm	Complies	NO	Complies
01:45	2.44	2.47	0.05mm	Complies	NO	Complies
02:10	2.44	2.47	0.02 mm	Complies	NO	Complies
02:35	2.45	2.49	0.02mm	Complies	NO	Complies
03:00	2.43	2.46	0.10 mm	Complies	NO	Complies
03:25	2.48	2.45	0.08 mm	Complies	NO	Complies
03:50	2.43	2.47	0.06 mm	Complies	NO	Complies
04:15	2.46	2.48	0.00 mm	Complies	NO	Complies
04:40	2.48	2.47	0.00mm	Complies	NO	Complies
05:05	2.48	2.47	0.08 mm	Complies	NO	Complies
05:30	2.44	2.46	0.05 mm	Complies	NO	Complies
05:55	2.44	2.47	0.00 mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	36	36	-16
23:00 00:00	36	28	-8
00:00 01:00	36	26	-10
01:00 02:00	36	20	-16
02:00 03:00	36	28	-8
03:00 04:00	36	26	-10
04:00 05:00	36	20	-16
05:00 06:00	36	21	-15
Total	288	187	-101

Remarks: *No colour change
*No thickness change
*Several line cuts due to material fall from mixing mill.

Checked By QA: BETTY

Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 12/10/2026

Shift: B

Color: 928

Thickness: 13.0mm

Batch: 40205

Mixer Operator: ALFRED

CPW: 79KG kg

Line Speed: 50.00 Hz

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25			0.10mm	Complies		Complies
14:50			0.13mm	Complies		Complies
15:15			0.13mm	Complies		Complies
15:40			0.08mm	Complies		Complies
16:05			0.09mm	Complies		Complies
16:30			0.08mm	Complies		Complies
16:55			0.10mm	Complies		Complies
17:20	CHANGING		KNIVES			
17:45	KK15	1.60	40215			
18:10	CHANGING		KNIVES			
18:35	"		"		"	"
19:00	KK15	1.60	40215			
19:25	1.55	1.57	0.10mm	Complies	NO	Complies
19:50	1.57	1.59	0.13mm	Complies	NO	Complies
20:15	KK15	2.00	40215			
20:40	1.94	1.98	0.10mm	Complies	NO	complies
21:05	1.95	1.97	0.13mm	Complies		
21:30	KK15	2.50	40215		NO	Complies
21:55	2.43	2.46	0.10mm	Complies	NO	Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
14:00 – 15:00	48	31	-17
15:00 – 16:00	48	34	-14
16:00 – 17:00	48	34	-14
17:40 – 18:00	36	7	Changing colour
19:00 – 20:00	36	11	
20:00 – 21:00	36	32	-4
21:00 – 22:00	36	18	
Total	288	167	

Remarks: Colour Change & Thickness change & Knives change

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 12/10/2026

Shift: A

Color: 928

Thickness: 1.30 mm

Batch: 40205

Mixer Operator: REFILWE

CPW: 79 kg

Line Speed: 50 Hz

Time	Thickness Range: 1.17–1.43 Min (mm)	Thickness Range: 1.17–1.43 Max (mm)	Squareness	Edges	Color	Surface
06:25	HEATING UP		MACHINER			
06:50						
07:15						
07:40						
08:05						
08:30						
08:55						
09:20						
09:45						
10:10						
10:35						
11:00						
11:25						
11:50						
12:15						
12:40						
13:05						
13:30	RESTART					
13:55	~~928~~	BULK	0.10 mm	complies	BULK	complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
14:50 15:20	48	3	
Total	48	3	

Remarks: * no colour and thickness change

* cleaning production line, repacking bulk into 1m2 boxes

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 9/10/2026

Shift: C

Color: 972

Thickness: 1.30mm

Batch: 40195

Mixer Operator: BOAGO

CPW: 75 kg

Line Speed: 50.00 Hz

Time	Thickness Range: 1.17-1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25			0:10mm	Complies		Complies
22:50			0:13mm	Complies		Complies
23:15			0:08mm	Complies		Complies
23:40			0:06mm	Complies		Complies
00:05			0:07mm	Complies		Complies
00:30			0:09mm	Complies		Complies
00:55			0:11mm	Complies		Complies
01:20			0:10mm	Complies		Complies
01:45			0:13mm	Complies		Complies
02:10			0:15mm	Complies		Complies
02:35			0:15mm	Complies		Complies
03:00			0:09mm	Complies		Complies
03:25			0:10mm	Complies		Complies
03:50			0:06mm	Complies		Complies
04:15			0:10mm	Complies		Complies
04:40			0:13mm	Complies		Complies
05:05	PRODUCTION		STOPPED			
05:30						
05:55						

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00			
23:00	48	36	-12
23:00			
00:00	48	38	-10
00:00			
01:00	48	37	-11
01:00			
02:00	48	40	-8
02:00			
03:00	48	36	-12
03:00			
04:00	48	33	-15
04:00			
05:00	48	46	-2
05:00			
06:00	48	—	
Total	384	266	-118

Remarks: No Colour Change
No Thickness Change

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 09/10/2026 Shift: B

Color: 049 Thickness: 1.30 mm Batch: 40175

Mixer Operator: REFILOE CPW: 79 kg Line Speed: 50 Hz

Time	Thickness Range: Min (mm)	Thickness Range: Max (mm)	Squareness	Edges	Color	Surface
14:25			0.10 mm	Complies		Complies
14:50			0.05 mm	Complies		Complies
15:15			0.00 mm	Complies		Complies
15:40	0.89	1.30	40185			
16:05			0.02 mm	Complies		Complies
16:30			0.05 mm	Complies		Complies
16:55			0.10 mm	Complies		Complies
17:20			0.00 mm	Complies		Complies
17:45			0.08 mm	Complies		Complies
18:10			0.02 mm	Complies		Complies
18:35			0.05 mm	Complies		Complies
19:00			0.00 mm	Complies		Complies
19:25			0.10 mm	Complies		Complies
19:50			0.02 mm	Complies		Complies
20:15			0.05 mm	Complies		Complies
20:40			0.08 mm	Complies		Complies
21:05	0.72	1.30	40195			
21:30			0.05 mm	Complies	BLACK	Complies
21:55	BLACK		0.10 mm	Complies		Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
14:00 15:00	28	28	—
15:00 16:00	28	4/24	Colour change
16:00 17:00	48	40	−8
17:00 18:00	48	40	−8
18:00 19:00	48	38	−10
19:00 20:00	48	42	−6
20:00 21:00	48	26	Colour change
21:00 22:00	48	40	−8
Total	344	282	−62

Remarks: * Colour Change
* NO THICKNESS change

Checked By QAI: KARABO Supervisor: THEMBATHI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 09/10/2026

Shift: A

Color: 849

Thickness: 1.30

Batch: 40175

Mixer Operator: BOAGO

CPW: 79 kg

Line Speed: 50 Hz

Time	Thickness Range: 1.17-1.43 Min (mm)	Thickness Range: 1.17-1.43 Max (mm)	Squareness	Edges	Color	Surface
06:25	BULK		0.08 mm	Complies	BULK	Complies
06:50			0.05 mm	Complies		Complies
07:15			0.02 mm	Complies		Complies
07:40			0.00 mm	Complies		Complies
08:05			0.02 mm	Complies		Complies
08:30	DIY		0.10 mm	Complies	DIY	Complies
08:55			0.08 mm	Complies		Complies
09:20			0.00 mm	Complies		Complies
09:45			0.10 mm	Complies		Complies
10:10			0.05 mm	Complies		Complies
10:35			0.03 mm	Complies		Complies
11:00			0.08 mm	Complies		Complies
11:25			0.10 mm	Complies		Complies
11:50			0.00 mm	Complies		Complies
12:15	PRODUCTION	STOPPED - chains for coupling tray broken.				
12:40	RESTART					
13:05	DIY		0.10 mm	Complies	DIY	Complies
13:30			0.08 mm	Complies		Complies
13:55			0.02 mm	Complies		Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
06:00 07:00	48	48	-
07:00 08:00	48	35½	Bulk/DIY
08:00 09:00	28	24	-4
09:00 10:00	28	18	-10
10:00 11:00	28	26	-2
11:00 12:00	28	26	-2
12:00 13:00	28	27	Prod stopped
13:00 14:00	28	27	
Total	~~267~~	233	31

Remarks: *No colour change
*No thickness change

Checked By QAI: BETTY

Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 08/10/2026

Shift: C

Color: 6238

Thickness: 1.30mm

Batch: 40/65

Mixer Operator: ALFRED

CPW: 75 kg

Line Speed: 50,00 Hz

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25			0:10mm	Complies		Complies
22:50			0:08mm	Complies		Complies
23:15			0:06mm	Complies		Complies
23:40			0:13mm	Complies		Complies
00:05			0:13mm	Complies		Complies
00:30			0:10mm	Complies		Complies
00:55			0:13mm	Complies		Complies
01:20			0:13mm	Complies		Complies
01:45			0:08mm	Complies		Complies
02:10			0:06mm	Complies		Complies
02:35			0:10mm	Complies		Complies
03:00			0:08mm	Complies		Complies
03:25	6249	1.30	40/65			
03:50			0:10mm	Complies		Complies
04:15			0:13mm	Complies		Complies
04:40			0:12mm	Complies		Complies
05:05			0:10mm	Complies		Complies
05:30			0:10mm	Complies		Complies
05:55			0:06mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 – 23:00	28	26	-2
23:00 – 00:00	28	30	+2
00:00 – 01:00	28	29	+1
01:00 – 02:00	28	30	+2
02:00 – 03:00	28	33	+5
03:00 – 04:00	48	31	Changing colour
04:00 – 05:00	48	41	-7
05:00 – 06:00	48	45	-3
Total	284	265	-19

Remarks: * Colour change & No Thickness change

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 08/10/2026 Shift: B

Color: Q10 Thickness: 1.30mm Batch: 40155

Mixer Operator: REFILWE CPW: 59 kg Line Speed: 50 Hz

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25			0.10 mm	complies		complies
14:50			0.05 mm	complies		complies
15:15			0.00 mm	complies		complies
15:40			0.02 mm	complies		complies
16:05			0.05 mm	complies		complies
16:30			0.08 mm	complies		complies
16:55			0.10 mm	complies		complies
17:20			0.06 mm	complies		complies
17:45			0.08 mm	complies		complies
18:10			0.05 mm	complies		complies
18:35			0.10 mm	complies		complies
19:00			0.02 mm	complies		complies
19:25			0.10 mm	complies		complies
19:50			0.08 mm	complies		complies
20:15			0.05 mm	complies		complies
20:40			0.00 mm	complies		complies
21:05	Q38	1.30	4016.5			
21:30			0.10 mm	complies		complies
21:55			0.02 mm	complies		complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 – 15:00	28	28	–
15:00 – 16:00	28	25	-3
16:00 – 17:00	28	29	+1
17:00 – 18:00	28	28	–
18:00 – 19:00	28	27	-1
19:00 – 20:00	28	28	–
20:00 – 21:00	28	19/2	colour change
21:00 – 22:00	28	26	-2
Total	224	212	-12

Remarks: * colour change
* NO thickness change

Checked By QAI: KAMABO Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 08/10/2026 Shift: A

Color: Q05 Thickness: 1.30mm Batch: 40145

Mixer Operator: BOAGO CPW: 59 kg Line Speed: 50 Hz

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25			0.08 mm	Complies		Complies
06:50			0.00 mm	Complies		Complies
09:15			0.07 mm	Complies		Complies
07:40			0.05mm	Complies		Complies
08:05			0.10 mm	Complies		Complies
08:30			0.08 mm	Complies		Complies
08:55			0.05 mm	Complies		Complies
09:20			0.00 mm	Complies		Complies
09:45	1.10	1.30	40155			
10:10			0.00 mm	Complies		Complies
10:35			0.10 mm	Complies		Complies
11:00			0.05 mm	Complies		Complies
11:25			0.10 mm	Complies		Complies
11:50			0.08 mm	Complies		Complies
12:15			0.05 mm	Complies		Complies
12:40			0.05mm	Complies		Complies
13:05			0.08 mm	Complies		Complies
13:30			0.10mm	Complies		Complies
13:55			0.04mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	48	40	-8
07:00 08:00	48	48	-
08:00 09:00	48	48	-
09:00 10:00	48	11 ~~19~~	BULK DIY
10:00 11:00	28	28	-
11:00 12:00	28	28	-
12:00 13:00	28	~~30~~	+2
13:00 14:00	28	30	+2
Total	275	274	-1

Remarks: *Colour change
*No thickness change

Checked By QAI: BETTY Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 07/10/2026

Shift: C

Color: 9238

Thickness: 13mm

Batch: 40125

Time	Thickness Range: 1.17 – 1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25			0:10mm	Complies		Complies
22:50			0:06mm	Complies		Complies
23:15			0:10mm	Complies		Complies
23:40			0:08mm	Complies		Complies
00:05			0:13mm	Complies		Complies
00:30			0:15mm	Complies		Complies
00:55			0:10mm	Complies		Complies
01:20			0:07mm	Complies		Rough
01:45			0:14mm	Complies		"
02:10			0:06mm	Complies		Complies
02:35			0:10mm	Complies		Complies
03:00			0:09mm	Complies		Complies
03:25			0:06mm	Complies		Complies
03:50			0:10mm	Complies		Complies
04:15	9905	1.30	40/45			
04:40			0:10mm	Complies		Complies
05:05			0:12mm	Complies		Complies
05:30			0:13mm	Complies		Complies
05:55			0108	Complies		Complies

BULK

BULK

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	28	28	—
23:00 00:00	28	29	+1
00:00 01:00	28	28	—
01:00 02:00	28	30	+2
02:00 03:00	28	29	+1
03:00 04:00	28	26	-2
04:00 05:00	48	28	Changing colour
05:00 06:00	48	36	-12
Total	264	234	-30

Remarks: Colour change
& No thickness change
& Speed 150H2

Checked By QAI: SEPTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 07/10/2026

Shift: B

Color: Q41

Thickness: 1.30mm

Batch: 40115

	Thickness Range: 1.17 – 1.43						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
14:25			0.10mm	complies		complies	14:00 – 15:00	48	40	
14:50			0.05 mm	complies		complies	15:00 – 16:00	48	41	
15:15			0.00 mm	complies		complies				
15:40			0.02 mm	complies		complies	16:00 – 17:00	48	42	
16:05			0.08 mm	complies		complies				
16:30			0.10 mm	complies		complies	17:00 – 18:00	48	40	
16:55			0.02 mm	complies		complies				
17:20			0.05 mm	complies		complies	18:00 – 19:00	~~48~~	Rolls	
17:45			0.06 mm	complies		complies				
18:10			0.02 mm	complies		complies	19:00 – 20:00	36	19/11	colour + thickness change
18:35	KF 15	1.60	40135							
19:00	1.55	1.58	0.05 mm	complies	NO	complies	20:00 – 21:00	28	27	-1
19:25	1.52	1.60	0.10 mm	complies	NO	complies				
19:50	Q 38	1.30	40125				21:00 – 22:00	28	28	–
20:15			0.05 mm	complies		complies				
20:40			0.02 mm	complies		complies				
21:05			0.08 mm	complies		complies				
21:30			0.10 mm	complies		complies				
21:55			0.00 mm	complies		complies	Total	284	248	-36

Remarks: * Colour change

* Thickness change

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 07/10/2026 Shift: A

Color: 983 Thickness: 1.30mm Batch: 40105

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25			0.00 mm	Complies		Complies
06:50			0.08 mm	Complies		Complies
07:15			0.05 mm	Complies		Complies
07:40			0.00 mm	Complies		Complies
08:05			0.02 mm	Complies		Complies
08:30			0.05 mm	Complies		Complies
08:55			0.10 mm	Complies		Complies
09:20			0.02 mm	Complies		Complies
09:45			0.08 mm	Complies		Complies
10:10			0.00 mm	Complies		Complies
10:35			0.08 mm	Complies		Complies
11:00			0.10 mm	Complies		Complies
11:25			0.08 mm	Complies		Complies
11:50	941	1.30	40115			
12:15			0.00 mm	Complies		Complies
12:40			0.08 mm	Complies		Complies
13:05			0.05 mm	Complies		Complies
13:30			0.00 mm	Complies		Complies
13:55			0.00 mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	28	28	–
07:00 08:00	28	30	+2
08:00 09:00	28	26	-2
09:00 10:00	28	28	–
10:00 11:00	28	28	–
11:00 12:00	28	21	colour change
12:00 13:00	48	40	-8
13:00 14:00	48	39	-9
Total	281	240	-41

Remarks: *Colour change
*140 thickness change

Checked By QAI: BETTY

Supervisor: MALO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 06/10/2026 Shift: C

Color: G83 Thickness: 1.30mm Batch: 40095

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	B		0.10mm	Complies	B	Complies
22:50			0.08mm	Complies		Complies
23:15			0.06mm	Complies		Complies
23:40			0.10mm	Complies		Complies
00:05			0.13mm	Complies		Complies
00:30			0.10mm	Complies		Complies
00:55			0.11mm	Complies		Complies
01:20			0.08mm	Complies		Complies
01:45	D		0.10mm	Complies	D	Complies
02:10			0.13mm	Complies		Complies
02:35	G46	2.00	40075			
03:00	195	198	0.10mm	Complies	No	Complies
03:25	192	196	0.08mm	Complies	No	Complies
03:50	196	198	0.10mm	Complies	No	Complies
04:15	193	196	0.06mm	Complies	No	Complies
04:40	195	199	0.10mm	Complies	No	Complies
05:05	192	196	0.08mm	Complies	No	Complies
05:30	190	198	0.10mm	Complies	No	Complies
05:55	G83	1.30	40105			

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 – 23:00	48	40	-8
23:00 – 00:00	48	42	-6
00:00 – 01:00	48	46	-2
01:00 – 02:00	48	49	
02:30 – 03:00	36	14	Changing Colour
03:00 – 04:00	36	32	-4
04:00 – 05:00	36	28	-8
05:00 – 06:00	36		
Total	336	246	

Remarks: * Colour change
* Thickness change
* Speed: 1:30: 50Hz 2.00: 40Hz
* G46 2.00 40075 failed dimensional stability 6m tile (machine direction) with a minimum of 298.

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 06/01/2026

Shift: B

Color: Q46

Thickness: 2.00mm

Batch: 40075

Time	Thickness Range: 1.87–2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	1.94	1.97	0.05mm	complies	NO	complies
14:50	1.92	1.98	0.10 mm	complies	NO	complies
15:15	1.90	1.98	002 mm	complies	NO	complies
15:40	1.93	1.99	008 mm	complies	NO	complies
16:05	Q19	2.00	40085			
16:30	1.91	1.97	0.00 mm	complies	NO	complies
16:55	1.94	1.97	0.05 mm	complies	NO	complies
17:20	1.94	1.96	0.02 mm	complies	NO	complies
17:45	1.92	1.99	0.10 mm	complies	NO	complies
18:10	1.93	1.98	0.08 mm	complies	NO	complies
18:35	1.94	1.97	0.10 mm	complies	NO	complies
19:00	1.91	1.99	0.00 mm	complies	NO	complies
19:25	1.92	1.98	0.02 mm	complies	NO	complies
19:50	1.94	1.97	0.10 mm	complies	NO	complies
20:15	Q83	1.30	40095			
20:40			0.12 mm	complies		complies
21:05	BULK		0.10 mm	complies	BULK	complies
21:30			0.05 mm	complies		complies
21:55			0.02 mm	complies		complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 15:00	36	29	−7
15:00 16:00	36	8/10	Colour change
16:00 17:00	36	18	Line curb −18
17:00 18:00	36	22	Line cut −14
18:00 19:00	36	26	−10
19:00 20:00	36	19	colour + thickness change
20:00 21:00	48	30	−18
21:00 22:00	48	38	−10
Total	312	200	−112

Remarks: * Colour change
* Thickness change

Checked By QAI: KARABO

Supervisor: THEMBA H

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 06/10/2026

Shift: A

Color: CL49

Thickness: 2.50mm

Batch: 40065

	Thickness Range: 2.37 - 2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
06:25	2.44	2.45	0.08mm	Complies	NO	Complies	06:00 07:00	36	30	-6
06:50	2.43	2.47	0.10 mm	Complies	No	Complies	07:00 08:00	36	28	Line cut -8
07:15	2.42	2.47	0.05 mm	Complies	NO	Complies	08:00 09:00	36	28	-8
07:40	2.44	2.46	0.00 mm	Complies	NO	Complies	09:00 10:00	36	~~24~~	Line cut -12
08:05	2.40	2.47	0.00 mm	Complies	NO	Complies	10:00 11:00	36	6/6	Line cuts -
08:30	2.44	2.47	0.08 mm	Complies	NO	Complies	11:00 12:00	36	22	Line cut -14
08:55	2.44	2.49	0.05 mm	Complies	NO	Complies	12:00 13:00	36	21	Colour + thickness change
09:20	2.42	2.47	0.08mm	Complies	NO	Complies	13:00 14:00	36	34	-2
09:45	2.41	2.47	0.00mm	Complies	NO	Complies				
10:10	2.43	2.48	0.05mm	Complies	NO	Complies				
10:35	CL49	2.50	40065							
11:00	2.44	2.48	0.08 mm	Complies	NO	Complies				
11:25	2.42	2.47	0.05mm	Complies	NO	Complies				
11:50	2.44	2.47	0.00mm	Complies	NO	Complies				
12:15	CL46	2.00	40075							
12:40	1.94	1.97	0.00mm	Complies	NO	Complies				
13:05	1.92	1.95	0.00mm	Complies	NO	Complies				
13:30	1.94	1.96	0.08mm	Complies	NO	Complies				
13:55	1.93	1.99	0.05mm	Complies	NO	Complies	Total	288	199	-89

Remarks: *Colour change
*Thickness Change
SPEED: ~~34~~ H² SPEED FOR 2.00mm: 46H² *Several line cuts due to material fall from mixing mill

Checked By QAI: BETTY

Supervisor: MAICO

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 05/10/2026 Shift: C

Color: 938 Thickness: 1.30mm Batch: 40055

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	PRODUCTION		STOPPED – Breakdown – Boiler pressure was low			
22:50	RESTART →			RESTART →		
23:15	BULK		0.10mm	Complies	BULK	Complies
23:40			0.08mm	Complies		Complies
00:05			0.13mm	Complies		Complies
00:30	938 2.00		40055 →			
00:55	1.94	1.96	0.10mm	Complies	No	Complies
01:20	1.92	1.95	0.13mm	Complies	No	Complies
01:45	1.90	1.97	0.11mm	Complies	No	Complies
02:10	1.95	1.99	0.10mm	Complies	No	Complies
02:35	1.91	1.97	0.13mm	Complies	No	Complies
03:00	1.92	1.96	0.08mm	Complies	No	Complies
03:25	1.95	1.98	0.10mm	Complies	No	Complies
03:50	CL 49 2.150		40055 →			
04:15	2.46	2.49	0.06mm	Complies	No	Complies
04:40	2.43	2.47	0.10mm	Complies	No	Complies
05:05	2.40	2.45	0.13mm	Complies	No	Complies
05:30	2.45	2.46	0.10mm	Complies	No	Complies
05:55	2.43	2.49	0.12mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00–23:00	48	11	Prod stopped
23:00–00:00	48	47	−1
00:00–01:00	36	7/16	changing thickness
01:00–02:00	36	32	−4
02:00–03:00	36	28	−8
03:00–04:00	36	23	changing colour
04:00–05:00	36	20	−16
05:00–06:00	36	32	−4
Total	312	216	−96

Remarks: • Colour change
• Thickness change
• Speed: 2.00 (42Hz) 2.50mm (33Hz)

Checked By QAI: SEITO Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 05/10/2026 Shift: B

Color: Q70 Thickness: 1.30mm Batch: 40045

Time	Thickness Range: 1.17 - 1.43 Min (mm)	Thickness Range: 1.17 - 1.43 Max (mm)	Squareness	Edges	Color	Surface
14:25	D	1	0.10mm	Complies	D	complies
14:50			0.05mm	complies	1	complies
15:15	PRODUCTION		STOPPED -	conveyor belts at pp were		broken
15:40						
16:05	RESTART					
16:30			0.02mm	complies		complies
16:55			0.08mm	complies		complies
17:20	D		0.10mm	complies	D	complies
17:45		1	0.00mm	complies		complies
18:10			0.05mm	complies	1	complies
18:35	Q38	1.30	40055			
19:00			0.05mm	complies		complies
19:25	B		0.08mm	complies	B	complies
19:50			0.02mm	complies		complies
20:15			0.10mm	complies		complies
20:40			0.08mm	complies		complies
21:05			0.05mm	complies		complies
21:30			0.10mm	complies		complies
21:55			0.02mm	complies		complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 - 15:00	28	23	-5
15:00 - 16:00	28	18	prod - stopped
16:00 - 17:00	28	28	
17:00 - 18:00	28	29	
18:00 - 19:00	28	3/26	Colour change
19:00 - 20:00	48	42	-6
20:00 - 21:00	48	42	-6
21:00 - 22:00	48	42	-6
Total	284	245	-39

Remarks: * Colour change
* NO thickness change

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 05/10/2026

Shift: A

Color: 870

Thickness: 1.30mm

Batch: 40045

Time	Thickness Range: 1.17–1.43 Min (mm)	Thickness Range: 1.17–1.43 Max (mm)	Squareness	Edges	Color	Surface
07:45	D		0.05mm	Complies	D I Y	Complies
08:10		I Y	0.10 mm	Complies		Complies
08:35			0.03mm	Complies		Complies
09:00			0.05 mm	Complies		Complies
09:25	PRODUCTION		STOPPED-	CHANGING	KNIVES →	
09:50	D I Y		0.00 mm	Complies	D I Y	Complies
10:15			0.02mm	Complies		Complies
10:40	PRODUCTION STOPPED – Conveyer belt (2)			derailed →		
11:05						
11:30						
11:55						
12:20						
12:45						
13:10						
13:35	RESTART →					
14:00	D I Y		0.00 mm	Complies	D I Y	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
07:00 – 08:00	28	4	in 15 mins
08:00 – 09:00	28	8	Contamination on tiles
09:00 – 10:00	CHANGING	KNIVES	
10:00 – 11:00	28	14	Production Stopped
11:00 – 12:00	↓	↓	↓
12:00 – 13:00	↓	↓	↓
13:00 – 14:00	28	6	in 30 mins
Total	66	32	-34

Remarks: * No colour change
* No thickness change

Checked By QAI: BETTY

Supervisor: MAHLO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 28/09/2026

Shift: A

Color: Q49

Thickness: 13.0mm

Batch: 40035

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25			0.10mm	Complies		Complies
06:50			0.13mm	Complies		Complies
07:15			0.10mm	Complies		Complies
07:40			0.06mm	Complies		Complies
08:05			0.02mm	Complies		Complies
08:30	1270	1.30	400.45			
08:55			0.10mm	Complies		Complies
09:20			0.08mm	Complies		Complies
09:45			0.10mm	Complies		Complies
10:10			0.08mm	Complies		Complies
10:35			0.10mm	Complies		Complies
11:00			0.15mm	Complies		Complies
11:25			0.13mm	Complies		Complies
11:50			0.10mm	Complies		Complies
12:15			0.13mm	Complies		Complies
12:40			0.10mm	Complies		Complies
13:05			0.06mm	Complies		Complies
13:30	PRODUCTION		STOPPED –	Breakdown at	punching	press
13:55	11		11		11	

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 – 07:00	38	31	+3
07:00 – 08:00	28	31	+3
08:00 – 09:00	48	45	Changing colour
09:00 – 10:00	48	44	−4
10:00 – 11:00	48	46	−2
11:00 – 12:00	48	40	−8
12:00 – 13:00	48	46	−2
13:00 – 14:00	48	4	Pred stopped
Total	344	267	−77

Remarks: Colour change
No Thickness change
& Speed 1.50Hz

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 27/09/2026 Shift: C

Color: Q49 Thickness: 1.30mm Batch: 40035

Time	Thickness Range: 1.17 - 1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	BULK		0.04mm	Complies	BULK	Complies
22:50			0.07mm	Complies		Complies
23:15			0.03mm	Complies		Complies
23:40			0.05mm	Complies		Complies
00:05			0.06mm	Complies		Complies
00:30			0.04mm	Complies		Complies
00:55			0.07mm	Complies		Complies
01:20			0.09mm	Complies		Complies
01:45	PRODUCTION STOPPED					
02:10	RESTART					
02:35	Q49	1.30mm	40035			
03:00			0.06mm	Complies		Complies
03:25			0.03mm	Complies		Complies
03:50	DRY		0.10mm	Complies	DRY	Complies
04:15			0.05mm	Complies		Complies
04:40			0.07mm	Complies		Complies
05:05			0.04mm	Complies		Complies
05:30			0.08mm	Complies		Complies
05:55			0.06mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	48	36	-12
23:00 00:00	48	43	-5
00:00 01:00	48	48	-
01:00 02:00	48	21	-27
02:00 03:00	28	3/23	
03:00 04:00	28	28	-
04:00 05:00	28	28	-
	28	34	+6
Total	304	264	40

Remarks: * No colour change
* No Thickness change
* Production Stopped due to an broken mixer mill relay, hence it was changed
* There was shortage of 36 Mal Boxes for the second pallet of Q49, 1.30 40035 (BULK), therefore, will have to be Repacked when boxes arrive.

Checked By QAI: TMATO Supervisor: MALLO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 27/09/2026 Shift: B

Color: Q446 Thickness: 1.30mm Batch: 40025

	Thickness Range: 1.17–1.43						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
14:25	B		0:10mm	Complies	B	Complies	14:00 – 15:00	48	46	-2
14:50			0:13mm	Complies		Complies	15:00 – 16:00	48	43	-5
15:15			0:13mm	Complies		Complies	16:00 – 17:00	48	47	-1
15:40			0:11mm	Complies		Complies	17:00 – 18:00	28	16/28	
16:05			0:08mm	Complies		Complies	18:00 – 19:00	28	28	—
16:30			0:15mm	Complies		Complies	19:00 – 20:00	28	27	-1
16:55			0:10mm	Complies		Complies	20:00 – 21:00	28	24/11	
17:20			0:13mm	Complies		Complies	21:00 – 22:00	48	38	-10
17:45			0:15mm	Complies		Complies				
18:10			0:10mm	Complies		Complies				
18:35			0:04mm	Complies		Complies				
19:00			0:08mm	Complies		Complies				
19:25			0:07mm	Complies		Complies				
19:50			0:10mm	Complies		Complies				
20:15			0:06mm	Complies		Complies				
20:40	Q449	1.30	40035							
21:05	B		0:10mm	Complies	B	Complies				
21:30	BULK		0:06mm	Complies	BULK	Complies				
21:55			0:10mm	Complies		Complies	Total	304	298	-6

Remarks: 2 Colour change
1 No thickness change

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 27/09/2026

Shift: A

Color: 914

Thickness: 1.30 mm

Batch: 40015

Time	Thickness Range: 1.17 – 1.43 Min (mm)	Thickness Range: 1.17 – 1.43 Max (mm)	Squareness	Edges	Color	Surface
06:25	BULK		0.05mm	Complies	BULK	complies
06'50			0.10 mm	complies		complies
07:15			002mm	Complies		complies
07:40			0.00mm	Complies		complies
08:05			0.08mm	complies		complies
08:30			0.05mm	Complies		complies
05'55			0.10 mm	complies		complies
09'20			0.02mm	complies		complies
09:45			0.08 mm	complies		complies
10:10			0.10mm	complies		complies
10:35			0.00 mm	complies		complies
11:00			0.05mm	complies		complies
11:25			0.02mm	complies		complies
11:50			0.08 mm	complies		complies
12:15			0.10mm	complies		complies
12:40	0.46	1.30	A0025			
13:05	BULK		0.05mm	complies	BULK	complies
13:30			0.00 mm	complies		complies
13:55			0.10mm	complies		complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	48	26/12	
09:00 08:00	28	22	–6
08:00 09:00	28	28	–
09:00 10:20	28	28	–
10:00 11:00	28	28	–
11:00 12:00	28	28	–
12:00 13:00	28	14/6	Colour change
13:00 14:00	48	48	–
Total	264	234	–30

Remarks: * Colour Change
* No thickness change

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 26/09/2026

Shift: C

Color: Q54

Thickness: 1.30mm

Batch: 40005

Time	Thickness Range: 1.17-1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25			0.10mm	complies		complies
22:50			0.04mm	complies		complies
23:15			0.05mm	complies		complies
23:40			0.07mm	complies		complies
00:05			0.00mm	complies		complies
00:30			0.06mm	complies		complies
00:55			0.08mm	complies		complies
01:20			0.07	complies		complies
01:45	Q14	1.30	40015			
02:10			0.07mm	complies		complies
02:35			0.03mm	complies		complies
03:00			0.04mm	complies		complies
03:25			0.09mm	complies		complies
03:50			0.07mm	complies		complies
04:15			0.04mm	complies		complies
04:40			0.03mm	complies		complies
05:05			0.05mm	complies		complies
05:30			0.07mm	complies		complies
05:55			0.04mm	complies		complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	28	24	-4
23:00 00:00	28	30	+2
00:00 01:00	28	28	-
01:00 02:00	48	11/12	
02:00 03:00	48	40	-8
03:00 04:00	48	38	-10
04:00 05:00	48	44	-4
05:00 06:00	48	40	-8
Total	324	267	60

Remarks: * Colour Change
* No Thickness change

Checked By QAI: TI-HATO

Supervisor: MAILO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 26/09/2026

Shift: B

Color: Q86

Thickness: 1.30mm

Batch: 39995

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	Q54	1.30	40005			
14:50			0.15mm	Complies		Complies
15:15			0.13mm	Complies		Complies
15:40			0.15mm	Complies		Complies
16:05			0.10mm	Complies		Complies
16:30			0.15mm	Complies		Complies
16:55			0.11mm	Complies		Complies
17:20			0.13mm	Complies		Complies
17:45			0.10mm	Complies		Complies
18:10			0.08mm	Complies		Complies
18:35			0.07mm	Complies		Complies
19:00			0.06mm	Complies		Complies
19:25			0.10mm	Complies		Complies
19:50			0.13mm	Complies		Complies
20:15			0.10mm	Complies		Complies
20:40			0.10mm	Complies		Complies
21:05			0.13mm	Complies		Complies
21:30			0.08mm	Complies		Complies
21:55			0.06mm	Complies		Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
14:00 – 15:00	48	38	-10
15:00 – 16:00	48	40	-8
16:00 – 17:00	48	48	—
17:00 – 18:00	48	43	-5
18:00 – 19:00	48	41	-7
19:00 – 20:00	~~25~~ 48	31	+3
20:00 – 21:00	28	30	+2
21:00 – 22:00	28	29	+1
Total	324	300	-24

Remarks: * No colour change
* No thickness change
* Speed 50HZ

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 26/09/2026

Shift: A

Color: Q 28

Thickness: 1.30mm

Batch: 39985

Time	Thickness Range: 1.17 – 1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25			0.05mm	Complies		complies
06:50			0.02mm	complies		complies
07:15			0.10mm	complies		complies
07:40			0.00mm	complies		complies
08:05			0.02mm	complies		complies
08:30			0.08mm	complies		complies
08:55	Q 86	1.30	39995			
09:20			0.10mm	complies		complies
09:45			0.08mm	complies		complies
10:10			0.05mm	complies		complies
10:35			0.00mm	complies		complies
11:00			0.08mm	complies		complies
11:25			0.02mm	complies		complies
11:50			0.10mm	complies		complies
12:15			0.05mm	complies		complies
12:40			0.00mm	complies		complies
13:05			0.08mm	complies		complies
13:30			0.05mm	complies		complies
13:55			0.02mm	complies		complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 – 07:00	28	24	-4
07:00 – 08:00	28	28	-
08:00 – 09:00	28	14/14	Colour change
09:00 – 10:00	48	44	-4
10:00 – 11:00	48	46	-2
11:00 – 12:00	48	40	-8
12:00 – 13:00	48	40	-8
13:00 – 14:00	48	41	-7
Total	324	291	-33

Remarks: * Colour change
* NO thickness change

Checked By QAI: KARABO

Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 25/09/2026 Shift: C

Color: Q28 Thickness: 1.30mm Batch: 39985

Time	Thickness Range: 1.17–1.43 Min (mm)	Thickness Range: 1.17–1.43 Max (mm)	Squareness	Edges	Color	Surface
22:25			0.00 mm	Complies		Complies
22:50			0.08 mm	Complies		Complies
23:15			0.05 mm	Complies		Complies
23:40			0.10 mm	Complies		Complies
00:05			0.00 mm	Complies		Complies
00:30			0.10mm	Complies		Complies
00:55			0.08mm	Complies		Complies
01:20			0.05 mm	Complies		Complies
01:45			0.00mm	Complies		Complies
02:10			0.00mm	Complies		Complies
02:35	-		0.00 mm	Complies		Complies
03:00			0.00mm	Complies		Complies
03:25			0.05mm	Complies		Complies
03:50			0.08mm	Complies		Complies
04:15			0.10 mm	Complies		Complies
04:40			0.02mm	Complies		Complies
05:05			0.05mm	Complies		Complies
05:30			0.00 mm	Complies		Complies
05:55			0.08mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 – 23:00	48	44	~~-4~~
23:00 – 00:00	48	48	-8
00:00 – 01:00	48	40	-8
01:00 – 02:00	48	42	-6
02:00 – 03:00	48	16/10	BULK DIY
03:00 – 04:00	28	28	-
04:00 – 05:00	28	28	-
05:00 – 06:00	28	30	+2
Total	297	278	-19

Remarks: *No odour change
*No thickness change

Checked By QAI: BETTY Supervisor: MAICO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 25/09/2026

Shift: B

Color: Q77

Thickness: 13mm

Batch: 39975

Time	Thickness Range: 1.12–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25			0.10mm	Complies		Complies
14:50			0.08mm	Complies		Complies
15:15			0.10mm	Complies		Complies
15:40			0.08mm	Complies		Complies
16:05			0.05mm	Complies		Complies
16:30			0.13mm	Complies		Complies
16:55			0.10mm	Complies		Complies
17:20			0.10mm	Complies		Complies
17:45	Q19	1.13	39965			
18:10			0.10mm	Complies		Complies
18:35			0.13mm	Complies		Complies
19:00			0.06mm	Complies		Complies
19:25			0.10mm	Complies		Complies
19:50			0.08mm	Complies		Complies
20:15			0.10mm	Complies		Complies
20:40	CHANGING		KNIVES			
21:05	"		"			
21:30	Q28	1.30	39985			
21:55	BULK		0.10mm	Complies	BULK	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00–15:00	28	26	-2
15:00–16:00	28	26	-2
16:00–17:00	28	27	-1
17:00–18:00	28	9/12	Changing Colour
18:00–19:00	28	26	-2
19:00–20:00	28	29	+1
20:00–21:00	28	15	Changing Knives
21:00–22:00	28	18	-10
Total	224	188	-36

Remarks: *Colour change
& No thickness change
& Speed 150HZ

Checked By QAI: SENTO

Supervisor: DANIEL

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

Kalahari FLOOR TILES (Pty) Ltd

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 25/09/2026 Shift: A

Color: Q77 Thickness: 1.30mm Batch: 39975

Time	Thickness Range: 1.17 – 1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25			0.10mm	complies		complies
06:50			0.05mm	complies		complies
07:15			0.02mm	complies		complies
07:40			0.08mm	complies		complies
08:05			0.00mm	complies		complies
08:30			0.05mm	complies		complies
08:55			0.15mm	complies		complies
09:20			0.10mm	complies		complies
09:45			0.08mm	complies		complies
10:10			0.02mm	complies		complies
10:35			0.15mm	complies		complies
11:00			0.08mm	complies		complies
11:25			0.12mm	complies		complies
11:50			0.10mm	complies		complies
12:15			0.00mm	complies		complies
12:40			0.05mm	complies		complies
13:05			0.02mm	complies		complies
13:30			0.10mm	complies		complies
13:55			0.05mm	complies		complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 – 07:00	28	20	-8
07:00 – 08:00	28	20	-8
08:00 – 09:00	28	24	-4
09:00 – 10:00	28	24	-4
10:00 – 11:00	28	23	-5
11:00 – 12:00	28	22	-6
12:00 – 13:00	28	20	-8
13:00 – 14:00	28	20	-8
Total	224	171	-53

Remarks: * no colour and thickness change
* Speed: 50H2
* KK55 2.50mm 39955 failed dimensional stability with a minimum of 299.06 machine direction (TIK 2

Checked By QAI: KARABO

Supervisor: THEMBANI

DOC NO: KFT-QC-8.5.1-OCCT-F-01

PREPARED BY: B. K

REVISION NUMBER: 02_24/09/2026

APPROVED BY: M. K

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 24/09/2026

Shift: C

Color: 977

Thickness: 1.30mm

Batch: 39975

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25			0.00 mm	Complies		Complies
22:50			0.05 mm	Complies		Complies
23:15			0.02 mm	Complies		Complies
23:40			0.00 mm	Complies		Complies
00:05			0.00 mm	Complies		Complies
00:30			0.10 mm	Complies		Complies
00:55			0.08 mm	Complies		Complies
01:20			0.00 mm	Complies		Complies
01:45			0.00 mm	Complies		Complies
02:10			0.02 mm	Complies		Complies
02:35			0.05 mm	Complies		Complies
03:00			0.00 mm	Complies		Complies
03:25			0.05 mm	Complies		Complies
03:50			0.02mm	Complies		Complies
04:15			0.00mm	Complies		Complies
04:40			0.00mm	Complies		Complies
05:05			0.00mm	Complies		Complies
05:30			0.00mm	Complies		Complies
05:55			0.05mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	48	36	-12
23:00 00:00	48	24	Line out 24
00:00 01:00	48	38	-10
01:00 02:00	48	30	-18
02:00 03:00	48	30	-18
03:00 04:00	48	30	-18
04:00 05:00	48	12 21	Bulk DIY
05:00 06:00	28	30	+2
Total	357	251	-106

Remarks: *No colour change 39935 KK22250 Machine failed ~~dimensions~~ with a minimum of 299.82 and DM of 299.95 Tile 4
*No thickness change KK 28 failed machine direction with a minimum of 299.95 and DM 298.90
SPEED: 30M² *several line cuts due to material fall from mixing mill.

Checked By QAI: BETTY

Supervisor: MTALO

DOC NO: KFT-QC-8.5.1-OCCT-F-01

REVISION NUMBER: 02_24/09/2026

PREPARED BY: B. K

APPROVED BY: M. K

Kalahari FLOOR TILES (Pty) Ltd

ONLINE CONTROLS FOR COLOUR & THICKNESS

Date: 24/09/2026 Shift: B

Color: 204 Thickness: 20mm Batch: 5215

Thickness Range: 1.87–2.13

Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	1.87	1.96	0.10mm	Complies	No	Complies
14:50	1.90	1.95	0.08mm	Complies	No	Complies
15:15	1.94	1.97	0.06mm	Complies	No	Complies
15:40	PRODUCTION STOPPED — MEETING					
16:05	KK22 2.50 39935					
16:30	2.43	2.47	0.10mm	Complies	No	Complies
16:55	2.40	2.46	0.08mm	Complies	No	Complies
17:20	2.43	2.48	0.06mm	Complies	No	Complies
17:45	KK28 2.50 39945					
18:10	2.40	2.46	0.10mm	Complies	No	Complies
18:35	2.45	2.53	0.06mm	Complies	No	Complies
19:00	2.43	2.46	0.02mm	Complies	No	Complies
19:25	2.45	2.47	0.08mm	Complies	No	Complies
19:50	2.40	2.45	0.10mm	Complies	No	Complies
20:15	KK58 2.50 39955					
20:40	2.43	2.47	0.10mm	Complies	No	Complies
21:05	2.45	2.50	0.08mm	Complies	No	Complies
21:30	2.43	2.48	0.06mm	Complies	No	Complies
21:55	OFF	1.30	39975			

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
14:00 – 15:00	36	37	+1
15:00 – 15:25	36	12	Changing colour
16:00 – 17:00	36	28	-8
17:00 – 18:00	36	11/14	Changing Colour
18:00 – 19:00	36	24	-12
19:00 – 20:00	36	26	-10
20:00 – 21:00	36	4	Line out
21:00 – 22:00	36	17	
Total	288	163	

Remarks: *Colour change
*Thickness
*Speed 1.34H2
*Machine direction sizes (dimensions) too low for both tile 1 and 2 with a minimum of 2.58/1.87mm
*Shortage of 1 box-KK28

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 24/09/2026 Shift: A

Color: 204 Thickness: 2.00mm Batch: 5215

	Thickness Range: 1.97 – 2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
06:25	1.92	1.97	0.10 mm	Complies	No	Complies	06:00 07:00	36	32	-4
06:50	1.94	1.98	0.05mm	complies	No	complies	07:00 08:00	36	32	-4
07:15	1.92	1.98	0.02mm	complies	NO	complies				
07:40	1.93	1.96	0.00mm	Complies	No	Complies	08:00 09:00	36	36	–
08:05	1.91	1.97	0.08mm	complies	NO	complies				
08:30	1.94	1.97	0.05mm	Complies	NO	complies	09:00 10:00	36	36	–
08:55	1.92	1.99	0.10 mm	complies	No	complies				
09:20	1.90	1.98	0.02mm	complies	NO	complies	10:00 11:00	36	32	-4
09:45	1.94	1.97	0.08mm	complies	NO	complies				
10:10	1.92	1.98	0.10mm	complies	NO	complies	11:00 12:00	36	32	-4
10:35	1.96	1.99	0.03mm	complies	No	complies				
11:00	1.93	1.97	0.06mm	Complies	No	Complies	12:00 13:00	36	36	–
11:25	1.94	1.98	0.05mm	Complies	NO	Complies				
11:50	1.93	1.98	0.04mm	Complies	NO	Complies	13:00 14:00	36	31	-5
12:15	1.92	1.97	0.02mm	complies	NO	complies				
12:40	1.90	1.99	0.00mm	complies	NO	complies				
13:05	1.91	1.98	0.08mm	Complies	NO	complies				
13:30	1.92	1.97	0.10mm	Complies	NO	Complies				
13:55	1.94	1.97	0.05mm	complies	NO	complies	Total	288	267	-21

Remarks: * No colour and thickness change
* Speed: 42 H²

Checked By QAI: KARABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 23/09/2026 Shift: C

Color: KK72 Thickness: 2.50mm Batch: 39925

Time	Thickness Range: 2.37–2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.41	2.49	0.00 mm	Complies	No	Complies
22:50	2.44	2.47	0.08 mm	Complies	No	Complies
23:15	2.43	2.45	0.10 mm	Complies	No	Complies
23:40	2.44	2.47	0.05mm	Complies	No	Complies
00:05	2.42	2.48	0.08mm	Complies	No	Complies
00:30	2.43	2.46	0.00mm	Complies	No	Complies
00:55	2.41	2.46	0.00mm	Complies	No	Complies
01:20	2.44	2.47	0.08 mm	Complies	No	Complies
01:45	2.44	2.47	0.10 mm	Complies	No	Complies
02:10	2.42	2.48	0.08 mm	Complies	No	Complies
02:35	2.44	2.48	0.00 mm	Complies	No	Complies
03:00	CHANGING KNIVES / MARBLING 2.00				9246	→
03:25	↓		↓	↓	↓	↓
03:50						
04:15						
04:40	↓		↓	↓	↓	↓
05:05	2.04	2.00	5215	→	→	→
05:30	1.94	1.97	0.00 mm	Complies	No	Complies
05:55	1.94	1.98	0.02mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	36	32	−4
23:00 00:00	36	30	−6
00:00 01:00	36	38	−4
01:00 02:00	36	28	−8
02:00 03:00	36	22	−14
03:00 04:00	CHANGING KNIVES MARBLING 2.00		9246
04:00 05:00	↓	↓	↓
05:00 06:00	36	24	In 45 mins −12
Total	288	166	−122

Remarks: *Colour Change
*Thickness Change
*SPEED 35Hz (2.50mm) 42Hz for 2.00mm

Checked By QAI: BETTY Supervisor:

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 23/09/2026 Shift: B

Color: KK72 Thickness: 2.150mm Batch: 39925

Time	Thickness Range: 2.137 – 2.163 Min (mm)	Thickness Range: 2.137 – 2.163 Max (mm)	Squareness	Edges	Color	Surface
14:25	PRODUCTION	STOPPED –	Breakdown at punching			Press
14:50	RESTART				RESTART	
15:15	2.144	2.146	0.10mm	Complies	No	Complies
15:40	2.140	2.145	0.106mm	Complies	No	Complies
16:05	2.143	2.147	0.102mm	Complies	No	Complies
16:30	2.145	2.145	0.106mm	Complies	Slight shade variation	Complies
16:55	2.140	2.146	0.10mm	Complies	"	Complies
17:20	2.145	2.148	0.105mm	Complies	No	Complies
17:45	2.143	2.149	0.102mm	Complies	No	Complies
18:10	2.140	2.147	0.106mm	Complies	No	Complies
18:35	2.145	2.145	0.108mm	Complies	Slight shade variation	Complies
19:00	2.144	2.146	0.10mm	Complies	"	Complies
19:25	2.140	2.145	0.106mm	Complies	No	Complies
19:50	2.143	2.147	0.10mm	Complies	No	Complies
20:15	2.140	2.145	0.13mm	Complies	No	Complies
20:40	2.143	2.149	0.10mm	Complies	No	Complies
21:05	2.14	2.147	0.106mm	Complies	No	Complies
21:30	2.143	2.145	0.10mm	Complies	No	Complies
21:55	2.140	2.146	0.10mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
15:00 – 16:00	36	23	-13
16:00 – 17:00	36	26	-10
17:00 – 18:00	36	28	-8
18:00 – 19:00	36	28	-8
19:00 – 20:00	36	32	-4
20:00 – 21:00	36	32	-4
21:00 – 22:00	36	30	-6
Total	288	199	-89

Remarks: *No Colour Change
*No Thickness Change
*Speed 1.84HZ

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 23/09/2026 Shift: A

Color: KK41 Thickness: 2.50mm Batch: 39905

	Thickness Range: 2.37 – 2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
06:25	2.42	2.48	0.05mm	complies	NO	complies	06:00 07:00	36	2/8	colour change
06:50	KK 22	2.50	39915	→			07:00 08:00	36	22	-14
07:15	2.44	2.47	0.00mm	complies	NO	complies	08:00 09:00	36	4/4	Colour change
07:40	2.41	2.49	0.02mm	complies	NO	complies	09:00 10:00	36	24	-12
08:05	2.40	2.47	0.05mm	complies	NO	complies	10:00 11:00	36	16	colour change -20
08:30	2.42	2.48	0.05mm	complies	NO	complies	11:00 12:00	36	24	-12
08:55	KK 72	2.50	39925	→			12:00 13:00	36	20	-16
09:20	2.42	2.48	0.00mm	complies	NO	complies	13:00 14:00	36	27	-9
09:45	2.44	2.46	0.02mm	complies	NO	complies				
10:10	2.41	2.49	0.05mm	complies	NO	complies				
10:35	2.43	2.49	0.08mm	Complies	NO	Complies				
11:00	2.41	2.49	0.10mm	Complies	NO	Complies				
11:25	2.44	2.48	0.08mm	Complies	NO	Complies				
11:50	2.42	2.47	0.05mm	complies	NO	complies				
12:15	2.40	2.47	0.10mm	complies	NO	complies				
12:40	2.43	2.49	0.00mm	complies	NO	complies				
13:05	2.41	2.48	0.02mm	complies	NO	complies				
13:30	2.42	2.47	0.05mm	complies	NO					
13:55	2.40	2.49	0.10mm	complies	NO		Total	288	151	137

Remarks: * Colour change
* No thickness change *Speed: 34 H²
* Several line cuts due to material falling at mixing mill

Checked By QAI: KAKABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 22/09/2026 Shift: C

Color: KK07 Thickness: 2.50mm Batch: 39885

Time	Thickness Range: 2.37–2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.44	2.46	0.00 mm	Complies	No	Complies
22:50	2.43	2.47	0.08 mm	Complies	No	Complies
23:15	2.40	2.48	0.08mm	Complies	No	Complies
23:40	2.43	2.45	0.10 mm	Complies	No	Complies
00:05	2.44	2.47	0.00mm	Complies	No	Complies
00:30	2.44	2.47	0.10 mm	Complies	No	Complies
00:55	KK07	2.00	39895			
01:20	~~KK~~ 1.94	1.97	0.08 mm	Complies	No	Complies
01:45	1.94	1.98	0.10 mm	Complies	No	Complies
02:10	1.92	1.95	0.08 mm	Complies	No	Complies
02:35	1.94	1.97	0.02 mm	Complies	No	Complies
03:00	1.94	1.97	0.00 mm	Complies	Slight shade variation	Complies
03:25	1.90	1.98	0.08 mm	Complies	No	Complies
03:50	KK 41	2.50	39905			
04:15	2.44	2.47	0.08 mm	Complies	No	Complies
04:40	2.40	2.46	0.10 mm	Complies	No	Complies
05:05	2.44	2.47	0.05 mm	Complies	No	Complies
05:30	2.43	2.47	0.00mm	Complies	No	Complies
05:55	2.44	2.47	0.00mm	Complies	No	Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
22:00 – 23:00	36	30	−6
23:00 – 00:00	36	24	−12
00:00 – 01:00	36	19 / 18	~~Thickness change~~
01:00 – 02:00	36	32	−4
02:00 – 03:00	36	30	−6
03:00 – 04:00	36	17 / 16	Colour + thickness change
04:00 – 05:00	36	30	
05:00 – 06:00	36	24	4 mincut −12
Total	288	220	−68

Remarks: *Colour change
*Thickness change

Checked By QAI: BETTY Supervisor: MAIKO

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 22/09/2026 Shift: B

Color: KK07 Thickness: 2.50mm Batch: 39885

Time	Thickness Range: 2.37~2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	2.43	2.46	0.10mm	Complies	No	Complies
14:50	2.45	2.48	0.06mm	Complies	No	Complies
15:15	2.40	2.45	0.06mm	Complies	No	Complies
15:40	2.45	2.47	0.10mm	Complies	No	Complies
16:05	2.44	2.48	0.10mm	Complies	No	Complies
16:30	2.43	2.47	0.06mm	Complies	No	Complies
16:55	2.45	2.55	0.10mm	Complies	Slight shade variation	Complies
17:20	2.43	2.46	0.10mm	Complies	11	Complies
17:45	2.40	2.44	0.08mm	Complies	No	Complies
18:10	2.45	2.55	0.06mm	Complies	No	Complies
18:35	2.41	2.46	0.02mm	Complies	Slight shade variation	Complies
19:00	2.43	2.48	0.08mm	Complies	11	Complies
19:25	2.45	2.50	0.10mm	Complies	11	Complies
19:50	2.41	2.47	0.06mm	Complies	No	Complies
20:15	2.45	2.46	0.10mm	Complies	No	Complies
20:40	2.40	2.45	0.08mm	Complies	No	Complies
21:05	2.42	2.48	0.09mm	Complies	No	Complies
21:30	2.45	2.46	0.10mm	Complies	No	Complies
21:55	2.40	2.45	0.08mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 – 15:00	36	36	—
15:00 – 16:00	36	32	-4
16:00 – 17:00	36	28	-8
17:00 – 18:00	36	28	-8
18:00 – 19:00	36	32	-4
19:00 – 20:00	36	34	-2
20:00 – 21:00	36	33	-3
21:00 – 22:00	36	35	-1
Total	288	253	-30

Remarks: * No colour change
* No thickness change
* Slight shade variation observed

Checked By QAI: SENTO

Supervisor: ~~SENTO~~ DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 22/09/2026 Shift: A

Color: KK07 Thickness: 2.50mm Batch: 39885

Time	Thickness Range: 2.37 – 2.63 Min (mm)	Thickness Range: 2.37 – 2.63 Max (mm)	Squareness	Edges	Color	Surface
06:25	2.42	2.48	0.10mm	complies	NO	complies
06:50	PRODUCTION STOPPED – MEETING					
07:15						
07:40						
08:05	RESTART					
08:30	2.44	2.47	0.02mm	complies	Slight shade variation	complies
08:55	2.41	2.48	0.00mm	complies	NO	complies
09:20	2.43	2.46	0.05mm	complies	NO	complies
09:45	2.44	2.49	0.10mm	complies	NO	complies
10:10	2.40	2.47	0.00mm	complies	NO	complies
10:35	2.43	2.47	0.08mm	complies	NO	complies
11:00	2.44	2.48	0.02mm	complies	NO	complies
11:25	2.41	2.46	0.10mm	complies	NO	complies
11:50	2.44	2.49	0.00mm	complies	NO	complies
12:15	2.42	2.47	0.05mm	complies	NO	complies
12:40	2.40	2.47	0.02mm	complies	NO	complies
13:05	2.43	2.48	0.08mm	complies	NO	complies
13:30	2.44	2.46	0.00mm	complies	NO	complies
13:55	2.41	2.49	0.08mm	complies	NO	complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
06:00 – 07:00	36	22	-14
08:00 – 09:00	36	24	prod-stopped
09:00 – 10:00	36	24	-12
10:00 – 11:00	36	24	-12
11:00 – 12:00	36	32	-4
12:00 – 13:00	36	32	-4
13:00 – 14:00	36	34	-2
Total	252	192	-60

Remarks: * NO colour change
* NO thickness change
Speed: 37Hz

Checked By QAI: KARABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 21/09/2026 Shift: C

Color: KK07 Thickness: 2.50mm Batch: 39885

Time	Thickness Range: 2.37–2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.44	2.47	0.00 mm	Complies	NO	Complies
22:50	2.40	2.47	0.08 mm	Complies	NO	Complies
23:15	2.43	2.48	0.05 mm	Complies	NO	Complies
23:40	2.44	2.49	0.02 mm	Complies	NO	Complies
00:05	2.41	2.47	0.10 mm	Complies	NO	Complies
00:30	2.42	2.46	0.08 mm	Complies	NO	Complies
00:55	2.44	2.47	0.00 mm	Complies	NO	Complies
01:20	2.40	2.49	0.10 mm	Complies	NO	Complies
01:45	2.41	2.47	0.00 mm	Complies	NO	Complies
02:10	2.44	2.47	0.08 mm	Complies	Slight shade variation	Complies
02:35	2.44	2.48	0.08 mm	Complies	NO	Complies
03:00	2.44	2.47	0.05 mm	Complies	NO	Complies
03:25	2.43	2.47	0.02 mm	Complies	NO	Complies
03:50	2.42	2.46	0.08 mm	Complies	NO	Complies
04:15	2.40	2.48	0.02 mm	Complies	NO	Complies
04:40	2.44	2.47	0.08 mm	Complies	NO	Complies
05:05	2.42	2.48	0.00 mm	Complies	NO	Complies
05:30	2.43	2.47	0.00mm	Complies	NO	Complies
05:55	2.44	2.49	0.08 mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	36	28	−8
23:00 00:00	36	24	−12
00:00 01:00	36	28	−8
01:00 02:00	36	30	−6
02:00 03:00	36	30	−6
03:00 04:00	36	34	Line Cut +12
04:00 05:00	36	22	−14
05:00 06:00	36	21	Line cut −15
Total	288	207	−81

Remarks: *No colour change
*No thickness change
SPEED: 36 HZ

Checked By QAI: BETTY Supervisor: MAILO

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 21/09/2026 Shift: A

Color: KK77 Thickness: 2.50mm Batch: 39875

Time	Thickness Range: 2.37–2.63 Min (mm)	Thickness Range: 2.37–2.63 Max (mm)	Squareness	Edges	Color	Surface
14:25	Marb	ling 2.00	92	12 / CHANGING	KNIVES →	
14:50						
15:15						
15:40						
16:05						
16:30						
16:55	MEETING →			MEETING →		
17:20	Marb	ling	2.00	9101 →		
17:45						
18:10						
18:35						
19:00						
19:25	KK07	2.50	398855 →			
19:50	2.46	2.49	0.10mm	Complies	NO	Complies
20:15	2.43	2.46	0.06mm	Complies	NO	Complies
20:40	2.48	2.48	0.02mm	Complies	NO	Complies
21:05	2.45	2.50	0.08mm	Complies	NO	Complies
21:30	2.45	2.55	0.08mm	Complies	NO	Complies
21:55	2.46	2.46	0.06mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
19:20 – 20:00	36	20	-16
20:00 – 21:00	36	24	-12
21:00 – 22:00	36	25	-11
Total	288	69	

Remarks: * Colour change
* Thickness change
* Speed: 35Hz

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 21/05/2026 Shift: A

Color: KK 77 Thickness: 250 mm Batch: 39875

Time	Thickness Range: 237-263 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25	Cleaning		Production line			
06:50			↓			
07:15	RESTART					
07:40	2.42	2.47	0.05mm	complies	NO	Complies
08:05	2.44	2.48	0.10 mm	complies	NO	complies
08:30	2.42	2.49	0.02mm	complies	NO	complies
08:55	2.40	2.47	0.00mm	complies	NO	complies
09:20	2.43	2.46	0.08mm	complies	NO	complies
09:45	2.41	2.47	0.00 mm	complies	NO	complies
10:10	2.44	2.47	0.10 mm	complies	NO	complies
10:35	2.40	2.48	0.05 mm	complies	NO	complies
11:00	2.43	2.49	0.02 mm	complies	NO	complies
11:25	2.41	2.47	0.00 mm	complies	NO	complies
11:50	2.44	2.48	0.08 mm	complies	NO	complies
12:15	2.42	2.46	0.10 mm	complies	NO	complies
12:40	2.43	2.49	0.05 mm	complies	NO	complies
13:05	2.44	2.47	0.10 mm	complies	NO	complies
13:30	2.40	2.46	0.00 mm	complies	NO	complies
13:55	2.42	2.48	0.05 mm	complies	NO	complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
07:00 08:00	36	15	line cut -21
08:00 09:00	36	20	-16
09:00 10:00	36	26	-10
10:00 11:00	36	22	-14
11:00 12:00	36	28	-8
12:00 13:00	36	24	-12
13:00 14:00	36	18	-18
Total	252	153	-99

Remarks: * No colour change
* No thickness change
* material falling at mixing mill

Checked By QAI: KARABO

Supervisor: THEMBANI