Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 18/09/2026 Shift: C

Color: KK72 Thickness: 2.50mm Batch: 35865

Time	Thickness Range: 2.37–2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.44	2.47	0.10mm	Complies	NO	Complies
22:50	2.43	2.45	0.106mm	Complies	NO	Complies
23:15	2.42	2.46	0.102mm	Complies	NO	Complies
23:40	2.43	2.45	0.106mm	Complies	NO	Complies
00:05	2.44	2.46	0.102mm	Complies	NO	Complies
00:30	2.46	2.55	0.10mm	Complies	NO	Complies
00:55	2.47	2.49	0.108mm	Complies	NO	Complies
01:20	2.43	2.46	0.106mm	Complies	NO	Complies
01:45	2.44	2.49	0.102mm	Complies	NO	Complies
02:10	KK72 2.50 3985					
02:35	2.43	2.47	0.108mm	Complies	slight shade variation	Complies
03:00	2.44	2.45	0.106mm	Complies	NO	Complies
03:25	2.40	2.45	0.108mm	Complies	NO	Complies
03:50	2.43	2.49	0.106mm	Complies	NO	Complies
04:15	2.40	2.46	0.102mm	Complies	NO	Complies
04:40	2.45	2.46	0.100mm	Complies	NO	Complies
05:05	2.43	2.47	0.10mm	Complies	NO	Complies
05:30	2.45	2.49	0.106mm	Complies	NO	Complies
05:55	PRODUCTION STOPPED					

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	36	32	-4
23:00 00:00	36	25	-11
00:00 01:00	36	28	-8
01:00 02:00	36	31	-5
02: 03:00	36	20	Changing colour
03:00 04:00	36	24	-12
04:00 05:00	36	28	-8
05:00 06:00	36	29	-7
Total	288	217	-7

Remarks: * Colour change
* No thickness change
* Speed 134 m²

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 18/09/2026 Shift: B

Color: KK72 Thickness: 2.50mm Batch: 39865

Time	Thickness Range: 2.37 - 2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25	2.42	2.48	0.00mm	Complies	NO	complies
14:50	2.44	2.47	0.10 mm	complies	NO	complies
15:15	2.40	2.47	0.02 mm	complies	NO	complies
15:40	2.43	2.49	0.05 mm	complies	NO	complies
16:05	2.44	2.46	0.02 mm	complies	NO	complies
16:30	2.41	2.48	0.00 mm	complies	NO	complies
16:55	2.42	2.47	0.02 mm	complies	NO	complies
17:20	2.44	2.47	0.10 mm	complies	NO	complies
17:45	2.41	2.46	0.00 mm	complies	NO	complies
18:10	2.42	2.49	0.05 mm	complies	NO	complies
18:35	2.46	2.48	0.02 mm	complies	NO	complies
19:00	2.43	2.47	0.08 mm	complies	NO	complies
19:25	2.42	2.48	0.10 mm	complies	NO	complies
19:50	2.40	2.47	0.00 mm	complies	NO	complies
20:15	2.44	2.49	0.02 mm	complies	NO	complies
20:40	2.42	2.47	0.05 mm	complies	NO	complies
21:05	2.43	2.48	0.10 mm	complies	NO	complies
21:30	2.41	2.49	0.00 mm	complies	NO	complies
21:55	2.44	2.46	0.05 mm	complies	NO	complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 - 15:00	36	23	line cut -13
15:00 - 16:00	36	20	-16
16:00 - 17:00	36	24	-12
17:00 - 18:00	36	28	-8
18:00 - 19:00	36	28	-8
19:00 - 20:00	36	28	-8
20:00 - 21:00	36	26	-10
21:00 - 22:00	36	26	-10
Total	288	203	-85

Remarks: * no colour change
* no thickness change * Speed: 35 H²
* Several line cuts due to material falling from mixing mill

Checked By QAI: KARABO Supervisor: MAHLODANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 18/09/2026 Shift: A

Color: KK05 Thickness: 2.50mm Batch: 39855

	Thickness Range: 2.37–2.63						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
06:25	2.44	2.47	0.00mm	Complies	No	Complies	06:00 07:00	36	20	-16
06:50	2.40	2.48	0.08mm	Complies	No	Complies	07:00 08:00	36	19	Colour change
07:15	2.44	2.47	0.02mm	Complies	No	Complies	08:00 09:00	36	20	Line cut -16
07:40	2.41	2.47	0.00mm	Complies	No	Complies	09:00 10:00	36	34	-2
08:05	KK 72	2.50	39865				10:00 11:00	36	28	-8
08:30	2.44	2.46	0.08 mm	Complies	No	Complies	11:00 12:00	36	24	-12
08:55	2.42	2.47	0.00 mm	Complies	No	Complies	12:00 13:00	36	27	-9
09:20	2.43	2.47	0.05 mm	Complies	No	Complies	13:00 14:00	36	28	-8
09:45	2.44	2.49	0.00 mm	Complies	No	Complies				
10:10	2.42	2.47	0.08 mm	Complies	No	Complies				
10:35	2.44	2.45	0.00 mm	Complies	No	Complies				
11:00	2.40	2.49	0.05 mm	Complies	No	Complies				
11:25	2.41	2.47	0.00 mm	Complies	No	Complies				
11:50	2.44	2.46	0.10 mm	Complies	No	Complies				
12:15	2.44	2.48	0.08 mm	Complies	No	Complies				
12:40	2.44	2.46	0.00 mm	Complies	No	Complies				
13:05	2.42	2.49	0.10 mm	Complies	No	Complies				
13:30	2.43	2.47	0.00 mm	Complies	No	Complies				
13:55			0.08mm	Complies	No	Complies	Total	288	182	-106

Remarks: *Colour change
*No thickness change. SPEED: 35Hz
*Material fall from mixing mill causing several line cuts.

Checked By QAI: BETTY Supervisor: MAICO

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 17/09/2026 Shift: C

Color: KK05 Thickness: 2.15mm Batch: 39855

Time	Thickness Range: 2.137–2.163 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.143	2.146	0.06mm	Complies	No	Complies
22:50	2.145	2.150	0.08mm	Complies	No	Complies
23:15	2.144	2.149	0.08mm	Complies	slight shade variation	Complies
23:40	2.143	2.147	0.10mm	Complies	11	Complies
00:05	2.145	2.149	0.08mm	Complies	11	Complies
00:30	2.142	2.147	0.10mm	Complies	No	Complies
00:55	2.145	2.150	0.06mm	Complies	No	Complies
01:20	2.148	2.147	0.08mm	Complies	No	Complies
01:45	2.141	2.145	0.06mm	Complies	No	Complies
02:10	2.145	2.149	0.02mm	Complies	No	Complies
02:35	2.143	2.146	0.00mm	Complies	No	Complies
03:00	2.144	2.149	0.02mm	Complies	slight shade variation	Complies
03:25	PRODUCTION	STOPPED: Conductor		burnt at the control	panels:-	
03:50	Fastened it then RES	ART				
04:15	2.143	2.146	0.1mm	Complies	No	Complies
04:40	2.140	2.145	0.1mm	Complies	No	Complies
05:05	2.143	2.147	0.08mm	Complies	slight shade variation	Complies
05:30	2.144	2.150	0.10mm	Complies		Complies
05:55	2.145	2.155	0.08mm	Complies & breakdown at pressing		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 – 23:00	36	32	-4
23:00 – 00:00	36	32	-4
00:00 – 01:00	36	32	-4
01:00 – 02:00	36	30	-6
02:00 – 03:00	36	30	-6
03:00 – 04:00	36	18	*prod stopped
04:00 – 05:00	36	28	-8
05:00 – 06:00	36	8	*prod stopped
Total	288	210	-78

Remarks: *No colour change & no thickness change
*Inconsistent shade variation:- Separated light shade to another pallet 20 boxes (101-120)
*Speed: 35Hz *Prod stopped: Pulling chain at punching press was loose-It was attended to

Checked By QAI: SEFFO Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 16/09/2026 Shift: A

Color: CL18 Thickness: 2.00mm Batch: 39825

Time	Thickness Range: 1.87–2.13 Min (mm)	Thickness Range: 1.87–2.13 Max (mm)	Squareness	Edges	Color	Surface
06:25	1.94	1.98	0.00mm	Complies	NO	Complies
06:50	1.90	1.96	0.00 mm	Complies	NO	Complies
07:15	1.94	1.97	0.08 mm	Complies	NO	Complies
07:40	1.94	1.97	0.10 mm	Complies	NO	Complies
08:05	1.94	1.98	0.00 mm	Complies	NO	Complies
08:30	1.92	1.97	0.08mm	Complies	NO	Complies
08:55	1.90	1.97	0.08 mm	Complies	NO	Complies
09:20	1.94	1.97	0.00 mm	Complies	NO	Complies
09:45	1.92	1.98	0.05 mm	Complies	NO	Complies
10:10	1.94	1.97	0.00 mm	Complies	NO	Complies
10:35	1.92	1.97	0.08 mm	Complies	NO	Complies
11:00	1.94	1.98	0.02 mm	Complies	NO	Complies
11:25	CHANGING KNIVES, MARBLING 2.00				9212	
11:50	↓		↓	↓	↓	↓
12:15						
12:40	↓		↓	↓	↓	↓
13:05	KK 12	2.50	39845			
13:30	2.44	2.47	0.00mm	Complies	NO	Complies
13:55	2.44	2.49	0.08mm	Complies	NO	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 – 07:00	36	26	−10
07:00 – 08:00	36	32	−6
08:00 – 09:00	36	30	−6
09:00 – 10:00	36	30	−6
10:00 – 11:00	36	25	−11
11:00 – 12:00	MARBLING 2.00 9212 CHANG KNIVES		Colour Change
12:00 – 13:00	↓	↓	↓
13:00 – 14:00	36	28	−8
Total	220	169	−51

Remarks: * Colour change
* Thickness change

Checked By QAI: BETTY Supervisor: MAICO

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 15/09/2026 Shift: C

Color: KK15 Thickness: 2.50mm Batch: 39835

Time	Thickness Range: 2.37–2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.43	2.46	0.10mm	Complies	No	Complies
22:50	2.45	2.50	0.13mm	Complies	No	Complies
23:15	2.42	2.45	0.108mm	Complies	No	Complies
23:40	2.40	2.45	0.10mm	Complies	No	complies
00:05	2.43	2.47	0.13mm	Complies	No	Complies
00:30	2.45	2.50	0.12mm	Complies	No	Complies
00:55	2.43	2.49	0.10mm	Complies	No	Complies
01:20	2.40	2.45	0.108mm	Complies	No	Complies
01:45	2.45	2.55	0.10mm	Complies	No	Complies
02:10	2.46	2.47	0.106mm	Complies	No	Complies
02:35	2.43	2.49	0.10mm	Complies	No	Complies
03:00	2.45	2.55	0.106mm	Complies	No	Complies
03:25	2.44	2.46	0.102mm	Complies	No	Complies
03:50	2.41	2.47	0.06mm	Complies	No	Complies
04:15	2.43	2.46	0.10mm	Complies	No	Complies
04:40	CL18	2.100	39825			
05:05	1.94	1.96	0.10mm	Complies	No	Complies
05:30	1.93	1.95	0.06mm	Complies	No	Complies
05:55	1.92	1.95	0.08mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 – 23:00	36	31	−5
23:00 – 00:00	36	27	−9
00:00 – 01:00	36	29	−7
01:00 – 02:00	36	28	−8
02:00 – 03:00	36	28	−8
03:00 – 04:00	36	28	−8
04:00 – 05:00	36	10 2/12	Change colour
05:00 – 06:00	36	34	−2
Total	288	227	−61

Remarks: * Colour change
* Thickness change
* Speed: 2.50 (33 H²) 2.00 (40 H²
* Tile 2 machine direction (Failed dimensional stability with a minimum of 298.66 (KK15)

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 15/09/2026 Shift: B

Color: CC15 Thickness: 2.00mm Batch: 39805

	Thickness Range: 1.87 - 2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
14:25	1.94	1.97	0.05mm	complies	NO	complies	14:00 15:00	36	16/3	colour + thickness change
14:50	KK15	2.50	39835				15:00 16:00	36	24	-12
15:15	2.44	2.46	0.02mm	complies	NO	complies				
15:40	2.42	2.48	0.10mm	complies	NO	complies	17:00	36	26	-10
16:05	2.41	2.47	0.00mm	complies	NO	complies				
16:30	2.43	2.49	0.05mm	complies	NO	complies	17:00 18:00	36	26	-10
16:55	2.44	2.47	0.02mm	complies	NO	complies				
17:20	2.40	2.48	0.08mm	complies	NO	complies	18:00 19:00	36	24	-12
17:45	2.42	2.46	0.10mm	complies	NO	complies				
18:10	2.40	2.49	0.00mm	complies	NO	complies	19:00 20:00	36	30	-6
18:35	2.43	2.47	0.05mm	complies	No	complies				
19:00	2.44	2.47	0.02mm	complies	NO	complies	20:00 21:00	36	32	-4
19:25	241	2.48	0.00mm	complies	NO	complies				
19:50	2.40	2.48	0.10mm	complies	NO	complies	21:00 22:00	36	4	production stopped
20:15	2.42	2.46	0.08mm	complies	NO	complies				
20:40	2.45	2.49	0.05mm	complies	NO	complies				
21:05	241	2.47	0.02mm	complies	NO	complies				
21:30	PRODUCTION	STOPPED —	breakdown at		punching	press				
21:55	RESTART						Total	288	185	103

Remarks: * NO colour change
* Thickness change

Checked By QAI: KARABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 15/09/2026 Shift: A

Color: CL12 Thickness: 2.50mm Batch: 39795

Time	Thickness Range: 2.37–2.63 Min (mm)	Thickness Range: 2.37–2.63 Max (mm)	Squareness	Edges	Color	Surface
06:25						
06:30	RESTART →				RESTART →	
07:15	2.43	2.46	0.08mm	Complies	No	Complies
07:40	2.41	2.45	0.10mm	Complies	No	Complies
08:05	CL15 2:00 39805 →					
08:30	1.94	1.96	0.10mm	Complies	No	Complies
08:55	1.93	1.95	0.06mm	Complies	No	Complies
09:20	1.90	1.95	0.09mm	Complies	slight shade variation	Complies
09:45	1.95	1.99	0.10mm	Complies	No	Complies
10:10	1.94	1.96	0.06mm	Complies	No	Complies
10:35	1.93	1.95	0.00mm	Complies	No	Complies
11:00	1.94	1.99	0.10mm	Complies	No	Complies
11:25	1.90	1.97	0.08mm	Complies	No	Complies
11:50	1.92	1.96	0.06mm	Complies	No	Complies
12:15	1.93	1.95	0.10mm	Complies	No	Complies
12:40	1.94	1.96	0.06mm	Complies	No	Complies
13:05	1.94	1.98	0.10 mm	Complies	No	Complies
13:30	1.93	1.97	0.05 mm	Complies	No	Complies
13:55	1.94	1.97	0.00 mm	Complies	No	Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
07:00 07:45	36	19	Changing colour
08:00 09:00	36	24	-12
09:00 10:00	36	28	-8
10:00 11:00	36	28	-8
11:00 12:00	36	20	-16
12:00 13:00	36	24	-12
13:00 14:00	36	28	-8
-	-	-	-
Total	270	171	-99

Remarks: * Colour change
* Thickness change
& Several line cuts

Checked By QAI: SENTO/BETTY

Supervisor: MALLO

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 14/09/2026 Shift: C

Color: CL12 Thickness: 2.50mm Batch: 39795

Time	Thickness Range: 2.37–2.63 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	2.46	2.45	0.10mm	Complies	NO	Complies
22:50	241	2.46	0.06mm	Complies	NO	Complies
23:15	2.43	249	0.02mm	Complies	NO	Complies
23:40	2.43	2.48	0.06mm	Complies	NO	Complies
00:05	241	2.46	0.10mm	Complies	NO	Complies
00:30	2.43	2.49	0.08mm	Complies	NO	Complies
00:55	2.49	2.47	0.10mm	Complies	NO	Complies
01:20	2.43	2.46	0.06mm	Complies	NO	Complies
01:45	2.45	2.50	0.10mm	Complies	NO	Complies
02:10	2.43	2.46	0.08mm	Complies	NO	Complies
02:35	PROD – STOPPED – Boiler pressure was down					
03:00						
03:25						
03:50						
04:15						
04:40						
05:05						
05:30						
05:55						

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
22:00 – 23:00	36	25	-11
23:00 – 00:00	36	22	-14
00:00 – 01:00	36	27	-9
01:00 – 02:00	36	23	-13
02:00 – 03:00	36	11	-25
Total	288 180	108	180 -72

Remarks: * No colour change 288 – 108 LOST 180 BOXES DUE TO BOILER BREAKDOWN
* No thickness change
* Material falling at mixing mill causing several line cuts

Checked By QAI: SEMTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 14/09/2026 Shift: B

Color: Q46 Thickness: 2.00mm Batch: 39895

	Thickness Range: 1.87 – 2.13						Number of Boxes Produced Per Hour			
Time	Min (mm)	Max (mm)	Squareness	Edges	Color	Surface	Time	Target	Actual	Difference
14:25	1.94	1.98	0.10mm	complies	NO	complies	14:00 15:00	36	12	Line Adj -24
14:50	1.92	1.97	0.05mm	complies	NO	complies	15:00 16:00	36	10	Colour Thickness change
15:15	1.92	1.97	0.02mm	complies	NO	complies				
15:40	1.91	1.96	0.05mm	complies	NO	complies	16:00 17:00	36	24	-12
16:05	CL12	2.50	39795							
16:30	2.42	2.48	0.08mm	complies	NO	complies	17:00 18:00	36	22	-14
16:55	2.44	2.46	0.00mm	complies	NO	complies				
17:20	2.41	2.47	0.02mm	complies	NO	complies	18:00 19:00	36	22	-14
17:45	2.43	2.47	0.05mm	complies	NO	complies				
18:10	2.44	2.49	0.10mm	complies	NO	complies	19:00 20:00	36	24	-12
18:35	2.41	2.48	0.02mm	complies	NO	complies				
19:00	2.42	2.47	0.05mm	complies	NO	complies	20:00 21:00	36	24	-10
19:25	2.40	2.48	0.10mm	complies	NO	complies				
19:50	2.44	2.46	0.00mm	complies	NO	complies	21:00 22:00	36	-25	-11
20:15	2.41	2.49	0.08mm	complies	NO	complies				
20:40	2.42	2.47	0.10mm	complies	NO	complies				
21:05	2.41	2.47	0.02mm	complies	NO	complies				
21:30	2.44	2.48	0.00mm	complies	NO	complies	Total	288	163	-125
21:55	2.43	2.47	0.05mm	complies	NO	complies				

Remarks: * Colour change
* Thickness change
* Speed 2.00mm : 39 Hz 2.50mm : 33 Hz

Checked By QAI: KARABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 14/09/2026 Shift: A

Color: 946 Thickness: 2.00mm Batch: 39815

Time	Thickness Range: 1.87-2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
12:40	1.94	1.97	0.00 mm	Complies	No	Complies
13:05	1.94	1.98	0.00mm	Complies	No	Complies
13:30	1.92	1.97	0.10mm	Complies	No	Complies
13:55	1.94	1.97	0.08mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
12:00 13:00	36	8	1h 15 mins
13:00 14:00	36	16	Nine cuts
-	-	-	-
Total	43	24	-19

Remarks: *No colour change
*No thickness change

Checked By QAI: BETTY Supervisor: MAILO

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 11/09/2026 Shift: C

Color: 9277 Thickness: 1·30mm Batch: 39785

Time	Thickness Range: 1·17 – 1·43 Min (mm)	Thickness Range: 1·17 – 1·43 Max (mm)	Squareness	Edges	Color	Surface
22:25			0·10mm	Complies		Complies
22:50			0·08mm	Complies		Complies
23:15			0·02mm	Complies		Complies
23:40			0·00mm	Complies		Complies
00:05			0·05mm	Complies		Complies
00:30			0·10mm	Complies		Complies
00:55			0·02mm	Complies		Complies
01:20			0·08mm	Complies		Complies
01:45			0·00mm	Complies		Complies
02:10			0·05mm	Complies		Complies
02:35	CHANGING KNIVES / MARBLING				9254	
03:00						
03:25						
03:50						
04:15						
04:40	MARBLING		9101 – 200			
05:05						
05:30						
05:55						

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
22:00 – 23:00	48	40	−8
23:00 – 00:00	48	25	Circuits −23
00:00 – 01:00	48	42	−6
01:00 – 02:00	48	32	−16
02:00 – 03:00	~~48~~		
Total	192	139	−53

Remarks: * Colour change
* Thickness change
* Several line cuts due to material falling from mixing mill

Checked By QAI: KARABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 10/09/2026 Shift: B

Color: Q72 Thickness: 1.30mm Batch: 39305

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
14:25			0.00 mm	Complies		Complies
14:50			0.10 mm	Complies		Complies
15:15			0.08 mm	Complies		Complies
15:40			0.05 mm	Complies		Complies
16:05			0.02 mm	Complies		Complies
16:30			0.00 mm	Complies		Complies
16:55	Q77	1.30	39785			
17:20			0.00 mm	Complies		Complies
17:45			0.08 mm	Complies		Complies
18:10			0.05 mm	Complies		Complies
18:35			0.10 mm	Complies		Complies
19:00			0.08 mm	Complies		Complies
19:25			0.05 mm	Complies		Complies
19:50			0.10 mm	Complies		Complies
20:15			0.05 mm	Complies		Complies
20:40			0.08 mm	Complies		Complies
21:05			0.10 mm	Complies		Complies
21:30			0.05 mm	Complies		Complies
21:55			0.00 mm	Complies		Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
14:00 – 15:00	48	44	−4
15:00 – 16:00	48	48	−
16:00 – 17:00	48	17/12	Colour Change
17:00 – 18:00	48	38	Wire Cut
18:00 – 19:00	48	38	−10
19:00 – 20:00	48	36	Wire Cut −12
20:00 – 21:00	48	30	−18
21:00 – 22:00	48	33	−15
Total	358	296	−62

Remarks: *Colour change
*No thickness change
*Material fall from mixing mill causing several line cuts.

Checked By QAI: BETTY

Supervisor: MAICO

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 11/09/2026 Shift: A

Color: 954 Thickness: 10mm Batch: 357775

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25			0.10mm	Complies		Complies
06:50			0.10mm	Complies		Complies
07:15			0.108mm	Complies		Complies
07:40			0.13mm	Complies		Complies
08:05			0.10mm	complies		Complies
08:30			0.15mm	Rough		Complies
08:55			0.13mm	Complies		Complies
09:20			0.10mm	Complies		Complies
09:45			0.108mm	Complies		Complies
10:10			0.04mm	complies		complies
10:35			0.07mm	complies		Complies
11:00			0.10mm	Complies		Rough
11:25			0.06mm	Complies		
11:50			0.108mm	Complies		Complies
12:15			0.10mm	Complies		Complies
12:40			0.13mm	Complies		Complies
13:05			0.15mm	Complies		Complies
13:30			0.10mm	Complies		Complies
13:55	1.272	1.130	89305			

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
07:00	48	36	-12
08:00	48	45	-3
09:00	48	44	-4
10:00	48	45	-3
11:00	48	40	-8
12:00	48	36	-12
13:00	48	43	-5
14:00	48	29	-19
Total	384	318	-66

Remarks: * Colour change
* No thickness change
* Speed 1 50.00 Hz

Checked By QAI: SETHO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 10/09/2026

Shift: C

Color: Q46

Thickness: 1.30mm

Batch: 39755

Time	Thickness Range: 1.17 - 1.43 Min (mm)	Thickness Range: 1.17 - 1.43 Max (mm)	Squareness	Edges	Color	Surface
22:25	BLACK		0.10mm	Complies	BLACK	Complies
22:50			0.05mm	Complies		Complies
23:15			0.02mm	Complies		Complies
23:40			0.00mm	Complies		Complies
00:05			0.08mm	Complies		Complies
00:30			0.05mm	Complies		Complies
00:55	1.83	1.30	39765			
01:20			0.10mm	Complies		Complies
01:45	BLACK		0.08mm	Complies		Complies
02:10			0.05mm	Complies		Complies
02:35			0.10mm	Complies	BLACK	Complies
03:00			0.02mm	Complies		Complies
03:25			0.00mm	Complies		Complies
03:50			0.10mm	Complies		Complies
04:15			0.05mm	Complies		Complies
04:40			0.02mm	Complies		Complies
05:05			0.10mm	Complies		Complies
05:30			0.00mm	Complies		Complies
05:55	1.54	1.30	39775			

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	48	40	-8
23:00 00:00	48	40	-8
00:00 01:00	48	9/4	Colour change
01:00 02:00	48	44	-4
02:00 03:00	48	30	-18
03:00 04:00	48	24	Line cut -24
04:00 05:00	48	27	-21
05:00 06:00	48	10/5	Colour change
Total	384	233	-151

Remarks: * Colour change
* no thickness change
* several line cuts due to material falling from mixing mill.

Checked By QAI: KARABO

Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 10/09/2026

Shift: B

Color: 870

Thickness: 1·30mm

Batch: 39725

Time	Thickness Range: 1.17 – 1.43 Min (mm)	Thickness Range: 1.17 – 1.43 Max (mm)	Squareness	Edges	Color	Surface
14:25	D	Y	0.00 mm	Complies	D Y	Complies
14:50			0.05 mm	Complies		Complies
15:15	Q49	1.30	39735			
15:40			0.10 mm	Complies		Complies
16:05			0.05 mm	Complies		Complies
16:30			0.10 mm	Complies		Complies
16:55			0.08 mm	Complies		Complies
17:20			0.00 mm	Complies		Complies
17:45			0.00 mm	Complies		Complies
18:10			0.05 mm	Complies		Complies
18:35			0.10 mm	Complies		Complies
19:00	Q46	1.30	39755			
19:25	B		0.08 mm	Complies	B	Complies
19:50			0.10 mm	Complies		Complies
20:15			0.05 mm	Complies		Complies
20:40			0.00 mm	Complies		Complies
21:05			0.05 mm	Complies	L K	Complies
21:30			0.02 mm	Complies		Complies
21:55			0.10 mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 – 15:00	28	13	Colour change
15:00 – 16:00	28	26	-2
16:00 – 17:00	28	28	–
17:00 – 18:00	28	30	+2
18:00 – 19:00	28	14/16	Colour change DJ BULK
19:00 – 20:00	48	48	-8
20:00 – 21:00	48	42	-6
21:00 – 22:00	48	37	Line cut
Total	279	246	-33

Remarks: * Colour change
* No thickness change

Checked By QAI: BETTY

Supervisor: MAICO

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 09/09/2026 Shift: A

Color: 970 Thickness: 1.30mm Batch: 39725

Time	Thickness Range: 1.17–1.43 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
06:25			0.10mm	Complies		Complies
06:50			0.08mm	Complies		Complies
07:15			0.06mm	Complies		Complies
07:40			0.13mm	Complies		Complies
08:05			0.10mm	Complies		Complies
08:30			0.08mm	Complies		Complies
08:55			0.10mm	Complies		Complies
09:20			0.08mm	Complies		Complies
09:45			0.10mm	Complies		Complies
10:10			0.10mm	Complies		Complies
10:35			0.07mm	Complies		Complies
11:00			0.06mm	Complies		Complies
11:25	970	1.30	39725			
11:50			0.10mm	Complies		Complies
12:15			0.06mm	Complies		Complies
12:40			0.10mm	Complies		Complies
13:05			0.08mm	Complies		Complies
13:30			0.13mm	Complies		Complies
13:55			0.10mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00 07:00	48	38	-10
07:00 08:00	48	36	-12
08:00 09:00	48	38	-10
09:00 10:00	48	38	-10
10:00 11:00	48	48	—
11:00 12:00	28	22	-6
12:00 13:00	28	26	-2
13:00 14:00	28	26	-2
Total	324	272	-52

Remarks: * No Colour Change
* No Thickness Change
* Speed 1.50/100 H2

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 09/09/2026 Shift: C

Color: Q41 Thickness: 1.30 mm Batch: 39715

Time	Thickness Range: 1.17 - 1.43 Min (mm)	Thickness Range: 1.17 - 1.43 Max (mm)	Squareness	Edges	Color	Surface
22:25			0.10mm	complies		complies
22:50	BULK		0.05mm	complies	BULK	complies
23:15			0.02mm	complies		complies
23:40			0.00mm	complies		complies
00:05	Q 70	1.30	39725			
00:30			0.08mm	complies		complies
00:55			0.05mm	complies		complies
01:20			0.02mm	complies		complies
01:45			0.00mm	complies		complies
02:10			0.10mm	complies		complies
02:35			0.05mm	complies		complies
03:00			0.08mm	complies		complies
03:25			0.00mm	complies		complies
03:50			0.10 mm	complies		complies
04:15			0.02mm	complies		complies
04:40			0.00 mm	complies		complies
05:05			0.10 mm	complies		complies
05:30			0.08 mm	complies		complies
05:55			0.02mm	complies		

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	48	41	-7
23:00 00:00	48	35	colour change
00:00 01:00	48	40	-8
01:00 02:00	48	36	-12
02:00 03:00	48	32	-16
03:00 04:00	48	32	-16
04:00 05:00	48	30	-18
05:00 06:00	48	32	-16
Total	384	278	-106

Remarks: * Colour change
* No thickness change
* several line cuts due to material fall from mixing mill

Checked By QAI: KARABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 09/09/2026 Shift: B

Color: Q41 Thickness: 1.30mm Batch: 39715

Time	Thickness Range: 1.17 – 1.43 Min (mm)	Thickness Range: 1.17 – 1.43 Max (mm)	Squareness	Edges	Color	Surface
14:25	B		0.08mm	Complies	B	Complies
14:50			0.05mm	Complies		Complies
15:15			0.00mm	Complies		Complies
15:40			0.05 mm	Complies		Complies
16:05			0.07 mm	Complies		Complies
16:30			0.03 mm	Complies		Complies
16:55			0.05 mm	Complies		Complies
17:20	G		0.08 mm	Complies	G	Complies
17:45			0.10 mm	Complies		Complies
18:10			0.10 mm	Complies		Complies
18:35			0.05 mm	Complies		Complies
19:00			0.08 mm	Complies		Complies
19:25	L		0.03 mm	Complies	K	Complies
19:50			0.05 mm	Complies		Complies
20:15			0.05 mm	Complies		Complies
20:40			0.08 mm	Complies		Complies
21:05			0.10mm	Complies		Complies
21:30		K	0.05	Complies	K	Complies
21:55			0.05	Complies		Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
15:00	48	45	-3
16:00	48	44	-4
17:00	48	41	-7
18:00	48	42	-6
19:00	48	41	-7
20:00	48	42	-6
21:00	48	44	-4
22:00	48	44	-4
Total	384	343	-41

Remarks: No thickness and Colour change

Speed 50.00Hz

Checked By QAI: ISHIDI Supervisor: Mailo

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 09/09/2026 Shift: A

Color: Q38 Thickness: 130mm Batch: 39705

Time	Thickness Range: Min (mm)	Thickness Range: Max (mm)	Squareness	Edges	Color	Surface
06:25	BULK		0.10mm	Complies	BULK	Complies
06:50			0.06mm	Complies		Complies
07:15			0.08mm	Complies		Complies
07:40			0.06mm	Complies		Complies
08:05			0.10mm	Complies		Complies
08:30			0.09mm	Complies		Complies
08:55	Marbling	200	9101 / CHANGING	KNIVES		
09:20						
09:45						
10:10						
10:35	Q41	130	39715			
11:00	BULK		0.10mm	Complies	BULK	Complies
11:25			0.13mm	Complies		Complies
11:50			0.09mm	Complies		Complies
12:15			0.10mm	Complies		Complies
12:40			0.13mm	Complies		Complies
13:05			0.10mm	Complies		Complies
13:30			0.10mm	Complies		Complies
13:55			0.06mm	Complies		Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
06:00			
07:00	48	45	-3
07:00			
08:00	48	42	-6
08:00			Changing colour/Knives
09:00	48	32	
10:30			Changing colour
11:00	48	40	
11:00			
12:00	48	45	-3
12:00			
13:00	48	42	-6
13:00			
14:00	48	45	-3
Total	336	261	-75

Remarks: & Colour Change
& Thickness Change
& Speed, 50 HZ

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 08/09/2026 Shift: C

Color: Q05 Thickness: 1.30 mm Batch: 39695

Time	Thickness Range: 1.17 – 1.43 Min (mm)	Thickness Range: 1.17 – 1.43 Max (mm)	Squareness	Edges	Color	Surface
22:25			0.10 mm	Complies		Complies
22:50			0.02 mm	Complies		Complies
23:15			0.05 mm	Complies		Complies
23:40			0.08 mm	Complies		Complies
00:05			0.00 mm	Complies		Complies
00:30			0.05 mm	Complies		Complies
00:55			0.10 mm	Complies		Complies
01:20			0.08 mm	Complies		Complies
01:45	PRODUCTION		STOPPED			
02:10			↓		↓	→
02:35	RESTART					
03:00	BULK		0.02 mm	Complies	BULK	Complies
03:25	Q 38	1.30	39705			→
03:50			0.10 mm	Complies		Complies
04:15			0.05 mm	Complies		Complies
04:40			0.02 mm	Complies		Complies
05:05			0.08 mm	Complies		Complies
05:30			0.05 mm	Complies		Complies
05:55			0.10 mm	Complies		Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
22:00 – 23:00	48	36	-12
23:00 – 00:00	48	38	-10
00:00 – 01:00	48	26	-22
01:00 – 02:00	48	4	prod – stopped
02:00 – 03:00	48	22	colour change
03:00 – 04:00	48	40	-8
04:00 – 05:00	48	40	-8
05:00 – 06:00	48	37	-11
Total	384	243	-141

Remarks: * colour change
* No thickness change
* Production stopped due to conveyor chain derailed

Checked By QAI: KARABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 03/09/2026 Shift: B

Color: Q10 Thickness: 1.30mm Batch: 39685

Time	Thickness Range: 1.17–1.43 Min (mm)	Thickness Range: 1.17–1.43 Max (mm)	Squareness	Edges	Color	Surface
14:25	BULK		0.00 mm	Complies	BULK	Complies
14:50			0.08mm	Complies		Complies
15:15	Q05	1.30	39695			
15:40			0.05 mm	Complies		Complies
16:05			0.10 mm	Complies		Complies
16:30			0.08 mm	Complies		Complies
16:55			0.02 mm	Complies		Complies
17:20			0.10 mm	Complies		Complies
17:45			0.05 mm	Complies		Complies
18:10			0.00 mm	Complies		Complies
18:35			0.10 mm	Complies		Complies
19:00			0.08 mm	Complies		Complies
19:25			0.05 mm	Complies		Complies
19:50			0.00 mm	Complies		Complies
20:15			0.02 mm	Complies		Complies
20:40			0.00 mm	Complies		Complies
21:05			0.10 mm	Complies		Complies
21:30			0.05 mm	Complies		Complies
21:55			0.02 mm	Complies		Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
14:00 15:00	48	41	-7
15:00 16:00	48	48	–
16:00 17:00	48	48	–
17:00 18:00	48	48	-4
18:00 19:00	48	44	-4
19:00 20:00	48	40	-8
20:00 21:00	48	38	Line Cut
21:00 22:00	48	38	Line Cut
Total	384	341	-43

Remarks: *Colour change
*No thickness change

Checked By QAI: BETTY Supervisor: MAICO

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 08/09/2026 Shift: A

Color: 910 Thickness: 1.30mm Batch: 39885

Time	Thickness Range: 1.17–1.43 Min (mm)	Thickness Range: 1.17–1.43 Max (mm)	Squareness	Edges	Color	Surface
06:25			0.10mm	Complies		Complies
06:50			0.08mm	Complies		Complies
07:15			0.06mm	Complies		Complies
07:40			0.13mm	Complies		Complies
08:05			0.08mm	Complies		Complies
08:30			0.10mm	Complies		Complies
08:55			0.06mm	Complies		Complies
09:20			0.02mm	Complies		Complies
09:45			0.10mm	Complies		Complies
10:10			0.13mm	Complies		Complies
10:35			0.10mm	Complies		Complies
11:00			0.06mm	Complies		Complies
11:25			0.10mm	Complies		Complies
11:50			0.13mm	Complies		Complies
12:15			0.10mm	Complies		Complies
12:40			0.10mm	Complies		Complies
13:05			0.06mm	Complies		Complies
13:30			0.08mm	Complies		Complies
13:55			0.07mm	Complies		Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
06:00 07:00	48	43	-5
07:00 08:00	48	45	-3
08:00 09:00	48	43	-5
09:00 10:00	48	44	-4
10:00 11:00	48	47	-1
11:00 12:00	48	43	-5
12:00 13:00	48	44	-4
13:00 14:00	48	45	-3
Total	384	354	-30

Remarks: * No colour change
** No thickness change
* Speed: 50 ft²

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 07/09/2026 Shift: C

Color: Q10 Thickness: 2.00mm Batch: 39685

Time	Thickness Range: 1.87-2.13 Min (mm)	Thickness Range: 1.87-2.13 Max (mm)	Squareness	Edges	Color	Surface
22:25	1.92	1.97	0.10 mm	Complies	NO	complies
22:50	1.94	1.99	0.05 mm	complies	Slight shade variation	complies
23:15	1.91	1.98	0.02 mm	complies	NO	complies
23:40	1.92	1.96	0.00 mm	complies	NO	complies
00:05	1.92	1.97	0.02 mm	complies	NO	complies
00:30	1.93	1.97	0.05 mm	complies	NO	complies
00:55	1.94	1.98	0.08 mm	complies	NO	complies
01:20	1.91	1.99	0.10 mm	complies	NO	complies
01:45	1.92	1.96	0.00 mm	complies	NO	complies
02:10	1.90	1.97	0.02 mm	complies	NO	complies
02:35	1.94	1.98	0.05 mm	complies	NO	complies
03:00	Q10	1.30	39685			
03:25			0.02 mm	complies		Complies
03:50			0.05 mm	complies		complies
04:15			0.10 mm	complies		complies
04:40			0.08 mm	complies		complies
05:05			0.00 mm	complies		complies
05:30			0.10 mm	complies		complies
05:55			0.02 mm	complies		complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	36	25	-11
23:00 00:00	36	28	-8
00:00 01:00	36	36	-
01:00 02:00	36	32	-4
02:00 03:00	36	22/12	thickness change
03:00 04:00	48	40	-8
04:00 05:00	48	40	-8
05:00 06:00	48	40	-8
Total	324	275	-49

Remarks: * No colour change
* Thickness change

Checked By QAI: KARABO Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 07/09/2026

Shift: B

Color: Q10

Thickness: 2.00mm

Batch: 39685

Time	Thickness Range: 1.87 - 2.13 Min (mm)	Thickness Range: 1.87 - 2.13 Max (mm)	Squareness	Edges	Color	Surface
18.45	1.94	1.99	0.00 mm	Complies	No	Complies
19:10	1.94	1.96	0.10 mm	Complies	No	Complies
19:35	1.93	1.98	0.08 mm	Complies	No	Complies
20:00	1.94	1.97	0.05mm	Complies	No	Complies
20:35	1.92	1.97	0.00 mm	Complies	No	Complies
20:50	1.90	1.95	0.00mm	Complies	No	Complies
21:15	1.94	1.97	0.02 mm	Complies	No	Complies
21:40	1.92	1.97	0.08 mm	Complies	No	Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
18:00 19:00	36	4	in 15 mins
19:00 20:00	36	24	-12
20:00 21:00	36	30	-6
21:00 22:00	36	33	-3
Total	113	91	-22

Remarks: *No colour change
*No thickness change

Checked By QAI: BETTY

Supervisor: MAILO

Kalahari Floor Tiles (Pty) Ltd

Quality Control Checksheet (Online Control)

Date: 07/09/2026

Shift: A

Color: —

Thickness:

Batch:

Time	Thickness Range: Min (mm)	Thickness Range: Max (mm)	Squareness	Edges	Color	Surface
06:00						
14:00						

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
Total			

Remarks: * No production.
* Maintenance going on

Checked By QAI: SEHTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 04/09/2026

Shift: C

Color: Q49

Thickness: 2.00mm

Batch: 39665

Time	Thickness Range: 1.87-2.13 Min (mm)	Max (mm)	Squareness	Edges	Color	Surface
22:25	1.94	1.97	0.00 mm	Complies	NO	Complies
22:50	1.93	1.97	0.08 mm	Complies	NO	Complies
23:15	KK 05	2.50	39675			
23:40	2.44	2.48	0.07 mm	Complies	NO	Complies
00:05	2.41	2.47	0.00 mm	Complies	NO	Complies
00:30	2.40	2.48	0.00 mm	Complies	NO	Complies
00:55	2.44	2.47	0.02 mm	Complies	NO	Complies
01:20	2.41	2.46	0.08 mm	Complies	NO	Complies
01:45	Q10	2.00	39685			
02:10	1.92	1.99	0.02 mm	Complies	NO	Complies
02:35	1.90	1.97	0.10 mm	Complies	NO	Complies
03:00	1.94	1.97	0.08 mm	Complies	NO	Complies
03:25	1.94	1.98	0.05 mm	Complies	NO	Complies
03:50	1.94	1.96	0.00 mm	Complies	NO	Complies
04:15	1.93	1.97	0.02 mm	Complies	NO	Complies
04:40	1.94	1.97	0.05 mm	Complies	NO	Complies
05:05	1.93	1.97	0.10 mm	Complies	NO	Complies
05:30	1.94	1.97	0.08 mm	Complies	NO	Complies
05:55	PRODUCTION		STOPPED			

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
22:00 23:00	36	16	Line cut
23:00 00:00	36	13	Colour + thickness change
00:00 01:00	36	24	-12
01:00 02:00	36	13	Colour change
02:00 03:00	36	28	-8
03:00 04:00	36	32	-4
04:00 05:00	36	28	-8
05:00 06:00	36	29	-7
Total	288	183	-105

Remarks: *Colour change
*Thickness change
*Several line cuts due to material fall from mixing mill.

Checked By QAI: BETTY

Supervisor: MAICO

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 04/09/2026 Shift: B

Color: 204 Thickness: 2.00mm Batch: 5205

Time	Thickness Range: 1.87–2.13 Min (mm)	Thickness Range: 1.87–2.13 Max (mm)	Squareness	Edges	Color	Surface
14:25	1.96	1.99	0.00mm	Complies	No	Complies
14:50	1.95	1.97	0.00mm	Complies	No	Complies
15:15	1.94	1.98	0.03mm	Complies	No	Complies
15:40	1.97	2.00	0.00mm	Complies	No	Complies
16:05	193	198	0.08mm	Complies	No	Complies
16:30	192	195	0.10mm	Complies	No	Complies
16:55	194	199	0.10mm	Complies	No	Complies
17:20	EX49	2.00	39665			→
17:45	194	198	0.10mm	Complies	No	Complies
18:10	193	196	0.10mm	Complies	No	Complies
18:35	192	195	0.08mm	Complies	No	Complies
19:00	193	196	0.06mm	Complies	No	Complies
19:25	193	198	0.10mm	Complies	No	Complies
19:50	PROD STOPPED & RESTARTED: POWER CUT					
20:15	194	199	0.10mm	Complies	No	Complies
20:40	195	197	0.08mm	Complies	No	Complies
21:05	193	196	0.06mm	Complies	No	Complies
21:30	190	195	0.07mm	Complies	No	Complies
21:55	194	199	0.10mm	Complies	No	Complies

Number of Boxes Produced Per Hour			
Time	Target	Actual	Difference
14:00 15:00	36	28	-8
15:00 16:00	36	32	-4
16:00 17:00	36	32	-4
17:00 18:00	36	31	-5
18:00 19:00	36	33	-3
19:00 20:00	36	25	* paper cut
20:00 21:00	36	31	-5
21:00 22:00	36	25	-11
Total	288	237	-51

Remarks: * No colour change
* No thickness change
* Speed:

Checked By QAI: SENTO

Supervisor: DANIEL

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 04/09/2026 Shift: A

Color: 205 Thickness: 2.00mm Batch: 5195

Time	Thickness Range: 1.87 - 2.13 Min (mm)	Thickness Range: 1.87 - 2.13 Max (mm)	Squareness	Edges	Color	Surface
06:25	1.92	1.97	0.00mm	Complies	No	Complies
06:50	1.94	1.98	0.05mm	complies	No	complies
07:15	1.91	1.97	0.10mm	complies	No	complies
07:40	1.92	1.99	002mm	Complies	No	complies
08:05	193	1.96	0.08mm	Complies	No	complies
08:30	1.90	1.98	0.10mm	complies	No	complies
08:55	204	2.00	5205			
09:20	192	1.97	0.05mm	Complies	No	complies
09:45	190	1.96	000mm	complies	No	Complies
10:10	194	1.98	0.10mm	complies	No	complies
10:35	193	1.99	002mm	complies	No	complies
11:00	192	1.97	005mm	complies	No	complies
11:25	1.94	1.98	002mm	complies	No	complies
11:50	PRODUCTION STOPPED					
12:15						
12:40						
13:05						
13:30						
13:55	RESTART					

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
06:00 07:00	36	28	-8
07:00 08:00	36	21	-15
08:00 09:00	36	10/8	colour change
09:00 10:00	36	32	-4
10:00 11:00	36	20	-16
11:00 12:00	36	20	-16
12:00 13:00	PRODUCTION STOPPED		
13:00 14:00	36	7	-29
Total	216	146	-70

Remarks: ~~No~~ colour change
~~No~~ thickness change

Checked By QAI: KAHABO

Supervisor: THEMBANI

Kalahari Floor Tiles (Pty) Ltd
Quality Control Checksheet (Online Control)

Date: 03/09/2026

Shift: C

Color: KK12

Thickness: 2.00mm

Batch: 39655

Time	Thickness Range: 1.87–2.13 Min (mm)	Thickness Range: 1.87–2.13 Max (mm)	Squareness	Edges	Color	Surface
22:25	1.90	1.98	0.00 mm	Complies	NO	Complies
22:50	1.94	1.97	0.08 mm	Complies	NO	Complies
23:15	1.94	1.97	0.10 mm	Complies	NO	Complies
23:40	1.92	1.95	0.02 mm	Complies	NO	Complies
00:05	1.94	1.97	0.10 mm	Complies	NO	Complies
00:30	1.94	1.96	0.08 mm	Complies	NO	Complies
00:55	1.92	1.97	0.00 mm	Complies	NO	Complies
01:20	1.91	1.98	0.08 mm	Complies	NO	Complies
01:45	205	2.00	5195			
02:10	1.90	1.97	0.05 mm	Complies	NO	Complies
02:35	1.94	1.99	0.08 mm	Complies	NO	Complies
03:00	1.94	1.97	0.00 mm	Complies	Slight Shade variation	Complies
03:25	1.92	1.95	0.10 mm	Complies	NO	Complies
03:50	1.91	1.97	0.08 mm	Complies	NO	Complies
04:15	1.94	1.97	0.05 mm	Complies	NO	Complies
04:40	1.94	1.96	0.00 mm	Complies	NO	Complies
05:05	1.93	1.97	0.10 mm	Complies	NO	Complies
05:30	1.90	1.97	0.05 mm	Complies	NO	Complies
05:55	1.94	1.98	0.02 mm	Complies	NO	Complies

Number of Boxes Produced Per Hour

Time	Target	Actual	Difference
22:00 – 23:00	36	32	−4
23:00 – 00:00	36	32	−4
00:00 – 01:00	36	30	−6
01:00 – 02:00	36	6/12	Colour change
02:00 – 03:00	36	36	−6
03:00 – 04:00	36	28	Line Cut
04:00 – 05:00	36	34	−2
05:00 – 06:00	36	30	−6
Total	288	234	−54

Remarks: *Colour change
*No thickness change

Checked By QAI: BETTY

Supervisor: MAICO