

Modeling scrap characteristics for Electric Arc Furnaces

"The research will focus on modelling how key scrap characteristics - such as size, shape, density, and material heterogeneity - interact with scrap handling and transport systems, discharging equipment such as vibratory feeders, and industrial loading strategies employed in scrap yards for feeding Electric Arc Furnaces (EAFs)." *Generated by LeapSpace*

The evidence supports a **multi-physics, operations-aware modelling agenda** for EAF scrap handling: scrap **size/shape/density/porosity/heterogeneity** affect melting, charge collapse, arc stability, and energy use, while **transport and loading strategy** affect how the charge arrives, layers, moves, and melts in practice [1] [2] [3] [4] [5] [6] [7].

What the literature says your model should include

Modelling target	Relevant evidence	Why it matters for your research
Scrap physical characteristics	Packing density, size, preheat, and stirring affect melting time in the heel of the furnace [1]; scrap porosity increases melting time [2] [8]; heterogeneous scrap quality materially changes electricity demand [5] [6]	These variables are not just descriptors; they are drivers of melt rate and energy consumption [1] [5]
Charge layering and furnace loading strategy	More layers in the first bucket improved melting by 12%, but dense material at the bottom reduced the benefit [9] [10]; charge movement and cave-ins disrupt power supply and require electrode adjustments [3]	Loading strategy should be modelled as a causal control variable , not a background assumption [3] [9]
Scrap transport / feeding systems	Continuous scrap transport affects melting in Consteel EAFs, where transport temperature and speed influence melting rate and furnace temperature [11]; vibratory feeding is used in logistics, and scrap size/appearance makes speed measurement difficult [4]	Scrap handling systems shape the timing, distribution, and consistency of furnace charge input [4] [11]
Discharging / melting equipment interaction	Coherent jet burners were modelled with scrap melting and re-solidification; burner power, scrap	Discharging and heating equipment need to be represented as coupled with the scrap state

	porosity, preheat temperature, and blockage all changed energy utilization [8] [12]	rather than independently [8]
Chemical heterogeneity and composition uncertainty	Scrap composition uncertainty can be estimated statistically, including Cu and Cr, and confidence intervals can be derived [13] [14]; imperfect compositional information raises costs, while perfect information reduced production costs by 8-10% [6]	Material heterogeneity is not only physical but also chemical , and it affects both prediction and decision quality [6] [13]

Bottom line

Your proposed focus aligns well with existing work, but the strongest modelling direction is **integrated rather than isolated**: the literature repeatedly shows that scrap characteristics, handling/transport behaviour, furnace loading pattern, and heating/melting hardware jointly determine melting performance, energy demand, and operational stability [3] [5] [7] [8] [9] [11]. In practice, that means the most defensible model would treat scrap as a **variable, uncertain feedstock entering a coupled process chain**, not as a fixed input [6] [13] [14].

Confidence level: **High** — multiple independent sources across reviews, CFD studies, process-control models, and industrial data consistently support the same coupling between scrap properties, handling/loading, and EAF performance [1] [5] [7] [9] [15].

References

1. Li, J., Provatas, N., Irons, G.A. (2008) Modeling of scrap melting in the heel of an EAF. *Iron and Steel Technology*. <https://www.scopus.com/pages/publications/50849117531>
2. Nath, D., Maji, S., Singh, A.K. (2025) Modeling of Arcing, Scrap Melting, and Temperature Evolution in the Refractory of a Lab-Scale Direct Current-Electric Arc Furnace. *Steel Research International*. <https://doi.org/10.1002/srin.202300696>
3. Guö, D., Irons, G.A. (2008) Modelling of steel scrap movement. *Applied Mathematical Modelling*. <https://doi.org/10.1016/j.apm.2007.06.037>
4. Xiao, X., Zhong, X., Ma, M., Wu, X. (2025) A Visual Based Algorithm for Measuring the Speed of Scrap Metal Vibration Feeding. *8th International Conference on Computer Science and Application Engineering, CSAE 2024*. <https://doi.org/10.1145/3704814.3704817>
5. Haupt, M., Vadenbo, C., Zeltner, C., Hellweg, S. (2017) Influence of Input-Scrap Quality on the Environmental Impact of Secondary Steel Production. *Journal of Industrial Ecology*. <https://doi.org/10.1111/jiec.12439>

6. Compañero, R.J., Feldmann, A., Samuelsson, P., (...), Gyllenram, R. (2023) Appraising the value of compositional information and its implications to scrap-based production of steel. *Mineral Economics*. <https://doi.org/10.1007/s13563-022-00361-z>
7. Cheng, J., Ang, Z., Zhang, P., (...), Chen, L. (2026) Research progress on multi-physics field coupling and optimization control technology in the electric arc furnace steelmaking process. *Progress in Natural Science: Materials International*.
<https://doi.org/10.1016/j.pnsc.2026.04.001>
8. Chen, Y., Luo, Q., Ryan, S., (...), Zhou, C.Q. (2022) Effect of coherent jet burner on scrap melting in electric arc furnace. *Applied Thermal Engineering*.
<https://doi.org/10.1016/j.applthermaleng.2022.118596>
9. Ugarte, O., Li, J., Haeberle, J., (...), Zhou, C.Q. (2024) CFD Modeling of HBI/scrap Melting in Industrial EAF and the Impact of Charge Layering on Melting Performance. *Materials*.
<https://doi.org/10.3390/ma17215139>
10. Ugarte, Orlando, Li, Jianghua, Haeberle, Jeff, (...), Zhou, Chenn Q. (2024) CFD Modeling of HBI/scrap Melting in Industrial EAF and the Impact of Charge Layering on Melting Performance. *Materials*. <https://doi.org/10.3390/ma17215139>
11. Zhang, H., Wei, G., Xu, A., (...), Zhu, R. (2024) Modelling and Simulation of the Scrap Melting in the Consteel EAF. *Minerals, Metals and Materials Series*. https://doi.org/10.1007/978-3-031-50304-7_52
12. Chen, Y., Luo, Q., Ryan, S., (...), Zhou, C.Q. (2022) Effect of coherent jet burner on scrap melting in electric arc furnace. *Applied Thermal Engineering*.
<https://doi.org/10.1016/j.applthermaleng.2022.118596>
13. Arzpeyma, N., Alam, M., Gyllenram, R., Jönsson, P.G. (2021) Model development to study uncertainties in electric arc furnace plants to improve their economic and environmental performance. *Metals*. <https://doi.org/10.3390/met11060892>
14. Sandberg, E., Lennox, B., Undvall, P. (2007) Scrap management by statistical evaluation of EAF process data. *Control Engineering Practice*.
<https://doi.org/10.1016/j.conengprac.2007.01.001>
15. Hay, T., Visuri, V.-V., Aula, M., Echterhof, T. (2021) A Review of Mathematical Process Models for the Electric Arc Furnace Process. *Steel Research International*.
<https://doi.org/10.1002/srin.202000395>