

Particle-based models in conveyor systems

"The theory of particle-based models (such as DEM), with a particular focus on conveyor systemsThe current state of the art in the literature and the knowledge gaps in the field of scrap modelling, with the aim of capturing the infeed of scrap into an Electric Arc Furnace (EAF)"
Generated by LeapSpace

Particle-based models, especially DEM, are already well established for conveyor-type handling of bulk solids, but the literature on scrap infeed to an EAF is still fragmented: conveyor and hopper transport are well covered, while scrap-specific modeling is dominated by melting/heat-transfer studies inside the furnace rather than by detailed charging, packing, and infeed dynamics. [1] [2] [3] [4] [5] [6] [7] [8] [9]

Where particle-based modeling stands

Area	State of the art	What it means for scrap infeed
DEM fundamentals	DEM tracks each particle individually in a Lagrangian framework and resolves contact forces, friction, damping, and shape effects; modern reviews emphasize calibrated contact models, non-spherical particles, and multiphysics extensions. [1] [3] [10] [11] [12] [13] [14] [15] [16]	Scrap infeed can, in principle, be represented as a particle system with geometry, contact, and collision effects captured explicitly. [1] [3] [10] [15]
Conveyor systems	DEM is widely used for belt conveyors, transfer chutes, feeders, vibratory conveyors, and scraper conveyors; studies report accurate prediction of flow, impact, wear, and transfer behavior when calibration is good. [2] [4] [17] [18] [19] [20] [21] [22] [23] [24] [25] [26] [27] [28] [29]	This is the closest mature modeling base for the <i>infeed</i> part of scrap handling, because scrap charging often behaves like irregular bulk transport through a feeder, chute, hopper, or conveyor. [22] [27] [29]
EAF scrap modeling	EAF literature is much richer in thermal/CFD models for melting, arc heating, burners, and collapse than in detailed granular charging models. [6] [7] [8] [9] [30] [31] [32] [33] [34] [35] [36] [37] [38] [39] [40] [41]	The charging stage remains undermodeled relative to melting, so the link between incoming scrap structure and downstream furnace behavior is not yet fully resolved. [6] [7] [9] [30]

What the scrap/EAF literature currently emphasizes

1) Melting and heat transfer are the dominant themes

Several studies model scrap melting in the heel, charge layering, porosity effects, burner performance, arc heat dissipation, and solid collapse mechanisms. [6] [7] [9] [30] [31] [32] [34] [36] [37] [38] [39] [41]

This shows the field has strong **thermophysical** coverage, but it is mostly focused on what happens *after* scrap is already in the furnace. [7] [9] [30] [34] [36]

2) Scrap characterization is treated more statistically than mechanically

Some work estimates scrap composition, impurity levels, and uncertainty from process data or state-space models. [42] [43] [44] [45]

That helps for **chemistry and mass balance**, but it does not describe the **mechanical infeed architecture**: fragmented geometry, packing, bridging, segregation, and motion during charging. [42] [43] [44] [45]

3) Scrap packing and preheating are emerging interfaces between mechanics and thermodynamics

Recent studies on scrap preheating, packed structure, and gas permeability show that porosity, random packing, and flow nonuniformity strongly affect heat transfer and utilization. [29] [41] [46] [47] [48]

This is relevant because the same packing features that control preheating also influence how scrap discharges, lands, and re-packs in the furnace. [29] [41] [46] [47]

Main knowledge gaps for modeling scrap infeed into an EAF

Gap	Why it matters	Evidence basis
Coupling of handling and furnace physics	There is little direct integration of conveyor/chute DEM with EAF melting models, even though the charging geometry and layer formation affect melting performance. [2] [4] [6] [9] [30]	Conveyor DEM is mature; EAF models are mature; the interface is not. [2] [4] [9] [30]
Realistic scrap shape and packing	Scrap is highly irregular, and many EAF models still simplify it into averaged beds or porosity fields. [7] [9] [36] [47]	Random packing, void structure, and porosity are repeatedly identified as important, but not yet captured in a unified charging model. [41] [46] [47]

Charge dynamics during delivery	The literature gives much less attention to the motion of scrap from feeder to bath, including impacts, segregation, and layer buildup. [22] [27] [49] [50]	Existing granular-flow studies address conveyors and hoppers, not scrap charging into EAFs. [20] [22] [27] [51]
Validation with industrial scrap data	Many DEM and CFD studies are validated in related materials or lab-scale systems, but scrap charging into real EAFs remains hard to observe directly. [2] [9] [34] [52]	Industrial-scale validation exists for melting models, yet charging-process validation is still sparse. [9] [34]
Multiphysics at the charge surface	Infeed scrap quickly transitions from mechanical handling to heating, oxidation, re-solidification, and collapse, which current models usually treat separately. [9] [30] [31] [32] [36] [41]	A single model spanning transport, packing, and melting is still missing. [9] [30] [41]

Bottom line

The best-supported research direction is to treat **scrap infeed as a coupled granular-transport problem**: use DEM-style particle mechanics for the conveyor/chute/charging stage, then hand off to a furnace model that resolves packing-dependent heat transfer and melting. [2] [3] [4] [5] [9] [36] [41] [46] [47] The main gap is not whether DEM works in principle—it does—but whether it can be linked to realistic scrap geometry, validated charging dynamics, and downstream EAF melting in one industrially usable workflow. [2] [9] [10] [34] [41] [47]

Confidence level: **High** — the evidence consistently supports DEM maturity for conveyors and highlights EAF modeling strength in melting/CFD, while also showing that scrap charging/infeed itself is comparatively underdeveloped. [2] [3] [4] [5] [8] [9] [34] [41] [47]

References

1. Kryszak, D., Bartoszewicz, A., Szufa, S., (...), Olejnik, T.P. (2020) Modeling of transport of loose products with the use of the non-grid method of discrete elements (DEM). *Processes*. <https://doi.org/10.3390/pr8111489>
2. Rossow, J., Coetzee, C.J. (2021) Discrete element modelling of a chevron patterned conveyor belt and a transfer chute. *Powder Technology*. <https://doi.org/10.1016/j.powtec.2021.06.012>
3. Blais, B., Vidal, D., Bertrand, F., (...), Chaouki, J. (2019) Experimental Methods in Chemical Engineering: Discrete Element Method—DEM. *Canadian Journal of Chemical Engineering*. <https://doi.org/10.1002/cjce.23501>

4. Wheeler, C.A., Robinson, P.W., Munzenberger, P.J., (...), Reid, S.C. (2023) Belt Conveyor Design and Troubleshooting. *Simulations in Bulk Solids Handling: Applications of DEM and other Methods*. <https://doi.org/10.1002/9783527835935.ch3>
5. Sakai, M. (2016) How should the discrete element method be applied in industrial systems?: A review. *KONA Powder and Particle Journal*. <https://doi.org/10.14356/kona.2016023>
6. Zhang, H., Wei, G., Xu, A., (...), Zhu, R. (2024) Modelling and Simulation of the Scrap Melting in the Consteel EAF. *Minerals, Metals and Materials Series*. https://doi.org/10.1007/978-3-031-50304-7_52
7. Li, J., Provatas, N., Irons, G.A. (2008) Modeling of scrap melting in the heel of an EAF. *Iron and Steel Technology*. <https://www.scopus.com/pages/publications/50849117531>
8. Hay, T., Visuri, V.-V., Aula, M., Echterhof, T. (2021) A Review of Mathematical Process Models for the Electric Arc Furnace Process. *Steel Research International*. <https://doi.org/10.1002/srin.202000395>
9. Chen, Y., Ryan, S., Silaen, A.K., Zhou, C.Q. (2022) Simulation of Scrap Melting Process in an AC Electric Arc Furnace: CFD Model Development and Experimental Validation. *Metallurgical and Materials Transactions B: Process Metallurgy and Materials Processing Science*. <https://doi.org/10.1007/s11663-022-02559-6>
10. Rojek, J. (2018) Contact modeling in the discrete element method. *CISM International Centre for Mechanical Sciences, Courses and Lectures*. https://doi.org/10.1007/978-3-319-90155-8_4
11. Cundall, P.A., Strack, O.D.L. (1979) A discrete numerical model for granular assemblies. *Geotechnique*. <https://doi.org/10.1680/geot.1979.29.1.47>
12. Johnson, K.L. (1985) Contact mechanics. <https://www.scopus.com/pages/publications/85040875608>
13. Brilliantov, N.V., Spahn, F., Hertzsch, J.-M., Pöschel, T. (1996) Model for collisions in granular gases. *Physical Review E - Statistical Physics, Plasmas, Fluids, and Related Interdisciplinary Topics*. <https://doi.org/10.1103/PhysRevE.53.5382>
14. Foerster, S.F., Louge, M.Y., Chang, H., Allia, K. (1994) Measurements of the collision properties of small spheres. *Physics of Fluids*. <https://doi.org/10.1063/1.868282>
15. Džugys, A., Peters, B. (2001) An approach to simulate the motion of spherical and non-spherical fuel particles in combustion chambers. *Granular Matter*. <https://doi.org/10.1007/pl00010918>
16. Ramírez, R., Pöschel, T., Brilliantov, N.V., Schwager, T. (1999) Coefficient of restitution of colliding viscoelastic spheres. *Physical Review E - Statistical Physics, Plasmas, Fluids, and Related Interdisciplinary Topics*. <https://doi.org/10.1103/PhysRevE.60.4465>

17. Hastie, D.B., Wypych, P.W. (2012) The sensitivity of particle parameters in discrete element modelling of belt conveyor transfers. *7th International Conference for Conveying and Handling of Particulate Solids, CHoPS 2012*.
<https://www.scopus.com/pages/publications/84897585620>
18. Cai, L., Wang, X.-W., Wang, S.-P., (...), Yu, Q. (2016) Motion characteristics and force properties of bulk coal in middle pan of scraper conveyor. *Meitan Xuebao/Journal of the China Coal Society*. <https://doi.org/10.13225/j.cnki.jccs.2015.0887>
19. Dallinger, N., Risch, T., Nendel, K. (2012) Simulation of conveying processes in vibratory conveyors. *Logistics Journal*. https://doi.org/10.2195/lj.Proc.dallinger_de.201210.01
20. Wang, X., Li, B., Yang, Z. (2018) Analysis of the bulk coal transport state of a scraper conveyor using the discrete element method. *Journal of Mechanical Engineering*.
<https://doi.org/10.5545/sv-jme.2017.4790>
21. Song, W., Wang, B., Wang, F. (2016) Simulation design of transfer station on conveying system and research of particle degenerate problem with DEM. *ICBMH 2016 - 12th International Conference on Bulk Materials Storage, Handling and Transportation, Proceedings*. <https://www.scopus.com/pages/publications/85016943714>
22. Loughran, J.G., Leonardi, C. (2005) Application of discrete element methods to modelling of belt feeders. *4th Australasian Congress on Applied Mechanics, ACAM 2005*.
<https://www.scopus.com/pages/publications/84878182944>
23. Karolewski, B., Ligocki, P. (2014) Modelling of long belt conveyors. *Eksploracja i Niezawodnosc*. <https://www.scopus.com/pages/publications/84896464072>
24. Whittles, D.N., Kingman, S., Lowndes, I.S., Griffiths, R. (2005) An investigation into the parameters affecting mass flow rate of ore material through a microwave continuous feed system. *Advanced Powder Technology*. <https://doi.org/10.1163/156855205774483370>
25. Motaln, M., Lerher, T. (2024) Innovative Approaches to Wear Reduction in Horizontal Powder Screw Conveyors: A Design of Experiments-Guided Numerical Study. *Applied Sciences (Switzerland)*. <https://doi.org/10.3390/app14073064>
26. Tian, J., Hastie, D.B., Roberts, J.M., (...), Pan, R. (2023) A Review of Simulation Methods for Belt Conveyors. *ICBMH 2023 - 14th International Conference on Bulk Materials Storage, Handling and Transportation, Proceedings*.
<https://www.scopus.com/pages/publications/85215372883>

27. Nogueira, L.R., Patrocínio, M., Marinho, C., (...), Mesquita, A.L.A. (2012) Transfer chute and belt conveyor performance using the discrete element method for coasting analysis. *6th Int. Congress on the Science and Technology of Ironmaking 2012, ICSTI 2012 - Including Proceedings from the 42nd Ironmaking and Raw Materials Seminar, and the 13th Brazilian Symp. on Iron Ore*. <https://www.scopus.com/pages/publications/84883672795>
28. Maksarov, V., Zlotnikov, E., Olt, J. (2017) Determining the load on support rollers the pipe conveyor belt. *Annals of DAAAM and Proceedings of the International DAAAM Symposium*. <https://doi.org/10.2507/28th.daaam.proceedings.028>
29. Fan, G., Su, F., Zhao, Q., (...), Li, B. (2024) Study on Heat Transfer Process between High-Temperature Slag Particles and Scrap in Drum Based on DEM Method. *Processes*. <https://doi.org/10.3390/pr12040815>
30. Ugarte, O., Li, J., Haeberle, J., (...), Zhou, C.Q. (2024) CFD Modeling of HBI/scrap Melting in Industrial EAF and the Impact of Charge Layering on Melting Performance. *Materials*. <https://doi.org/10.3390/ma17215139>
31. Chen, Y., Luo, Q., Ryan, S., (...), Zhou, C.Q. (2022) Effect of coherent jet burner on scrap melting in electric arc furnace. *Applied Thermal Engineering*. <https://doi.org/10.1016/j.applthermaleng.2022.118596>
32. Chen, Y., Ryan, S., Silaen, A.K., Zhou, C.Q. (2022) Numerical investigation of AC electric arc plasma heat dissipation in EAF. *Ironmaking and Steelmaking*. <https://doi.org/10.1080/03019233.2021.1989970>
33. Gruber, J.C., Echterhof, T., Pfeifer, H. (2016) Investigation on the Influence of the Arc Region on Heat and Mass Transport in an EAF Freeboard using Numerical Modeling. *Steel Research International*. <https://doi.org/10.1002/srin.201400513>
34. Chen, Y., Luo, Q., Ryan, S., (...), Zhou, C.Q. (2022) Effect of coherent jet burner on scrap melting in electric arc furnace. *Applied Thermal Engineering*. <https://doi.org/10.1016/j.applthermaleng.2022.118596>
35. Luo, Q., Chen, Y., Abraham, S., (...), Zhou, C. (2022) Effects of EAF Operations on Water-Cooling Panel Overheating. *Steel Research International*. <https://doi.org/10.1002/srin.202100844>
36. Ugarte, Orlando, Li, Jianghua, Haeberle, Jeff, (...), Zhou, Chenn Q. (2024) CFD Modeling of HBI/scrap Melting in Industrial EAF and the Impact of Charge Layering on Melting Performance. *Materials*. <https://doi.org/10.3390/ma17215139>
37. Yiğit, C., Coskun, G., Büyükkaya, E., (...), Güven, H.R. (2015) CFD modeling of carbon combustion and electrode radiation in an electric arc furnace. *Applied Thermal Engineering*. <https://doi.org/10.1016/j.applthermaleng.2015.07.066>

38. Zhang, Y., Barr, P.V., Ray Meadowcroft, T. (2008) Continuous scrap melting in a short rotary furnace. *Minerals Engineering*. <https://doi.org/10.1016/j.mineng.2007.09.009>
39. Stahl, F., Kühnemund, M., Krüger, K., (...), Matschullat, T. (2016) Controlling in the electric ARC properties in an AC-EAF at Dörrenberg Edelstahl. *Chernye Metally*.
<https://www.scopus.com/pages/publications/85031920311>
40. Korostelev, A.A., Kotel'nikov, G.I., Semin, A.E., Bozheskov, A.N. (2017) Analysis of HBI effect in charge on technological parameters of EAF melting. *Chernye Metally*.
<https://www.scopus.com/pages/publications/85032888315>
41. Li, S., Huo, W., Hu, Y., (...), Yao, X. (2026) Numerical Simulation of Scrap Melting Utilizing Converter Gas Oxygen-Enriched Combustion in a Hot Metal Ladle. *Processes*.
<https://doi.org/10.3390/pr14132042>
42. Zhou, Y., Naert, K., Nuyens, D. (2025) Sensitivity Analysis of State Space Models for Scrap Composition Estimation in EAF and BOF. *Journal of Physics: Conference Series*.
<https://doi.org/10.1088/1742-6596/3050/1/012001>
43. Arzpeyma, N., Alam, M., Gyllenram, R., Jönsson, P.G. (2021) Model development to study uncertainties in electric arc furnace plants to improve their economic and environmental performance. *Metals*. <https://doi.org/10.3390/met11060892>
44. Sandberg, E., Lennox, B., Undvall, P. (2007) Scrap management by statistical evaluation of EAF process data. *Control Engineering Practice*.
<https://doi.org/10.1016/j.conengprac.2007.01.001>
45. Kleimt, B., Kargar, Z., Peiss, V., (...), Unamuno, I.U. (2025) AI-based monitoring of steel scrap properties for improved utilization in scrap based steelmaking. *Metallurgia Italiana*.
<https://www.scopus.com/pages/publications/105006989979>
46. Tange, M., Fujii, H., Fujizoe, H., (...), Tsutsumi, K. (2024) Relationship between the Nonuniformity of Packed Structure and Fluid Permeability in a Model Scrap Preheating Vessel. *ISIJ International*. <https://doi.org/10.2355/isijinternational.ISIJINT-2023-458>
47. Luo, P., Liu, G., Wang, J., Liu, Y. (2025) Optimization of Scrap Preheating in Hot Metal Ladles by Computational Modeling to Address Disordered Packing. *JOM*.
<https://doi.org/10.1007/s11837-025-07763-8>
48. Xiao, P., Jin, Y., Zhu, L., (...), Zhu, R. (2024) Comparative Study of Heat Transfer Simulation and Effects of Different Scrap Steel Preheating Methods. *Metals*.
<https://doi.org/10.3390/met14080913>
49. Song, W.-G., Chen, H.-L., Li, Q.-L., Yang, Y.-H. (2011) Simulation of handling impact load of bulk material by DEM method. *Dongbei Daxue Xuebao/Journal of Northeastern University*.
<https://www.scopus.com/pages/publications/82755183477>

50. Guö, D., Irons, G.A. (2004) Simulation of steel scrap movement. *AIStech - Iron and Steel Technology Conference Proceedings*.
<https://www.scopus.com/pages/publications/12844261385>
51. Balevičius, R., Kačianauskas, R., Mröz, Z., Sielamowicz, I. (2006) Numerical modeling of filling and discharge processes in hoppers of different shapes. *AIChE Annual Meeting, Conference Proceedings*. <https://www.scopus.com/pages/publications/56749106242>
52. Brusa, E.G.M., Bosso, N., Zampieri, N., (...), Picciotto, M. (2012) Electromechanical coupled response of the ac electric arc furnace structures during the scrap melting process. *ASME 2012 11th Biennial Conference on Engineering Systems Design and Analysis, ESDA 2012*.
<https://doi.org/10.1115/ESDA2012-82366>