



Heidelberg Materials

Technical Services Clarinda

(ABN 90 009 679 734)

69 Carroll Road,

South Oakleigh, Vic 3167

Phone:

03 9570 3244

SIEVE ANALYSIS

Sample Type:

10/16

Date:

5/12/2025

Weight (g):

127.6

SIEVE APPERTURE mm	Weight Retained (g)	Weight Retained (%)	Cumulative Retained (%)	Cumulative Passing (%)
2.800	7.8	6.1	6.1	93.9
2.360	14.2	11.1	17.3	82.7
2.000	12.7	10.0	27.2	72.8
1.700	14.3	11.2	38.4	61.6
1.400	29.6	23.2	61.6	38.4
1.180	28.8	22.6	84.2	15.8
1.000	14.1	11.1	95.3	4.7
0.850	2.6	2.0	97.3	2.7
0.710	1.1	0.9	98.2	1.8
0.600	0.7	0.5	98.7	1.3
0.500	0.5	0.4	99.1	0.9
0.425	0	0.0	99.1	0.9
0.300	0	0.0	99.1	0.9
0.212	0	0.0	99.1	0.9
0.150	0	0.0	99.1	0.9
Pan	1.1	0.9	100.0	0.0
TOTAL	127.5	100.0		

E.S. = 1.1

U.C.= 1.54

Tested By :

Shane

Comments :