



Heidelberg Materials

Technical Services Clarinda

(ABN 90 009 679 734)

69 Carroll Road,
South Oakleigh, Vic 3167

Phone: 03 9570 3244

SIEVE ANALYSIS / A.F.S. WORKSHEET

Sample Type : HM40 W/S No. _____
Date : 5/12/2025
Weight: 157.3

SIEVE APPERTURE			Weight Retained (grams)	Weight Retained (%)	Cumulative Retained (%)	Passing (%)	A.F.S. Factor	Product
MM	BSS	ASTM						
2.000	8	10	0.0	0.0	0.0	100.0	5	0
1.000	16	16	1.5	1.0	1.0	99.0	5	5
0.850	18	20	1.5	1.0	2.0	98.0	10	10
0.600	25	30	10.3	6.9	9.0	91.0	20	139
0.425	36	40	18.8	12.7	21.6	78.4	30	380
0.300	52	50	50.7	34.1	55.7	44.3	40	1365
0.212	72	70	56.0	37.7	93.4	6.6	50	1884
0.150	100	100	8.1	5.5	98.9	1.1	70	382
0.106	150	140	1.4	0.9	99.8	0.2	100	94
0.075	200	200	0.3	0.2	100.0	0.0	140	28
0.053	300	270	0.0	0.0	100.0	0.0	200	0
PAN			0.0	0.0	100.0	0.0	300	0
TOTAL			149	100				4286

A.F.S. = 43

Tested By : Shane

Comments : _____

