APPENDIX W1
SPECIFICATION AND TEST REQUIREMENT FOR KNITTED ITEMS
[PS Section 1.120]

Test Item 項目		Test Method 測試方法	In Direct Contact with Skin 直接接觸皮膚	With No Direct Contact with Skin 非直接接觸皮膚
PH 值 (PH Value)		AATCC81	4.0 - 7.5	4.0 - 9.0
甲醛含量(mg/kg) (Formaldehyde Content)		ISO14184 or GB/T 2912.1	≤ 75ppm	≤ 300ppm
可分解芳香胺染料 (AZO Dyes)		EN14362	Not Detected 禁用	Not Detected 禁用
異味 Determination Of Odour		SNV 195 651 or GB Test Method 2	Odourless 無異味	Odourless 無異味
水洗尺寸變化率(單面織物)(%) (Dimensional Stability to Washing)	直向 (Length) 橫向 (Width)	ISO5077 ISO6330 (1st & 3rd washes)	≤ +/- 5% (Non-Garment washed) ≤ +/- 3% (Garment washed)	≤ +/- 5% (Non-Garment washed) ≤ +/- 3% (Garment washed)
水洗後扭曲率(%) (Spirality)	上衣(Top) 褲子 (Pants)	ISO16322 ISO6330	Top : ≤ 5% Bottom & one piece : ≤ 2.5%	Top : ≤ 5% Bottom & one piece : ≤ 2.5%
耐洗色牢度(級) (Colour Fastness to Washing)	變色 (Colour Change)	ISO105-C06	≥ 4	≥ 4
	沾色 (Colour Staining)		≥ 3-4	≥ 3-4
	自身沾色 (Crossing Staining)		≥ 4 (contrast colour)	

Test Item 項目		Test Method 測試方法	In Direct Contact with Skin 直接接觸皮膚	With No Direct Contact with Skin 非直接接觸皮膚
耐摩擦色牢度(級) (Colour Fastness to Rubbing)	乾(Dry) 濕(Wet)	ISO105-X12	≥ 4 ≥ 3	≥ 4 ≥ 3
耐汗漬色牢度(級) (Colour Fastness to Perspiration) -酸(Acid) & 鹼 (Alkaline)	變色 (Colour Change) 沾色 (Colour Staining)	ISO105-E04	≥ 4 ≥ 3-4	≥ 4 ≥ 3-4
塗料印花耐洗色牢度(級) (Colour Fastness to Washing(Pigment))	變色 (Colour Change) 沾色 (Colour Staining)	ISO105-C06 (For Pigment)	≥ 3-4 ≥ 3	≥ 3-4 ≥ 3
塗料印花耐摩擦牢度(級) (Colour Fastness to Rubbing(Pigment))	乾(Dry) 濕(Wet)	ISO105-C07 (For Pigment)	≥ 3-4 ≥ 2-3	3-4 2-3
耐光色牢度(級) (Colour Fastness to Light)		ISO105-B02	≥ 4	≥ 4
耐水色牢度(級) (Colour Fastness to Water)	變色 (Colour Change) 沾色 (Colour Staining)	ISO105-E01	≥ 4 ≥ 3-4	≥ 4 ≥ 3-4

Test Item 項目		Test Method 測試方法	In Direct Contact with Skin 直接接觸皮膚	With No Direct Contact with Skin 非直接接觸皮膚
洗水後外觀 Appearance after Wash (including retroreflective strips and logo)		Visual Assessment	1st & 3rd washes No undesirable effect	1st & 3rd washes No undesirable effect
彈子頂破强力(N) (Ball Bursting Strength)	單面 (Single)	ASTM D3786	Fabric : ≥ 40 lb/sq. in ; Seam : ≥ 35 lb/sq. in	Fabric : ≥ 40 lb/sq. in ; Seam : ≥ 35 lb/sq. in
	雙面、絨類 (Double、Fleece)			
起球(級) Please refer Note A (Pilling Resistance as Received)		ASTM D3512	≥ 3-4	≥ 3-4

Note A - 全棉、剪毛、絲絨、磨毛、起絨類產品不須測試起球. (Pilling test is not required for 100% cotton, velour, peached, brushed fabric)

[BLANK PAGE]