

Liquid oil road bitumen TDS 788 - 2016



№	Indicators	Values for grades					
		MG 40/70	MG 70/130	MG 130/200	MGO 40/70	MGO 70/130	MGO 70/130
		ÖÜK 02 5611 0302	ÖÜK 02 5611 0303	ÖÜK 02 5611 0304	ÖÜK 02 5611 0403	ÖÜK 02 5611 0401	ÖÜK 02 5611 0402
1	Conditional displacement at 60 °C from a viscometer with a flow diameter	40 - 70	71 - 130	131 - 200	40 - 70	71 - 130	131 - 200
2	Evaporator quantity, not less than%	8	7	5	-	-	-
3	After determining the amount of steam in the evaporator, the residual soft temperature, °C, not lower	28	29	3	-	-	-
4	Flashing temperature determined in open crucible, °C, not lower	100	110	110	120	160	180
5	Combined test with marble or sand	Tolerances according to protocol No. 2					