

PETROLEUM TOTAL COKE FOR GRAPHITE PRODUCTION

TŞ 05766698-13-2015



№	Description of index	Standard value
1	Mass fraction of total moisture, %, not more than	3,0
2	Ash content, %, not more than	0,6
3	Mass fraction of sulfur, %, not more than	0,6
4	Mass fraction of volatile substances, %, not more than	11,0
5	Actual density after heating for 5 hours at 1300 °C, g/cm ³ , not less than	2,08
6	Mass fraction of coke with particles less than 8 mm in size, %, not more than	60,0

NOTE: Mass fraction of total moisture is not a rejection indicator when shipped in open gondola cars and is used for settlement with the consumer