

Lesson Plan: Kohiki Slip Decoration for Slab Building

Objectives

- Introduce participants to the history and aesthetics of kohiki slip decoration.
- Teach slab-building fundamentals with emphasis on surface treatment.
- Guide students through applying kohiki slip and integrating it into functional or sculptural forms.

Materials

- Clay body (dark stoneware recommended).
- White slip (prepared to a thick cream consistency).
- Brushes, sponges, etc...
- Straight edges, rulers, tar paper for patterns.
- Rolling pins or slab roller.
- Canvas boards for rolling slabs.
- Wooden boards for working surfaces.
- Bevel cutters, knives, and scoring tools.
- Reference images of kohiki ware.

Activities

1. **Introduction (20 min):** Brief history of kohiki slip; show examples.
2. **Slab Preparation (20 min):** Demonstrate rolling slabs evenly; discuss thickness control.
3. **Slip Application (60 min):** Demonstrate brushing, dipping, or pouring slip; encourage freedom and experimentation—see discussion and exercises below. Before lunch break, demonstrate stretching technique to distort brushwork for dramatic effect.
4. **Lunch and Patience (≈ 1.5 hr):** Allow time for slip and clay to firm up.
 - **Structured Lunch/Teapot Demo (40 min):** Provide entertainment in creating a teapot during lunch.
 - **Structured Lunch/Practice Slot (20–30 min):** Provide short guided exercises students can do while waiting.
 - Goal:** Turn downtime into deliberate practice focused on slip observation and simple brushwork.
5. **Slab Construction (1 hr):** Demonstrate joining slabs into simple forms; emphasize simple forms, scoring, and compression.
6. **Wrap-Up Discussion (30 min):** Share results. Encourage discussion and reflection on slip application and surface effects; consider surface effects from the firing process.

Teaching Notes


- Stress patience: kohiki slip rewards subtlety.
- Encourage integration of surface decoration with form.
- Highlight how firing atmosphere alters slip appearance.

Recommended Tools/Materials to Bring


Create list of personal items recommended for participants to bring to the workshop, such as aprons, notebooks, personal brushes, etc.

Kohiki Slip

Timeline: History of Kohiki Slip



Parallel Timeline: Import of Korean and Chinese Potters to Japan



A couple modern examples of popular kohiki slip decoration by Akira Satake and Robert Fornell, as shown in the images below. I started experimenting with kohiki slip decoration after seeing Satake's work.



A beautiful example of a more traditional kohiki piece is this tea bowl identified as Agano ware on this website: <https://qualitychanoyu.com/2023/01/13/antique-agano-ware-kobiki-chawan/>

ANTIQUÉ AGANO SHIRO-KOHIKI CHAWAN



Although Europeans later came to prize East Asian porcelain and reshaped its markets, the white surfaces used in Punch'ōng and kohiki developed within East Asia before Europeans had sustained contact. These whiteslip techniques grew from local aesthetics and kiln practice, not from European influence. European demand in the 17th–19th centuries expanded export production in China and inspired European porcelain manufacture, but it did not influence Korea's (and later Japan's shino ware) whiteslip aesthetics.

Other links of interest about kohiki ware:

- <https://turuta.jp/ceramics-story/archives/21164>
- <https://dawan-chawan-chassabal.blogspot.com/2010/02/powdery-matsudaira-at-hatakeyama-museum.html>
- <https://dawan-chawan-chassabal.blogspot.com/2010/11/powdery-matsudaira-revisited.html>

After we work through the slabs, the following section will become apparent why we need to think about thickness of the slabs we are making.

Slab Thickness: Importance and Tradeoffs

The thickness of your clay slab is important for both the construction process and the final appearance of your work.

- **Structural Integrity:** Thicker slabs are less prone to warping and cracking during handling and drying, making them more forgiving for experimental work or for larger forms.
- **Workability:** Thinner slabs are easier to bend, shape, and join, but require more careful handling to avoid tearing or distortion during firing.
- **Surface Techniques:** Very thin slabs may dry too quickly for certain slip or texture applications, while thick slabs can retain moisture longer, allowing more time for surface work.
- **Aesthetics:** The visual weight and tactile feel of the finished piece are directly affected by slab thickness. Thicker walls can feel more robust, while thinner ones may appear more delicate or refined.

Tradeoff: Choose slab thickness based on your intended technique and form. For kohiki slip decoration, a medium thickness (typically 6-8 mm) balances workability, surface quality, and structural strength. Always test and adjust based on your clay body and project needs.

Exercises With the Brush

The following are exercises I encourage you to practice. Please take these with you when you leave and work on them in your own studio time.

Practice (30–40 min)

Keep materials minimal: work on wooden bats for slip applications.

1. **Single-Stroke Studies (6 min):** Make one confident stroke across the bat—experiment with pressure and angle.
2. **Opacity Ladder (6 min):** Apply 3 horizontal bands with decreasing slip thickness (heavy → medium → thin). Let dry and note differences.
3. **Quick Pair Share (3 min):** Swap bats with a partner; each gives one suggestion for the other's next step.
4. **Identify Area for Cutting and Construction (3 min):** On your bat, mark an area you might cut out later for slab construction; consider how the slip application will interact with form.

Brushwork Patterns (Step-by-step)

1. **Stippling (6 min):** Load brush, dab vertically using the tip only; vary density for tonal control.
2. **Drag-and-Stop (6 min):** Pull brush in a steady stroke, lift quickly for crisp ends.
3. **Combing (2 min):** Use a fork or comb dragged through semi-wet slip for parallel texture.
4. **Ribs (2 min):** Drag a rib or flat tool through wet slip to create texture; vary angle and pressure for different effects.

Slip Application Tests

- **Brush-Load Test:** Dip brush and make a 10 cm stroke; note opacity and pooling.
- **Adhesion Test:** Apply slip to a scrap of the class body, bend gently when leatherhard—does it crack or flake?
- **Drying Rate:** Make a thin swatch and time until it is no longer tacky—record for next session.
- **Hypothesis:** Suggest one hypothesis on slip application and test.

Observation Prompts

- Changes in color/value as the slip dries.
- Areas of pooling vs even coverage.
- Edges where slip has feathered or pulled away.
- Any textural interaction where slip meets tool marks.

Lunch / Patience

Below are some more exercises I want you to try during lunch or downtime. These are designed to help you build your skills and understanding of kohiki slip decoration. We will also be talking a bit about various subjects during this time.

Exercise: Slab Forming and Stretching

For a more exaggerated & dramatic appearance of the brush work on your slab pieces, try the following exercise during lunch or downtime:

- **Slab forming:** Get a small slab of clay (about 8 mm thick) from the instructor with kohiki slip already applied.
- **Stretching:** Carefully pick the small slab up from one edge and practice stretching it by carefully throwing it back down onto the table or canvas at roughly a 45 degree angle. The goal is to elongate the slab and distort the brushwork in an interesting way without tearing the clay.
- **Repeat:** Try this several times, varying the side you pick up from and the angle of impact. Observe how the brushwork changes with each stretch.
- **Notes:** Take a moment to write down your impressions about how to throw the clay to get different effects, and any challenges you faced in keeping the slab intact and well textured.

Slip Consistency & Quick Recipe (for reference)

- Basic $\Delta 10$ Kohiki Slip Recipe:

EPK kaolin:	500 g
Ball clay:	400 g
Feldspar:	600 g
Silica:	500 g
- Water: variable—depends on deflocculant use if any.
 1. Thin toothpaste consistency
 2. Thick cream consistency
 3. Any range in between depending on your application style and decorative goals
- Deflocculant (sodium silicate or Darvan): 1–3 g if needed, to thin without settling¹

¹Deflocculants help reduce the amount of water needed, but can reduce the workability of the clay beneath the slip. Use sparingly and test.

Lunch Discussions

Aesthetics of Kohiki

Discuss wabi-sabi, the value of subtlety, and how controlled imperfection enhances form.

Wabi-sabi vs. Mingei



Aspect	Mingei (Yanagi)	Wabi-sabi
Origin	1920s–30s folk craft movement led by Yanagi Sōetsu	16th century Zen tea aesthetics
Focus	Everyday, utilitarian objects made by an anonymous craftsman*	Imperfection, impermanence, rustic simplicity
Philosophy	Collective recognition of “beyond beauty and ugliness”	Contemplative, insight into transience
Social Dimension	Communal craft traditions, cultural preservation	Elite tea culture, spiritual refinement

* Please understand I am using the term “craftsman” in the same form as “human.”

How Yanagi Differentiated Them

- **Mingei as collective beauty:** Yanagi argued that folk crafts are beautiful precisely because they are made by nameless artisans for everyday use, not for individual artistic expression. This contrasts with *wabi-sabi*, which often highlights the personal, contemplative experience of imperfection.
- **Functional vs. contemplative:** Mingei objects are functional tools of daily life (bowls, textiles, furniture). Wabi-sabi objects (tea bowls, gardens, architecture) are often vehicles for meditation and aesthetic reflection.
- **Democratic vs. elite aesthetics:** Yanagi saw mingei as a democratic art form, accessible to all. Wabi-sabi, though humble, was historically tied to the tea ceremony and elite Zen culture.


Why This Matters

Yanagi's distinction is important because it shows that there are different ways of thinking about beauty—some focus on everyday objects made by many people (mingei), while others focus on quiet, simple beauty, and personal reflection (wabi-sabi). Mingei is about community, utility, and cultural survival, while wabi-sabi is about solitude, impermanence, and spiritual refinement. Both overlap in valuing simplicity and naturalness, but they diverge in social function and philosophical grounding.

Put simply, Mingei is a social philosophy of creation and use, while Wabi-sabi is *a way of seeing the world* and objects within it. Objects do not possess a quality of wabi-sabi; rather, wabi-sabi is a lens through which we appreciate them.



Images exemplifying the wabi-sabi aesthetic.



Selected works by Hamada and Kawai, exemplary Mingei works.

Work on the following sections to complete the lesson plan.

Kiln Transformations

Explain how wood/soda firing interacts with clay and slip surface—ash deposition, reduction/oxidation effects, and how slip texture traps or resists glaze.

Slab Expansion & Construction

Wrap-up; Reflection, Critique, Expectations, and Next Steps

Safety & Handling Notes

- Wash hands after handling slips containing deflocculants.
- Keep sanding and dry-scraping to a minimum.
- Label slip containers; avoid cross-contamination between different slips.

What I Notice / What I Would Change (Fill This Out)

1. Identification: _____

2. Observations: _____

3. One change I would make next time: _____

Recommended Reading Materials

Create a list of recommended books, articles, and online resources for further study on kohiki slip decoration and wood-fired soda firing.

Lesson Plan: Wood-Fired Soda Firing

Objectives

- Review fundamental principles of firing across all types of kilns.
- Discuss the unique characteristics of wood firing.
- Explain the chemistry and effects of soda firing.
- Introduce participants to the principles of soda firing in a wood kiln.
- Teach preparation of work for soda atmosphere (wadding, glazing, placement).
- Explore how soda interacts with clay and slip surfaces.

Materials

- Bisque-fired student work (preferably with surfaces prepped for wood+soda).
- Wadding materials (refractory wadding mix, alumina hydrate, kiln wash).
- Kiln shelves, posts, protective gear.
- Wood for firing (species discussion: pine, oak, etc.).
- Soda mix (soda ash + baking soda + whiting, in water) – following the suggestions of Gail Nichols.

Activities

1. **Introduction:** Explain soda firing chemistry; show examples.
2. **Preparation of Work:** Demonstrate wadding placement; discuss glaze choices.
3. **Kiln Loading:** Explain loading strategies; emphasize safety and teamwork.
4. **Firing Process:** Walk through firing stages; demonstrate soda introduction; discuss temperature targets.
5. **Cooling & Unloading:** Explain cooling protocols; plan for unloading and critique.
6. **Wrap-Up Discussion:** Anticipate results; encourage embracing variation and unpredictability.

Teaching Notes

- Stress safety: protective gear, teamwork, kiln etiquette.
- Highlight unpredictability as part of the aesthetic.
- Connect back to constructed works: how soda atmosphere transforms surfaces.