



OVERVIEW

HIGHLIGHTS:

Water base, non-toxic, solvent free

Can be applied to damp surfaces

Excellent adhesion

Quick drying

Highly flexible rubber coating

Easy to apply

Excellent crack-bridging properties

Low V.O.C. and non-flammable

TECHNICAL DATA:

Product Type:

Styrene-Butadiene

Solids (%):

58.0 ± 2% by weight

54.0 ± 2% by volume

Weight/Gallon:

9.8 ± 0.05lbs.

4.22 ± 0.02kg.

Color:

Applies dark blue, Dries black

Drying Time:

30 - 60 mins to touch,

2 hours to recoat

Coverage:

On concrete: 80 ft²/gal (7.4 m²/gal)

at 11dry mils, 20 wet mils

VOC: 4g/L

MANUFACTURER:

U.S. Roof Shield, LLC

PO Box 104

Matador, TX 79244 USA

PHONE: (806) 777-9977

EMAIL: u.s.roofshield@gmail.com

WEBSITE: alligatorhide.com

PRIMER

Styrene-Butadiene Acrylic Membrane

PRODUCT DATA SHEET

DESCRIPTION: AlligatorHide Primer Membrane is a liquid membrane made up of styrene-butadiene and acrylic that provides an excellent green alternative for many roofing and waterproofing applications as a primer membrane. This monolithic membrane provides excellent performance when used as a base coat over horizontal or vertical surfaces and performs extremely well during continuous water immersion testing. May be used under plaster, or between concrete slabs as a weather or vapor barrier.

USES: AlligatorHide Primer Membrane has proven excellent as a main waterproof coating or as part of a roofing system over a variety of substrates like concrete surfaces, modified asphalt membranes, built-up roofs, polyurethane foam, granulated shingles, metal, EPDM, aged TPO, and bonded tar.

SURFACE PREPARATION: Surface must be clean, sound, and free of dust, contaminants or loose material. Remove all debris and loose coatings by means of high-pressure water blasting or wire brushing. Any existing mildew on the surface must be completely killed and removed prior to the application of this product. Surface should not accumulate water for more than 48 hours.

MIXING: Premix for 3 minutes prior to application only if necessary. Use a drill and Jiffy-type mixer to mix at slow speed (less than 500 rpm) to avoid air entrainment.

PLACEMENT: Apply with a 3/4" nap rough surface roller or airless spray. Drying time will be approximately 60 minutes to touch. Cure time is controlled by thickness of the applied coating, relative humidity, and temperature. Wait 2 - 4 hours between coats at 75°F (24°C) degrees or higher at 18 mils or below. Apply only when temperature is above 50°F (10°C). Do not apply if temperature is expected to drop below 50°F (10°C) before the coating has completely dried. Two full coats are needed for proper sealing. Always apply coats in different directions. Never thin or dilute from full strength.

RECOMMENDED EQUIPMENT: Use an airless pump with a pressure of 1,500 to 2,000 psi. A fluid delivery of 1 to 4 gallons per minute with a spray tip of 0.035 to 0.060. The hoses should be at least 3/8" inside diameter and of the high-pressure rate type. If the hose length is more than fifty feet, a larger inside diameter will be required.

JOINTS & REPAIRS: Make sure joints, cracks, seams, and flashing are sound, clean, and dry. If applying on joints or seams, ensure backer rod is used. Apply crack filler and a polyester weave over cracks, seams, flashing and around any standing objects about 3 inches to both sides, and let dry thoroughly.

CLEAN-UP: Clean roller and equipment after use with warm soapy water.

PACKAGING: 5-gal Pail, 55-gal Drum, and 250-gal Tote.

WARNING! Do not allow the product to freeze. NIOSH approved, organic vapor respirators are recommended in confined areas, or when conditions (such as heated polymer, sanding) may cause high vapor concentrations. Avoid skin or eye contact. Wash skin with soap and water if contact occurs. If eye contact occurs, flush with water for 15 minutes and obtain medical attention. Read and understand all cautions on container labels and safety data sheets before using this material. Please refer to the SDS for additional safety information regarding this material. **KEEP OUT OF REACH OF CHILDREN.**