



OVERVIEW

HIGHLIGHTS:

Low VOC & Non-Flammable

Fiber reinforced

UV resistant

High sunlight reflectivity

Easy to apply

Excellent wind uplift resistance

Fast Cure

TECHNICAL DATA:

Product Type:

Siliconized Acrylic with ceramic

Solids (%):

65.4 ± 1% by weight

54.0 ± 1% by volume

Weight/Gallon:

11.43 ± 0.05lbs.

5.18 ± 0.02kg.

Color:

Applies light blue,

Dries ultra-white

Drying Time:

60 mins to touch,

2 hours to recoat

MANUFACTURER:

U.S. Roof Shield, LLC

PO Box 104

Matador, TX 79244 USA

PHONE: (806) 777-9977

EMAIL: u.s.roofshield@gmail.com

WEBSITE: alligatorhide.com



SUNSCREEN

Siliconized Acrylic Topcoat

PRODUCT DATA SHEET

DESCRIPTION: AlligatorHide Sunscreen Topcoat is a high-performance blend of siliconized acrylic components, micro-ceramic spheres, and rubberized elastomeric creating a dynamic roof and wall membrane sealer. An exceptionally durable, UV resistant, fiber reinforced coating with superior adhesion properties. The micro-ceramic spheres will significantly lower the interior temperature of structures by reflecting the sun's rays and reducing heat by 80%. AlligatorHide Sunscreen Topcoat provides a seamless, waterproof, and weather protective seal that tightly adheres to the substrate.

SURFACE PREPARATION: Surface must be clean, sound, and free of dust, contaminants or loose material. Remove all debris and loose coatings by means of high-pressure water blasting or wire brushing. Any existing mildew on the surface must be completely killed and removed prior to the application of this product. Surface should not accumulate water for more than 48 hours. Coat entire top surface with AlligatorHide Primer. This surface primer is specially designed to penetrate concrete, seal surface porosity, and waterproof the substrate.

MIXING: Premix for 3 minutes prior to application only if necessary. Use a drill and Jiffy-type mixer to mix at slow speed (less than 500 rpm) to avoid air entrainment.

PLACEMENT: Apply with a 3/4" nap rough surface roller or airless spray. Drying time will be approximately 60 minutes to touch. Cure time is controlled by thickness of the applied coating, relative humidity, and temperature. Wait 2 - 4 hours between coats at 75°F (24°C) degrees or higher at 18 mils or below. Apply only when temperature is above 50°F (10°C). Do not apply if temperature is expected to drop below 50°F (10°C) before the coating has completely dried. Two full coats are needed for proper sealing. Always apply coats in different directions. Never thin or dilute from full strength.

RECOMMENDED EQUIPMENT: Use an airless pump with a pressure of 1,500 to 2,000 psi. A fluid delivery of 1 to 4 gallons per minute with a spray tip of 0.035 to 0.060. The hoses should be at least 3/8" inside diameter and of the high-pressure rate type. If the hose length is more than fifty feet, a larger inside diameter will be required.

JOINTS & REPAIRS: Make sure joints, cracks, seams, and flashing are sound, clean, and dry. If applying on joints or seams, ensure backer rod is used. Apply crack filler and a polyester weave over cracks, seams, flashing and around any standing objects about 3 inches to both sides, and let dry thoroughly.

CLEAN-UP: Clean roller and equipment after use with warm soapy water.

PACKAGING: 5-gal Pail, 55-gal Drum, and 250-gal Tote.

WARNING! Do not allow the product to freeze. NIOSH approved, organic vapor respirators are recommended in confined areas, or when conditions (such as heated polymer, sanding) may cause high vapor concentrations. Avoid skin or eye contact. Wash skin with soap and water if contact occurs. If eye contact occurs, flush with water for 15 minutes and obtain medical attention. Read and understand all cautions on container labels and safety data sheets before using this material. Please refer to the SDS for additional safety information regarding this material. **KEEP OUT OF REACH OF CHILDREN**