

Multi-scale Modeling of Hydrogen Transport in a Porous Fuel Cell Anode

Rosa Zhang^{1,2}, Anamika Chowdhury^{1,2}, Justin C. Bui^{1,2}, Clayton J. Radke¹, and Adam Z. Weber²

¹University of California, Berkeley, ²Lawrence Berkeley National Lab



Introduction: Hydrogen Transport Resistances

Gas transport in proton exchange membrane fuel cells encounters multiple length-scales and phases:

- 1) electrode pores at the length scale of electrode thickness (micrometer)
- 2) diffusion into the agglomerate through an ionomer film at the length scale of agglomerate radius (nanometer).

Herein, we present an analytical model of H₂ transport through porous anode catalyst layer (CL):

- **multi-scale:** 1+1D (along electrode thickness and catalyst particle radius)
- **multi-phase:** porous carbon agglomerate with Pt particles; ionomer film
- **purely analytical:** derived from spherical diffusion & Butler-Volmer kinetics




Figure 1. Diagram of 1-D micrometer-scale model of H₂ transport from the gas diffusion layer (GDL) through the porous electrode catalyst layer (CL), and onto the proton exchange membrane (PEM).

Multi-Scale Model: Derivation

I. Agglomerate

$$\frac{1}{z^2(R_a + \delta_f)} \frac{\partial}{\partial z} \left(z^2 D_{eff} \frac{\partial c_{H_2,agg}}{\partial z} \right) + r_{H_2} = 0$$

$$\text{BC 1: } \frac{\partial c_{H_2,agg}}{\partial z} \Big|_{z=0} = 0$$

$$\text{BC 2: } D_{eff} \frac{\partial c_{H_2,agg}}{\partial z} \Big|_{z=\frac{R_a}{R_a + \delta_f}} = D_{film} \frac{\partial c_{H_2,film}}{\partial z} \Big|_{z=\frac{R_a}{R_a + \delta_f}}$$

II. Ionomer film

$$\frac{1}{z^2(R_a + \delta_f)} \frac{\partial}{\partial z} \left(z^2 D_{eff} \frac{\partial c_{H_2,film}}{\partial z} \right) = 0$$

$$\text{BC 1: } c_{H_2,film} \Big|_{z=1} = S_{CL \rightarrow film} c_{H_2,CL}$$

$$\text{BC 2: } D_{eff} \frac{\partial c_{H_2,agg}}{\partial z} \Big|_{z=\frac{R_a}{R_a + \delta_f}} = D_{film} \frac{\partial c_{H_2,film}}{\partial z} \Big|_{z=\frac{R_a}{R_a + \delta_f}}$$

$$\text{BC 3: } c_{H_2,agg} \Big|_{z=\frac{R_a}{R_a + \delta_f}} = S_{film \rightarrow agg} c_{H_2,film} \Big|_{z=\frac{R_a}{R_a + \delta_f}}$$

III. Electrode thickness

$$D_{CL} \frac{\partial^2 c_{H_2}}{\partial x^2} + r_{H_2} = 0$$

$$\text{BC 1: } c_{H_2}(x=0) = c_{feed}$$

$$\text{BC 2: } \frac{\partial c_{H_2}}{\partial x} \Big|_{x=L} = 0$$




Figure 2. Diagram of radial H₂ transport into the catalyst particle through the ionomer film layer (δ_f) and into the agglomerate (R_a).

Derived analytical expressions

$$c_{H_2,agg} = \xi_{c_{H_2,CL}} \frac{1}{\gamma} \frac{D_{film}}{D_{eff}} \sinh(\kappa z) \frac{1}{z}$$

$$c_{H_2,film} = c_{CL \rightarrow film} + \xi_{c_{H_2,CL}} \left(1 - \frac{1}{z} \right)$$

$$c_{H_2,CL} = c_{feed} (\cosh(\sqrt{\nu}x) - \tanh(\sqrt{\nu}L) \sinh(\sqrt{\nu}x))$$

I. Effectiveness Factor

$$E_R = \frac{W_{AR}}{W_{AR,0}} = \frac{\text{actual rxn rate in catalyst particle}}{\text{rxn rate assuming surface concentration}}$$

$$= \frac{D_{film} \xi}{\frac{1}{3}(R_a + \delta_f)^2 \left(\frac{a_v i_0}{2F} \right) \frac{1}{c_{ref}} \exp\left(\frac{\alpha_a F}{RT}(E - E_0)\right)}$$

II. Current

$$i = A \left(-\frac{3a_v i_0 (1 - \phi_c)}{c_{ref}} \right) \left(\exp\left(\frac{\alpha_a F}{RT}(E - E_0)\right) \right)$$

$$\int_0^{CL} \left(\int_0^{\frac{R_a}{R_a + \delta_f}} c_{H_2}(z) z^2 dz \right) x dx$$

★ Where γ, κ, ν, ξ are constants
 $\xi \propto R_a, \delta_f, D_{film}, D_{eff}, S_{film \rightarrow agg}, S_{CL \rightarrow film}$

Transport is sensitive to porosity, particle size




Figure 3. Polarization curve for varying particle porosity.

In **Figure 4** (right):

$$\text{as } i \rightarrow i_{max}, E_R \rightarrow 0$$

This behavior is expected; as applied potential increases, reaction kinetics overtake transport and the particle becomes transport-limited.

H₂ concentration within the particle reduces to zero, causing:

$$\nabla c_{H_2} \rightarrow 0$$


$$W_{AR} \rightarrow 0$$

$$E_R \rightarrow 0$$

Figure 4 (right). Sensitivity analysis of total current generated (top) and effectiveness factors (bottom) for varying catalyst particle radii.

Sensitivity analysis found that **overall, current generation is sensitive to particle size and porosity**. Physically, this is caused by the following:

- Higher porosity reduces available catalyst surface for reaction, slowing down reaction kinetics (**Figure 3**, left).
- Larger particle size measured by radius increases transport resistance, which reduces available H₂.



Catalyst particle is dominantly transport-limited




Figure 5. Diagram of H₂ transport through a 1-dimensional radial axis through the catalyst particle film towards the center of the carbon-Pt agglomerate, assumed as a spherical particle.

Notable features of concentration profile across the electrode:

- 1) Steep gradient within the ionomer film layer surrounding the agglomerate.
- 2) At E~1V, the concentration gradient drops to 0 while the CL concentration (not shown) outside of the particle is positive and non-zero.

- 3) H₂ only declines at a small radial volume between

$$0.9 \geq z \geq z|_{\text{film boundary}}$$

These characteristics imply that:

- 1) The ionomer film poses significant transport resistance H₂ transport into the catalyst particle, especially at high overpotential.
- 2) H₂ transport into the catalyst particle is dominantly transport-limited.
- 3) The catalyst particle is not being fully utilized. Reaction only occurs from the outer 10% of the agglomerate up to the film interface.

Conclusions

This model

- builds upon understanding of H₂ transport resistance within a porous electrode.
- uses purely analytical operations allow for extremely fast simulations of the porous electrode set-up.

Key observations

- Electrode is dominantly transport-limited.
- Electrode reaches an upper-limit of catalyst volume utilization.
- Porosity and size (radius) of the catalyst particle strongly impacts electrode's current generation.

Future development of the model for more sensitive, complex physical behavior to:

- 1) optimizes catalyst particle morphology (radius, catalyst loading, porosity, ionomer content, etc.)
- 2) compare performance enhancement against cost (reducing underutilized catalyst).

Acknowledgements

This material is based on work performed by Yoon and Weber (2011). Presentation of this material is made possible through funding by the UC Berkeley Fiat Lux Koret Discovery Scholarship. The author deeply thanks Justin Bui, Anamika Chowdhury, Prof. Radke, and Dr. Weber for their continued support and community!