

09/29/15

AllSPPactiveInterfaces.dat

1

1 #	Substrate	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
2	Ag	Air	800.000000	Yes	Yes	787.002350	141.297977	4383.641529
	0.995419							
3	Ag	SiC	800.000000	Yes	Yes	269.300102	126.733718	572.268419
	0.989880							
4	Ag	Ge	800.000000	Yes	Yes	97.108710	81.009692	117.104025
	0.862508							
5	Ag	Si	800.000000	Yes	Yes	162.167525	107.524760	244.596166
	0.984717							
6	Ag	ZnO	800.000000	Yes	Yes	382.259286	134.454103	1086.828319
	0.991771							
7	Ag	a-C	800.000000	Yes	Yes	397.764547	136.748536	1416.839952
	0.591289							
8	Ag	Graphite(o)	800.000000	Yes	Yes	286.997744	137.335670	1119.038669
	0.371655							
9	Ag	SiO2	800.000000	Yes	Yes	531.402636	138.656459	2036.696051
	0.993572							
10	Ag	Al2O3	800.000000	Yes	Yes	431.228247	136.271913	1364.667870
	0.992444							
11	Ag	Diamond	800.000000	Yes	Yes	300.067518	129.555408	695.026467
	0.990439							
12	Ag	H2O	800.000000	Yes	Yes	584.754581	139.485799	2451.524219
	0.994060							
13	Ag	GaAs	800.000000	Yes	Yes	163.207109	107.860519	247.174409
	0.946535							
14	Ag	InP	800.000000	Yes	Yes	182.308470	112.984462	295.522333
	0.886018							
15	Ag	GaP	800.000000	Yes	Yes	205.214220	117.673888	357.893424
	0.988672							
16	Ag	W	800.000000	Yes	Yes	337.678426	156.734863	2146.856890
	0.237253							
17	Ag	Ge	400.000000	No	Yes	1535.300837	684.805149	210.868106
	0.462503							
18	Ag	Si	400.000000	No	Yes	4519.556190	3553.215004	1232.690853
	0.884459							
19	Ag	a-C	400.000000	Yes	Yes	265.907327	176.677818	588.391400

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

19	0.446724							
20	Ag	Graphite(o)	400.000000	No	Yes	583.889545	344.945243	760.702089
	0.410473							
21	Ag	Graphite(e)	400.000000	Yes	Yes	179.646583	130.678677	247.270231
	0.935238							
22	# Substrate	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
	Reflectivity							
23	Ag	SiO2	400.000000	Yes	Yes	194.914719	136.149767	279.201465
	0.956357							
24	Ag	Al2O3	400.000000	Yes	Yes	119.118763	101.021547	140.537571
	0.954188							
25	Ag	Diamond	400.000000	No	Yes	1128.446049	1039.495577	1321.801418
	0.954136							
26	Ag	GaAs	400.000000	No	Yes	1671.291273	755.107346	215.488686
	0.497081							
27	Ag	InP	400.000000	No	Yes	1702.477020	832.139846	273.004495
	0.553983							
28	Ag	GaP	400.000000	No	Yes	3106.181586	2326.561733	2301.152469
	0.866982							
29	Ag	W	400.000000	Yes	Yes	1216.625534	493.749920	189.806594
	0.320412							
30	Au	Air	800.000000	Yes	Yes	783.268357	159.592968	3847.974602
	0.975838							
31	Au	SiC	800.000000	Yes	Yes	258.236513	137.870277	484.160658
	0.949357							
32	Au	Ge	800.000000	Yes	Yes	94.169704	84.972034	105.935279
	0.819283							
33	Au	Si	800.000000	Yes	Yes	143.346551	107.721599	190.961838
	0.938492							
34	Au	ZnO	800.000000	Yes	Yes	374.526164	149.479452	939.307146
	0.957859							
35	Au	a-C	800.000000	Yes	Yes	398.131757	153.602086	1306.182936
	0.541274							
36	Au	Graphite(o)	800.000000	Yes	Yes	308.665089	159.010491	1388.895191
	0.332887							
37	Au	SiO2	800.000000	Yes	Yes	525.860605	155.707187	1777.695621
	0.966533							

09/29/15

AllSPPactiveInterfaces.dat

3

38	Au	Al2O3	800.000000	Yes	Yes	424.384628	152.180607	1184.635567
	0.961046							
39	Au	Diamond	800.000000	Yes	Yes	290.168522	142.140658	592.935013
	0.951787							
40	Au	H2O	800.000000	Yes	Yes	579.721697	156.929474	2143.677140
	0.968957							
41	Au	GaAs	800.000000	Yes	Yes	145.378497	108.703864	195.010562
	0.900557							
42	Au	InP	800.000000	Yes	Yes	167.838999	117.419653	242.000093
	0.840522							
43	# Substrate	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
	Reflectivity							
44	Au	GaP	800.000000	Yes	Yes	190.530436	123.907213	293.262911
	0.944423							
45	Au	W	800.000000	Yes	Yes	396.553031	190.468766	1095.191382
	0.214487							
46	Au	Si	400.000000	No	Yes	241.417826	374.724825	2635.033672
	0.350290							
47	Au	Graphite(e)	400.000000	No	Yes	263.821921	179.198503	635.982574
	0.291021							
48	Au	SiO2	400.000000	No	Yes	271.807806	179.429931	657.447412
	0.306386							
49	Au	Al2O3	400.000000	No	Yes	231.753782	175.324116	501.466188
	0.271740							
50	Au	Diamond	400.000000	No	Yes	200.373830	182.951455	401.363299
	0.249264							
51	Au	GaP	400.000000	No	Yes	225.910156	282.865224	921.390907
	0.276800							
52	Al	Air	800.000000	Yes	Yes	795.748463	96.081920	7296.539157
	0.868184							
53	Al	SiC	800.000000	Yes	Yes	294.197128	92.358017	1037.641673
	0.706768							
54	Al	Ge	800.000000	Yes	Yes	155.934064	84.482422	337.142658
	0.521466							
55	Al	Si	800.000000	Yes	Yes	201.502098	88.165061	510.697883
	0.632731							
56	Al	ZnO	800.000000	Yes	Yes	400.065323	94.275993	1879.655673

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

56	0.764755								
57	Al	a-C	800.000000	Yes	Yes	411.411391	95.468139	3580.731357	
	0.540164								
58	Al	SiO2	800.000000	Yes	Yes	544.302498	95.373276	3439.248133	
	0.816401								
59	Al	Al2O3	800.000000	Yes	Yes	447.062244	94.746081	2335.545086	
	0.784303								
60	Al	Diamond	800.000000	Yes	Yes	322.542311	93.044171	1237.990629	
	0.724547								
61	Al	H2O	800.000000	Yes	Yes	596.492936	95.594202	4120.857524	
	0.830129								
62	Al	GaAs	800.000000	Yes	Yes	203.064442	88.410249	525.131685	
	0.613976								
63	Al	InP	800.000000	Yes	Yes	219.360786	89.666781	622.308660	
	0.595814								
64	#	Substrate	Layer	Wavelength (nm)	OldSPPActive	NewSPPActive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
		Reflectivity							
65	Al	GaP	800.000000	Yes	Yes	237.190476	90.272025	690.144527	
	0.664959								
66	Al	Ge	400.000000	Yes	Yes	159.526123	95.754535	15689.346360	
	0.285343								
67	Al	Si	400.000000	No	Yes	131.633410	113.841975	183.348135	
	0.717171								
68	Al	a-C	400.000000	Yes	Yes	226.515231	80.919388	846.244112	
	0.527440								
69	Al	Graphite(o)	400.000000	Yes	Yes	158.581202	79.595636	518.280630	
	0.377016								
70	Al	Graphite(e)	400.000000	Yes	Yes	247.448762	80.349917	771.334575	
	0.879259								
71	Al	SiO2	400.000000	Yes	Yes	258.953086	80.704762	839.000011	
	0.894510								
72	Al	Al2O3	400.000000	Yes	Yes	207.767746	78.644032	554.255589	
	0.878034								
73	Al	Diamond	400.000000	Yes	Yes	139.688612	72.671734	271.131779	
	0.851085								
74	Al	GaAs	400.000000	Yes	Yes	155.138367	96.905132	2818.151077	
	0.310484								

09/29/15

AllSPPactiveInterfaces.dat

5

75	Al 0.374707	InP	400.000000	Yes	Yes	133.684589	89.644108	464.080976
76	Al 0.721223	GaP	400.000000	Yes	Yes	63.540498	52.870633	78.975781
77	Al 0.187502	W	400.000000	Yes	Yes	197.903146	96.137016	661.981830
78	Ni 0.318123	Si	400.000000	No	Yes	187.146035	230.587716	799.018167
79	Ni 0.383797	Graphite(e)	400.000000	Yes	Yes	255.041141	139.267203	687.766196
80	Ni 0.401900	SiO2	400.000000	Yes	Yes	264.809175	139.852923	725.099554
81	Ni 0.354178	Al2O3	400.000000	Yes	Yes	218.121817	135.147518	512.775322
82	Ni 0.301050	Diamond	400.000000	No	Yes	167.297610	129.735249	326.628982
83	Ni 0.266825	GaP	400.000000	No	Yes	169.866189	174.568975	454.776546
84	Ni 0.741281	Air	800.000000	Yes	Yes	791.022753	160.709305	4693.842343
85	# Substrate Reflectivity	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
86	Ni 0.508909	SiC	800.000000	Yes	Yes	284.904040	145.702190	673.120264
87	Ni 0.360391	Ge	800.000000	No	Yes	178.474544	138.415943	323.478879
88	Ni 0.441941	Si	800.000000	Yes	Yes	196.521827	133.559794	353.558998
89	Ni 0.580010	ZnO	800.000000	Yes	Yes	391.792773	153.092276	1209.489293
90	Ni 0.655386	SiO2	800.000000	Yes	Yes	537.701143	157.657771	2211.142707
91	Ni 0.607269	Al2O3	800.000000	Yes	Yes	439.379109	155.022330	1501.855463
92	Ni 0.529090	Diamond	800.000000	Yes	Yes	313.388900	148.247333	799.870388
93	Ni	H2O	800.000000	Yes	Yes	590.379571	158.601176	2649.617423

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

93	0.677189							
94	Ni	GaAs	800.000000	Yes	Yes	200.719989	135.257228	373.263817
	0.423645							
95	Ni	InP	800.000000	Yes	Yes	219.411953	139.627369	451.035612
	0.402489							
96	Ni	GaP	800.000000	Yes	Yes	228.857897	138.804885	457.553162
	0.467615							
97	Ti	Air	800.000000	Yes	Yes	796.731254	195.790591	5234.003658
	0.621854							
98	Ti	SiC	800.000000	No	Yes	303.512502	179.451888	837.875178
	0.331695							
99	Ti	Ge	800.000000	No	Yes	209.754259	182.955854	533.811922
	0.199665							
100	Ti	Si	800.000000	No	Yes	226.065712	171.745775	504.714462
	0.259829							
101	Ti	ZnO	800.000000	Yes	Yes	404.370260	186.726784	1418.150946
	0.415164							
102	Ti	SiO2	800.000000	Yes	Yes	546.410402	191.978769	2512.601468
	0.508954							
103	Ti	Al2O3	800.000000	Yes	Yes	450.361131	188.879588	1736.949572
	0.448492							
104	Ti	Diamond	800.000000	Yes	Yes	329.907687	181.777348	974.001071
	0.354836							
105	Ti	H2O	800.000000	Yes	Yes	598.224504	193.131974	2992.824332
	0.537016							
106	# Substrate Reflectivity	Layer	Wavelength (nm)	OldSPPActive	NewSPPActive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
107	Ti	GaAs	800.000000	No	Yes	230.003989	173.823872	540.698184
	0.247669							
108	Ti	InP	800.000000	No	Yes	246.560800	177.742495	656.057162
	0.236652							
109	Ti	GaP	800.000000	No	Yes	253.369850	174.224654	609.999568
	0.286037							
110	Ti	Si	400.000000	No	Yes	150.429549	170.974375	506.625470
	0.267612							
111	Ti	Graphite(e)	400.000000	Yes	Yes	256.993129	125.175903	809.155870
	0.407160							

09/29/15

AllSPPactiveInterfaces.dat

7

112	Ti	SiO2	400.000000	Yes	Yes	267.180277	125.632049	855.548550
	0.425854							
113	Ti	Al2O3	400.000000	Yes	Yes	219.556450	122.083276	597.065904
	0.371365							
114	Ti	Diamond	400.000000	No	Yes	163.206868	115.979255	355.072696
	0.301229							
115	Ti	GaP	400.000000	No	Yes	141.405733	135.892986	352.549271
	0.232492							
116	Be	Graphite(e)	400.000000	No	Yes	261.825783	120.574904	1075.317172
	0.392671							
117	Be	SiO2	400.000000	No	Yes	272.150455	120.868886	1132.259178
	0.411366							
118	Be	Al2O3	400.000000	No	Yes	224.817422	118.396358	791.620247
	0.349210							
119	Be	Diamond	400.000000	No	Yes	167.012916	113.592407	463.156653
	0.261281							
120	Cr	Air	800.000000	Yes	Yes	798.975198	226.174803	5179.866199
	0.568313							
121	Cr	SiC	800.000000	No	Yes	312.056641	206.824698	881.702494
	0.270137							
122	Cr	Si	800.000000	No	Yes	240.426002	201.597651	570.805596
	0.207001							
123	Cr	ZnO	800.000000	No	Yes	409.813493	214.790705	1443.651635
	0.351394							
124	Cr	SiO2	800.000000	No	Yes	549.986843	221.231648	2513.089689
	0.447642							
125	Cr	Al2O3	800.000000	No	Yes	455.017569	217.373603	1754.594893
	0.385106							
126	Cr	Diamond	800.000000	No	Yes	337.362257	209.218985	1012.639021
	0.292112							
127	# Substrate	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
	Reflectivity							
128	Cr	H2O	800.000000	Yes	Yes	601.405346	222.705376	2983.318296
	0.477196							
129	Cr	GaAs	800.000000	No	Yes	244.417847	204.211989	616.884685
	0.196261							
130	Cr	GaP	800.000000	No	Yes	265.021754	202.324781	665.892561

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

130	0.228728							
131	Cr	Si	400.000000	No	Yes	157.766392	183.691362	562.565147
	0.274947							
132	Cr	Graphite(e)	400.000000	Yes	Yes	256.934556	129.219195	783.902084
	0.396625							
133	Cr	SiO2	400.000000	Yes	Yes	267.021494	129.702131	827.975722
	0.415190							
134	Cr	Al2O3	400.000000	Yes	Yes	219.639250	125.896852	580.020040
	0.361930							
135	Cr	Diamond	400.000000	No	Yes	164.416338	119.816984	350.495632
	0.295412							
136	Cr	GaP	400.000000	No	Yes	147.295243	144.478206	375.525040
	0.235497							
137	Cu	Air	800.000000	Yes	Yes	784.051198	156.383681	3941.001989
	0.962024							
138	Cu	SiC	800.000000	Yes	Yes	260.672168	136.167578	500.293943
	0.920406							
139	Cu	Ge	800.000000	Yes	Yes	100.055662	88.206233	115.754925
	0.788384							
140	Cu	Si	800.000000	Yes	Yes	148.005381	108.691160	202.093962
	0.904951							
141	Cu	ZnO	800.000000	Yes	Yes	376.181141	146.943069	965.504407
	0.933838							
142	Cu	a-C	800.000000	Yes	Yes	400.059926	150.998730	1372.793053
	0.531777							
143	Cu	Graphite(o)	800.000000	Yes	Yes	307.606553	155.909696	1475.186933
	0.322691							
144	Cu	SiO2	800.000000	Yes	Yes	527.031267	152.751365	1823.043040
	0.947450							
145	Cu	Al2O3	800.000000	Yes	Yes	425.840727	149.460185	1216.404903
	0.938845							
146	Cu	Diamond	800.000000	Yes	Yes	292.323832	140.122549	611.406289
	0.924262							
147	Cu	H2O	800.000000	Yes	Yes	580.782247	153.893279	2197.436136
	0.951246							
148	# Substrate Reflectivity	Layer	Wavelength (nm)	OldSPPActive	NewSPPActive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)

09/29/15

AllSPPactiveInterfaces.dat

9

149	Cu 0.868596	GaAs	800.000000	Yes	Yes	150.303735	109.756233	206.968350
150	Cu 0.811740	InP	800.000000	Yes	Yes	172.397833	117.756384	255.629297
151	Cu 0.912502	GaP	800.000000	Yes	Yes	193.903488	123.324750	305.655020
152	Cu 0.204899	W	800.000000	Yes	Yes	383.880452	184.215238	1126.076896
153	Cu 0.393811	Si	400.000000	No	Yes	257.008022	363.927594	2243.554028
154	Cu 0.355082	Graphite(e)	400.000000	Yes	Yes	253.538795	162.471988	563.354103
155	Cu 0.371492	SiO2	400.000000	Yes	Yes	262.041768	163.032966	588.170213
156	Cu 0.336700	Al2O3	400.000000	No	Yes	219.620666	157.601574	434.634918
157	Cu 0.311787	Diamond	400.000000	No	Yes	187.715336	162.598714	336.311959
158	Cu 0.325204	GaP	400.000000	No	Yes	231.991740	267.269568	800.651910
159	Li 0.928136	Air	800.000000	Yes	Yes	772.008212	204.222668	2935.114659
160	Li 0.867970	SiC	800.000000	Yes	Yes	223.104647	153.972365	325.140522
161	Li 0.754351	Ge	800.000000	No	Yes	466.705917	399.528386	714.781160
162	Li 0.856552	Si	800.000000	Yes	Yes	103.761431	96.442505	112.607966
163	Li 0.883894	ZnO	800.000000	Yes	Yes	350.663000	181.433226	681.632089
164	Li 0.446568	a-C	800.000000	Yes	Yes	405.604888	195.279414	1160.044316
165	Li 0.278297	Graphite(o)	800.000000	Yes	Yes	405.994064	231.306472	17588.414178
166	Li 0.903838	SiO2	800.000000	Yes	Yes	509.005348	195.578307	1332.323005
167	Li	Al2O3	800.000000	Yes	Yes	403.401535	187.614691	872.357325

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

167	0.890863							
168	Li	Diamond	800.000000	Yes	Yes	259.063598	164.249207	410.961275
	0.872051							
169	# Substrate Reflectivity	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
170	Li	H2O	800.000000	Yes	Yes	564.456584	198.311653	1615.839527
	0.909911							
171	Li	GaAs	800.000000	Yes	Yes	119.283752	108.823188	132.705077
	0.820401							
172	Li	InP	800.000000	Yes	Yes	142.673795	122.769223	169.848240
	0.761415							
173	Li	GaP	800.000000	Yes	Yes	143.009188	119.304564	172.437458
	0.861424							
174	Li	W	800.000000	Yes	Yes	598.546063	300.523302	551.002538
	0.196353							
175	Li	Ge	400.000000	No	Yes	995.886914	852.208226	202.746573
	0.438208							
176	Li	Si	400.000000	No	Yes	1152.416449	1785.260019	1485.844979
	0.762895							
177	Li	a-C	400.000000	Yes	Yes	419.918437	290.657978	4784.652737
	0.315959							
178	Li	Graphite(o)	400.000000	No	Yes	692.557126	502.763396	502.208793
	0.338985							
179	Li	Graphite(e)	400.000000	Yes	Yes	183.835012	156.121087	227.119181
	0.682145							
180	Li	SiO2	400.000000	Yes	Yes	182.835106	152.757234	227.367506
	0.699178							
181	Li	Al2O3	400.000000	No	Yes	228.244056	204.139881	277.296244
	0.697964							
182	Li	Diamond	400.000000	No	Yes	599.215815	579.929790	925.121535
	0.716127							
183	Li	GaAs	400.000000	No	Yes	1013.339539	910.085730	208.563525
	0.468001							
184	Li	InP	400.000000	No	Yes	1000.411173	944.357341	264.751662
	0.506354							
185	Li	GaP	400.000000	No	Yes	1018.846415	1261.458918	3858.596422
	0.715933							

09/29/15

AllSPPactiveInterfaces.dat

11

186	Mg	Air	800.000000	Yes	Yes	793.369677	103.363579	6145.899224
	0.952299							
187	Mg	SiC	800.000000	Yes	Yes	287.433233	98.056992	850.350127
	0.889691							
188	Mg	Ge	800.000000	Yes	Yes	139.097449	84.067562	236.640861
	0.745794							
189	Mg	Si	800.000000	Yes	Yes	190.924331	91.623929	401.668422
	0.858746							
190	# Substrate	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
	Reflectivity							
191	Mg	ZnO	800.000000	Yes	Yes	395.221246	100.828657	1563.502294
	0.912558							
192	Mg	a-C	800.000000	Yes	Yes	405.059013	101.838037	2183.211411
	0.614451							
193	Mg	Graphite(o)	800.000000	Yes	Yes	275.863448	101.357192	1564.976867
	0.389633							
194	Mg	SiO2	800.000000	Yes	Yes	540.793109	102.376867	2883.117107
	0.932615							
195	Mg	Al2O3	800.000000	Yes	Yes	442.754380	101.495060	1949.318064
	0.920192							
196	Mg	Diamond	800.000000	Yes	Yes	316.432120	99.058733	1020.165292
	0.896727							
197	Mg	H2O	800.000000	Yes	Yes	593.299714	102.685553	3459.718265
	0.937879							
198	Mg	GaAs	800.000000	Yes	Yes	192.072114	91.810918	407.602930
	0.830655							
199	Mg	InP	800.000000	Yes	Yes	208.623461	93.537029	477.046237
	0.790857							
200	Mg	GaP	800.000000	Yes	Yes	228.538706	94.933652	555.268022
	0.873139							
201	Mg	W	800.000000	Yes	Yes	272.198087	106.485175	7370.956972
	0.243903							
202	Mg	Ge	400.000000	Yes	Yes	312.315653	182.621049	419.740524
	0.337731							
203	Mg	Si	400.000000	No	Yes	701.998680	576.281754	7294.860001
	0.805527							
204	Mg	a-C	400.000000	Yes	Yes	223.209341	104.114280	611.169172

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

204	0.494184							
205	Mg	Graphite(o)	400.000000	Yes	Yes	179.957992	108.763234	539.149879
	0.373733							
206	Mg	Graphite(e)	400.000000	Yes	Yes	235.519117	102.217106	544.728895
	0.913916							
207	Mg	SiO2	400.000000	Yes	Yes	247.570248	103.125060	595.838603
	0.931211							
208	Mg	Al2O3	400.000000	Yes	Yes	193.397583	97.864954	383.151947
	0.922266							
209	Mg	Diamond	400.000000	Yes	Yes	117.321069	81.632659	169.038771
	0.910059							
210	Mg	GaAs	400.000000	No	Yes	324.736669	194.399263	424.420251
	0.369195							
211	#	Substrate Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
		Reflectivity						
212	Mg	InP	400.000000	No	Yes	294.831534	191.137535	884.804252
	0.434584							
213	Mg	GaP	400.000000	No	Yes	236.181074	203.465887	328.007390
	0.795975							
214	Mg	W	400.000000	Yes	Yes	318.892241	158.695090	329.050688
	0.213871							
215	Na	Air	800.000000	Yes	Yes	766.966179	218.171565	2696.626460
	0.987058							
216	Na	SiC	800.000000	Yes	Yes	203.504180	151.711474	273.020193
	0.976558							
217	Na	Ge	800.000000	No	Yes	1413.140489	1097.286807	3982.759627
	0.856642							
218	Na	Si	800.000000	No	Yes	491.836777	471.151234	518.385341
	0.972159							
219	Na	ZnO	800.000000	Yes	Yes	339.108993	188.971056	608.625072
	0.979171							
220	Na	a-C	800.000000	Yes	Yes	395.897127	205.042107	971.410044
	0.485547							
221	Na	Graphite(o)	800.000000	Yes	Yes	455.950538	262.424652	29537.406046
	0.321802							
222	Na	SiO2	800.000000	Yes	Yes	501.254310	207.218937	1212.699818
	0.982675							

09/29/15

AllSPPactiveInterfaces.dat

13

223	Na	Al2O3	800.000000	Yes	Yes	393.481733	197.002087	786.040344
	0.980379							
224	Na	Diamond	800.000000	Yes	Yes	242.741061	166.032432	354.944199
	0.977196							
225	Na	H2O	800.000000	Yes	Yes	557.498105	210.696375	1475.354007
	0.983764							
226	Na	GaAs	800.000000	No	Yes	242.877060	229.939567	259.883030
	0.931287							
227	Na	InP	800.000000	Yes	Yes	117.299075	109.043925	127.379040
	0.863759							
228	Na	GaP	800.000000	Yes	Yes	105.289842	95.592318	115.988970
	0.975663							
229	Na	W	800.000000	Yes	Yes	772.114481	359.156733	494.194925
	0.238278							
230	Na	Ge	400.000000	No	Yes	2600.826902	1355.611370	194.111298
	0.537997							
231	Na	Si	400.000000	No	Yes	4124.115440	5202.306927	1156.039906
	0.884749							
232	# Substrate Reflectivity	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
233	Na	a-C	400.000000	No	Yes	587.181849	389.691085	8987.336116
	0.426355							
234	Na	Graphite(o)	400.000000	No	Yes	1404.594168	787.006247	425.179037
	0.449704							
235	Na	Graphite(e)	400.000000	No	Yes	158.554779	149.571876	169.963024
	0.879284							
236	Na	SiO2	400.000000	Yes	Yes	107.736093	102.154556	114.069860
	0.899611							
237	Na	Al2O3	400.000000	No	Yes	841.712774	772.519843	1009.090317
	0.901006							
238	Na	Diamond	400.000000	No	Yes	2516.834040	2535.829950	4134.713959
	0.910184							
239	Na	GaAs	400.000000	No	Yes	2731.065284	1484.626136	199.598069
	0.569497							
240	Na	InP	400.000000	No	Yes	2768.052659	1638.192621	249.538718
	0.615197							
241	Na	GaP	400.000000	No	Yes	3566.747144	3729.373224	1844.875111

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

241	0.860882							
242	Na	W	400.000000	No	Yes	2220.566549	978.333872	171.902812
	0.405210							
243	Bi	Air	800.000000	Yes	Yes	795.129880	206.570633	4711.870301
	0.611670							
244	Bi	SiC	800.000000	No	Yes	301.897190	186.992628	760.611256
	0.330194							
245	Bi	Ge	800.000000	No	Yes	220.562656	197.621546	540.147201
	0.215457							
246	Bi	Si	800.000000	No	Yes	228.660386	180.063733	475.372748
	0.268683							
247	Bi	ZnO	800.000000	Yes	Yes	402.095566	195.484717	1278.163446
	0.408083							
248	Bi	SiO2	800.000000	Yes	Yes	544.320083	201.871154	2261.634678
	0.499160							
249	Bi	Al2O3	800.000000	Yes	Yes	448.102255	198.086297	1564.249504
	0.440123							
250	Bi	Diamond	800.000000	Yes	Yes	327.939160	189.637868	881.260792
	0.351354							
251	Bi	H2O	800.000000	Yes	Yes	596.244142	203.288628	2693.798065
	0.526884							
252	Bi	GaAs	800.000000	No	Yes	233.141028	182.541319	510.209294
	0.255667							
253	# Substrate Reflectivity	Layer	Wavelength (nm)	OldSPPActive	NewSPPActive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
254	Bi	InP	800.000000	No	Yes	249.547313	186.586832	614.545654
	0.241251							
255	Bi	GaP	800.000000	No	Yes	253.462115	181.581172	562.117421
	0.290093							
256	Bi	Si	400.000000	No	Yes	221.072465	313.055413	1532.224203
	0.337434							
257	Bi	Graphite(e)	400.000000	No	Yes	258.983675	162.463689	644.743134
	0.325111							
258	Bi	SiO2	400.000000	Yes	Yes	267.789950	162.951951	672.445663
	0.341722							
259	Bi	Al2O3	400.000000	No	Yes	224.521475	158.023927	495.259524
	0.301428							

09/29/15

AllSPPactiveInterfaces.dat

15

260	Bi	Diamond	400.000000	No	Yes	184.896748	158.783228	361.234241
	0.266682							
261	Bi	GaP	400.000000	No	Yes	204.210711	236.019901	692.152502
	0.271423							
262	Pt	Air	800.000000	Yes	Yes	794.069357	158.816254	5288.051799
	0.710592							
263	Pt	SiC	800.000000	Yes	Yes	293.094171	146.384647	784.184096
	0.451567							
264	Pt	Ge	800.000000	No	Yes	183.045359	139.849031	381.631746
	0.292907							
265	Pt	Si	800.000000	Yes	Yes	206.902045	136.858357	424.219188
	0.373518							
266	Pt	ZnO	800.000000	Yes	Yes	397.889267	152.398151	1384.865049
	0.531664							
267	Pt	SiO2	800.000000	Yes	Yes	542.173131	156.218145	2506.754015
	0.615451							
268	Pt	Al2O3	800.000000	Yes	Yes	444.833767	154.003186	1712.292952
	0.562040							
269	Pt	Diamond	800.000000	Yes	Yes	320.911628	148.432441	926.161577
	0.474486							
270	Pt	H2O	800.000000	Yes	Yes	594.456021	157.017554	2997.930982
	0.639608							
271	Pt	GaAs	800.000000	Yes	Yes	210.536612	138.276691	448.438400
	0.358240							
272	Pt	InP	800.000000	Yes	Yes	228.252609	141.882728	542.399850
	0.343895							
273	Pt	GaP	800.000000	Yes	Yes	238.576555	140.942953	542.204791
	0.403799							
274	# Substrate	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
	Reflectivity							
275	Pt	Si	400.000000	No	Yes	175.282606	200.545886	618.118829
	0.326473							
276	Pt	Graphite(e)	400.000000	Yes	Yes	252.902854	127.895307	697.720441
	0.427055							
277	Pt	SiO2	400.000000	Yes	Yes	263.043970	128.477825	739.506800
	0.445683							
278	Pt	Al2O3	400.000000	Yes	Yes	215.090244	124.104102	514.144694

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

278	0.396310						
279	Pt	Diamond	400.000000	No	Yes	160.042625	117.269078
	0.336857						308.860129
280	Pt	GaP	400.000000	No	Yes	156.019924	150.865907
	0.283274						371.407652
281	Ta	Air	800.000000	Yes	Yes	775.803610	221.325741
	0.731696						2996.810594
282	Ta	SiC	800.000000	Yes	Yes	253.667779	177.380644
	0.552597						402.152431
283	Ta	Ge	800.000000	No	Yes	313.218138	280.728136
	0.474182						580.751013
284	Ta	Si	800.000000	No	Yes	213.887136	182.644033
	0.531591						293.766190
285	Ta	ZnO	800.000000	Yes	Yes	363.539963	197.884160
	0.595667						736.835284
286	Ta	a-C	800.000000	Yes	Yes	444.751626	221.040152
	0.283048						2111.618093
287	Ta	SiO2	800.000000	Yes	Yes	515.863413	211.906134
	0.654304						1384.242069
288	Ta	Al2O3	800.000000	Yes	Yes	413.444915	203.774873
	0.615633						925.016666
289	Ta	Diamond	800.000000	Yes	Yes	281.920891	183.842140
	0.563221						478.113376
290	Ta	H2O	800.000000	Yes	Yes	570.317287	214.822777
	0.673046						1668.776488
291	Ta	GaAs	800.000000	No	Yes	222.167169	187.392490
	0.508038						317.055634
292	Ta	InP	800.000000	No	Yes	231.935180	187.106203
	0.469500						355.164236
293	Ta	GaP	800.000000	Yes	Yes	210.459852	168.336082
	0.536741						296.408267
294	Ta	Si	400.000000	No	Yes	226.889708	300.031824
	0.366680						1333.891349
295	# Substrate	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)
	Reflectivity						DecayDepth2 (nm)
296	Ta	Graphite(e)	400.000000	Yes	Yes	253.029640	151.149290
	0.372209						602.640865

09/29/15

AllSPPactiveInterfaces.dat

17

297	Ta 0.389521	SiO2	400.000000	Yes	Yes	262.240788	151.801200	632.949031
298	Ta 0.348997	Al2O3	400.000000	Yes	Yes	217.199875	146.279773	455.661589
299	Ta 0.311851	Diamond	400.000000	No	Yes	175.117934	144.632336	318.481308
300	Ta 0.304810	GaP	400.000000	No	Yes	203.424017	221.369266	608.292748
301	V 0.544624	Air	800.000000	No	Yes	800.341572	241.713666	5204.108480
302	V 0.244427	SiC	800.000000	No	Yes	316.684743	221.132984	913.749914
303	V 0.185387	Si	800.000000	No	Yes	247.360036	217.390051	609.871243
304	V 0.324251	ZnO	800.000000	No	Yes	412.938296	229.247060	1472.131492
305	V 0.421055	SiO2	800.000000	No	Yes	552.113347	236.211042	2539.283225
306	V 0.357940	Al2O3	800.000000	No	Yes	457.730642	232.007431	1782.133402
307	V 0.265767	Diamond	800.000000	No	Yes	341.483311	223.488560	1043.451478
308	V 0.451121	H2O	800.000000	No	Yes	603.310502	237.838902	3008.988984
309	V 0.205084	GaP	800.000000	No	Yes	270.970955	217.175209	701.419263
310	V 0.428665	Graphite(e)	400.000000	Yes	Yes	261.108297	109.548390	1147.950166
311	V 0.447379	SiO2	400.000000	Yes	Yes	271.593226	109.796448	1211.903755
312	V 0.384205	Al2O3	400.000000	No	Yes	223.881634	107.787207	840.835850
313	V 0.290521	Diamond	400.000000	No	Yes	164.791382	103.524826	479.726719
314	W 0.237253	Ag	800.000000	Yes	Yes	337.678426	2146.856890	156.734863
315	W	Au	800.000000	Yes	Yes	396.553031	1095.191382	190.468766

/home/thibault/Documents/Codes/SPP-extended-theory/SimpleSPP/AllSPPactiveInterfaces.dat

315	0.214487							
316	# Substrate	Layer	Wavelength (nm)	OldSPPactive	NewSPPactive	Period (nm)	DecayDepth1 (nm)	DecayDepth2 (nm)
	Reflectivity							
317	W	Cu	800.000000	Yes	Yes	383.880452	1126.076896	184.215238
	0.204899							
318	W	Li	800.000000	Yes	Yes	598.546063	551.002538	300.523302
	0.196353							
319	W	Mg	800.000000	Yes	Yes	272.198087	7370.956972	106.485175
	0.243903							
320	W	Na	800.000000	Yes	Yes	772.114481	494.194925	359.156733
	0.238278							
321	W	Ag	400.000000	Yes	Yes	1216.625534	189.806594	493.749920
	0.320412							
322	W	Al	400.000000	Yes	Yes	197.903146	661.981830	96.137016
	0.187502							
323	W	Mg	400.000000	Yes	Yes	318.892241	329.050688	158.695090
	0.213871							
324	W	Na	400.000000	Yes	Yes	2220.566549	171.902812	978.333872
	0.405210							
325								