


Computational Absorbance Scaling Factors




K3NbO8
R:213
G:186
B:173

Expt. $L^*:77.33$ $a^*:3.3$ $b^*:14.62$

Sim. $L^*:77.4$ $a^*:7.56$ $b^*:9.97$

$\Delta E^* = 6.31$




Rb3NbO8
R:214
G:188
B:177

Expt. $L^*:78.01$ $a^*:3.54$ $b^*:14.62$

Sim. $L^*:78.17$ $a^*:7.44$ $b^*:9.02$

$\Delta E^* = 6.83$



Cs₃NbO₈
R:200
G:166
B:148

Expt. L*:66.9 a*:3.64 b*:8.29

Sim. L*:70.6 a*:9.98 b*:13.95

$\Delta E^* = 9.27$