## 1

A cylindrical specimen of a titanium alloy having an elastic modulus of 107 GPa (15.5 x 106 psi) and an original diameter of 3.8 mm (0.15 in.) experiences only elastic deformation when a tensile load of 2000 N (450 lbf) is applied. Compute the maximum length of the specimen before deformation if the maximum allowable elongation is 0.42 mm (0.0165 in.).

```
 E = 107 \ GPa 
 A_0 = 3.61\pi \ mm^2 
 F_y = 2 \ kN 
 \Delta L_y = 0.42 \ mm 
 \sigma_y = \frac{F_y}{A_0} = \frac{2}{3.61\pi} \ GPa 
 \epsilon_y = \frac{\Delta L_y}{L_0} = \frac{0.42}{L_0} 
 E = \frac{\sigma_y}{\epsilon_y} = \frac{2L_0}{(0.42)3.61\pi} = 107 \ GPa 
 L_0 = \frac{107(0.42)3.61\pi}{2} \ mm = 254.84 \ mm
```

### 2

A cylindrical specimen of aluminum having a diameter of 0.505 in. (12.8 mm) and a gauge length of 2.000 in. (50.800 mm) is pulled in tension. Use the load–elongation characteristics shown in the following table to complete parts (a) through (f).

```
-tx-

| Load || Length ||

| N | Ibf | mm | in. |

| ----- | ----- | ------ |

| 0 | 0 | 50.800 | 2.000 |

| 7330 | 1650 | 50.851 | 2.002 |

| 15100 | 3400 | 50.902 | 2.004 |

| 23100 | 5200 | 50.952 | 2.006 |

| 30400 | 6850 | 51.003 | 2.008 |

| 34400 | 7750 | 51.054 | 2.010 |
```

```
| 38400 | 8650 | 51.308 | 2.020 |

| 41300 | 9300 | 51.816 | 2.040 |

| 44800 | 10100 | 52.832 | 2.080 |

| 46200 | 10400 | 53.848 | 2.120 |

| 47300 | 10650 | 54.864 | 2.160 |

| 47500 | 10700 | 55.880 | 2.200 |

| 46100 | 10400 | 56.896 | 2.240 |

| 44800 | 10100 | 57.658 | 2.270 |

| 42600 | 9600 | 58.420 | 2.300 |

| 36400 | 8200 | 59.182 | 2.330 |

| Fracture ||||
```

#### a

Plot the data as engineering stress versus engineering strain.

```
✓ Answer
 let d = 12.8
 let l = 50.8
 let data = [
          [0, 50.8],
          [7330, 50.851],
          [15100, 50.902],
          [23100, 50.952],
          [30400, 51.003],
          [34400, 51.054],
          [38400, 51.308],
          [41300, 51.816],
          [44800, 52.832],
          [46200, 53.848],
          [47300, 54.864],
          [47500, 55.880],
          [46100, 56.896],
          [44800, 57.658],
          [42600, 58.420],
          [36400, 59.182]
 ]
 let a = Math.pow(d/2,2) * Math.PI
 let epsi = data.map(i \Rightarrow [(i[1]-l)/l, i[0]/a/1000])
 let renderObj = {
          data: [
                  {
                           points: epsi,
```

```
fnType: 'points',
                              graphType: 'polyline',
                    }
          ],
          xAxis: {
                    label: "Strain",
                    domain: [
                              Math.min(...epsi.map(a \Rightarrow a[0])),
                              Math.max(...epsi.map(a \Rightarrow a[0])),
                    ]
          },
          yAxis: {
                    label: "Strength (GPa)",
                    domain: [
                              Math.min(...epsi.map(a \Rightarrow a[1])),
                              Math.max(...epsi.map(a \Rightarrow a[1])),
                    ]
          }
}
console.log(JSON.stringify(renderObj))
8.0 Strength (GPa)
0.35
0.25
 0.2
0.15
 0.1
0.05
                                                                        Strain
          0.02
                   0.04
                            0.06
                                     0.08
                                              0.1
                                                      0.12
                                                               0.14
                                                                        0.16
```

# b

Compute the modulus of elasticity.



```
let d = 12.8
  let l = 50.8
  let data = [
          [0, 50.8],
          [7330, 50.851],
          [15100, 50.902],
          [23100, 50.952],
          [30400, 51.003],
          [34400, 51.054],
          [38400, 51.308],
          [41300, 51.816],
          [44800, 52.832],
          [46200, 53.848],
          [47300, 54.864],
          [47500, 55.880],
          [46100, 56.896],
          [44800, 57.658],
          [42600, 58.420],
          [36400, 59.182]
  ]
 let a = Math.pow(d/2,2) * Math.PI
  let epsi = data.map(i \Rightarrow [(i[1]-l)/l, i[0]/a/1000])
  let e = Math.max(...epsi.slice(1).map(i \Rightarrow i[1]/i[0]))
  console.log(e)
   59.995998220175025
E = 59.995998220175025 \; GPa
```

### C

Determine the yield strength at a strain offset of 0.002.

```
Answer

let d = 12.8
let l = 50.8
let data = [
       [0, 50.8],
       [7330, 50.851],
```

```
[15100, 50.902],
          [23100, 50.952],
          [30400, 51.003],
          [34400, 51.054],
          [38400, 51.308],
          [41300, 51.816],
          [44800, 52.832],
          [46200, 53.848],
          [47300, 54.864],
          [47500, 55.880],
          [46100, 56.896],
          [44800, 57.658],
          [42600, 58.420],
          [36400, 59.182]
 1
 let a = Math.pow(d/2,2) * Math.PI
 let epsi = data.map(i \Rightarrow [(i[1]-l)/l, i[0]/a/1000])
 let e = 59.995998220175025
 let x = 0.002
 let mapped = epsi.map(i \Rightarrow [i[0]-(i[1]/e), i[1]])
 let bounds = mapped.reduce((i, j) \Rightarrow i.length = 0 | j[0] < x ? [j]
 : i.length < 2 & j[0] \ge x ? [...i, j] : i, [] as number[][])
 let pos = (x - bounds[0][0]) / (bounds[1][0] - bounds[0][0]) *
 (bounds[1][1] - bounds[0][1]) + bounds[0][1]
 console.log(pos)
   0.27742759187638605
Y_u = 0.27742759187638605 \; GPa
```

### d

Determine the tensile strength of this alloy.

```
let d = 12.8
let l = 50.8
let data = [
```

```
[0, 50.8],
          [7330, 50.851],
          [15100, 50.902],
          [23100, 50.952],
          [30400, 51.003],
          [34400, 51.054],
          [38400, 51.308],
          [41300, 51.816],
          [44800, 52.832],
          [46200, 53.848],
          [47300, 54.864],
          [47500, 55.880],
          [46100, 56.896],
          [44800, 57.658],
          [42600, 58.420],
          [36400, 59.182]
 ]
 let a = Math.pow(d/2,2) * Math.PI
 let epsi = data.map(i \Rightarrow [(i[1]-l)/l, i[0]/a/1000])
 let max = Math.max(...epsi.map(i \Rightarrow i[1]))
 console.log(max)
   0.3691337791438002
\sigma_U = 0.3691337791438002 \; GPa
```

### e

What is the approximate ductility, in percent elongation?

```
✓ Answer

let e = 59.995998220175025
let y = 0.27742759187638605

console.log(Math.pow(y,2) / (2*e))


16.50%
```

## f

Compute the modulus of resilience.

# 3

A cylindrical specimen of a brass alloy 7.5 mm (0.30 in.) in diameter and 90.0 mm (3.54 in.) long is pulled in tension with a force of 6000 N (1350 lbf); the force is subsequently released.



Compute the final length of the specimen at this time. The tensile stress—strain behavior for this alloy is shown in the Figure.

### ✓ Answer

$$rac{6\ kN}{(rac{7.5}{2})^2\pi\ mm^2}=0.136\ GPa$$

The force remains within the elastic limit.

$$L_f = 90.0 \ mm$$

### b

Compute the final specimen length when the load is increased to 16,500 N (3700 lbf) and then released.

#### ✓ Answer


$$rac{16.5 \ kN}{(rac{7.5}{2})^2 \pi \ mm^2} = 0.373 \ GPa$$

The force does not remain within the elastic limit.

$$L_f = 90.0 * (1 + 0.08) \ mm = 97.2 \ mm$$

### 4

From the stress–strain data for poly(methyl methacrylate) shown in the Figure, determine the modulus of elasticity and tensile strength at room temperature [20°C (68°F)], and compare these values with those given in Tables below



Reprinted by permission from T. S. Carswell and H. K. Nason, "Effect of Environmental Conditions on the Mechanical Properties of Organic Plastics," in *Symposium on Plastics*. Copyright ASTM International, West Conshohocken, PA.

-tx-| | Modulus of Elasticity | | | | Material | GPa |  $10^6$  psi | Poisson's Ratio | ------| Phenol-formaldehyde | 2.76-4.83 | 0.40-0.70 | — | | Poly(vinyl chloride) (PVC) | 2.41-4.14 | 0.35-0.60 | 0.38 | | Poly(ethylene terephthalate) (PET) | 2.76-4.14 | 0.40-0.60 | 0.33 | | Polystyrene (PS) | 2.28-3.28 | 0.33-0.48 | 0.33 | | Poly(methyl methacrylate) (PMMA) | 2.24-3.24 | 0.33-0.47 | 0.37-0.44 | -tx-| | Yield Strength | Tensile Strength | | | | Material | MPa | ksi | MPa | ksi | Ductility, %EL [in 50mm (2 in.)] | ----- | | Nylon 6,6 | 44.8-82.8 | 6.5-12 | 75.9-94.5 | 11.0-13.7 | 15-300 | | Polycarbonate (PC) | 62.1 | 9.0 | 62.8-72.4 | 9.1-10.5 | 110-150 | | Poly(ethylene terephthalate) (PET) | 59.3 | 8.6 | 48.3-72.4 | 7.0-10.5 | 30-300 | | Poly(methyl methacrylate) (PMMA) | 53.8-73.1 | 7.8-10.6 | 48.3-72.4 | 7.0-10.5 | 2.0-5.5 |

#### ✓ Answer

$$E=rac{40}{0.02}=2~GPa \ \sigma_U=53~MPa$$

My estimated values line up very closely with the table values of E=2.24~GPa and  $\sigma_U=53.8~MPa$ 

# 5

Find a reference on the internet that gives a value for the tensile strength of optical glass fiber made from silica.



https://www.sciencedirect.com/science/article/pii/S0022309313004171

"estimated strengths of  $\sim 7-8~GPa$ "