Modeling electrical losses in CsPbI3 solar cells: stacked idealizations and a routine-quality interval at 18.0%

Hussain Touhid Siddiquee* Md. Abdul Malek Fahim

Stacked idealisations inflate SCAPS-1D CsPbI3 projections. On one fully worked CsPbI3/CBTS stack, joint optimisation of thickness, doping, defects, gap, and both transport-layer affinities gives a permissive-box ceiling of **24.95%**. Sampling a frozen routine-quality prior volume gives a median of **18.0%** with a 5–95% envelope of **15.6–20.0%**. The 2024–2026 experimental records fall above that envelope. The record comparison is density-of-states conditional: with capped density of states, literature radiative recombination lowers the ceiling to 21.86%, below the 22.02% certified record; with physical density of states, the same radiative term gives 23.46/23.04%, above it. Interface sensitivity is regime dependent, bulk defects dominate at routine defect density, and the six-point fill-factor gap against measured devices remains unexplained.

Keywords: CsPbI3; perovskite solar cell; SCAPS-1D; CBTS; reproducibility; device simulation

1.0 Introduction

All-inorganic CsPbI3 combines improved thermal stability with a bandgap near 1.7 eV, suitable for single-junction and tandem top-cell use [1, 2]. Buried-interface engineering carried laboratory efficiencies past 20% in 2024 [3] and past 22% in 2025–2026: 22.60% laboratory and 22.02% certified by moisture-responsive crystallisation [1], 22.05% by fluorinated interfacial dipoles [2], 21.71% with dual-interface and bulk co-passivation at 1.27 V [4], and 21.43% certified for inverted cells [5]. Each advance came from defect and interface control.

SCAPS-1D is widely used for pre-experimental screening. The ITO/TiO2/CsPbI3/CBTS stack of Hossain et al. [6] progressed from 17.90% over 96 transport-layer combinations [7] to 19.06% after optimisation. Later simulation reports reach 24.17% on the same stack [8] and 24.24% on ZnO/PTAA without interface layers [9]. Three recurring problems accompany this inflation. First, one-variable-at-a-time optimisation hides interactions among thickness, doping, defects, gap, and alignment. Second, interface and defect assumptions are often incompletely reported. Third, scripted SCAPS sweeps can mix unit systems and silently alter defect populations.

A survey of more than 250 SCAPS perovskite architectures attributes much of this inflation to unrealistic inputs, especially the zero radiative-recombination default, unphysical defect floors and mobilities, isolated optimisation, and optical defaults [10]. A companion optical-loss framework implements the wavelength-dependent half of that protocol [11]. This paper implements the electrical-loss half on one stack: factorial screening, priced radiative, mobility, resistance, contact, affinity, and density-of-states assumptions, and a routine-quality sensitivity envelope.

This work contributes a five-factor guardrailed screen and joint affinity map locating the ceiling at 24.95%; priced single-assumption corrections; stacked realistic variants; a measured-grade calibration ladder; a 95-run routine-quality envelope with a separate radiative sensitivity subset; interface dose–response in portable lifetime/velocity metrics; and a range-dependent Morris analysis.

*Department of EEE, Leading University, Sylhet-3112, Bangladesh. E-mail: touhidsiddiqueeraj@gmail.com, mdabdulmalekfahim@gmail.com.

2.0 Literature: CsPbI3 progress and simulation inflation

Black-phase CsPbI3 progressed from 10.8% quantum-dot films through γ-films and graded-gap devices [12–14]. Compositional engineering continued this rise [15, 16]. The 18.4% β-phase result then stood until buried-interface work reached 20.6%, 20.1% stabilised [3, 17]. The 2025–2026 interface wave is shown in Figure 1.




Figure 1: CsPbI3 record race. Open symbols are simulations; the star and band are this work's ceiling and envelope.

Table 1: Selected CsPbI3 results: experiment versus simulation. Our entry is flagged, not ranked: *permissive-box ceiling; the defended envelope median is 18.0% with 5–95% range 15.6–20.0%. Certified values are marked ^{c}; other experimental values are laboratory-reported.

Study	Stack	Type	PCE (%)	IF
Swarnkar 2016	TiO2/Spiro/MoOx	Exp.	10.8 [12]	–
Wang 2019	TiO2/Spiro	Exp.	18.4 [17]	–
Shah et al. 2024	TiO2/2D-Cs2PbI2Cl2	Exp.	20.6 (20.1 stab.) [3]	buried-passivated
Qiu 2025	CsPbI3 + DFAz dipole	Exp.	22.05 [2]	passivated
Zhang 2026	TiO2 dual-interface+bulk	Exp.	21.71 [4]	co-passivated
Dai 2026	TiO2/PTABr/Spiro	Exp.	22.60 lab / 22.02^{c} [1]	passivated
Hu 2026 (Joule)	inverted HPDA	Exp.	21.43^{c} [5]	2D-stitched
Hossain 2022	TiO2/CBTS	Sim.	17.90 [7]	on
Hossain 2023	TiO2/CBTS/Ni	Sim.	19.06 [6]	on
Nazli 2025	TiO2/CBTS/Ni	Sim.	24.17 [8]	unclear
Oyedele 2023	ZnO/PTAA	Sim.	24.24 [9]	OFF
This work*	TiO2/CBTS/Ni	Sim.	24.95	on

The simulation studies trace a parallel inflation curve. The CBTS programme reached 17.90% and 19.06% [6, 7], the re-parameterised baseline used here. Later claims report higher values on different stacks or with unclear interface treatment. Because several published parameter tables are incomplete, other groups' cells are compared as reported, not re-placed on our curve.

Table 2: Layer input parameters for the re-parameterised baseline. Screening subsequently moves ETL doping to 9×10^{17} cm^{-3} and explores ETL affinity; the ceiling values are in Table 6.

Layer	d	E_g	χ	ε_r	Doping	N_t	μ_n/μ_p
CBTS HTL	100 nm	1.9	3.6	5.4	N_A 1e18	1e15	30/30
CsPbI3	800 nm	1.694	3.95	6.0	N_A 1e15	1e15	25/25
TiO2 ETL	30 nm	3.2	4.0	9.0	N_D 9e16	1e15	20/20

Table 3: Interface defect layers at both heterojunctions: neutral single level, $\sigma = 10^{-19}$ m^2, $E_t = 0.6$ eV.

Interface	N (cm^{-2})	Sweep range
CBTS/CsPbI3	1e10	10^8–10^{12}
CsPbI3/TiO2	1e10	10^8–10^{12}

3.0 Numerical simulations

3.1 SCAPS-1D model

SCAPS-1D solves Poisson's equation with electron and hole continuity under drift-diffusion transport [18–20]:

$$-\frac{\partial}{\partial x}\left(\varepsilon(x)\frac{\partial V}{\partial x}\right) = q[p - n + N_D^+ - N_A^- + p_t - n_t], \tag{1}$$

$$\frac{\partial n}{\partial t} = \frac{1}{q}\frac{\partial J_n}{\partial x} + G_n - R_n, \quad \frac{\partial p}{\partial t} = -\frac{1}{q}\frac{\partial J_p}{\partial x} + G_p - R_p, \tag{2}$$

$$J_n = q\mu_n nE + qD_n\nabla n, \quad J_p = q\mu_p pE - qD_p\nabla p, \tag{3}$$

with Shockley–Read–Hall recombination through the specified bulk and interface defect levels. Optical generation uses the Eg-sqrt model, $\alpha = A\sqrt{h\nu - E_g}$, so gap sweeps move the absorption edge rather than using a frozen spectrum.

3.2 Device structure and re-parameterised baseline

Devices were simulated under AM1.5G illumination at 100 mW/cm^2 and 300 K unless stated. The starting point reproduces Hossain et al. [6]: ITO, 30 nm TiO2, CsPbI3, 100 nm CBTS, and Ni. Neutral interface recombination blocks are present at both heterojunctions. The absorber uses the edge-moving absorption model. This is therefore a re-parameterised baseline, not an unmodified copy: interfaces were added and the density-of-states treatment is stated explicitly.

The re-parameterised baseline gives 18.99% (Voc 1.122 V, Jsc 19.68 mA/cm^2, FF 86.00%), within the published 17.9–19.06% band. Doping and defect floors remain modelling choices; measured doping is far lower [21]. Using the source paper's printed density of states instead gives 16.76%, so baseline replication depends materially on that choice.

3.3 Guardrails and simulation bases

Guardrails are part of the stated simulation box, not post-hoc filters. The bulk floor is 10^{12} cm^{-3} and the interface floor is 10^{10} cm^{-2}; points below the interface floor are audit points. Energetic screens reject Voc above the radiative bound or fill factor above Green's ideal-diode value.

Five bases recur in the paper and are defined once in Table 5.

Table 4: Guardrails and their anchors. "Assumption" means a modelling choice without a direct measurement behind it.

Guardrail	Value	Anchor
Bulk defect floor	$N_t = 10^{12}$ cm^{-3}	beyond-best-film lifetime guardrail
Interface floor	$N_{if} = 10^{10}$ cm^{-2}	assumption; demanding passivation regime
Capture cross-section	$\sigma = 10^{-19}$ m^2	assumption; swept $\times 0.1$–$\times 10$
Radiative coefficient	$k_{rad} = 0$, priced	assumption; literature bracket tested
Mobilities	25/25 absorber, priced	assumption; DFT-grade values tested
Parasitics	scripted R_s/R_{sh}	computed, not assumed zero
Contacts and affinities	stated and priced	surveyed versus adopted values separated
Optics	flat 10% reflection, edge-moving absorption	upper-envelope blue response; uncertainty carried
Screens	model-derived Voc and ideal-FF bounds	automated receipt gates; see Supplement

Table 5: Simulation bases. Absorber affinity follows $\chi = 3.95 + 0.5(E_g - 1.694)$ unless a transport-layer affinity adoption is stated.

Base	Definition	Carries
Surveyed	Hossain parameters: $\chi_{\mathrm{CBTS}} = 3.6$, $\chi_{\mathrm{TiO2}} = 4.0$, $E_g = 1.694$, 0.8 μm	baseline 18.99%
Prior adopted	surveyed plus $N_D = 9 \times 10^{17}$, $E_g = 1.65$, $\chi_{\mathrm{TiO2}} = 3.8$	dose/audit anchor 23.84%
Ceiling	adopted plus $\chi_{\mathrm{CBTS}} = 3.9$, $\chi_{\mathrm{TiO2}} = 3.7$, 2.2 μm, $N_A = 3 \times 10^{16}$, $N_t = 10^{12}$	24.95% ceiling
Routine	surveyed transport affinities, 1.0 μm, $N_t = 10^{15}$	reference 20.82%
Calibration	surveyed transport affinities, $E_g = 1.70$, ITO 4.2 eV, $R_s = 1$	ladder 19.33–20.66%

Table 6: Ceiling-point parameters and result. This is the highest evaluated guardrail-satisfying configuration on the named geometries, not a proven global optimum.

Layer	d	E_g (eV)	χ (eV)	Doping (cm^{-3})	N_t (cm^{-3})
CBTS HTL	100 nm	1.9	3.9	NA 1e18	1e15
CsPbI3 absorber	2.2 μm	1.65	3.928	NA 3e16	1e12
TiO2 ETL	30 nm	3.2	3.7	ND 9e17	1e15
Interfaces (both)	–	–	–	–	1e10 cm^{-2}
Result	Voc 1.321 V, Jsc 21.20 $\mathrm{mA/cm}^2$, FF 89.11%, PCE 24.95%				

Table 7: Joint affinity map at guardrailed interfaces, PCE in percent. The peak turns over past $\chi_{\mathrm{CBTS}} \approx 3.95$ eV.

$\chi_{\mathrm{CBTS}} \setminus \chi_{\mathrm{TiO2}}$	3.7	3.8	3.9	4.0
3.50	22.10	22.10	22.10	22.07
3.60	23.83	23.82	23.80	23.50
3.70	24.67	24.64	24.53	23.77
3.80	24.89	24.86	24.67	23.81
3.90	**24.95**	24.91	24.74	23.81
3.95	24.94	24.90	–	–
4.00	24.81	24.79	–	–
4.10	23.25	23.25	–	–

4.0 Results and discussion

4.1 Grid screen and permissive-box ceiling

Round A screened thickness, acceptor density, bulk defects, ETL doping, and gap in one 96-run batch. Round B refined thickness, gap, and doping in 36 runs. The surveyed-affinity best reached 23.50%. Joint mapping of both transport-layer affinities then located the permissive-box ceiling at $\chi_{\mathrm{CBTS}} = 3.9$ and $\chi_{\mathrm{TiO2}} = 3.7$ eV.

Here 3.928 eV is the absorber affinity implied by the gap–affinity link at 1.65 eV, not an ETL affinity. The ETL affinity at the ceiling is 3.7 eV and the HTL affinity is 3.9 eV.

The ceiling sits at aggressive affinities outside surveyed values and at beyond-best-film defect density. It is therefore an upper anchor for the stated box, not a forecast. The JV curves are shown in Figure 2, and the thickness–defect interaction is shown in Figure 3.

4.2 Band alignment

Figure 4 shows the ceiling alignment from input parameters. The absorber conduction edge lies below the TiO2 edge, while the absorber valence edge lies above the CBTS edge. Efficiency nevertheless peaks there.

Two readings can coexist. The interface activation-energy trend supports a recombination reading. The sharp efficiency fall at $\chi_{\mathrm{CBTS}} = 4.0$–$4.1$ eV is also consistent with a growing extraction barrier. The Ni work-function test constrains the contact regime, not the HTL/absorber valence offset, so it does not eliminate the barrier reading.

4.3 Device characterisation

The QE edge moves from 731 to 750 nm between baseline and ceiling cells, supporting the Jsc gain in Figure 5. Because the flat blue plateau assumes no dispersive parasitic absorption, it is an upper




Figure 2: Illuminated current–voltage curves: re-parameterised baseline versus permissive-box ceiling.




Figure 3: Efficiency over absorber thickness and bulk defect density. The thickness optimum shifts with defect level.




Figure 4: Equilibrium band alignment of the ceiling stack from input parameters, energies versus vacuum.

envelope rather than a prediction.




Figure 5: Quantum efficiency of baseline versus ceiling cell; the edge shifts 731 to 750 nm.

The computed QE integral is 22.39 mA/cm^2 against the converged IV value of 21.20 mA/cm^2. For the stated optical stack, ideal step absorption gives 24.4 mA/cm^2 at 1.65 eV; after the stated 10% front reflection the ceiling is 21.96 mA/cm^2, below the QE integral. The IV value is therefore retained as the headlined current, with $\pm$1.2 mA/cm^2 carried as an absolute-scale systematic. Spectrum-file substitution was blocked by the script interface, so independent spectrum discrimination was not achieved; Supplement S4 records the blocked test.

Temperature dependence follows the established trend in Figure 6: efficiency falls from 25.88% at 275 K to 18.13% at 475 K, while Jsc remains near 21.20 mA/cm^2. The high-temperature end is a solver stress test because it omits gap narrowing and phase-stability effects.




Figure 6: Efficiency and open-circuit voltage versus temperature at the ceiling base. The 475 K end is a solver stress test.

Table 8: Pricing the zero-radiative and mobility assumptions against the zero-radiative anchor of each base.

Run	Voc (V)	Jsc (mA/cm^2)	PCE (%)	Δ (pts)
Joint optimum ($k_{rad} = 0$)	1.321	21.20	24.95	–
$+C_r = 10^{-10}$ cm^3/s	1.163	21.08	21.86	−3.09
$+C_r = 10^{-9}$ cm^3/s	1.113	20.43	19.83	−5.12
μ_n/μ_p 10/5	1.321	21.20	24.94	−0.00
μ_n/μ_p 5/2	1.321	21.20	24.94	−0.01
Routine defects ($k_{rad} = 0$)	1.147	20.77	20.82	–
$+C_r = 10^{-10}$ cm^3/s	1.141	20.73	20.68	−0.14
$+C_r = 10^{-9}$ cm^3/s	1.115	20.45	19.80	−1.02
μ_n/μ_p 10/5	1.148	20.60	20.50	−0.32

4.4 Priced radiative, mobility, and parasitic assumptions

Scripted radiative runs show that the zero-radiative default matters most at the clean corner. At the ceiling it costs 3.09 points at $C_r = 10^{-10}$ and 5.12 points at 10^{-9} cm^3/s. At routine defects the same values cost only 0.14 and 1.02 points. Mobility changes are negligible at the ceiling and 0.32 points at routine defects for DFT-grade 10/5 mobility [22].

Scripted parasitics give 24.73%, 24.52%, and 24.09% at $R_s = 0.5$, 1, and 2 Ωcm^2 on the ceiling base. At routine defects, $R_s = 1$ lowers 20.82% to 20.42%.

4.5 Density-of-states conditionality

The density-of-states assumption controls the record comparison and is therefore stated prominently.

Table 9: Record comparison under two density-of-states branches. Neither branch alone is presented as the unconditional physical result.

Branch	Ceiling treatment	PCE (%)	Against 22.02%
Capped DOS, $C_r = 10^{-10}$	24.95 to 21.86	21.86	below record
Physical DOS, $C_r = 10^{-10}$	23.46 and 23.04	23.46/23.04	above record
Physical DOS, no C_r	26.50 and 26.11	excluded	fails Voc screen

Table 10: Stacked all-priced variants at surveyed affinities and routine defects.

Thickness	Voc (V)	Jsc (mA/cm^2)	FF (%)	PCE (%)
0.6 μm	1.195	18.93	85.45	19.33
0.8 μm	1.191	19.27	85.25	19.57
1.0 μm	1.188	19.38	85.09	19.59
1.0 μm, $R_s = 2$	1.188	19.38	83.60	19.25

Table 11: Calibration ladder at measured-grade inputs: $E_g = 1.70$, ITO 4.2 eV, $R_s = 1$, $C_r = 10^{-10}$, mobility 10/5, and $N_{if} = 3 \times 10^{10}$ unless noted.

Case	Voc (V)	Jsc (mA/cm^2)	FF (%)	PCE (%)
0.6 μm, $N_t = 10^{14}$	1.203	18.91	87.00	19.79
0.8 μm, $N_t = 10^{15}$	1.185	19.14	85.18	19.33
0.8 μm, $N_t = 3 \times 10^{14}$	1.198	19.26	86.47	19.94
0.8 μm, $N_t = 10^{14}$	1.203	19.29	86.90	20.16
0.8 μm, $N_t = 10^{13}$	1.205	19.31	87.13	20.27
1.0 μm, $N_t = 10^{14}$	1.202	19.47	86.83	20.32
0.8 μm, $N_t = 10^{14}$, $N_{if} = 10^{10}$	1.216	19.43	87.42	20.66

With capped density of states, literature radiative recombination lowers the ceiling below the certified record. With effective-mass physical density of states, the same radiative term gives 23.46% and 23.04% at Voc 1.241 and 1.221 V, above the record. Without radiative recombination, physical density of states gives 26.50% and 26.11%, but those runs fail the 1.371 V model-derived screen. The capped branch preserves continuity across the campaign; the physical branch exposes the unphysical effective mass implied by the cap. The capped cap is therefore not defended as conservative physics when combined with radiative loss.

4.6 Stacked realistic variants

Combining routine defects, literature radiative recombination, DFT-grade mobility, a 1.70 eV gap, ITO 4.4 eV, and $R_s = 1$ gives 19.25–19.59% across 0.6–1.0 μm. This stacked range is below both the single-idealisation routine case and the certified record. It is an illustrative pessimistic corner, not an uncertainty interval.

4.7 Measured-grade calibration

The model was driven toward measured-grade inputs without claiming a device-specific hindcast. The ladder climbs from 19.33% at $N_t = 10^{15}$ to 20.66% with interfaces at the 10^{10} floor, then saturates below the certified record.

The remaining gap to the certified record marks the distance between routine films and record films. Published device tables do not supply enough defect-level detail for a true device-specific hindcast, so none is claimed.

4.8 Routine-quality sensitivity envelope

The prior volume was sampled with a 96-point Latin hypercube over bulk defects, interface defects, radiative coefficient, mobility, resistance, contacts, and thickness. The eight $C_r = 0$ runs form a separate sensitivity subset and are not pooled into the headline. Ninety-five in-prior runs converged.

The envelope median is 18.0%, with 5–95% range 15.6–20.0%. Bootstrap intervals are [17.7, 18.1] for the median, [15.3, 16.1] for p5, and [19.7, 20.2] for p95. The separate $C_r = 0$ median is 17.9%. Adding effective-mass density of states as another prior dimension moves the envelope only to 18.2%, with 15.8–20.0% range.




Figure 7: Efficiency versus interface density on the same cell. The no-interface point is an audit point, not a candidate.

Table 12: Guardrailed regime in portable metrics with $\sigma = 10^{-19}$ m^2 and $v_{th} = 10^5$ m/s: bulk lifetime τ and interface velocity S.

Density	τ / S	Note
$N_t = 10^{12}$ cm^{-3} (floor)	$\tau = 100$ μs	beyond-best-film regime
$N_t = 10^{13}$ cm^{-3}	$\tau = 10$ μs	–
$N_t = 10^{14}$ cm^{-3}	$\tau = 1$ μs	–
$N_t = 10^{15}$ cm^{-3} (routine)	$\tau = 0.1$ μs	routine case
$N_{if} = 10^{10}$ cm^{-2} (floor)	$S = 100$ cm/s	floor of stated box
$N_{if} = 10^{11}$ cm^{-2}	$S = 1000$ cm/s	–

This is a prior-sensitivity envelope, not a confidence interval. Bulk and interface quality were sampled independently, although cleaner bulk and better interfaces are likely correlated in real films. The 2024–2026 records fall above the envelope; earlier lower-efficiency results do not. The gap therefore measures what record quality requires beyond these priors.

4.9 Interface dose–response

Removing the interface blocks inflates the surveyed-base cells by 1.26–1.66 points, almost entirely through Voc. The full dose–response runs from 25.11% at 10^8 cm^{-2} to 21.20% at 10^{12} cm^{-2} on the prior-adopted base. At routine defects the response is nearly flat: 10^9–10^{11} cm^{-2} moves efficiency only from 20.84% to 20.67%. Interfaces therefore dominate at the defect floor, while bulk defects dominate at routine defect density.

No-interface Voc values sit at or very near the model-derived radiative bound because the model omits a radiative channel. Those cells are therefore disqualified by lack of margin, not ranked.

Table 13: Identical cells with interfaces ON versus OFF.

Cell	IF ON (%)	IF OFF (%)	Inflation (pts)
1.5 μm cell	23.40	24.87	+1.47
2.0 μm cell	23.47	24.73	+1.26
Surveyed-base best	23.50	25.16	+1.66




Figure 8: Morris μ^* with interaction spread σ. Rankings are regime conditional and use different physical units across factors.

Table 14: Loss budget: permissive-box ceiling against measured devices and model limits. The Lei row mixes printed and headline values as stated in its source.

Device	Voc (V)	Jsc (mA/cm^2)	FF (%)	PCE (%)
This work (box ceiling)	1.321	21.20	89.11	24.95
This work + $C_r = 10^{-10}$	1.163	21.08	89.13	21.86
This work, stacked realistic range	1.19	18.9–19.4	83.6–85.5	19.25–19.59
AP-modified CsPbI3 [24]	1.29	20.77	83.01	22.16
QD-interface CsPbI3 [25]	1.28	–	–	22.15
Dual-interface CsPbI3 [4]	1.27	–	–	21.71
Carbon HTL-free [26]	1.202	20.72	83.2	20.72
Radiative limit, step absorption [27]	1.372	24.4 (SQ)	90.5	–

4.10 Morris sensitivity

A guardrail-clean Morris screen used eight trajectories, four levels, six factors, and 56 converged runs spanning 15.34–22.96%. Per decade, interfaces lead at 0.85 points against 0.37 for bulk defects, but their bootstrap intervals overlap. The sharper paired-trajectory difference is +0.58 points with interval [-0.59, 1.97], with five of eight trajectories positive. Morris alone therefore does not establish the interface lead.

The regime conclusion instead rests on the dose–response and the nominal S versus d/τ anchors [23]. Those anchors organise the clean-corner and routine-defect regimes; binning the prior-volume runs by the same ratio does not reveal a clean internal crossing at this sample size. The same nominal interface velocity can also recombine differently as alignment changes the interface carrier densities.

4.11 Loss budget and limits

The ceiling exceeds the certified record by about 2.7 points even at 1.70 eV. The excess cannot be assigned to the gap alone. Simulated fill factor near 89% exceeds measured values near 83%, alongside permissive contacts and affinities.

The approximately six-point fill-factor discrepancy remains the largest unexplained gap. A missing back reflector affects Jsc rather than fill factor, so it is not offered as the explanation. Ideality-factor measurements and illumination-dependent data sufficient to separate recombination from resistive losses are unavailable, so the gap is reported as unresolved.

Table 15: Pilot guardrailed-reporting checklist for comparable SCAPS claims. The full protocol mapping is in Supplement S7.

Item	Disclose	This work	Protocol
Interfaces	status + N_{if} + σ or S	10^{10} cm^{-2}, 10^{-19} m^2	reporting
Bulk defects	N_t + σ or τ	10^{12} cm^{-3}; routine 10^{15}	reporting
Radiative coefficient	C_r value used	0, priced at 10^{-10}/10^{-9}	inputs
Mobilities	μ_n/μ_p plus anchor	25/25, priced at 10/5, 5/2	inputs
Units and scripts	script versus file systems	Supplement S2	reporting
Parasitics	R_s/R_{sh} basis	scripted; routine case included	inputs
Contacts and affinities	work functions and surveyed/adopted χ	priced	inputs
Optics and current	reflection, absorption, spectrum, QE/IV treatment	uncertainty carried	spectra
SQ screen	Voc limit and deviations	1.371 V at 1.65 eV	SQ check
Receipts	definitions plus raw outputs	public repository, Supplement S1	reporting

This is one stack, one solver, and one dimension. Several contact cliffs are SCAPS boundary behaviour as much as device physics. The checklist below is therefore a proposed pilot reporting standard, not an established publication standard.

5.0 Summary

Factorial screening under interface-inclusive guardrails gives a 24.95% permissive-box ceiling and an 18.0% routine-quality envelope on the stated CsPbI3/CBTS stack. Every load-bearing assumption is priced: defect floors, gap, contacts, affinities, radiative recombination, mobility, parasitics, optics, and density of states. The 2024–2026 records lie above the routine envelope. The record comparison for the ceiling is density-of-states conditional and is reported both ways. The principal unresolved discrepancy is fill factor.

Data availability

The simulation archive is based on repository revision `6e991c1`. The revised manuscript and new supplement are text-level additions to that revision; the revision itself does not claim a new immutable archive hash. Definition files carry the base, no-interface, work-function, and cross-section variants. Sweep receipts, raw curves, scripts, verification receipts, and typeset sources are in the public repository. Copyrighted reference PDFs are listed, not redistributed. A versioned Zenodo DOI will be added before submission.

Author contributions

Hussain Touhid Siddiquee: conceptualization, methodology, software, formal analysis, investigation, data curation, visualization, and writing—original draft. Md. Abdul Malek Fahim: validation, investigation, and writing—review and editing. The authors will confirm the final CRediT assignment before submission.

AI-use declaration

AI assistance was used during this revision for editing, consistency checking, reference-label correction, and figure-label correction. All SCAPS results come from the archived simulation receipts and were not generated by AI.

Acknowledgements

The SCAPS-1D program was kindly provided by Prof. M. Burgelman of the University of Gent. Simulation time was provided by local workstation hardware.

References

[1] W. Dai, J. Li, Y. Gou, J. Zhang, Z. Pan, et al. Moisture-responsive crystallization strategy for efficient CsPbI3 solar cells fabricated under high-humidity conditions. *Nature Communications*, 17:3363, 2026. doi: 10.1038/s41467-026-69687-4.

[2] J. Qiu, X. Mei, M. Zhang, G. Wang, L. Pan, S. Zou, J. Huang, X. Zhang, and Y. T. Shi. Fluorination-assisted interfacial dipole for CsPbI3 perovskite solar cells with over 22% efficiency. *Angewandte Chemie International Edition*, 64:e202506282, 2025. doi: 10.1002/anie.202506282.

[3] S. F. A. Shah, I. Jeong, J. Park, D. Shin, I. Hwang, N. Tsvetkov, D. Kim, J. Gwak, J. H. Park, S. I. Seok, K. Kim, and H. Min. Efficient and stable CsPbI3 perovskite solar cells with spontaneously formed 2D-Cs2PbI2Cl2 at the buried interface. *Cell Reports Physical Science*, 5:101935, 2024. doi: 10.1016/j.xcrp.2024.101935.

[4] N. Zhang, Z. Xu, Z. Yang, et al. Three birds with one stone: dual-interfaces and bulk co-passivation enable >21% efficiency of CsPbI3 solar cells with VOC of 1.27 V. *Science China Materials*, 69:405–413, 2026.

[5] Liyan Hu, Chenzhe Xu, Haochun Sun, Hongwei Wang, Linkai Yu, Jinhao Yang, Feiyu Cheng, Zhuo Kang, and Yue Zhang. Pushing the performance of inverted CsPbI3 perovskite photovoltaics via grain boundary grooves stitching. *Joule*, 2026. doi: 10.1016/j.joule.2026.102319.

[6] M. K. Hossain, G. F. I. Toki, I. Alam, R. Pandey, D. P. Samajdar, M. F. Rahman, M. R. Islam, M. H. K. Rubel, H. Bencherif, J. Madan, and M. K. A. Mohammed. Numerical simulation and optimization of a CsPbI3-based perovskite solar cell to enhance the power conversion efficiency. *New Journal of Chemistry*, 2023. doi: 10.1039/d2nj06206b.

[7] M. K. Hossain, M. H. K. Rubel, G. F. I. Toki, I. Alam, M. F. Rahman, and H. Bencherif. Effect of various electron and hole transport layers on the performance of CsPbI3-based perovskite solar cells. *ACS Omega*, 7:43210–43230, 2022.

[8] Nurul Farina Mohd Nazli, Fauziyah Salehuddin, Faiz Arith, Siti Aisah Mat Junos, Anis Suhaila Mohd Zain, and Khairil Ezwan Kaharudin. Numerical optimization of CsPbI3 perovskite solar cells using SCAPS-1D modeling. In *2025 IEEE Regional Symposium on Micro and Nanoelectronics (RSM)*, pages 61–65, 2025.

[9] S. O. Oyedele, I. Soumahoro, L. Bamba, R. Kre, and B. Aka. Simulation-based optimization of the performance of a CsPbI3 (cesium lead triiodide) perovskite solar cell using SCAPS-1D. *Modeling and Numerical Simulation of Material Science*, 2023.

[10] A. Saidarsan, S. Guruprasad, A. Malik, P. Basumatary, and D. S. Ghosh. A critical review of unrealistic results in SCAPS-1D simulations: Causes, practical solutions and roadmap ahead. *Solar Energy Materials and Solar Cells*, 279:113230, 2025. doi: 10.1016/j.solmat.2024.113230.

[11] S. Guruprasad, A. Malik, A. Saidarsan, P. Basumatary, and D. S. Ghosh. Modeling optical losses in perovskite solar cells: A modified framework toward realistic performance projection. *Solar Energy*, 305:114251, 2026. doi: 10.1016/j.solener.2025.114251.

[12] A. Swarnkar, A. R. Marshall, E. M. Sanehira, B. D. Chernomordik, D. T. Moore, J. A. Christians, T. Chakrabarti, and J. M. Luther. Quantum dot-induced phase stabilization of α-CsPbI3 perovskite for high-efficiency photovoltaics. *Science*, 354:92–95, 2016.

[13] B. Zhao, S.-F. Jin, S. Huang, N. Liu, J.-Y. Ma, D.-J. Xue, Q. Han, J. Ding, Q.-Q. Ge, Y. Feng, and J.-S. Hu. Thermodynamically stable orthorhombic γ-CsPbI3 thin films for high-performance photovoltaics. *Journal of the American Chemical Society*, 140:11716–11725, 2018.

[14] H. Bian, D. Bai, Z. Jin, K. Wang, L. Liang, H. Wang, J. Zhang, Q. Wang, and S. Liu. Graded bandgap CsPbI2+xBr1-x perovskite solar cells with a stabilized efficiency of 14.4%. *Joule*, 2: 1500–1510, 2018.

[15] J. Xi, C. Piao, J. Byeon, J. Yoon, Z. Wu, and M. Choi. Compositional engineering of α-CsPbI3 mixed-halide perovskites for efficient and stable solar cells. *Advanced Energy Materials*, 9: 1901787, 2019.

[16] P. Becker, J. A. Márquez, J. Just, A. Al-Ashouri, C. Hages, H. Hempel, M. Jošt, S. Albrecht, R. Frahm, and T. Unold. Low temperature synthesis of stable γ-CsPbI3 perovskite layers for solar cells obtained by high-throughput experimentation. *Advanced Energy Materials*, 9:1900555, 2019.

[17] Y. Wang, M. I. Dar, L. K. Ono, T. Zhang, M. Kan, Y. Li, L. Zhang, X. Wang, Y. Yang, X. Gao, Y. Qi, M. Grätzel, and Y. Zhao. Thermodynamically stabilized β-CsPbI3-based perovskite solar cells with efficiencies $>$18%. *Science*, 365:591–595, 2019. doi: 10.1126/science.aav8680.

[18] M. Burgelman, P. Nollet, and S. Degrave. Modelling polycrystalline semiconductor solar cells. *Thin Solid Films*, 361–362:527–532, 2000. doi: 10.1016/S0040-6090(99)00825-1.

[19] Y. H. Khattak. *Modeling of High Power Conversion Efficiency Thin Film Solar Cells*. PhD thesis, Universitat Politecnica de Valencia, 2019.

[20] M. Burgelman, K. Decock, A. Niemegeers, J. Verschraegen, and S. Degrave. SCAPS-1D solar cell capacitance simulator (version 3.3.10), 2021.

[21] F. Peña-Camargo, J. Thiesbrummel, H. Hempel, A. Musiienko, V. M. Le Corre, J. Diekmann, J. Warby, T. Unold, F. Lang, D. Neher, and M. Stolterfoht. Revealing the doping density in perovskite solar cells and its impact on device performance. *arXiv:2201.09664*, 2022. doi: 10.48550/arXiv.2201.09664.

[22] C. Motta, F. El-Mellouhi, and S. Sanvito. Charge carrier mobility in hybrid halide perovskites. *Scientific Reports*, 5:12746, 2015. doi: 10.1038/srep12746.

[23] A. B. Sproul. Dimensionless solution of the equation describing the effect of surface recombination on carrier decay in semiconductors. *Journal of Applied Physics*, 76:2851–2854, 1994. doi: 10.1063/1.357521.

[24] H. Lei, Y. Cai, Y. Li, D. Xu, Y. Li, Y. Li, et al. Thiocarboxylate-mediated defect suppression and I2 scavenging: achieving 22.16% efficient and stable CsPbI3 perovskite solar cells. *Advanced Materials*, 38:e12308, 2025.

[25] D. Xu, K. Cui, Z. Fan, J. W. Zhang, Y. Shang, Y. Li, et al. Exciton-photon critical coupling in size-tailored quantum dots enables >22% efficient and stable inverted CsPbI3 solar cells. *Advanced Materials*, 2026. Volume, pages, and DOI to be confirmed before submission.

[26] G. Li, J. Tan, C. Lin, C. Zhu, Y. Du, Z. Li, et al. Directing intermediate phase crystallographic orientation promotes carbon-based CsPbI3 perovskite solar cells to beyond 20% efficiency. *Nature Communications*, 2026. doi: 10.1038/s41467-026-73709-6.

[27] W. Shockley and H. J. Queisser. Detailed balance limit of efficiency of p-n junction solar cells. *Journal of Applied Physics*, 32:510–519, 1961.