

A Guardrailed 23.5%-Efficient CsPbI₃ Constrained Maximum by Multi-Parameter SCAPS-1D Screening: Interface Dose–Response, Sensitivity, and a Reproducibility Audit

Hussain Touhid Siddiquee*

Md. Abdul Malek Fahim

Abstract: We map how far a SCAPS-1D model of an ITO/TiO₂/CsPbI₃/CBTS/Ni cell can go inside a stated parameter box — and what the same model says at realistic settings. A five-factor grid screen (96 runs) plus refinement (36 runs; 126 converged) reaches 23.49% (Voc 1.234 V, Jsc 21.19 mA/cm², FF 89.78%) at 2.2 μm, $N_t = 10^{12}$ cm⁻³ (single-crystal grade), $R_s = 0$, and 10^{10} cm⁻² interface defects: the best point in the stated box, not a fab-ready recipe. At routine $N_t = 10^{15}$ cm⁻³ a dedicated thickness sweep peaks at 20.82% (1.0 μm), and a combined realistic case (ITO 4.4 eV, $N_t = 10^{15}$ cm⁻³, 10^{10} cm⁻² interfaces) gives 20.68%. A measured interface dose–response on our own cell runs 25.04% at 10^8 cm⁻² down to 20.64% at 10^{12} cm⁻²; the published 24.17% and 24.24% values fall below our no-interface band (24.73–25.16%), and we do not map other groups’ stacks onto our curve. Scripted parasitic sweeps give 23.07% at $R_s = 1$ Ωcm² and 23.38% at $R_{sh} = 10^4$ Ωcm². A Morris sensitivity screen ($r = 8$, $p = 4$, 56 runs) ranks interface quality first (1.02 points/decade), ahead of bulk defects (0.68) and bandgap. Measured band offsets (absorber CB 0.07 eV above ETL CB: downhill extraction; absorber VB 0.08 eV below HTL VB: shallow favourable offset) and contact work-function tests bound the remaining assumptions. All definition files, sweep receipts, and raw curves are archived for independent reproduction.

Keywords: CsPbI₃; perovskite solar cell; SCAPS-1D; CBTS; reproducibility; device simulation

1.0 Introduction

All-inorganic CsPbI₃ perovskite solar cells combine the thermal stability lacking in hybrid organic–inorganic perovskites with a bandgap near 1.7 eV that suits both single-junction and tandem top-cell applications [1, 2]. After years below 19%, certified laboratory efficiencies have recently passed 22%: 22.02% certified (22.60% laboratory) with a moisture-responsive propyltriethoxysilane crystallisation strategy [1], 22.05% by fluorination-assisted interfacial dipole engineering [2], 21.71% with dual-interface and bulk co-passivation at an open-circuit voltage of 1.27 V [3], and 21.43% certified for inverted architectures [4]. Each record was won at the interfaces and in the bulk defect chemistry, which motivates a simulation study that treats those exact levers honestly.

The one-dimensional solar cell capacitance simulator (SCAPS-1D) is the workhorse for such pre-experimental screening, and the ITO/TiO₂/CsPbI₃/CBTS (copper barium thiostannate) stack of Hossain et al. [5] is the most-prescribed CsPbI₃ baseline, progressing from 17.90% over 96 screened transport-layer combinations [6] to 19.06% after optimisation. Subsequent simulation studies report up to 24.17% on the same stack [7] and 24.24% on ZnO/PTAA [8], while large machine-learning-coupled screens now exceed 27% on other absorbers [9, 10]. Three problems accompany this inflation. First, nearly every study optimises one variable at a time (OVAT), so parameter interactions— notably absorber thickness versus defect-limited diffusion length—are invisible by construction. Second, the highest numbers are obtained with interface recombination removed (stated explicitly in [8]) or with defect densities far below experimental reach, and raw data are routinely withheld [5]. Third, scripted sweeps mix unit systems: SCAPS definition files store SI units while script ‘set’ commands

*Department of EEE, Leading University, Sylhet-3112, Bangladesh. E-mail: touhidsiddiqueeraj@gmail.com, mdabdulmalekfahim@gmail.com.




Figure 1: CsPbI₃ record race. Asterisks mark simulation studies without interface layers.

expect practical units, so SI-valued inputs silently inject a $10^6 \times$ overdose and fabricate ghost cells (scripting conventions are documented in Appendix A).

This work contributes (i) a five-factor grid screen (96 configurations) plus refinement (36 runs) of the ITO/TiO₂/CsPbI₃/CBTS/Ni cell under interface-inclusive guardrails, reaching **23.49%** as the best point in the stated box; (ii) a measured interface dose–response on our own cell running 25.04% to 20.64% as interface quality degrades; (iii) scripted (not analytic) series- and shunt-resistance accounting; and (iv) a Morris sensitivity screen that ranks interface quality above all bulk factors. Every definition file, sweep receipt, and raw curve is archived for independent reproduction.

2.0 Literature: a decade of CsPbI₃ progress

Black-phase CsPbI₃ has been stabilised stepwise since 2016: quantum-dot-induced α -phase retention at 10.8% [11], co-evaporated planar cells at 17.0% [12], thermodynamically stable γ -films [13], surface-passivated 14.5% devices [14], and compositionally engineered 13–14% cells [15, 16], all on TiO₂ with Spiro-OMeTAD, PTAA or carbon contacts [17–19]. The 2019 aziridinium result at 18.40% [20] stood for years until the 2025–2026 interface-engineering wave (Figure 1): fluorinated dipoles (22.05% [2]), dual-interface plus bulk co-passivation with Voc 1.27 V (21.71% [3]), moisture-responsive crystallisation (22.60% laboratory, 22.02% certified [1]), and stitched grain-boundary grooves in inverted cells (21.43% certified [4]). The certified frontier is therefore 22.02%, and every recent jump came from defect and interface control—the precise levers a simulation study must treat honestly.

Simulation studies trace a parallel inflation curve (Table 1). The CBTS screening programme reached 17.90% over 96 transport-layer combinations [6] and 19.06% after full optimisation [5], the baseline we reproduce. Later claims diverge upward as realism constraints are relaxed: 23.10% with ZnO/Spiro in one report [21], 24.17% on our exact stack [7], and 24.24% on ZnO/PTAA without interface layers (stated) [8]. The broader SCAPS literature shows the same pattern across absorbers—MAPbI₃ at 19.30% with inorganic contacts [22], gradient-doped FAPbI₃ at 20.34% [23], a 28.38% bifacial triple-cation cell [10], and an explicitly idealised 40.17% MASnI₃ result that exceeds the Shockley–Queisser bound [24, 25]. Our audit in Section 7.0 places these numbers on a common guardrailed footing.

Table 1: Selected CsPbI3 results: experiment versus simulation (IF = interface layers).

Study	Stack	Type	PCE (%)	IF
Swarnkar 2016	TiO2/Spiro/MoOx	Exp.	10.8	–
Frolova 2017	TiO2/PTAA	Exp.	17.0	–
Wang 2019	TiO2/Spiro	Exp.	18.4	–
Qiu 2025	DFAz dipole	Exp.	22.05	passivated
Dai 2026	TiO2/PTABr/Spiro	Exp.	22.60/22.02	passivated
Hu 2026 (Joule)	inverted HPDA	Exp.	21.43 cert.	2D-stitched
Hossain 2022	TiO2/CBTS	Sim.	17.90	on
Hossain 2023	TiO2/CBTS/Ni	Sim.	19.06	on
Ristiansyah 2026	ZnO/Spiro	Sim.	23.10	on
Nazli 2025	TiO2/CBTS/Ni	Sim.	24.17	unclear
Oyedele 2023	ZnO/PTAA	Sim.	24.24	OFF
This work	TiO2/CBTS/Ni	Sim.	23.49	on

3.0 Simulation framework and guardrails

Devices were simulated in SCAPS-1D v3.3.10 under AM1.5G illumination (100 mW/cm²) at 300 K unless stated. The baseline reproduces Hossain et al. [5]: ITO front contact (4.0 eV), 30 nm TiO2 electron transport layer (donor density 9×10^{16} cm⁻³), CsPbI3 absorber (800 nm initial, $E_g = 1.694$ eV, $\chi = 3.95$ eV, $N_A = 10^{15}$ cm⁻³, $N_t = 10^{15}$ cm⁻³), 100 nm CBTS hole transport layer ($N_A = 10^{18}$ cm⁻³), and Ni back contact (5.5 eV). Crucially, neutral interface recombination blocks ($N = 10^{10}$ cm⁻², $\sigma = 10^{-19}$ m²) are present at both heterojunctions, and the absorber uses the coefficients-A-and-B absorption model ($A = 10^7$ m⁻¹eV^{-1/2}) so that bandgap sweeps act on the absorption edge rather than a frozen file spectrum. Our unmodified baseline yields 18.99% (Voc 1.122 V, Jsc 19.68 mA/cm², FF 86.00%), reproducing the published 17.9–19.06% band and validating the harness.

Guardrails enforced throughout: bulk defect floor 10^{12} cm⁻³ (single-crystal grade; nothing lower), absorber doping ceiling 3×10^{16} cm⁻³, conduction-band offset 0 to +0.3 eV maintained by linking χ to E_g ($\chi = 3.95 + 0.5(E_g - 1.694)$), and automatic rejection of runs with Voc above $E_g/q - 0.28$ V (~ 1.37 V at 1.65 eV, the detailed-balance neighbourhood; the model sets $k_{rad} = 0$, so this is a plausibility ceiling, not a computed radiative limit) or FF above Green’s ideal-diode value at the measured Voc (90.0% at 300 K, 90.9% at 275 K) as non-physical. (An earlier draft used Voc > $E_g/q - 0.1$ V and FF > 90.5% cutoffs; both were too lax and are superseded here.) Series and shunt resistances are scriptable in SCAPS 3.3.10 (set external.Rs/Rsh; scriptdescription3310.txt), so this section reports measured parasitic sweeps. Sweeps ran in parallel on four workers with checkpointed receipts; of 132 grid configurations, 126 converged and enter the analysis (6 non-converged worker runs excluded and listed in the receipts). A duplicate champion run reproduces the coarse-grid value 23.5041% exactly, confirming determinism; a confirmatory run at finer IV step gives 23.4874% (FF 89.78%), reported as 23.49% throughout. Absorber densities of states are capped at $N_c = 1.1 \times 10^{19}/N_v = 8.2 \times 10^{19}$ cm⁻³, ten times below the Table-1 print (10^{20} cm⁻³, above solid density and hence unphysical).

SCAPS-1D solves the Poisson equation coupled to electron and hole continuity with drift-diffusion transport [26, 27]:

$$-\frac{\partial}{\partial x} \left(\epsilon(x) \frac{\partial V}{\partial x} \right) = q[p - n + N_D^+ - N_A^- + p_t - n_t], \quad (1)$$

$$\frac{\partial n}{\partial t} = \frac{1}{q} \frac{\partial J_n}{\partial x} + G_n - R_n, \quad \frac{\partial p}{\partial t} = -\frac{1}{q} \frac{\partial J_p}{\partial x} + G_p - R_p, \quad (2)$$

with Shockley–Read–Hall recombination through the specified bulk and interface defect levels. Optical generation uses the Eg-sqrt (Tauc) model $\alpha = A\sqrt{h\nu - E_g}$, so bandgap sweeps move the ab-

Table 2: Layer input parameters (script units; baseline values). Mobilities in cm^2/Vs ; $v_{th} = 10^5$ m/s all layers; contacts $S_n = S_p = 10^5$ m/s with Ni 5.5 eV / ITO 4.0 eV; front reflection filter 10%, back transmission filter 80%; radiative (K_{rad}) and Auger recombination off.

Layer	d	E_g	χ	ϵ_r	Doping	N_t	μ_n/μ_p	N_c/N_v ; defect σ_n/σ_p , E_t
CBTS HTL	100 nm	1.9	3.6	5.4	N_A 1e18	1e15	30/–	2.2e18/1.8e19; 1e-20/1e-19, 1.5 eV
CsPbI3	800 nm	1.694	3.95	6.0	N_A 1e15	1e15	25/25	1.1e19/8.2e19; 1e-19/1e-19, 0.6 eV
TiO2 ETL	30 nm	3.2	4.0	9.0	N_D 9e16	1e15	20/–	2.0e18/1.8e19; 1e-19/1e-18, 1.6 eV

Table 3: Interface defect layers (both heterojunctions): neutral single level, $\sigma = 10^{-19}$ m^2 all sides, $E_t = 0.6$ eV.

Interface	N (cm^{-2})	Sweep range (this work)
CBTS/CsPbI3	1e10	10^8 – 10^{12} (+ ETL/HTL-only, $\sigma \times 10$)
CsPbI3/TiO2	1e10	10^8 – 10^{12} (+ ETL/HTL-only, $\sigma \times 10$)

sorption edge self-consistently. Full input parameters are listed in Tables 2 and 3; transport-layer screenings that motivate the TiO2/CBTS choice are reviewed in [6, 28].

4.0 Grid screen and champion best point

Round A explored the full cross-product of absorber thickness (1.0–2.0 μm), acceptor density (10^{15} – 10^{16} cm^{-3}), bulk defect density (10^{12} – 10^{14} cm^{-3}), ETL donor density (9×10^{16} – 9×10^{17} cm^{-3}), and bandgap (1.694/1.65 eV with linked affinity)—96 configurations in a single parallel batch, rather than sequential OVAT slices. The winner (2.0 μm , $N_A = 10^{16}$ cm^{-3} , $N_t = 10^{12}$ cm^{-3} , $N_{D,ETL} = 9 \times 10^{17}$ cm^{-3} , $E_g = 1.65$ eV) reached 23.47%. Full parameters are collected in Table 4. Round B refined thickness (1.8–2.2 μm), gap (1.65–1.72 eV), and doping around this point (36 configurations) and reached **23.49%** (2.2 μm , $N_A = 3 \times 10^{16}$ cm^{-3} , $N_t = 10^{12}$ cm^{-3} , $E_g = 1.65$ eV, $\chi = 3.928$ eV): Voc 1.234 V, Jsc 21.19 mA/cm^2 , FF 89.78% (Figure 2). Two facts about this optimum must be stated plainly. First, it sits at the corner of the allowed box: N_A at its ceiling, N_t at its floor, $N_{D,ETL}$ at the top of its tested range, E_g at its bottom, thickness at the top of the refined range. Second, the best grid point at the literature gap $E_g = 1.694$ eV reaches only 22.51%, so roughly one point of the 23.49% comes from the gap choice alone. Every top-ten configuration carries $E_g = 1.65$ eV, gaining ~ 1.5 mA/cm^2 over 1.694 eV while the χ link holds the absorber CB 0.07 eV above the ETL CB (downhill extraction); the HTL side carries a shallow 0.08 eV hole-favourable offset outside the ideal window (Section 5.0).

The interaction map (Figure 3) shows why OVAT misses the optimum: thick absorbers (2.0–2.2 μm) win only jointly with $N_t = 10^{12}$ cm^{-3} , where the diffusion length still covers the thickness, while at 10^{14} cm^{-3} the optimum collapses below 1.5 μm . ETL donor density confirms the literature optimum (9×10^{17} cm^{-3}) and transport-layer thicknesses are insensitive (100/30 nm retained), both consistent with [5]. The current–voltage curve (Figure 2) is square and artefact-free, with a Voc deficit of 0.42 V against E_g/q —typical of realistic rather than idealised cells.

The 4.50-point stacked gain decomposes along the screening path (Table 4 parameters in sequence, illustrative ordering only): thickness 800 nm to 1.5 μm adds 0.19 points (19.18%), acceptor doping to 10^{16} cm^{-3} adds 0.93 points (20.11%), bulk-defect reduction to 10^{12} cm^{-3} adds ~ 1.6 points ($\sim 21.7\%$), and the joint E_g – χ move to 1.65 eV with ETL donor optimisation contributes the remaining ~ 1.8 points. This sequential attribution is order-dependent and illustrative, not causal. Open-circuit voltage climbs 1.122 to 1.234 V while the fill factor rises 86.0 to 89.8%, the signature of SRH-lifetime recovery rather than band-shift artefacts.

Round A's top ten (Table 5) all carry $E_g = 1.65$ eV; the top seven sit at $N_t = 10^{12}$ cm^{-3} while rows 8–10 at $N_t = 10^{13}$ cm^{-3} trail by ~ 0.4 points through Voc loss (1.233 to 1.221 V). Round B




Figure 2: Illuminated current–voltage curves: baseline (800 nm, 18.99%) versus champion (2.2 μm , 23.49%).

Table 4: Champion device parameters (script units) and result.

Layer	d	E_g (eV)	χ (eV)	Doping (cm^{-3})	N_t (cm^{-3})
CBTS HTL	100 nm	1.9	3.6	NA 1e18	1e15
CsPbI ₃ absorber	2.2 μm	1.65	3.928	NA 3e16	1e12
TiO ₂ ETL	30 nm	3.2	4.0	ND 9e17	1e15
Interfaces (both)	—	—	—	—	1e10 cm^{-2}
Result: Voc 1.234 V, Jsc 21.19 mA/cm^2 , FF 89.78%, PCE 23.49%					

Table 5: Round A leaderboard (best ten of 96; $N_{D,ETL} = 9 \times 10^{17} \text{ cm}^{-3}$).

$d \text{ (}\mu\text{m)}$	N_A	N_t	E_g	Voc	Jsc	PCE
2.0	1e16	1e12	1.65	1.233	21.18	23.47
1.8	1e16	1e12	1.65	1.233	21.16	23.45
1.5	1e16	1e12	1.65	1.234	21.11	23.40
1.5	1e15	1e12	1.65	1.233	21.11	23.29
2.0	1e15	1e12	1.65	1.233	21.18	23.29
1.0	1e16	1e12	1.65	1.234	20.90	23.18
1.0	1e15	1e12	1.65	1.233	20.90	23.11
1.8	1e16	1e13	1.65	1.221	21.16	23.04
2.0	1e16	1e13	1.65	1.219	21.18	23.03
1.5	1e16	1e13	1.65	1.223	21.11	23.03

Table 6: Round B leaderboard (best ten of 36; $N_{D,ETL} = 9 \times 10^{17} \text{ cm}^{-3}$).

$d \text{ (}\mu\text{m)}$	N_A	N_t	E_g	PCE
2.2	3e16	1e12	1.65	23.50
2.0	3e16	1e12	1.65	23.49
2.2	1e16	1e12	1.65	23.48
2.0	1e16	1e12	1.65	23.47
1.8	3e16	1e12	1.65	23.47
2.2	3e16	3e12	1.65	23.45
1.8	1e16	1e12	1.65	23.45
2.0	3e16	3e12	1.65	23.44
1.8	3e16	3e12	1.65	23.42
2.2	1e16	3e12	1.65	23.32

refined thickness (1.8–2.2 μm), gap (1.65–1.72 eV) and doping (36 runs) and moved the best from 23.47% to 23.50% (coarse grid), i.e. the landscape is converged rather than climbing.

Round B’s refinement is documented in full because its plateau is itself evidence: the best ten span only 23.32–23.50% (Table 6), with thickness 1.8–2.2 μm and N_A (1–3) $\times 10^{16} \text{ cm}^{-3}$ numerically indistinguishable at grid resolution once $N_t = 10^{12} \text{ cm}^{-3}$ and $E_g = 1.65 \text{ eV}$ are fixed (the ten span 23.32–23.50%, a 0.18-point range against a 0.017-point coarse/fine IV-step uncertainty, so the leading cluster cannot be separated even though the 10th entry trails observably). The $N_t = 3 \times 10^{12} \text{ cm}^{-3}$ entries trail by ~ 0.05 points, confirming the defect floor binds the optimum.

5.0 Band alignment

Figure 4 constructs the equilibrium alignment from the champion parameters. The absorber conduction edge (−3.928 eV) lies 0.07 eV *above* the TiO2 edge (−4.00 eV), so electrons move downhill into the ETL: a 0.07 eV cliff, not a spike, with no extraction barrier but a lowered interface recombination activation energy. On the hole side, the absorber valence edge (−5.578 eV) lies 0.08 eV *below* the CBTS edge (−5.50 eV), i.e. a shallow hole-favourable offset on the wrong side of the ideal −0.3 to −0.1 eV window (earlier drafts reported −0.22 eV and then a +0.08 eV barrier; both were sign errors, corrected here with the arithmetic shown). A χ_{CBTS} sweep at the champion confirms the picture: 3.4 eV gives 20.22%, 3.5 eV 22.07%, 3.7 eV 23.77%, 3.8 eV 23.81%, monotonic in the offset exactly as the downhill/uphill reading predicts. The literature 3.6 eV value is therefore not optimal, and the 23.49% stands inside the stated box rather than at any physical alignment limit.




Figure 3: Efficiency map over absorber thickness and bulk defect density (slice at $N_A = 10^{16} \text{ cm}^{-3}$, $E_g = 1.65 \text{ eV}$).




Figure 4: Equilibrium band alignment of the champion stack from input parameters (energies in eV vs vacuum).




Figure 5: Quantum efficiency of baseline versus champion; the edge shifts 731 to 752 nm.

6.0 Device characterisation

The quantum efficiency (Figure 5) is flat at $\sim 89\text{--}90\%$ from 300 nm with the absorption edge red-shifted from 731 nm (baseline, 1.694 eV) to 752 nm (champion, 1.65 eV), directly explaining the J_{sc} gain. The UV plateau assumes the definition file's flat 10% front reflection with no dispersive parasitic absorption in ITO or TiO₂, so it is an upper envelope in the blue rather than a prediction. Capacitance–voltage analysis at 1 MHz (Figure 6) shows rising capacitance with forward bias (31 to 39 nF/cm² over 0–0.5 V; SCAPS-extracted width 0.29 to 0.22 μm , far below the 2.2 μm absorber throughout). The forward-bias sweep admits no valid Mott–Schottky extraction— $1/C^2$ falls with voltage, and a naïve slope gives an unphysical doping—so no carrier density is inferred and the curve is reported as qualitative consistency only. (The parallel-plate check $\epsilon A/C$ gives 0.17 μm at 0 V versus the solver's 0.29 μm , a further reason not to over-read the electrostatics.) The illuminated band diagram at short circuit (Figure 7) exhibits clean quasi-Fermi splitting, and generation exceeds recombination by at least two orders of magnitude at every mesh point of the full 2.33 μm short-circuit profile (minimum ratio $\sim 3 \times 10^2$ at $x \approx 0.2 \mu\text{m}$ near the back contact, rising above 10^5 at both contacts; Figure 8). All profile statements in this section are at short circuit; nothing here constrains the maximum-power or open-circuit regime.

Temperature dependence (Figure 9, Table 7) follows the established trend [5]: efficiency falls from 24.44% at 275 K to 16.70% at 475 K, driven by V_{oc} (1.271 to 0.955 V) and FF while J_{sc} stays pinned at $\sim 21.19 \text{ mA/cm}^2$, i.e. $-0.16\%/K$ relative (-0.039 points/ K) over 300–400 K. The 275 K fill factor (90.75%) sits *below* Green's ideal-diode value at that V_{oc} and temperature (90.86%), so no artefact needs invoking; likewise the champion's 89.78% is within 0.2 points of ideal (90.0%), leaving essentially no FF headroom beyond series resistance. The 475 K end of the sweep ignores the temperature dependence of E_g and black-phase stability, so it is a solver stress test, not a prediction.

6.1 Parasitic-resistance accounting

Series and shunt resistances are scriptable in SCAPS 3.3.10 (`set external.Rs/Rsh; scriptdescription3310.txt`). Measured scripted sweeps on the champion give 23.29% at $R_s = 0.5 \Omega\text{cm}^2$, **23.07%** at $R_s = 1 \Omega\text{cm}^2$,




Figure 6: Capacitance–voltage (1 MHz) and Mott–Schottky plots for baseline and champion.




Figure 7: Illuminated band diagram of the champion at short circuit ($x=0$ at the back contact).




Figure 8: Generation and recombination profiles at short circuit (log scale).

Table 7: Temperature dependence of the champion (1 sun). The 300 K row uses the fine-IV-step confirmatory run (23.49%); all other rows use coarse-grid sweep values.

T (K)	Voc (V)	Jsc (mA/cm ²)	FF (%)	PCE (%)
275	1.271	21.19	90.75	24.44
300	1.234	21.19	89.78	23.49
350	1.157	21.20	87.91	21.57
400	1.078	21.20	85.92	19.64
475	0.955	21.20	82.50	16.70

and 22.64% at $R_s = 2 \Omega\text{cm}^2$ (Table 8), agreeing with the analytic derate to 0.02 points. Shunt paths cost 0.11 points at $R_{sh} = 10^4 \Omega\text{cm}^2$ (23.38%) and 1.27 points at $R_{sh} = 10^3 \Omega\text{cm}^2$ (22.22%); combined $R_s = 1/R_{sh} = 10^4$ gives 22.95%. The best point therefore survives realistic parasitics, but only just: at $R_s = 2 \Omega\text{cm}^2$ the margin over the 22.02% certified record is 0.6 points.

7.0 Reproducibility audit: what the 24%+ claims are made of

Deleting the interface blocks inflates efficiency by 1.26–1.67 points absolute: 23.40 to 24.87%, 23.47 to 24.73%, and 23.50% coarse (23.49% fine) to 25.16% (Figure 10), almost entirely through a ~ 0.13 V Voc rise as interface recombination vanishes. But the binary ON/OFF comparison understates the audit: the full dose–response (Table 9) runs 25.04% at 10^8 cm^{-2} , 24.54% at 10^9 cm^{-2} , 23.49% at the 10^{10} cm^{-2} guardrail, 22.88% at $3 \times 10^{10} \text{ cm}^{-2}$, 22.21% at 10^{11} cm^{-2} , and 20.64% at 10^{12} cm^{-2} . The published 24.17% [7] and 24.24% [8] values fall *below* our no-interface band (24.73–25.16%). Because their stacks, gaps, thicknesses and defect parameters all differ from ours, we do not map their numbers onto our curve; the dose–response is reported strictly as an own-cell result. We could not re-run either study from its published parameters (neither paper prints a complete parameter table), and we state this as a limitation rather than a finding. Under interface-inclusive




Figure 9: Efficiency and open-circuit voltage versus operating temperature (champion).

settings, the highest reported CsPbI₃ value in our survey remains 23.10% on ZnO/Spiro [21]; our 23.49% is the best point in the stated box on the TiO₂/CBTS stack, and Section 9.0 itemises what could still deflate it.

7.1 Where the missing points go


The inflation is almost entirely a Voc effect (+0.13 V) with Jsc unchanged to within 0.02 mA/cm²: removing the 10¹⁰ cm⁻² interface states eliminates the dominant SRH channel at the heterojunctions, unpinning the quasi-Fermi splitting toward the detailed-balance neighbourhood—indeed the no-interface Voc values (1.363–1.382 V) approach the ~ 1.37 V E_g -implied ceiling for 1.65 eV (the model sets $k_{rad} = 0$, so closeness to that ceiling marks the edge of the physical regime, not radiative-limited operation). Fill factor moves non-monotonically (89.8 to 87.0% on the champion) as the recombination profile reshapes. The no-interface 87.0% at Voc 1.364 V sits 3.7 points below Green’s ideal (90.7%): the archived JV curve stays flat to 1.16 V with no kink or S-shape, so there is no visible extraction barrier, but the knee remains SRH-rounded by the surviving bulk channel—removing interfaces unpins Voc without idealising the diode. This bounds the “no extraction barriers” claim to current collection, not to fill factor. Asymmetric tests show both heterojunctions matter: 10¹² cm⁻² on the ETL side alone gives 21.35%, on the HTL side alone 21.20%. Raising the capture cross-section 10 $\times$ at fixed $N_{if} = 10^{10}$ cm⁻² gives 22.21%, exactly reproducing the $N \times 10$ row, as expected for rate $\propto N\sigma$ with symmetric $\sigma_n = \sigma_p$. (A first attempt via `set ...capture_cross_section` instead silently neutralised one interface block, yielding 23.86%; that point is discarded and the verified definition-file variant reported. Bulk $N_t \times \sigma$ interacts: $\sigma \times 10$ costs 0.23 points at the 10¹² cm⁻³ floor but 1.5 points at routine 10¹⁵ cm⁻³ (17.44%), while $\sigma \times 0.1$ at the floor gains only 0.04 points (23.53%)—the floor is saturated.) The measured parasitic sweep applied to the guarded champion is tabulated below.

8.0 Morris sensitivity screening

Grid methods with uneven ranges cannot rank physical importance, so we ran a Morris sensitivity screen instead: $r = 8$ trajectories, $p = 4$ levels, $k = 6$ factors (absorber thickness, $\log N_A$, $\log N_t$,

Table 8: Champion under measured scripted parasitics (all values computed, none derated).

Parasitics	PCE (%)	vs 22.02% cert.	Status
$R_s = 0$ (box maximum)	23.49	+1.47	SCAPS box maximum
$R_s = 0.5 \Omega\text{cm}^2$	23.29	+1.27	realistic good contact
$R_s = 1 \Omega\text{cm}^2$	23.07	+1.05	realistic typical
$R_s = 2 \Omega\text{cm}^2$	22.64	+0.62	margin nearly gone
$R_{sh} = 10^4 \Omega\text{cm}^2$	23.38	+1.36	mild shunt
$R_{sh} = 10^3 \Omega\text{cm}^2$	22.22	+0.20	leaky cell
$R_s = 1 + R_{sh} = 10^4$	22.95	+0.93	combined realistic

**Figure 10:** Same cell at graded interface quality: efficiency vs N_{if} (both sides) with the 24%+ literature band and the no-interface point. The band is shown for scale only; cross-stack mapping is not claimed.**Table 9:** Interface dose–response on the champion (both sides unless noted).

$N_{if} (\text{cm}^{-2})$	PCE (%)	Note
10^8	25.04	above all literature
10^9	24.54	above 24.17/24.24 claims
10^{10} (guardrail)	23.49	this work
3×10^{10}	22.88	below laboratory pace
10^{11}	22.21	–
10^{12}	20.64	–
10^{12} ETL side only	21.35	HTL side guarded
10^{12} HTL side only	21.20	ETL side guarded
$10^{10}, \sigma \times 10$ (verified)	22.21	matches $N \times 10$ (rate $\propto N\sigma$)
removed (noIF)	25.16	near E_g -implied Voc ceiling

Table 10: Guardrail audit: identical cells with interfaces ON versus OFF.

Cell	IF ON (%)	IF OFF (%)	Inflation (pts)
1.5 μm cell	23.40	24.87	+1.47
2.0 μm cell	23.47	24.73	+1.26
Champion	23.49	25.16	+1.67

Table 11: Morris screen design and results ($r = 8$ trajectories, $p = 4$, $\Delta = 2/3$, seed 7; 56/56 converged). μ^* per normalised unit input; last column per physical decade (eV/ μm where noted); $n = 8$ unique directed effects per factor.

Factor	Range	μ^*	σ	n	per decade
$\log N_{if}$ (both IF)	10^8 – 10^{12} cm^{-2}	4.08	1.08	8	1.02
$\log N_t$ (absorber)	10^{12} – 10^{15} cm^{-3}	2.05	1.40	8	0.68
E_g (+ χ link)	1.65–1.75 eV	1.75	0.79	8	17.5/eV
Thickness	0.4–2.2 μm	1.29	0.99	8	0.72/ μm
$\log N_{D,ETL}$	10^{16} – 10^{19} cm^{-3}	0.68	1.04	8	0.23
$\log N_A$ (absorber)	10^{15} – $3 \times 10^{16} \text{ cm}^{-3}$	0.48	0.56	8	0.32




Figure 11: Morris μ^* (bars) with interaction spread σ (whiskers). Interfaces dominate; large σ throughout signals interactions.

$\log N_{D,ETL}$, E_g with the χ link applied deterministically, and $\log N_{if}$ tied on both interfaces), 56 fresh simulations, all converged, spanning 15.6–23.4% (Table 11, Figure 11). In physical units, interface quality leads at 1.02 points/decade, ahead of bulk defect density (0.68/decade); bandgap moves 17.5 points/eV, thickness 0.72 points/ μm , and the dopings trail (0.32 and 0.23/decade). The large σ values throughout confirm strong interactions/nonlinearity—notably thickness acting through defect-limited diffusion length—so these are screening ranks, not variance shares, and the range choices are printed in the table so the ranking can be re-weighted. Two disclosures: E_g moves together with χ by construction, and the two interfaces move together, so their scores bundle linked effects.

Interface-led sensitivity is consistent with passivation studies in which interface-adjacent defects gate the voltage [29], and with Bayesian optimisation on CsSnI₃ where the optimal thickness likewise shifts with defect density [9].

9.0 Discussion

Fabrication plausibility bounds the result, and new sensitivity runs tighten the bounds. $N_A = 3 \times 10^{16} \text{ cm}^{-3}$ is routinely achievable; $E_g = 1.65 \text{ eV}$ sits below the $\sim 1.7 \text{ eV}$ of the experimental records and contributes roughly one point (best 1.694 eV grid point: 22.51%); $N_t = 10^{12} \text{ cm}^{-3}$ demands near-single-crystal quality, and raising the capture cross-section $10\times$ costs a further 0.23 points there and 1.5 points at routine 10^{15} cm^{-3} . The contacts are not neutral choices: lowering Ni from 5.5 to 5.0 eV (the usual metal range) costs 0.23 points, and raising ITO from 4.0 to 4.7 eV collapses the cell to 18.60% (Voc 1.08 V), so the front contact must stay near 4.0–4.4 eV. A χ_{CBTS} sweep (3.4 to 3.8 eV) moves efficiency monotonically from 20.22% to 23.81%, confirming the corrected alignment reading

of Section 5.0 and showing the literature 3.6 eV value is not optimal—the box could be widened, but we keep the surveyed value and report the sensitivity instead. The honest headline at realistic settings is the combined case: ITO 4.4 eV, $N_t = 10^{15} \text{ cm}^{-3}$, 10^{10} cm^{-2} interfaces gives **20.68%**, and the routine-defect thickness sweep peaks at 20.82% (1.0 μm). Against experiment: 23.49% exceeds the 22.02% certified record by 1.47 points and the 22.60% laboratory value by 0.89 points; with measured $R_s = 1 \Omega\text{cm}^2$ (23.07%) the margin over certified is 1.05 points and over laboratory 0.47 points. The result sits at $\sim 78\%$ of the $\sim 30\%$ Shockley–Queisser limit at 1.65 eV ($\sim 1.45 \text{ V}$), well inside thermodynamics.

10.0 Outlook

A laboratory translation would need, simultaneously: $\sim 1.0 \mu\text{m}$ CsPbI3 films at routine defect levels for the 20.68% realistic case (time-resolved photoluminescence verified), interface passivation toward 10^{10} cm^{-2} following the fluorinated-dipole [2] or dual-interface [3] chemistries, a front contact near 4.0–4.4 eV, and $R_s \leq 1 \Omega\text{cm}^2$ (Table 8). We state plainly what is not demonstrated: 2.2 μm device-quality CsPbI3 at $N_t \sim 10^{12} \text{ cm}^{-3}$, and sputtered CBTS directly on CsPbI3 (CBTS typically requires high-temperature sulfurisation), for which we found no precedent—so this section is a requirements list, not a recipe. In-line controls, where applicable: QE edge at 752 nm (Figure 5) and the $-0.16\%/K$ temperature coefficient (Table 7).

11.0 Limitations and outlook

Five boundaries delimit this work. First, $N_t = 10^{12} \text{ cm}^{-3}$ at 2.2 μm demands near-single-crystal films, and with the modelled $\sigma = 10^{-19} \text{ m}^2$ implies $\tau_{\text{SRH}} \approx 100 \mu\text{s}$, one to two orders beyond the best reported perovskite films; at routine 10^{15} cm^{-3} a dedicated sweep peaks at 20.82% (1.0 μm) and the combined realistic case gives 20.68%. Second, the contacts (Ni 5.5 eV, ITO 4.0 eV) and the shallow off-window hole-side offset (+0.08 eV) are stated-box choices, each priced in Section 9.0. Third, phase stability of black CsPbI3 against the yellow δ -phase, ion migration, $E_g(T)$, and damp-heat degradation are outside SCAPS-1D steady-state scope and must be validated experimentally, following the passivation routes of [1–3]. Fourth, the grid is a screen, not an optimiser: the best point sits at the corner of the allowed box and the leading cluster is numerically inseparable. Fifth, the single-junction ceiling ($\sim 30\%$ at 1.65 eV [25]) caps how far any interface-inclusive screening can go.

12.0 Conclusion

Grid screening under interface-inclusive guardrails finds a 23.49%-efficient best point in the stated CsPbI3/CBTS box, with every load-bearing assumption priced: single-crystal-grade defects, a low gap, standard-surveyed but tuned contacts, and a shallow off-window hole-side offset. The same campaign prices the realistic-defect result at 20.68%, measures the interface dose–response on its own cell, replaces an analytic resistance derate with scripted parasitic sweeps, and ranks interfaces first by Morris screening. We recommend guardrailed reporting (interface status *with* dose level, defect floors *with* cross-sections, unit-system declaration, R_s basis, contact work functions) as a publication standard for SCAPS studies.

Data availability

All definition files (csPbI3-CBTS-r7.def with interfaces, csPbI3-CBTS-noIF.def without, plus work-function and cross-section variants), sweep receipts (roundA.jsonl, roundB.jsonl, char.jsonl, s0_verify.json, s1_dose.json, s4_sig.json, s5_morris.jsonl), raw curves (champion_JV.json),

analysis outputs and figure scripts are archived with the project under `leadpaper/` (inventory in Table 12; directories `defs/`, `outputs/`, `receipts/`, `logs/`). A public repository with DOI will be released on acceptance; until then all files are available from the authors.

Author contributions

The authors designed the screening study, built the SCAPS definition files, executed the simulation campaign, performed the audit and sensitivity analyses, and wrote the manuscript.

Acknowledgements

The SCAPS-1D program was kindly provided by Prof. M. Burgelman of the University of Gent. Simulation time was provided by local workstation hardware (four parallel workers).

References

- [1] W. Dai, J. Li, Y. Gou, J. Zhang, Z. Pan, et al. Moisture-responsive crystallization strategy for efficient cspbi₃ solar cells fabricated under high-humidity conditions. *Nature Communications*, 2026. 21.00% at 55% RH; 22.60% laboratory, 22.02% certified.
- [2] J. Qiu, X. Mei, M. Zhang, G. Wang, L. Pan, S. Zou, J. Huang, X. Zhang, and Y. T. Shi. Fluorination-assisted interfacial dipole for cspbi₃ perovskite solar cells with over 22% efficiency. *Angewandte Chemie International Edition*, 137:e202506282, 2025.
- [3] N. Zhang, Z. Xu, Z. Yang, et al. Three birds with one stone: dual-interfaces and bulk co-passivation enable >21% efficiency of cspbi₃ solar cells with voc of 1.27 v. *Science China Materials*, 69:405–413, 2026.
- [4] Liyan Hu, Chenzhe Xu, Haochun Sun, Hongwei Wang, Linkai Yu, Jinhao Yang, Feiyu Cheng, Zhuo Kang, and Yue Zhang. Pushing the performance of inverted cspbi₃ perovskite photovoltaics via grain boundary grooves stitching. *Joule*, 2026. doi: 10.1016/j.joule.2026.102319. Record certified 21.43% inverted CsPbI₃.
- [5] M. K. Hossain, G. F. I. Toki, I. Alam, R. Pandey, D. P. Samajdar, M. F. Rahman, M. R. Islam, M. H. K. Rubel, H. Bencherif, J. Madan, and M. K. A. Mohammed. Numerical simulation and optimization of a cspbi₃-based perovskite solar cell to enhance the power conversion efficiency. *New Journal of Chemistry*, 2023. doi: 10.1039/d2nj06206b.
- [6] M. K. Hossain, M. H. K. Rubel, G. F. I. Toki, I. Alam, M. F. Rahman, and H. Bencherif. Effect of various electron and hole transport layers on the performance of cspbi₃-based perovskite solar cells. *ACS Omega*, 7:43210–43230, 2022.
- [7] Nurul Farina Mohd Nazli, Fauziyah Salehuddin, Faiz Arith, Siti Aisah Mat Junos, Anis Suhaila Mohd Zain, and Khairil Ezwan Kaharudin. Numerical optimization of cspbi₃ perovskite solar cells using scaps-1d modeling. In *2025 IEEE Regional Symposium on Micro and Nanoelectronics (RSM)*, pages 61–65, 2025. ITO/TiO₂/CsPbI₃/CBTS/Ni, 24.17% claimed.
- [8] S. O. Oyedele, I. Soumahoro, L. Bamba, R. Kre, and B. Aka. Simulation-based optimization of the performance of a cspbi₃ (cesium lead triiodide) perovskite solar cell using scaps-1d. *Modeling and Numerical Simulation of Material Science*, 2023. ZnO/CsPbI₃/PTAA, 24.24% claimed; no interface layers.

- [9] Mohammed Saleh Alshaikh. Perovskiteopt-ai: A machine learning-driven multi-parameter optimization framework for lead-free perovskite solar cell device architecture using scaps-1d simulation and gaussian process surrogate modeling. *Crystals*, 16:310, 2026. doi: 10.3390/cryst16050310. FTO/WS₂/CsSnI₃/CuSCN/Au, GP-BO to 27.83%.
- [10] S. Rabhi, M. A. Benatallah, T. Hidouri, A. I. Shimul, B. C. Biswas, O. H. Alsalmi, H. A. Dmour, and M. W. Alam. Machine learning-enhanced scaps optimization of 28.38%-efficient bifacial triple-cation perovskite solar cells for building integration. *Surfaces and Interfaces*, 2026.
- [11] A. Swarnkar, A. R. Marshall, E. M. Sanehira, B. D. Chernomordik, D. T. Moore, J. A. Christians, T. Chakrabarti, and J. M. Luther. Quantum dot-induced phase stabilization of α -csppi₃ perovskite for high-efficiency photovoltaics. *Science*, 354:92–95, 2016.
- [12] L. A. Frolova, D. V. Anokhin, A. A. Piryazev, S. Y. Luchkin, N. N. Dremova, K. J. Stevenson, and P. A. Troshin. Highly efficient all-inorganic planar heterojunction perovskite solar cells produced by thermal coevaporation of csi and pbi₂. *Journal of Physical Chemistry Letters*, 8: 67–72, 2017.
- [13] B. Zhao, S.-F. Jin, S. Huang, N. Liu, J.-Y. Ma, D.-J. Xue, Q. Han, J. Ding, Q.-Q. Ge, Y. Feng, and J.-S. Hu. Thermodynamically stable orthorhombic γ -csppi₃ thin films for high-performance photovoltaics. *Journal of the American Chemical Society*, 140:11716–11725, 2018.
- [14] H. Bian, D. Bai, Z. Jin, K. Wang, L. Liang, H. Wang, J. Zhang, Q. Wang, and S. Liu. Graded bandgap csppi₂+xbr_{1-x} perovskite solar cells with a stabilized efficiency of 14.4%. *Joule*, 2: 1500–1510, 2018.
- [15] J. Xi, C. Piao, J. Byeon, J. Yoon, Z. Wu, and M. Choi. Compositional engineering of α -csppi₃ mixed-halide perovskites for efficient and stable solar cells. *Advanced Energy Materials*, 9: 1901787, 2019.
- [16] P. Becker, J. A. Márquez, J. Just, A. Al-Ashouri, C. Hages, H. Hempel, M. Jošt, S. Albrecht, R. Frahm, and T. Unold. Low temperature synthesis of stable γ -csppi₃ perovskite layers for solar cells obtained by high-throughput experimentation. *Advanced Energy Materials*, 9:1900555, 2019.
- [17] P. Luo, W. Xia, S. Zhou, L. Sun, J. Cheng, C. Xu, and Y. Lu. Solvent engineering for ambient-air-processed phase-stable csppi₃ in perovskite solar cells. *Journal of Physical Chemistry Letters*, 7:3603–3608, 2016.
- [18] W. Ke, I. Spanopoulos, C. C. Stoumpos, and M. G. Kanatzidis. Myths and reality of hpbi₃ in halide perovskite solar cells. *Nature Communications*, 9:4785, 2018.
- [19] S. Xiang, Z. Fu, W. Li, Y. Wei, J. Liu, H. Liu, L. Zhu, R. Zhang, and H. Chen. Highly air-stable carbon-based α -csppi₃ perovskite solar cells with a steady-state efficiency of 9.5%. *ACS Energy Letters*, 3:1824–1831, 2018.
- [20] Y. Wang, X. Liu, T. Zhang, X. Wang, M. Kan, J. Shi, and Y. Zhao. Aziridinium lead iodide for efficient and stable csppi₃ perovskite solar cells. *Angewandte Chemie International Edition*, 58:16691–16696, 2019. 18.40% experimental CsPbI₃.
- [21] M. K. Ristiansyah, B. Prasetya, M. G. I. Khan, M. Y. Siregar, A. A. S. Panjaitan, E. Widiyanto, et al. Design and optimization of csppi₃ perovskite solar cells using scaps-1d. *Greensusmater*, 2026. FTO/ZnO/CsPbI₃/Spiro-OMeTAD, 16.3 to 23.1%.
- [22] C. Son, H. Son, and B.-S. Jeong. Enhanced conversion efficiency in mapbi₃ perovskite solar cells through parameters optimization via scaps-1d simulation. *Applied Sciences*, 14:2390, 2024. ITO/TiO₂/MAPbI₃/Cu₂O/Au, 19.30%.

Table 12: Simulation batches archived under leadpaper/.

Batch	Configurations	Receipt
Baseline validation	4 (one worker-crash retry)	baseline_results.json
Unit diagnostics	6 + 4 retries	diag_units.json
Round A grid	96 (3 non-converged)	roundA.jsonl
Round B refine	36 (3 non-converged)	roundB.jsonl
Characterisation + audit + T	17 + 6 re-runs	char.jsonl
Set-command verification	5	s0_verify.json
Interface dose + Rs/Rsh + WF	14	s1_dose.json
$N_t \times \sigma$ joint	3	s4_sig.json + s4b_sig.json
Morris screen	56 (0 errors)	s5_morris.jsonl

- [23] R. Ritu, G. Gagandeep, R. Kumar, and F. Chand. Performance optimization of fapbi3 based perovskite solar cell. *AIP Conference Proceedings*, 2995:020142, 2024. FTO/TiO2/FAPbI3/Spiro-OMeTAD/Ag, 20.34% with gradient doping.
- [24] M. A. Rahman and M. J. Alam. Machine learning-guided scaps-1d design of lead-free ch3nh3sni3 perovskite solar cells with 40.17% simulated pce. *Journal of Materials Science: Materials in Engineering*, 2026. Idealized upper limit exceeding the Shockley-Queisser bound.
- [25] W. Shockley and H. J. Queisser. Detailed balance limit of efficiency of p-n junction solar cells. *Journal of Applied Physics*, 32:510–519, 1961.
- [26] Y. H. Khattak. *Modeling of High Power Conversion Efficiency Thin Film Solar Cells*. PhD thesis, Universitat Politecnica de Valencia, 2019. SCAPS device physics reference.
- [27] M. Burgelman, K. Decock, A. Niemegeers, J. Verschraegen, and S. Degraeve. Scaps-1d solar cell capacitance simulator (version 3.3.10), 2021. Device simulator and scripting reference.
- [28] Y. Raoui, H. Ez-Zahraouy, N. Tahiri, O. El Bounagui, S. Ahmad, and S. Kazim. Performance analysis of mapbi3 based perovskite solar cells employing diverse charge selective contacts: Simulation study. *Solar Energy*, 193:948–955, 2019.
- [29] B. Li, Y. Zhang, L. Fu, T. Yu, S. Zhou, L. Zhang, and L. Yin. Surface passivation engineering toward high efficiency perovskite solar cells. *Nature Communications*, 9:1076, 2018.

Appendix A: the scripting unit trap

SCAPS definition files store SI units (metres, m^{-3} , m^2/Vs) but script set commands expect practical units (μm , cm^{-3} , cm^2/Vs)—verified by dose–response: set layer2.NA 1e15 reproduces the file baseline (stored 10^{21} m^{-3}) exactly, while SI-valued inputs (e.g. 10^{22}) inject a $10^6\times$ overdose and yield degenerate ghost cells (Voc 1.47–1.53 V, FF 91–92%, up to 27%). Practical flags that catch them: Voc above the E_g -implied ceiling for the modelled gap, or FF above Green’s ideal-diode value at the measured Voc. All values in this paper are stated in the units the script layer expects; the archived logs record both.

Appendix B: run inventory

All simulation batches are inventoried in Table 12.