


Mathematical modelling for the next-generation All-solid-state batteries: Nucleation (SE|SSE)^(*)-interface

Rechargeable Lithium-ion battery (LIB) stays at the heart of electric vehicles, portable electric devices, and energy storage systems [1]. Nowadays, LIBs help human life become more efficient as well as to cope with global environment issues thanks to its zero emission. However, conventional LIB (cLIB) is sensible to temperature and pressure, easily prone to flammable and explosive. This is mainly due to liquid-based electrolyte found in cLIBs. **All-solid-state battery** (ASSB) is, therefore, one of promising candidates to overcome bottlenecks of conventional LIBs. It is because the solid-state electrolyte (SSE) in ASSB, e.g. SSE made of the highly ionic-conductive polycrystalline LLZO, is highly stable towards temperature and pressure. Nevertheless, metallic Lithium dendrite triggered at (SE|SSE)-interface is the main drawback as these dendritic threads extrapolate into grain boundary network of SSE, causing degradation of ionic conductivity and the likelihood of short-circuit.

$$a_{\text{Griffith}} := a^* = \arg \min_{a \in \mathbb{R}} \iint_{\Omega} f(a, \mathbf{u}; \lambda, \mu, \mathbf{d} \otimes \mathbf{d}) d\Omega - \iint_{\Gamma} f(a; \gamma) d\Gamma \Big|_{\mathbf{u}^{(s)}}$$

Next-generation All-solid-state battery (ng-ASSB) should, consequentially, be able to cope with micro-dendritic threads at the (SE|SSE)-interface, and hence, to foresee nucleation points caused by propagations



Next-generation All-solid-state battery

Interface between solid electrode and solid-state electrolyte (SE|SSE) taking place at space charge layer (SCL) [2] found in all-solid-state lithium-ion batteries (ASSLiBs) critically exhibits mechanical and electrochemical instability [3]. This evidence points directly to the fact that the soft metallic lithium negative electrode is erroneously prone to triggering dendritic by-products of silvery lithium metal, under cycles of electric charge & discharge [4]. Besides, polycrystalline garnet-typed solid-state electrolyte such as LLZO exhibit grain boundaries and various sizes and shapes of grains under microscopic observation. Therefore, this type of microstructure distinctively leads to nuance destruction of ceramic-like materials. Consequentially, dendritic by-products contribute to degradation of ionic conductivity and trace along grain boundaries in SSE.

$$\rho \partial_t^2 \mathbf{u}^{(s)} + \nabla \cdot \left(\mathbb{C}^{\text{D}(\Omega)}_{(\lambda, \mu)} : \nabla \mathbf{u}^{(s)} \right) + \rho \nabla V_e = \mathbf{0},$$


$$\text{s.t. } a_{\text{Griffith}} := a^* = \arg \min_{a \in \mathbb{R}} \iint_{\Omega} f(a, \mathbf{u}; \lambda, \mu, \mathbf{d} \otimes \mathbf{d}) d\Omega - \iint_{\Gamma} f(a; \gamma) d\Gamma \Big|_{\mathbf{u}^{(s)}}$$

where


Electrical field + Polarization + Structural tensor

Nucleation interface: Taking place at the critical dendritic interface


Nucleation interface: Taking place at the critical dendritic interface (SE|SSE)



Distribution of the analytical maximal shear stress component $\mathcal{W}_{\sigma}^{\Pi}$ around the crack tip a_c .



The set of boundary conditions is likewise the path of the pressure-centric dendritic crack.



Nucleation interface: Taking place at the critical dendritic interface (Solid electrode | Solid-state electrolyte) Nucleation interface: Taking place at the critical dendritic interface Nucleation interface: Taking place at the critical dendritic interface (Solid electrode | Solid-state electrolyte) Nucleation interface: Taking place at the critical dendritic interface

Contact

Tuan Vo
vo@acom.rwth-aachen.de



Scan me

References

- [1] **T.Vo**, *Modeling the swelling phenomena of li-ion batt. cells based on a numerical chemo-mech. coupled approach*. MA, Robert Bosch Battery Systems GmbH, 2018.
- [2] **S.Braun**, C.Yada and A.Latz, *Thermodynamically consistent model for Space-Charge-Layer formation in a solid electrolyte*. Jr. Phys. Chem., 119, 22281-22288, 2015.
- [3] **C.Hüter**, S.Fu, M.Finsterbusch, E.Figgemeier, L.Wells, and R.Spatschek, *Electrode-electrolyte interface stability in solid state electrolyte system: influence of coating thickness under varying residual stresses*. AIMS materials Science, 4(4):867-877, 2017.
- [4] **S.Kim**, J.S.Kim, L.Miara, Y.Wang, S.K.Jung, S.Y.Park, Z.Song, H.King, M.Badding, J.M.Chang, V.Roev, G.Yoon, R.Kim, J.H.Kim, K.Yoon, D.Im, and K.Kang, *High-energy and durable li metal batt. using garnet-type solid electrolytes with tailored li-metal compatibility*. Nature Communications, 13(1):1883, 2022.