

Plant	Casting Date	Customer Name	Grade	Cement Name	7 Days Testing		28 Days Testing	
					Strength & Strength %	Trial Status	Strength & Strength %	Trial Status
Rajarhat	27/05/2026	RDB ANEKANT (URBAN PARK)	M60	RAMCO 53 (OPC)	53.33 (89%)	55.69 (80%)	67.56 (113%)	73.22 (105%)
Rajarhat	02/06/2026	RDB ANEKANT (URBAN PARK)	M60	RAMCO 53 (OPC)	54.67 (91%)	55.69 (80%)		
Rajarhat	10/06/2026	RDB ANEKANT (URBAN PARK)	M60	RAMCO 53 (JP) (OPC)	49.11 (82%)	55.69 (80%)		
Rajarhat	13/06/2026	RDB ANEKANT (URBAN PARK)	M60	RAMCO 53 (JP) (OPC)	52.67 (88%)	55.69 (80%)		
Rajarhat	14/06/2026	RDB ANEKANT (URBAN PARK)	M60	RAMCO 53 (JP) (OPC)	54.89 (91%)	55.69 (80%)		