

Table of Contents

1	General	3
2	Dimensional Specification	3
3	Magnetic Input Specification	3
4	Magnet Supplier Information	5
Copyrigh	t	6
Disclaime	er	6

Revision History

Revision	Date	Owner	Description
0.2	8 Sept 2014	ekno	New design layout

www.ams.com page 2/6



1 General

This specification defines the dimensional and magnetic properties of a multi pole magnetic strip for use with the AS5304 magnetic linear motion and off-axis rotary angle encoder.

Material: rubber bonded Strontium Ferrite SrFe.

2 Dimensional Specification

Magnet Order # MS20-50 on ams web shop, refer to Figure 1

Parameter	Symbol	Min	Тур	Max	Unit	Note
Strip Width	W	100,8 4	101, 6	102,36	mm	4.00" +/- 0.030"
Strip Cut Length	S	4,62	5,0	5,38	mm	0.197" +/- 0.015"
Strip Thickness	Т	0,762	0,76 2	0,813	mm	0.030" +0.00" / - 0.002"
Thermal expansion			49		x10-6/K	Mechanical length expansion
Density			3,4		g/cm3	estimated
Delivery 4,00" x 0.030" x 200' Outdoor adhesive, cut thru .197". Minimum 1 rolls (~ 12.000 strips).						

3 Magnetic Input Specification


Magnet Order # MS20-50 on ams web shop, refer to Figure 1

Parameter	Symbol	Min	Тур	Max	Unit	Note
Pole length	Lp		2,00		mm	results in pole pair length of 4mm
						(50 poles @ 2,0mm, 2 border poles ~1,0mm)
Resolution	Res		25		μm	With AS5304 @ maximum interpolation
Pole length deviation				+/- 50	μm	Measured at Bz=0, all poles (Lp) within active region
Number of poles			50		poles	Excluding poles with L <lp at="" ends="" of="" strip<="" td="" the=""></lp>
Magnetic field amplitude @ 0.5mm distance	B _{pk}		15		mT	Vertical component of the magnetic field strength in the center of the strip at 25°C
Amplitude variation				+/-1,5	mT	All poles within active region
Active Region to strip edge	A			0,5	mm	estimated

www.ams.com page 3/6



Parameter	Symbol	Min	Тур	Max	Unit	Note
First Bz=0 position to strip edge	D1	TBD	1,0	TBD	mm	Tolerance estimated +/-0,25μm
Last Bz=0 position to strip edge	D2	TBD	1,0	TBD	mm	Tolerance estimated +/-0,25µm
Temperature range	Tamb	-18	25	80	°C	
Temperature drift	Tk _{Br}		+0.2		%/K	Magnetic field temp, drift



www.ams.com page 4/6



4 Magnet Supplier Information

ARNOLD Magnetic Technologies
107 Industry Road
Marietta, OH 45750
http://www.arnoldmagnetics.com/sales/index.htm

www.ams.com page 5/6



Copyright

Copyright © 1997-2014, ams AG, Tobelbader Strasse 30, 8141 Unterpremstaetten, Austria-Europe. Trademarks Registered ®. All rights reserved. The material herein may not be reproduced, adapted, merged, translated, stored, or used without the prior written consent of the copyright owner.

All products and companies mentioned are trademarks or registered trademarks of their respective companies.

Disclaimer

Devices sold by ams AG are covered by the warranty and patent indemnification provisions appearing in its Term of Sale. ams AG makes no warranty, express, statutory, implied, or by description regarding the information set forth herein or regarding the freedom of the described devices from patent infringement. ams AG reserves the right to change specifications and prices at any time and without notice. Therefore, prior to designing this product into a system, it is necessary to check with ams AG for current information.

This product is intended for use in normal commercial applications. Applications requiring extended temperature range, unusual environmental requirements, or high reliability applications, such as military, medical life-support or lifesustaining equipment are specifically not recommended without additional processing by ams AG for each application. For shipments of less than 100 parts the manufacturing flow might show deviations from the standard production flow, such as test flow or test location.

The information furnished here by ams AG is believed to be correct and accurate. However, ams AG shall not be liable to recipient or any third party for any damages, including but not limited to personal injury, property damage, loss of profits, loss of use, interruption of business or indirect, special, incidental or consequential damages, of any kind, in connection with or arising out of the furnishing, performance or use of the technical data herein. No obligation or liability to recipient or any third party shall arise or flow out of ams AG rendering of technical or other services.

Contact Information

Headquarters

ams AG
Tobelbader Strasse 30
8141 Unterpremstaetten
Austria
T. +43 (0) 3136 500 0
For Sales Offices, Distributors and Representatives, please visit: http://www.ams.com/contact

www.ams.com page 6/6