

HOFSTR. 1 CH-8181 HÖRI SWITZERLAND

Web: www.bomatec.ch

FON: +41 1 872 10 00 FAX: +41 1 872 10 01 Mail: contact@bomatec.ch

Data sheet for Magnet used with AMS AS5035 / 5040 / 5043 / 5045

Type: NdFeB sintered magnet

Quality: BMN-35H

Dimension: Ø6 x 2.5 mm, tolerances ±0.1 mm

Execution: diametral magnetized, Ni-coated

Remark: magnets are available ex our warehouse

Magnetic properties:

Quality	Remanence			Coercitivity	_	max. Energy Product		max. working
	Br		HcB		HcJ	(BH)max		temperature
	Т		kA/m		kA/m	kJ/m		Tw*
	kGs		kOe		kOe	MGOe		(L/D=0.7)
	Nom	Min	Nom	Min		Nom	Min	°C
BMN-35H	1.21	1.17	907	860	>1353	279	263	120
	12.1	11.7	11.4	10.8	>17	35	33	120

Demagnetization curve:

