Misorientation accumulation along columnar grains in GammaPrint-700 laser powder bed fusion: 3D-EBSD (Lamb et al.) versus SPPARKS

SURGE-kokkos branch, `additive/texture/kk` Moser deck

Revision 2, 2026-09-09

Abstract

Lamb et al. measured the starting reference orientation deviation (SROD) of columnar grains in a 3D-EBSD volume of laser powder bed fusion GammaPrint-700 (Scripta Materialia 2024) and, at higher resolution, within grains and cells (Met. Trans. A 2026). Re-analysing their population curves shows statistics consistent with a random-axis rotation walk, $\mathrm{RMS}^2 = Dh$ with $D \approx 0.42\,\mathrm{deg}^2/\mu\mathrm{m}$ against build height and a 5/95 width of about 1.4 times the mean, the Maxwell value; the published curves do not distinguish this from the authors' own two-regime reading over most of the height range, and the mechanism (Lamb: mushy-zone shrinkage and thermomechanical cycling in the heat-affected zone) is not identified by the statistics. Their example grains rotate along a directed path. SPPARKS `additive/texture` and `additive/texture/kk` carry a phenomenological two-term model applied at capture: a per-voxel walk inherited along each lineage and a coherent per-grain walk of the rotation vector, indexed by inheritance path length and correlated between levels. A Moser-source GP700 deck calibrated on the 2024 originating-grain curve (in-sample RMS 0.34°) reproduces two targets it was not tuned on: the established-grain curve of the same paper (RMS 0.28°, bias −0.11°) and the modal SROD trajectory of the 2026 dataset over its first 120 µm; the per-voxel model alone fails the first (bias 3.0°). Per grain, the model's accumulation rate (mean 0.84° per 30 µm) is half the 2026 average and its extremes fall well short of Lamb's (5 % of grains above 25° against "most"). Further limitations: the grain structure is locked to the registered hatch pattern of the deck, no surviving grains originate mid-build at any nucleation density tested, results are from single realisations pending the seed study, and a 2° re-segmentation changes the simulated grain population.

1 Summary

- Population SROD statistics in GP700 are those of a finite-variance rotation walk: mean $\propto \sqrt{h}$ within the resolution of the published curves, $D \approx 0.42\,\mathrm{deg}^2/\mu\mathrm{m}$, Maxwell width. The same statistics arise from any process with independent increments per unit height, so they constrain the process, not its mechanism. Lamb's example grains (2024 Fig. 4) rotate coherently along a path.
- Model, both SPPARKS additive apps: `misorientation_diffusion` D_v (per-voxel walk, inherited per hop) plus `misorientation_grain_walk` D_g ρ `path` (coherent per-grain walk, one Gaussian rotation-vector increment per unit of inheritance path length, shared by every voxel of the grain, correlated between levels with persistence ρ). Orientation is inherited from one parent voxel and never averaged. The model is an at-capture proxy for what Lamb attribute to post-solidification plasticity.
- Deck v10: D_v $0.065\,\mathrm{deg}^2/\mu\mathrm{m}$, D_g $0.010\,\mathrm{deg}^2/\mu\mathrm{m}$, $\rho = 0.9$ (correlation length $\approx 30\,\mu\mathrm{m}$ of path), calibrated on the 2024 originating curve (in-sample RMS 0.34°). Held-out: established curve RMS 0.28° / bias −0.11° (v8, per-voxel only: 2.99° / 2.98°); 2026 Fig. 7a mode 1.6 → 4.7° over 5–115 µm against the model's 0.8 → 4.8°.

- Per grain (96 filtered grains): drift of the mean orientation median 7.2° (v8 4.2°), spread 3.4° (v8 6.1°). Against Lamb: accumulation rate mean 0.84 / max 1.92° per 30 µm (2026: 1.7 / 5.8); grains with maximum SROD > 25°: 5 % (2024: "most"); per-layer mean at 300 µm median 10.8°, max 18° (2024 example grains: 20–25°).
- Path length per unit height measured from the d10 field: 1.47. The deck constants are per unit of growth path.
- Limitations: hatch-locked grain structure (boundary autocorrelation 0.6–0.7 at the 80 µm lag; sensitivity run pending); no surviving mid-build origins at nucleation 6.5×10^{12}–8.5×10^{13} $1/m^3$ (0–7 grains per run against Lamb's > 500); a 2° re-segmentation gives 139 filtered grains of ESD 29 µm (spin labels: 96, 148 µm) with the SROD curve within 0.6°; single realisations (seed study pending); the ⟨001⟩ fraction within 15° of BD is 0.15–0.19 against a random 0.10 and has no measured target.

2 Experimental methods (Lamb et al. 2024, 2026)

Material and process. CoNi-base superalloy GammaPrint-700 (SB-CoNi-10), laser powder bed fusion on an SLM Solutions SLM125 at 176 W and 1137 mm/s, 80 µm spot (the papers give the spot size only; the deck reads it as $D4\sigma$), 80 µm hatch, 30 µm layers, bidirectional scan with 90° interlayer rotation repeating every two layers, scan directions at 45° to the block edges, single 10 mm raster, 200 °C plate preheat. The hatch registration between layers of the same direction is not stated. The 2026 paper supplies the thermophysical set used for its 3DThesis simulations: $k = 22.5\,\mathrm{W/(m\,K)}$ (extrapolated to 950 °C), $\rho = 8650\,\mathrm{kg/m^3}$, $c_p = 600\,\mathrm{J/(kg\,K)}$ (IN718 at 1000 °C), liquidus 1373 °C (1646 K), and an absorptivity of 0.9 selected to reproduce measured pool dimensions; the solidus, 1319 °C (1592 K), is from the 2024 paper.

3D datasets. 2024: TriBeam tomography (femtosecond-laser serial sectioning with EBSD on each slice), 1.5 µm voxels, 385 slices, a 1400 × 412 × 477 µm volume with over 9000 grains, reconstructed in DREAM.3D and segmented at a 2° misorientation threshold before any SROD calculation. 2026: a 120 × 120 × 169 µm volume at 0.1 × 0.1 × 1 µm resolving cells.

SROD. For each grain the reference orientation sits near the origination point, "the lowest location of a grain's boundary along the build direction", offset one voxel layer (1.5 µm) upward so the reference is not a boundary pixel; offsets up to 8 µm do not change the result. *Originating* grains have their lowest point inside the volume; *established* grains are cut by the dataset floor and referenced at the centroid of their footprint on the lowest slice. Grains shorter than 60 µm (two layers) or under 40 µm equivalent spherical diameter (ESD) are excluded, leaving over 500 originating and 100 established grains. Each grain is sliced along the build direction; each slice gives a SROD histogram fitted to a normal distribution, and the mean and the 90 % interval of that fit are plotted against height above the origin (Fig. 5a) or above the dataset floor (Fig. 5c). Fig. 4 follows four grains (G1–G4) with IPF and SROD maps, the mean SROD per layer (20–25° after > 300 µm), and every voxel on the build-direction inverse pole figure with an arrow for the rotation path from bottom to top; G4 splits into two orientation clusters. The maximum SROD in any grain is 58.7°; "most columnar grains" contain over 25°. The 2026 paper's Fig. 7a is a heatmap of SROD against distance from the grain start over 0–120 µm, with quoted average and maximum accumulation rates of 1.7 and 5.8° per 30 µm for bulk grains (2.5 and 7.2° for cells); it also reports that cells switch ⟨100⟩ growth variants at fusion lines rather than rotating continuously. Both papers attribute the misorientation to plastic deformation: solidification shrinkage in the mushy zone and thermomechanical cycling in the heat-affected zone of subsequent layers.

3 Analysis of the experimental data

Fig. 5a and 5c of the 2024 paper were digitized from 300 dpi renders (`docs/srod_random_walk.py`; curves in `docs/lamb2023_fig5{a,c}_srod.json`); no digitization uncertainty is claimed beyond the line width, about 0.3°. The curves were compared with a rotation walk: independent small rotations of angle θ about random axes give

$$\mathrm{RMS}^2 = n\,\theta^2 = D\,d, \tag{1}$$

a Maxwell distribution (χ with three degrees of freedom) with mean = 0.921 RMS, and a 90 % interval of 1.38× the mean at every distance, which is also the value of 3.29σ/mean for the normal fits Lamb plot. D was fitted by least squares of $\mathrm{RMS}^2 = Dh$ to the digitized mean over 0–265 µm with the 0.921 factor applied.

Findings (Fig. 1): $D = 0.42\,\mathrm{deg}^2/\mu\mathrm{m}$ fits the originating mean, and the measured width ratio is 1.3–1.5 at every height for the originating grains. The established grains are described by the same D only after adding an initial spread of 6.2° RMS in quadrature (one fitted parameter, the orientation scatter already present at the dataset floor); with it, their width ratio falls to 1.1–1.25 beyond 150 µm, as expected for a non-central distribution, and their mean runs above the model past 300 µm. Over 30–260 µm the square-root curve and Lamb's own reading (a fast first 30 µm, then 0.85° per layer) lie within the line width of each other; the two differ only below 30 µm, where the digitization is least reliable. The population statistics therefore establish independent finite-variance increments per unit height and their magnitude, not the mechanism, and not whether the increments belong to voxel lineages or to whole grains: each grain's coherent walk is one realisation, and the Maxwell width appears across grains either way. Fig. 4 supplies the missing information for four grains: the mean orientation moves along a path, so at least part of the accumulation is coherent across a grain.




Figure 1: Lamb 2024 Fig. 5 digitized. (a) Mean SROD of originating grains with $\mathrm{RMS}^2 = Dh$, $D = 0.42\,\mathrm{deg}^2/\mu\mathrm{m}$, and the authors' two-regime reading. (b) Established grains with the same D plus a fitted 6.2° RMS initial spread. (c) Width ratio (90 % interval over mean) against height for both classes; the Maxwell value is 1.38.

4 Simulation methods

Code. SPPARKS, branch SURGE-kokkos, app `additive/texture/kk` (Kokkos/HIP on an AMD gfx1151 APU), one MPI rank. The CPU app `additive/texture` carries the same model and is the correctness reference; the temperature field is deterministic and bit-identical between the two (`examples/am_validation/`). Microstructure is not deterministic on the GPU, so every build is one realisation of its seed.

Thermal source. Moser Green's-function solution with the GP700 constants (`setup_temperature_source moser 176 0.9 22.5 4.335e-6 473 600 20e-6 20e-6 10e-6`: power, absorptivity, conductivity, diffusivity, preheat, heat capacity, and the Gaussian source widths $\sigma_x, \sigma_y, \sigma_z$ of 20, 20, 10 µm), evaluated on the device for every site each step. Scan lines with `hatch 80e-6 N serpentine pause 8.8e-3`, the pause being the 10 mm track length over the scan speed; the fast-forward predictor skips idle gaps. Single-hatch check: pool 147 × 69 µm, thermal gradient 1×10^7–2.9×10^7 K/m at the fusion boundary (paper: 3×10^7 K/m).

Build. Box-per-layer stitch continuation (`run_layers.sh`): each layer is a separate SPPARKS run of a 180 µm window below the laser plane, started from the preheat and from the previous layer's microstructure. Domain 801 µm square (267 voxels at 3 µm), 10 hatches at $40 + 80k$ µm with lines 100 µm past both edges, 12 layers of 30 µm, 90° rotation per layer; layers of the same direction have their hatches at the same positions (registered), which is the deck's assumption where the papers are silent. Substrate: 150 µm of 50 µm Voronoi grains with uniform random orientations (`make_substrate.py`); five overlapping hatches remelt 80–100 µm, so the analysable solid begins at 105 µm (the analysis floor is set at 100 µm). Timestep 4 µs, twice the front-advance limit $\Delta x/V(T_l - T_s)$; 2 and 4 µs agreed on grain count and size within the run-to-run scatter. Calibration used a 600 µm, 7-hatch, 8-layer proxy at 3 min of loop time per box.

Solidification kinetics. Front velocity is the 304L polynomial of undercooling used by the additive app, scaled ×3.5 (front at 25–35 K undercooling, about 0.56 m/s, keeping up with the 1.137 m/s scan); nucleation density $1.5 \times 10^{13}/\mathrm{m}^3$, critical undercooling $t_c = 15$ K, deviation 2 K. Parent selection per grain: candidate neighbours are grouped by grain, each grain weighted by the mobility $1 + c_2 \cos(c_3\theta)$ of its sign-aligned mean orientation against the local thermal gradient (θ the angle between the nearest $\langle 100 \rangle$ of that mean orientation and the gradient; $c_2 = 2.8$, $c_3 = 2.5$, negative clamped to zero), then the parent voxel is drawn uniformly inside the chosen grain. Weighting among the voxels of one grain instead rotated grains toward $\langle 001 \rangle$ with height and is not used.

Misorientation model. Two terms, both applied at capture in the sample frame. The model is a phenomenological proxy: it places at solidification the rotation that Lamb attribute to shrinkage in the mushy zone and to cycling in the heat-affected zone of later layers. It therefore cannot represent any dependence of a voxel's SROD on the number of layers deposited above it, and a 12-layer build is compared here with material from the interior of a 10 mm block.

- *Per-voxel walk*, `misorientation_diffusion` D_v `30`: the captured voxel takes its parent's orientation rotated by $\theta = \sqrt{D_v \, \mathrm{hop}}$ about a random axis (hop = lattice distance to the parent, so D_v is per unit of growth path). A rotation past 30° would start a new grain (never reached). Independent lineages of one grain diverge, so this term supplies intragranular spread and no net drift.
- *Coherent grain walk*, `misorientation_grain_walk` D_g ρ `path`: every voxel carries its inheritance path length s in lattice units (per-site field d10: zero at melt and at nuclei, parent plus hop at capture, copied with the orientation on a smoothing flip, exchanged with ghosts and continued through the stitch). Between path levels k and $k+1$ every voxel of grain g receives the same rotation, a Gaussian rotation vector v_k of RMS $\sqrt{D_g \Delta x}$ whose sequence in k is Ornstein–Uhlenbeck, $v_k = \rho\, v_{k-1} + \sqrt{1-\rho^2}\, v'_k$, with v'_k hashed from (g, k) so the sequence is a pure function of grain and level, path independent and without stored state. The correlation length is $\approx \Delta x/(1-\rho)$ of path and the long-range accumulation is $D_g(1+\rho)/(1-\rho)$ per unit path; ρ is defined per lattice level, so a change of Δx requires $\rho' = 1 - (1-\rho)\Delta x'/\Delta x$ to keep the correlation length and a corresponding rescaling of

D_g (Section 6.8). This term supplies the coherent drift. A device cache of the recurrence makes it cost nothing measurable.

Boundary smoothing. One greedy steepest-descent pass per captured voxel (`smooth_greedy_multiproposal on`, nrefine 1) the step after capture, and `smooth_orientation copy`: a voxel that changes grain takes one random neighbour's orientation and path length from that grain. The default `average` (sign-aligned mean of the new grain's neighbours) cancels the fresh rotations of a voxel-scale mixed front, retains only 0.3–0.45 of the input D and widens the population band to 1.8; it is not used.

5 Simulation analysis methods

`gp700_analysis.py` on the spparks-micro-analysis tools: read the last stitch frame; solid means `i2 == 3` (solidified; unremelted substrate, `i2 == 1`, is excluded); crop to the central 400 µm laterally (300 µm on the proxy), grains cut by the crop faces kept with their cropped volume; label grains as connected components of the spin field, or optionally re-segment at a disorientation threshold (`-segment-deg`); grain volume, ESD and extents; Lamb's filters (height $\geq$ 60 µm, ESD $\geq$ 40 µm); origin = the grain's lowest solid voxel, whose quaternion is the reference (exact in the simulation, so no offset); grains crossing the analysis floor are established and referenced at their floor-slice centroid. SROD is the symmetry-reduced disorientation of every voxel from its grain's reference, binned by height above the origin or floor in 10 µm steps with mean, p_5, p_{95} and RMS per bin. Score: RMS of (simulated mean − Lamb Fig. 5a mean) over 25–240 µm, its bias, the band ratio $(p_{95} - p_5)$/mean averaged over the same bins, the fraction of solid within 15° of $\langle 001 \rangle$ parallel to the build direction (random: 0.102 by Monte Carlo), and grain counts. Sobol designs (scipy `qmc`) on the proxy were used for calibration against the Fig. 5a score; the Fig. 5c established curve and the 2026 Fig. 7a heatmap were not used in calibration.

`grain_paths.py` reproduces Lamb's Fig. 4 per grain and extends it to every filtered grain: IPF-Z and SROD maps on the xz slice through the grain, mean SROD per 10 µm slab, the per-slab mean orientation as a path on the build-direction inverse pole figure, the drift of the mean orientation from the bottom three slabs to the top three, the RMS spread of the top slabs about their mean, the maximum SROD, the per-layer mean at 300 µm, the accumulation rate (drift per 30 µm of height), the path length per unit height from d10, and the fraction of slabs in which the mean SROD rises. Both scripts use the same labelling, so the filtered-grain counts agree except that `grain_paths.py` drops grains with fewer than 20 voxels in their bottom or top slabs (97 vs 96 in v10, 88 vs 86 in v8). `hatch_periodicity.py` measures the boundary-voxel density across the crop, its autocorrelation at the hatch lag, and in-plane grain widths by line intercept; `origin_census.py` counts filtered grains that originate more than 60 µm above the first remelt floor.

6 Results

6.1 Calibration path

Table 1: Full builds against Lamb 2024 Fig. 5a (all-originating SROD, central 400 µm crop, one realisation each).

build	model	RMS / bias vs Fig. 5a	band ratio	per-grain drift / spread (median)
v2	per-voxel walk, D_v 0.42, voxel-level parent selection	2.2° / 3.6° (linear growth)	1.4–1.8	–
v5	per-grain parent selection, average smoothing, D_v 1.15	0.59° / −0.16°	1.79	–
v8	copy smoothing, D_v 0.22	0.49° / 0.17°	1.41	4.2 / 6.1°
v10	**+ coherent path walk D_g 0.010, ρ 0.9; D_v 0.065**	**0.34° / −0.28°**	**1.50**	**7.2 / 3.4°**

The Fig. 5a score is the calibration target, so the v8 and v10 rows are in-sample fits, and their difference (0.49 vs 0.34°) is within the digitization line width; the population curve does not choose between the two models. v2's linear growth was selection drift among the voxels of one grain. v5 to v7 retained only 0.3–0.45 of the input D against height with a 1.8 band, both from the averaging smoothing rule; copy-mode smoothing (v8) put the population curve, shape and band on Lamb. v8's grains, however, spread without drifting, whereas Lamb's grains move along a path; the coherent grain walk (v10) supplies the drift. A memoryless coherent walk makes individual SROD(h) curves wander; correlating the rotation vector between levels (ρ) makes them rise along a directed path, and with Gaussian increments the population band stays at Lamb's value in both the ballistic and the diffusive regime.

6.2 Held-out comparisons

Table 2: Targets not used in calibration. Established class: simulated grains crossing a 240 µm floor, referenced at their floor-slice centroid, against Lamb Fig. 5c over 25–233 µm. 2026 Fig. 7a: voxel-weighted SROD distribution of originating grains against distance from the grain start, digitized from the heatmap (mode and density-weighted mean; the heatmap also contains a secondary band at 10–15° at all distances that raises its mean).

	v10	v8	Lamb
established vs Fig. 5c: RMS / bias	0.28° / −0.11°	2.99° / 2.98°	–
established band ratio	1.39	1.49	1.4 (2024, above 100 µm: 1.1–1.25)
established mean at 25 / 100 / 160 µm	5.5 / 7.3 / 8.8°	9.2 / 10.5 / 11.7°	6.2 / 7.5 / 8.9°
2026 Fig. 7a mode at 5 / 30 / 60 / 115 µm	0.8 / 1.8 / 2.8 / 4.8°	1.8 / 2.8 / 3.8 / 5.8°	1.6 / 2.9 / 3.7 / 4.7°
2026 Fig. 7a mean at 5 / 60 / 115 µm	1.3 / 3.6 / 5.8°	2.1 / 4.4 / 6.4°	4.9 / 5.2 / 6.2°




Figure 2: Voxel-weighted SROD against height above the grain origin over the first 120 µm for the filtered originating grains of v10 (left) and v8 (right), with the digitized mean and mode of Lamb 2026 Fig. 7a and the 2024 Fig. 5a mean.

The established class is the discriminating test. The per-voxel model's floor-referenced grains start 3° too high because their lineages have already diverged across the grain by the time they cross the floor, whereas the coherent model, whose intragranular spread is small, reproduces the curve to 0.28° with the Maxwell band. On the 2026 heatmap the modal trajectory of v10 follows Lamb's from 1.6 to 4.7° over 5–115 µm (the paper's quoted average rate of 1.7° per 30 µm is the slope of that ridge near the start); the experimental mean is higher than either model at small distances because of a secondary population at 10–15° present from the grain start, which the model does not produce and which resembles the split grain G4.

6.3 v10 against Lamb Fig. 5a

Table 3: v10: D_v 0.065 deg^2/µm, D_g 0.010 deg^2/µm, ρ 0.9 path, copy smoothing, nrefine 1, Voronoi substrate, nucleation 1.5×10^{13}/m^3, t_c 15 K, c_2 2.8, Δt 4 µs, 3 µm; single realisation.

	v10	v8 (per-voxel only)	Lamb 2024
SROD RMS deviation, 25–240 µm (in-sample)	0.34°	0.49°	–
mean bias	−0.28°	0.17°	–
mean SROD at 54 / 204 / 402 µm	3.6 / 8.2 / 12.1°	4.4 / 8.5 / 12.3°	3.8 / 8.8 / – (data end at 262 µm)
band ratio, 25–240 µm average	1.50	1.41	1.4
D-fit vs height	0.43 deg^2/µm	0.41 deg^2/µm	0.42
grains passing filters (400 µm crop)	97	86	> 600 (full volume)
ESD p_{10} / p_{50} / p_{90}	76 / 148 / 170 µm	73 / 151 / 182 µm	–
⟨001⟩ within 15° of BD (random 0.10)	0.15	0.19	not reported




Figure 3: v10, all-originating SROD against height above the origin (central 400 µm crop, floor 100 µm): simulated mean with the 5/95 band (blue) against Lamb 2024 mean and 90 % interval (orange).

6.4 Per-grain orientation paths

The coherent term changes the per-grain picture in the way Lamb's Fig. 4 requires: the mean orientation of a v10 grain drifts more than it spreads, the drift scales with height (about 2° at 100 µm, 8–15° at 400 µm), and the paths are directed; v8's grains spread more than they drift at every height. Against Lamb's numbers, however, both models fall short. The accumulation rate of the v10 grains is half the 2026 average and its maximum is a third of theirs; the per-layer means at 300 µm reach 18° at most against 20–25° for Lamb's example grains; and 5 % of the v10 grains exceed 25° anywhere, against "most" in the experiment. The population mean is matched, so the experimental population must carry a much heavier tail, a minority of grains rotating several times faster than the median, than a single Gaussian D_g produces; the 10–15° secondary band of the 2026 heatmap and the split grain G4 point the same way. The paths have no preferred direction on the triangle, as the isotropic rotation vector implies; the experimental direction is not reported. Monotonicity does not separate the models (0.79 vs 0.78): about a fifth of the grains reverse over 100 µm scales in both. The per-grain drift-to-spread ratio confirms




Figure 4: v10 IPF-Z colouring: xz and yz sections through the crop centre, and the xy section at 492 µm. Dark grey is the unremelted substrate. The boundaries at 80 µm intervals coincide with the hatch centrelines (Section 6.5).

Table 4: Every filtered grain of the two full builds (`grain_paths.py`), medians with p_{10} / p_{90} for the drift, against the per-grain quantities Lamb report.

	v10 (96 grains)	v8 (86 grains)	Lamb
drift of the mean orientation, bottom → top	7.2° (1.7 / 13.5)	4.2° (2.0 / 7.5)	directed paths (4 grains)
spread about the top-slab mean (RMS)	3.4°	6.1°	–
drift ÷ spread	1.66	0.60	–
accumulation rate, drift per 30 µm: mean / max	0.84 / 1.92°	0.57 / 1.47°	1.7 / 5.8° (2026, bulk grains)
per-layer mean SROD at 300 µm: median / p_{90} / max	10.8 / 15.6 / 18.0°	9.9 / 12.3 / 14.4°	20–25° (G1–G4)
maximum SROD in the grain: median / p_{90} / max	15.0 / 23.2 / 33.4°	16.0 / 26.7 / 34.6°	up to 58.7°
grains with maximum SROD > 25°	5 %	17 %	“most”
fraction of slabs with rising mean SROD	0.79	0.78	–
path length per unit height (d10)	1.47	–	–

the construction ($\sqrt{D_g(1+\rho)/(1-\rho)/D_v} = 1.7$) rather than an experimental value; Lamb's within-slice widths, which would fix it, are not published.

6.5 Grain structure and the hatch pattern

The grain boundaries of both full builds fall at 80 µm intervals in x and in y: the boundary-density autocorrelation at the 80 µm lag is 0.61 / 0.70 (x / y) in v10 and 0.58 / 0.71 in v8, and 43–62 % of the spectral power of the boundary density sits at the hatch period (`hatch_periodicity.py`, Fig. 7). In-plane grain widths by line intercept have medians of 30, 39 and 51 µm at 200, 300 and 405 µm height (p_{90} 72–84 µm). The cause is the deck's registered hatch pattern: layers n and $n+2$ have identical scan lines, so the pool centrelines, where the last liquid solidifies, recur at the same positions and select the same columns, and the grains become $\sim 80 \times 80$ µm columns spanning the build, which also compresses the ESD distribution (p_{10}–p_{90} 76–170 µm). Lamb describe serrated, irregular boundaries. The papers do not state the hatch registration of the SLM125 build. [B3: hatch-offset sensitivity run pending.]

6.6 Grain definition

Re-segmenting the simulated volume at Lamb's 2° disorientation threshold (`-segment-deg 2`) changes the grain population. v10: 411 000 labels, 139 pass Lamb's filters (spin labels: 96), ESD p_{50} 29 µm, two grains span 300 µm; the Fig. 5a score stays within 0.6° (bias −0.45°, band 1.49), and the per-grain drift / spread become 5.5 / 1.9°. v8: 758 000 labels, 54 filtered grains of ESD p_{50} 8 µm, no grain taller than 165 µm, score 1.19°. The per-voxel walk alone does not survive a 2° segmentation as columnar grains; the coherent model keeps its SROD curve but not its grain size, because the simulated same-grain neighbour disorientation (median 2.4° in v10) sits at the




Figure 5: v10: per-slab mean orientation of the 30 tallest filtered grains as paths on the build-direction inverse pole figure (colour: height; orange arrow: bottom to top). All 30 span the full analysable height and are substrate continuations.




Figure 6: v10, all 96 filtered grains: drift against spread (dashed: equal), drift and maximum SROD against grain height, and the monotonicity of the per-grain SROD(h).




Figure 7: v10: grain-boundary density across the crop with the hatch period marked, its autocorrelation, and the in-plane grain-width distribution at mid-height.

threshold. The simulated field carries voxel-scale orientation noise that the EBSD does not, so the two segmentations are not equivalent; the spin labelling is the one used elsewhere in this report.

6.7 Grain origins

Of the 88 filtered grains in the v8 crop, 83 originate at the layer-0 remelt floor (99 % of the filtered volume) and 3 above 160 µm: the columnar grains are epitaxial continuations of substrate grains, so the simulated "originating" SROD is an established-grain SROD referenced at the remelt floor. A census over 26 existing proxy runs spanning nucleation densities of 6.5×10^{12}–8.5×10^{13} $1/\mathrm{m}^3$ and critical undercoolings of 3–23 K finds 0–7 filtered grains per run originating more than 60 µm above the floor (0–4 % of the filtered volume); Lamb's volume has over 500 such grains against 100 established. No region of the tested parameter space produces surviving mid-build origins; nucleated grains are overgrown. Analysing v8 on the full 801 µm domain, the central 400 µm, the central 200 µm, or without the never-remelted top layer changes the SROD bias by under 0.2° and the band by under 0.03.

6.8 Resolution

The per-voxel model (v8 deck) was run at Lamb's 1.5 µm voxel on the proxy with the same D_v and geometry: SROD RMS / bias 0.49° / 0.41° against 0.44° / 0.03° at 3 µm, band 1.43 vs 1.41, same grain size and texture, with the finer lattice accumulating 10–18 % more per unit height because it resolves a slightly longer growth path. For the coherent term, ρ is per lattice level: keeping the 30 µm correlation length at 1.5 µm takes $\rho' = 0.95$ and, to keep the long-range accumulation, $D'_g = D_g(1+\rho)(1-\rho')/((1-\rho)(1+\rho')) = 0.0049\,\mathrm{deg}^2/\mu\mathrm{m}$. [B2: 1.5 µm v10 run pending.]

6.9 Seed scatter

[B1: pending.]

6.10 Texture

Neither paper quantifies a ⟨001⟩ fibre; the 2026 paper discusses both ⟨001⟩- and ⟨111⟩-oriented grains. A Sobol study over the mobility contrast c_2 and nucleation density with D fixed gave the ⟨001⟩-within-15° fraction flat at 0.22 below $c_2 \approx 5$ and rising by 0.0125 per unit c_2 above it, with the SROD score unaffected; on the full build $c_2 = 9$ gave 0.22 against 0.19 at $c_2 = 2.8$. The coherent walk lowers the fraction (v10: 0.15) because it carries grains out of the cone. Against a random baseline of 0.102, the builds sit at 1.5–2.2× random.

7 Findings and open issues

1. Population SROD in GP700 has the statistics of a finite-variance rotation walk, $D \approx 0.42\,\mathrm{deg}^2/\mu\mathrm{m}$ against height with a Maxwell width; individual grains rotate along a path. The statistics do not identify the mechanism, and the published curves do not distinguish $\sqrt{h}$ from the authors' two-regime reading above 30 µm.
2. The two-term model reproduces the calibration curve, and, without further tuning, the established-grain curve and the 2026 modal trajectory; the per-voxel model alone fails the established curve. Per grain the model produces directed paths but accumulates at half Lamb's average rate with far smaller extremes: the experiment has a heavy tail of fast-rotating grains that a single Gaussian D_g does not give.
3. Deck constants are per unit of growth path; the measured path length is 1.47 times the height. The per-voxel term is resolution independent to first order; the coherent term needs ρ and D_g rescaled with Δx.
4. The simulated grain structure is locked to the deck's registered hatch pattern; the experimental hatch registration is unknown.
5. No surviving grains originate mid-build at any tested nucleation density, against Lamb's 5:1 originating-to-established ratio.
6. A 2° re-segmentation of the simulation changes its grain population; the two grain definitions are not equivalent.
7. $D_g : D_v$ and ρ are fixed here by construction and by the held-out curves only loosely; Lamb's within-slice widths, per-grain rate distribution and path directions would fix them.
8. Not yet tested: the undercooling dependence of D_v; a heavy-tailed or grain-dependent D_g.

8 Reproduction

```
. /home/tron/spack/share/spack/setup-env.sh && spack env activate spparks-dev
# binary: build-verify/spparks (commit 6a47de77 or later); template = the v10 deck
E=examples/gp700_moser; R=/home/tron/gp700_runs
$E/run_layers.sh build-verify/spparks $R/wide12_v10 12 12345 267 10 4e-6 $R/
    substrate_800um_50um_d10.st
/home/tron/miniconda3/envs/WORK/bin/python $E/gp700_analysis.py $R/wide12_v10/gp700.st
     \
    --out $R/wide12_v10/analysis_floor100 --floor-um 100 --crop 200 600 200 600
/home/tron/miniconda3/envs/WORK/bin/python $E/grain_paths.py $R/wide12_v10/gp700.st \
    --out $R/wide12_v10/grain_paths --crop 200 600 200 600 --floor-um 100 --grid 30
/home/tron/miniconda3/envs/WORK/bin/python $E/hatch_periodicity.py $R/wide12_v10/gp700
    .st --out $R/wide12_v10/hatch --crop 200 600 200 600
```

Reproducible artefacts: the digitized curves `docs/lamb2023_fig5{a,c}_srod.json` (the 2024 paper; file names carry the manuscript year) and `docs/lamb2026_fig7a_srod.json`, the scripts above and `docs/srod_random_walk.py`, the per-grain tables `docs/gp700_results_v{8,10}/grain_stats.csv` and the review-response outputs in `docs/gp700_results_review/`. Key commits: fa8930f3 (per-voxel walk), ad23c1a5 (per-grain selection), 1a9712b3 (kk kernel parity), da2fad29 (`smooth_orientation`), b6e4ba5f / 47546146 / 60b2d711 / 6a47de77 (`misorientation_grain_walk`), f5d79cd3 (v10 deck), 71824e43 / 21de639b (review analyses). The development log is `docs/GP700_MOSER_SROD_DECK_PLAN.md`; the first review and the response are `docs/SROD_REPORT_REVIEW.md` and `docs/SROD_REPORT_RESPONSE.md`. This file is the reference version; `docs/SROD_ANALYSIS_REPORT.md` and the published HTML page mirror it.

Sources. J. Lamb, K. M. Pusch, A. T. Polonsky, S. A. J. Forsik, N. Zhou, A. D. Dicus, R. Geurts, M. P. Echlin, T. M. Pollock, Scripta Materialia 239 (2024) 115770 (3D-EBSD and

SROD of PBF-L GammaPrint-700; manuscript dated 2023); J. Lamb et al., Metallurgical and Materials Transactions A 57A (2026) 2430 (cellular structure, intragranular SROD, 3DThesis parameters).