



MALAYSIAN MOSAICS SDN BHD

IN-HOUSE TECHNICAL TESTING RECORD

PRODUCTION DATE : -
 PRODUCT NAME : ITSU0114-10X20
 SIZE : 100X200X14mm
 PRODUCT TYPE : Porcelain Tiles

☐ NEW DEV.PRODUCT
☐ SEMI-FINISHED PRODUCT
☒ FINISHED PRODUCT

TEST STANDARD UNI EN ISO	TECHNICAL CHARACTERISTICS	MEASURED RESULT	PRODUCT STANDARD UNI EN ISO
ISO-10545-2	DIMENSIONAL ~Length and width ~Thickness ~Rectangularity ~Straightness Of Side ~Surface Flatness : Centre curvature ~Surface Flatness : Edge curvature ~Surface Flatness : Warpage	$\pm 0.1\%$ $\pm 1.5\%$ $\pm 0.1\%$ $\pm 0.1\%$ $\pm 0.2\%$ $\pm 0.1\%$ $\pm 0.2\%$	$\pm 0.6\%$ ($\pm 2.0\text{mm}$) $\pm 5\%$ ($\pm 0.5\text{mm}$) $\pm 0.5\%$ ($\pm 2.0\text{mm}$) $\pm 0.5\%$ ($\pm 1.5\text{mm}$) $\pm 0.5\%$ ($\pm 2.0\text{mm}$) $\pm 0.5\%$ ($\pm 2.0\text{mm}$) $\pm 0.5\%$ ($\pm 2.0\text{mm}$)
ISO-10545-3	WATER ABSORPTION ~ Average, E(%)	0.05%	$E_b \leq 0.5\%$
ISO-10545-4	BREAKING STRENGTH ~Average, (N)	6542 N	min 1300 N
ISO-10545-4	MODULUS OF RUPTURE ~Average, (N/mm ²)	56 N/mm ²	min 35 N/mm ²
ISO-10545-6	RESISTANCE TO DEEP ABRASION	143 mm ³	Max 175 mm ³
ISO-10545-8	COEFFICIENT OF LINEAR THERMAL EXPANSION (K⁻¹)	6.2 MK ⁻¹	Test method available
ISO-10545-9	THERMAL SHOCK RESISTANCE	Resistant	Test method available
ISO-10545-12	FROST RESISTANCE	Resistant	Test method available
DIN 51094	RESISTANCE OF THE COLORS IN THE LIGHT	Resistant	Test method available
DIN 51130	SLIP RESISTANCE	R11	Test method available
DIN 51097	SLIPPERINESS BAREFOOT	A+B	Test method available
ISO-10545-13	CHEMICAL RESISTANCE	Resistant	Test method available
ISO-10545-14	RESISTANCE TO STAIN	5	Test method available

Chemical Test Classification		Wet Pendulum Rating	
GA/UA/ULA/UHA	No visible effect	V	P5 Very Low
GB/UB/ULB/UHB	Definite change in appearance	W	P4 Low
GC/UC/ULC/UHC	Partial/complete loss of the original surface	X	P3 Moderate
CLASS 1	Stain not removed	Z	P0/P1 Very High
CLASS 2	Immersed 24hours in solvent, stain removed	Surface Abrasion Test (PEI)	
CLASS 3	Strong cleaning agent and mechanical brushing, stain removed	Class	rpm
CLASS 4	Weak cleaning agent, stain removed	0	100
CLASS 5	Running hot water, stain removed	I	150
		II	600
		III	750, 1500
		IV	2100, 6000, 12000
		V	>12000

PREPARED BY : TARMIZI OTHMAN
 DATE : 26/7/2022

APPROVED BY : GAN SWEE HO
 DATE : 26/7/2022