



MALAYSIAN MOSAICS SDN BHD

IN-HOUSE TECHNICAL TESTING RECORD

PRODUCTION DATE : March-2021
 PRODUCT NAME : GRFOR215, GRFOR315 (R11)
 SIZE : 100X115X15mm
 PRODUCT TYPE : FULL BODY

☐ NEW DEV. PRODUCT
☐ SEMI-FINISHED PRODUCT
☒ FINISHED PRODUCT

TEST STANDARD UNI EN ISO	TECHNICAL CHARACTERISTICS	MEASURED RESULT	PRODUCT STANDARD ISO 13006 / EN 14411
ISO-10545-2	DIMENSIONAL ~Length and width ~Thickness ~Rectangularity ~Straightness Of Side ~Surface Flatness ~Surface Quality	± 0.3% ± 2.5mm ± 0.25mm ± 0.25mm ± 0.25mm 95%	±0.6% (±2.0mm) ±5% (± 0.5mm) ±0.5% (± 2.0mm) ±0.5% (± 1.5mm) ±0.5% (± 2.0mm) 95%
ISO-10545-3	WATER ABSORPTION ~ Average, E(%)	Ev ≤ 0.5%	Ev ≤ 0.50%
ISO-10545-4	BREAKING STRENGTH ~Average, (N)	5000 - 7000N	≥ 1300 N
ISO-10545-4	MODULUS OF RUPTURE ~Average, (N/mm ²)	≥ 35 N/mm ²	≥ 35 N/mm ²
ISO-10545-6	RESISTANCE TO DEEP ABRASION	≤ 175mm ³	≤ 175mm ³
ISO-10545-7	RESISTANCE TO SURFACE ABRASION	N/A	NO REQUIREMENT
ISO-10545-8	COEFFICIENT OF LINEAR THERMAL EXPANSION (K ⁻¹)	6.57 x 10 ⁻⁶ / °C	Test method available
ISO-10545-9	THERMAL SHOCK RESISTANCE	Passed	Test method available
ISO-10545-12	FROST RESISTANCE	Passed	Required
DIN 51130	SLIP RESISTANCE	R 11	NO REQUIREMENT
ISO-10545-10	MOISTURE EXPANSION (mm/m)	≤ 0.05%	NO REQUIREMENT
ISO-10545-16	SMALL COLOUR DIFFERENCES	xxxxx	xxxxx
ISO-10545-5	IMPACT RESISTANCE AS COEFFICIENT OF RESITUTION	0.83	xxxxx
CWT	REACTION TO FIRE	A1 _{FL}	A1 _{FL}
CEN/TS 15209	TACTILITY	xxxxx	xxxxx
ISO-10545-14	RESISTANCE TO STAIN	Class 3	≥ Class 3
ISO-10545-13	CHEMICAL RESISTANCE	min class B	min class B
ISO-10545-15	RELEASE OF DANGEROUS SUBSTANCES	xxxxx	xxxxx

xxxxx for files intended to be used for this purpose

Chemical Test Classification				Wet Pendulum Rating		
GA/UA/ULA/UHA	No visible effect			V	P5	Very Low
GB/UB/ULB/UHB	Definite change in appearance			W	P4	Low
GC/UC/ULC/UHC	Partial/complete loss of the original surface			X	P3	Moderate
st Classification (ISO-10545-14)				Y	P2	High
CLASS 1	Stain not removed			Z	P0/P1	Very High
CLASS 2	Immersed 24hours in solvent, stain removed					
CLASS 3	Strong cleaning agent and mechanical brushing, stain removed			Class		Surface Abrasion Test (PEI)
CLASS 4	Weak cleaning agent, stain removed			0		rpm
CLASS 5	Running hot water, stain removed			I		100
				II		150
				III		600
				IV		750, 1500
				V		2100, 6000, 12000
						>12000

PREPARED BY : TARMIZI OTHMAN
 DATE : 29/3/2021

APPROVED BY : AHMAD SOUFI
 DATE : 29/3/2021