

試驗報告



報告編號：TB-21-02546

C-21-06690

頁數：1 OF 2

報告日期：110年05月13日

工程名稱：自測
 承包商：---
 委託單位：金石發股份有限公司
 供料廠商：---
 樣品名稱：保時捷保養廠專用磚-六角磚系列 10×11.5×5.8(15 mm)
 面磚種類：無施釉、內外裝地磚、乾式、Ia類
 送驗人員：金石發股份有限公司-陳郁超
 收件日期：110年05月07日
 試驗日期：110年05月13日
 備註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製
 3.下述報告內容標示#處由顧客提供
 4.送樣方式：實驗室收件

試驗方法：CNS 3299-4(2009)陶瓷面磚試驗法-第4部：彎曲破壞載重及抗彎強度試驗法
 試驗結果：

試體編號	試驗結果				
	1	2	3	4	5
跨距(mm)	90	90	90	90	90
破壞載重(N)	3908	4034	4061	3931	3901
破壞載重平均值(N)	3967				
破壞載重最小值(N)	3901				
彎曲破壞載重(N)	5830	5919	6070	5848	5813
彎曲破壞載重平均值(N)	5896				
彎曲破壞載重最小值(N)	5813				
抗彎強度(N/mm ²)	44	44	46	44	44
抗彎強度平均值(N/mm ²)	44				
抗彎強度最小值(N/mm ²)	44				

#附表 CNS 9737(2016)彎曲破壞載重之基準

依主要用途之區分	彎曲破壞載重
內裝壁磚	108 N以上
內裝馬賽克壁磚	
內裝地磚	540 N以上
內裝馬賽克地磚	
外裝壁磚	720 N以上
外裝馬賽克壁磚	540 N以上
外裝地磚	1080 N以上
外裝馬賽克地磚	540 N以上
馬賽克面磚	540 N以上

----- 1 -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號: TB-21-02546

C-21-06690

頁數: 2 OF 2

報告日期: 110年05月13日

試驗方法: CNS 3299-5(2009)陶瓷面磚試驗法-第5部: 無釉地磚耐磨耗性試驗法

試驗結果:

試體編號	無釉地磚磨耗性試驗結果				
	6	7	8	9	10
磨耗體積(mm ³)	141	136	136	144	146
磨耗體積之平均值(mm ³)	141				
磨耗體積之最大值(mm ³)	146				

#附表 CNS 9737(2016)無釉地磚磨耗體積之基準

使用場所區分	磨耗體積 ^(a)
屋外地磚	345 mm ³ 以下
屋內地磚	540 mm ³ 以下 ^(b)
註: (a) 使用於行人眾多場所之地磚, 宜在175 mm ³ 以下。 (b) 不適用赤腳行走之場所。	

註: 本試驗報告之試驗地點同實驗室地址。

----- oOo -----

本報告若有提供規範值時, 該規範值僅供參考, 合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號: TB-21-02547

C-21-06691

頁數: 1 OF 1

報告日期: 110年05月21日

工程名稱: 自測
 承包商: ---
 委託單位: 金石發股份有限公司
 供料廠商: ---
 樣品名稱: 保時捷保養廠專用磚-六角磚系列 10×11.5×5.8(15 mm)
 面磚種類: 無施釉、內外裝地磚、乾式、I a類
 送驗人員: 金石發股份有限公司-陳郁超
 收件日期: 110年05月07日
 試驗日期: 110年05月21日
 備註:

1. 以上資料由顧客提供(收件及試驗日期除外)
2. 除非另有說明, 此報告結果僅對測試之樣品負責
未經本公司事先書面同意, 此報告不可部分複製
3. 下述報告內容標示#處由顧客提供
4. 送樣方式: 實驗室收件

試驗方法: CNS 3299-12(2011)陶瓷面磚試驗法-第12部: 防滑性試驗法

試驗結果:

試體編號	防滑性試驗結果		
	1	2	3
表面狀態	使用自來水做為媒介物, 散佈量約400g/m ²		
測試環境溫度(°C)	24.5		
最大值	0.669	0.707	0.667
最小值	0.654	0.692	0.660
C.S.R值穿鞋時之防滑係數	0.66	0.70	0.66

註: 1、試驗樣品由委託單位事先在合板上貼著成11.5×20.3×1.5 cm

送至本實驗室執行委託試驗項目。

2、本試驗報告之試驗地點同實驗室地址。

----- oOo -----

本報告若有提供規範值時, 該規範值僅供參考, 合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.