Calculation of Interfacial Energy in TiO_2/PTFE and ZnO/PTFE Composites: A Comparative Analysis

Executive Summary

This report analyzes the interfacial energy between metal oxide nanoparticles (TiO_2 and ZnO) and polytetrafluoroethylene (PTFE) in composite materials. Based on computational simulations and experimental studies, both TiO_2 and ZnO form attractive interfaces with PTFE through partially covalent chemical bonding, with the interface strength being composition-dependent and influenced by charge transfer mechanisms. Quantitative comparative data is limited due to differences in measurement methodologies, but available evidence indicates that ZnO/PTFE interfaces exhibit measurable binding energies, while TiO_2/PTFE interfaces are characterized through indirect performance metrics.

---

1. Introduction

Polytetrafluoroethylene (PTFE) is widely utilized in high-tech industries, including chemical engineering, aerospace, and automotive applications, due to its low friction coefficient, excellent chemical resistance, and high thermal stability . However, pure PTFE suffers from low wear resistance and severe creep deformation, necessitating reinforcement with inorganic fillers . Metal oxide nanoparticles such as titanium dioxide (TiO_2) and zinc oxide (ZnO) have emerged as effective reinforcing agents that enhance mechanical, tribological, and functional properties of PTFE-based composites.

Understanding the interfacial energy between these metal oxides and PTFE is fundamental to optimizing composite performance, as interface strength directly influences mechanical reinforcement, charge transfer, and long-term stability. This report examines the interfacial energy characteristics of TiO_2/PTFE and ZnO/PTFE systems through computational and experimental perspectives.

---

2. Methodology for Interface Energy Determination

2.1 Computational Approaches

First-principles calculations within the density functional theory (DFT) framework and density functional tight-binding (DFTB) methods have been employed to investigate interfacial properties of metal-oxide/PTFE composites. The binding energy between the oxide layer and PTFE is typically calculated using:

$$
E_b = \frac{1}{A} (E_{d=d_e} - E_{d=d_\infty})
$$

where E_b is the binding energy, A is the interface area, d_e is the equilibrium interlayer distance, and d_∞ represents infinite separation (typically ~20 Å) .

2.2 Experimental Approaches

Experimental characterization of interface strength utilizes techniques including X-ray photoelectron spectroscopy (XPS) for chemical bonding analysis, Fourier transform infrared spectroscopy (FTIR) for interfacial interactions, and adhesion force measurements using atomic force microscopy (AFM) .

---

3. TiO_2/PTFE Interfacial Energy

3.1 Chemical Bonding Characteristics

The TiO_2-PTFE interface exhibits significant chemical interaction through covalent bonding mechanisms. In TiO_2-intercalated CNT/PTFE composite membranes, XPS and FTIR analyses have confirmed the formation of Ti–O–C covalent bonds, which significantly enhance interfacial integrity . This robust chemical bonding prevents nanoparticle agglomeration and improves load transfer between the inorganic filler and the polymer matrix.

The formation of these interfacial bonds involves electron transfer from PTFE to TiO_2, with charge accumulation occurring at the interface. The strong Ti–O–C bonds are characterized by:

- Enhanced surface hydrophilicity (achieving water contact angles as low as 26.9°)

- Improved structural stability under operational stress

- Effective suppression of nanoparticle aggregation

3.2 Quantitative Energy Data

Direct quantitative measurements of TiO_2/PTFE interfacial binding energy are not explicitly reported in the available literature. However, the TiO_2/PTFE interface strength can be inferred from composite performance metrics:

Parameter	TiO_2/PTFE System	Observations
Interfacial Bonding	Ti–O–C covalent bonds	Robust, prevents CNT agglomeration
Adhesion Force*	Moderate (reference: TiO_2 adhesion ~10 mN on substrate)	Lower than ZnO
Composite Stability	Excellent anti-fouling performance	>99% oil removal, stable under cross-flow

> *Note: Adhesion force values from thin film studies provide relative comparison; precise interfacial binding energies require specialized measurement.

3.3 Interfacial Interactions

Computational simulations of the h-PTFE@TiO_2 core-shell system reveal that strain-induced space-charge piezoelectric polarization induces an internal electric field between unsaturated PTFE (fluorine vacancies) and the TiO_2 surface. This piezopotential plays a critical role in band bending at PTFE-TiO_2 interfaces, enhancing charge separation and photocatalytic activity. The piezoelectric coefficient of PTFE (d_{33} ≈ 79.77 pC/N) contributes to local dipole enhancement at the interface .

---

4. ZnO/PTFE Interfacial Energy

4.1 Quantitative Binding Energy

The ZnO/PTFE interface has been systematically investigated using DFTB molecular dynamics simulations and superlattice modeling. Table 1 summarizes the binding energies determined for ZnO/amorphous PTFE (a-PTFE) composites with varying ZnO weight fractions .

Table 1: Interlayer Binding Energy of ZnO/a-PTFE Composites

Model	PTFE Thickness (Å)	ZnO Weight %	Binding Energy E_b (meV)	Interlayer Distance d (Å)
Model 1	65.0	33.67%	-12.59	1.73
Model 2	92.5	25.78%	-13.18	1.56
Model 3	120.0	20.88%	-14.50	1.42
Model 4	147.5	18.03%	-17.01	1.25
Model 5	175.0	15.86%	-17.26	1.10

Key Observations:

1. **All binding energies are negative**, indicating attractive interaction between ZnO and PTFE layers .

2. **Magnitude increases with PTFE content** - as ZnO weight percentage decreases, binding energy becomes more negative (stronger attraction).

3. **Interlayer distance decreases** with higher PTFE content, suggesting stronger interaction at closer proximity.

4. **Short interlayer distances** (as low as 1.10 Å) imply strong interaction due to newly formed chemical bonds at the interface.

4.2 Charge Transfer and Bonding Mechanism

Electron density difference analysis reveals the interfacial bonding mechanism :

- **Charge accumulation** is observed around oxygen atoms of the ZnO outermost layer

- **Charge depletion** occurs around fluorine atoms of a-PTFE chains facing the ZnO surface

- **Electrons transfer** from a-PTFE to the ZnO layer

- **Covalent bond formation** is confirmed by significant charge accumulation in the space between ZnO and PTFE layers

4.3 Composition-Dependent Behavior

The binding energy increases in magnitude (becomes more negative) with increasing PTFE content:

- At 33.67% ZnO: E_b = -12.59 meV, d = 1.73 Å

- At 15.86% ZnO: E_b = -17.26 meV, d = 1.10 Å

This indicates that the interaction between ZnO and PTFE becomes **stronger as the PTFE fraction increases**, which is attributed to more extensive interfacial contact area and enhanced van der Waals interactions .

---

5. Comparative Analysis: TiO_2/PTFE vs. ZnO/PTFE

5.1 Interface Strength Comparison

Characteristic	TiO_2/PTFE	ZnO/PTFE
Quantitative Binding Energy	Not directly reported in available literature	-12.59 to -17.26 meV (composition-dependent)
Chemical Bonding	Ti–O–C covalent bonds	Partially covalent (Zn-O-F bonds)
Charge Transfer Direction	TiO_2 accepts electrons from PTFE	ZnO accepts electrons from PTFE
Interfacial Distance	Not directly measured	1.10 - 1.73 Å
Adhesion Force (Reference)*	Lower (TiO_2 ~10 mN)	Higher (ZnO ~50 mN)
Composite Performance	Excellent anti-fouling, corrosion resistance	Enhanced mechanical strength, wear resistance

> *Adhesion force values are from thin-film studies and serve as relative indicators.

5.2 Interfacial Bonding Mechanisms

Both systems exhibit similar bonding mechanisms involving charge transfer from PTFE to the metal oxide:

TiO_2/PTFE:

- Forms Ti–O–C covalent bonds at the interface

- Surface engineering strategy enables robust interfacial integrity

- Interfacial bonds prevent nanoparticle agglomeration

ZnO/PTFE:

- Forms partially covalent interfacial chemical bonds

- Electrons transfer from a-PTFE to ZnO layer

- Charge accumulation occurs in the middle space between layers

5.3 Factors Influencing Interface Strength

1. Surface Energy and Polarity:

- ZnO has higher surface energy and lower stiffness compared to TiO_2, enhancing adhesion to substrates and interfaces

- The wurtzite structure of ZnO provides better lattice matching with various substrates

2. Metal Oxide Crystallinity:

- ZnO exhibits semi-crystalline structure

- TiO_2 is often amorphous in composite coatings

- Crystallinity affects surface roughness and interfacial contact area

3. Processing Conditions:

- Both systems benefit from surface modification strategies

- PDA (polydopamine) interlayers enhance adhesion for both oxides

5.4 Implications for Composite Applications

| Application | TiO_2/PTFE Advantage | ZnO/PTFE Advantage |

|---|---|---|

| Mechanical Reinforcement | Moderate | High (binding energy quantified, strength enhancement confirmed) |

| Anti-fouling | Excellent (surface engineering demonstrated) | Moderate |

| Photocatalytic Activity | High (UV-activated) | Good |

| Thermal Stability | Good | Good |

| Corrosion Resistance | Excellent | Moderate |

---

6. Discussion and Limitations

6.1 Data Limitations

1. **Direct comparative quantitative data** for TiO_2/PTFE binding energy is not available in the reviewed literature. Most TiO_2/PTFE studies focus on composite performance rather than fundamental interface energetics.

2. **Methodological differences** complicate direct comparison: ZnO/PTFE binding energies were determined through DFTB quantum chemical calculations, while TiO_2/PTFE studies rely on indirect performance metrics and adhesion force measurements.

3. **Interface complexity**: Both systems are influenced by factors such as:

- Surface treatment

- Particle size and morphology

- Processing conditions

- Presence of other components (e.g., CNTs, PDA interlayers)

6.2 Recommendations for Future Work

1. Perform systematic DFT/DFTB calculations for TiO_2/PTFE interfaces to enable direct quantitative comparison with ZnO/PTFE systems.

2. Develop standardized experimental protocols for measuring interfacial binding energy in polymer nanocomposites.

3. Investigate the effect of TiO_2 and ZnO particle size, shape, and surface termination on interfacial energy.

4. Study the long-term stability of interfaces under various environmental conditions (thermal cycling, humidity, UV exposure).

---

7. Conclusions

Based on available computational and experimental evidence:

1. **Both TiO_2/PTFE and ZnO/PTFE interfaces exhibit attractive interactions** through covalent or partially covalent chemical bonding, with charge transfer from PTFE to the metal oxide.

2. **Quantitative binding energy data is available for ZnO/PTFE** (-12.59 to -17.26 meV), showing composition-dependent behavior where the interface strengthens with increasing PTFE content.

3. **TiO_2/PTFE binding energy** is not explicitly quantified in the reviewed literature, though the formation of Ti–O–C covalent bonds indicates significant interfacial interaction.

4. **The ZnO/PTFE interface demonstrates stronger quantified adhesion** in thin-film studies (adhesion force ~50 mN for ZnO vs. ~10 mN for TiO_2) , suggesting higher interfacial strength for ZnO/PTFE composites.

5. **Both systems have distinct application advantages**: TiO_2/PTFE excels in anti-fouling, photocatalytic, and corrosion-resistant applications, while ZnO/PTFE offers superior mechanical reinforcement and quantified interfacial energetics.

6. **The interface strength** in both systems is strongly influenced by composition, processing conditions, and surface chemistry, suggesting opportunities for optimization through interfacial engineering.

References

1. Ryu, C., Ri, J.-G., Kim, Y.-S., Rim, C.-H., Kim, C.-I., & Yu, C.-J. (2024). Interfacial properties of a ZnO/PTFE composite from density functional tight-binding simulations. *RSC Advances*, 14, 35097-35103.

2. TiO_2-intercalated CNT/PTFE composite membranes for water purification. *Applied Surface Science*.

3. Surface energy and adhesion force studies of ZnO/TiO_2 bilayers. *Journal of Materials Science: Materials in Electronics*, 36, 764.

4. Local dipole enhancement of space-charge piezophototronic catalysts of core-shell polytetrafluoroethylene@TiO_2 nanospheres.

5. PDA-PTFE-TiO_2-Ag composite coatings with enhanced corrosion resistance and antibacterial adhesion properties. *Materials Today Communications*.