Write a paper on the principle that nano-TiO2 enhances the dielectric pressure of NBR rubber

Nano-TiO_2 as a High-κ Filler for NBR Rubber: Principles of Dielectric Enhancement

---

Abstract

Nitrile butadiene rubber (NBR) is a polar elastomer with inherent high dielectric constant due to its nitrile (−C≡N) dipoles, but its mechanical weakness limits applications in dielectric elastomer actuators (DEAs). The incorporation of titanium dioxide (TiO_2) nanoparticles, which possess a high intrinsic dielectric constant (~48–100), provides a synergistic approach to enhance both dielectric and mechanical properties. This paper reviews the fundamental principles governing the dielectric reinforcement of NBR by TiO_2 nanoparticles, including the mechanisms of dielectric constant enhancement, the relationship between filler loading and electrical properties, the role of surface modification, and the critical balance between dielectric performance and breakdown strength. The analysis demonstrates that TiO_2/NBR composites are promising candidates for high-performance dielectric elastomer applications requiring high energy density and low operating voltages.

---

1. Introduction

Dielectric elastomer actuators (DEAs) represent a class of electroactive polymers capable of generating large deformation, fast response, and high energy density under an applied electric field . However, DEAs typically require high operating voltages (several kilovolts), which limits their commercial viability. The required operating voltage can be reduced by increasing the dielectric constant of the elastomeric material while maintaining high mechanical properties and electrical insulation .

Acrylonitrile butadiene rubber (NBR) is a polar copolymer containing acrylonitrile units with nitrile (−C≡N) functional groups, which confer a relatively high dielectric constant due to orientation polarization of the dipoles . However, NBR does not exhibit self-reinforcing behavior due to its irregular molecular structure, resulting in comparatively weak mechanical properties that limit its application as a dielectric elastomer .

Titanium dioxide (TiO_2) nanoparticles have attracted significant attention as high-dielectric-constant fillers ($\kappa \approx 48–100$) capable of simultaneously enhancing the dielectric and mechanical properties of elastomeric composites . The incorporation of TiO_2 into NBR creates a composite material with a synergistic combination of high dielectric constant, good mechanical strength, and acceptable breakdown strength, making it suitable for DEA applications .

This paper examines the fundamental principles by which nano-TiO_2 enhances the dielectric properties of NBR rubber, focusing on the mechanisms of dielectric constant enhancement, the influence of filler loading, the role of interfacial interactions, and the critical balance between dielectric and insulating properties.

---

2. Fundamentals of Dielectric Enhancement

2.1 The Need for High Dielectric Constant Materials

The actuation performance of a dielectric elastomer is governed by the relationship between the generated stress (σ) and the applied electric field (E) :

$$\sigma \propto \kappa \cdot E^2$$

where κ is the relative dielectric constant. This relationship demonstrates that increasing the dielectric constant allows the elastomer to generate equivalent actuation stress at a lower operating voltage, improving safety and practicality .

2.2 Intrinsic Dielectric Properties of NBR

NBR possesses a relatively high dielectric constant due to the presence of polar nitrile (−C≡N) groups that undergo orientation polarization under an applied electric field . At low frequencies (10^2 Hz), the dielectric constant of pure NBR can reach approximately 12.28–13.9 due to strong contributions from interfacial and dipolar polarization . As frequency increases, the dielectric constant decreases because the dipoles are incapable of reorienting rapidly enough to follow the applied field .

2.3 Intrinsic Dielectric Properties of TiO_2

TiO_2 nanoparticles are characterized by a high dielectric constant ($\kappa \approx 48–100$), significantly higher than that of the NBR matrix . This intrinsic property makes TiO_2 an effective filler for increasing the overall dielectric constant of the composite through the principles of dielectric mixing.

---

3. Mechanisms of Dielectric Enhancement by Nano-TiO_2

3.1 Dielectric Constant Enhancement

The addition of TiO_2 to NBR increases the dielectric constant of the resultant composites across the tested frequency range . This enhancement occurs through two primary mechanisms:

Filler Contribution: TiO_2 nanoparticles possess a higher dielectric constant than the NBR matrix. According to dielectric mixing laws, the incorporation of high-κ filler particles increases the effective dielectric constant of the composite . Studies have shown that the dielectric constant of TiO_2-filled NBR composites increases proportionally with the amount of TiO_2 filler .

Interfacial Polarization: The interfaces between TiO_2 nanoparticles and the NBR matrix contribute to dielectric enhancement through Maxwell-Wagner interfacial polarization. When the high-dielectric-constant TiO_2 particles are dispersed in a polymer matrix, charge accumulation at the interfaces creates additional polarization effects that increase the overall dielectric constant .

A comprehensive study investigating TiO_2 content from 0 to 110 phr reported that the 110 phr TiO_2-filled composite exhibited the highest dielectric constant of 20.28 at 10^2 Hz, compared to approximately 18.83 for pure NBR under the same conditions . This represents a significant improvement in the dielectric response.

3.2 Role of Surface Modification and Functionalization

Nitrile Group Modification: Surface modification of TiO_2 particles with nitrile group-containing silane coupling agents has been shown to significantly enhance the dielectric constant. The CN-modified TiO_2 composites achieved a relative dielectric constant of 22 at 100 Hz, which increased proportionally with the amount of CN-TiO_2 . This enhancement is attributed to the concentration of high-dipole nitrile groups at the particle-polymer interface, where the electric field is effectively applied .

Polydopamine Coating: Bio-inspired polydopamine (PDA) modification of TiO_2 nanoparticles improves compatibility between the filler and the NBR matrix. The relatively soft insulating PDA layer leads to better filler dispersion, lower elastic modulus, and higher electric breakdown field compared to composites with pristine TiO_2 .

Combined Modification: A combined covalent and noncovalent modification approach using polydopamine followed by silane coupling agents has demonstrated superior results. The TiO_2-(PDA+KH570)/NBR composites exhibited dielectric constants of 14.55–15.73 at 1 kHz, higher than both pure NBR (13.43) and unmodified TiO_2/NBR composites .

3.3 Polar-Nonpolar Interaction Principles

The dielectric enhancement mechanism is fundamentally based on the compatibility between the filler surface and the polar polymer matrix. The surface hydroxyl groups on TiO_2 nanoparticles interact favorably with the polar −C≡N groups of NBR through hydrogen bonding and dipole-dipole interactions .

This favorable interaction ensures good filler dispersion and effective transfer of the electric field to the polarizable filler surface.

When the filler surface is further functionalized with nitrile groups, the concentration of polar species at the interface increases, creating a "dipole-rich" interface that significantly enhances the overall dielectric response .

---

4. Dielectric Properties and Loading Dependence

4.1 Dielectric Constant vs. Filler Content

The relationship between TiO_2 content and dielectric constant is generally proportional, though the exact behavior depends on filler dispersion, particle size, and surface modification .

Filler Loading	Dielectric Constant	Conditions	Reference
Pure NBR (0 phr)	12.28–18.83	100–10^2 Hz	
52 phr CN-TiO_2	22.0	100 Hz	
110 phr TiO_2	20.28	10^2 Hz	
30 phr TiO_2-(PDA+KH570)	15.73	1 kHz	
50 vol% TiO_2 nanosheets	194.22	20 Hz	

4.2 Volume Resistivity and Breakdown Strength

While the addition of TiO_2 increases the dielectric constant, it also affects the insulating properties of the composite. The volume resistivity of TiO_2/NBR composites decreases with increasing filler content due to the formation of conductive paths and increased charge mobility . However, the dielectric breakdown strength can be maintained at high levels when appropriate filler dispersion and surface modification are achieved.

Unmodified TiO_2: The volume resistivity of NBR composites with non-modified TiO_2 (6.6 phr) is 3.6×10^{12} Ω·cm, which is the highest among fabricated samples, indicating excellent insulation .

CN-Modified TiO_2: The volume resistivity decreases exponentially with CN-TiO_2 content, reaching 4.5×10^{11} Ω·cm at 52 phr. Despite this decrease, the dielectric breakdown strength is maintained at 95–105 V/μm, comparable to the non-modified composite .

PDA-Modified TiO_2: Polydopamine-coated TiO_2 composites exhibit improved breakdown strength compared to pristine TiO_2 composites. The insulating PDA layer acts as a barrier to charge transport, suppressing space-charge accumulation and preventing premature breakdown .

The card-house structure of TiO_2 particles in the composite elastomer is presumed to suppress dielectric breakdown in a low electric field by creating a network of insulating barriers .

---

5. Mechanisms of Breakdown Strength Enhancement

5.1 Space-Charge Suppression

The dielectric breakdown strength is maintained or even improved through the suppression of space-charge accumulation. The TiO_2 nanoparticles act as scattering centers for free electrons, reducing their mobility and preventing the development of damaging charge channels . When nanoparticles are well-dispersed, they fill the voids and gaps within the polymer matrix, creating a more homogeneous material with fewer defect sites for breakdown initiation .

5.2 Card-House Structure

The card-house structure of TiO_2 particles in the composite elastomer is assumed to suppress dielectric breakdown in a low electric field. This network of interconnected particles creates numerous insulating barriers that prevent the propagation of electrical breakdown channels .

5.3 Effective Charge Trapping

The nanoparticles' high surface area and surface functional groups (hydroxyl, modified nitrile groups) can trap mobile charges, preventing them from accumulating to critical levels that would trigger breakdown . This is particularly important when the volume resistivity decreases at higher filler loadings.

---

6. Synergistic Enhancement: Dielectric and Mechanical Properties

The unique advantage of TiO_2/NBR composites is the simultaneous improvement of both dielectric and mechanical properties, which is essential for DEA applications where the material must withstand repeated mechanical deformation under electrical stress.

Dielectric Enhancement: The addition of TiO_2 increases the dielectric constant, reducing the required operating voltage for a given actuation strain .

Mechanical Enhancement: The addition of TiO_2 improves tensile strength (up to 144.8% increase at 90 phr) and modulus through filler-rubber interactions, stress transfer, and increased crosslink density . The optimal TiO_2 content for tensile strength (90 phr) differs from that for maximum dielectric constant (≥110 phr), requiring balance in composite design.

Actuation Performance: The generated stress of TiO_2/NBR composites is proportional to both the dielectric constant and the square of the electric field. CN-modified TiO_2 composites achieved a maximum generated stress of 1.9 MPa, nearly double that of non-modified composites . The actuated strain of polydopamine-modified TiO_2/NBR composites reached 5.2% at a relatively safe electric field of 12.5 kV/mm, a 140% increase compared to pure NBR .

---

7. Conclusions

The dielectric pressure enhancement of NBR rubber by nano-TiO_2 is governed by a combination of fundamental principles:

1. **Intrinsic Dielectric Contribution**: TiO_2 nanoparticles with high dielectric constant ($\kappa \approx 48–100$) increase the effective dielectric constant of the NBR composite through dielectric mixing.

2. **Interfacial Polarization**: The interfaces between TiO_2 and the polar NBR matrix create additional polarization contributions through Maxwell-Wagner effects, further enhancing the dielectric response.

3. **Surface Modification Effects**: Functionalization of TiO_2 with nitrile groups, polydopamine, or silane coupling agents concentrates polar species at the interface, significantly improving the dielectric constant and maintaining breakdown strength.

4. **Filler Dispersion and Loading**: The dielectric constant increases proportionally with TiO_2 content (e.g., 20.28 at 110 phr, $\kappa \approx 22$ at 52 phr CN-TiO_2), but must be balanced against volume resistivity and mechanical properties.

5. **Breakdown Strength Retention**: The dielectric breakdown strength (95–105 V/μm) can be maintained even at high filler loadings through space-charge suppression, the card-house structure, and surface modification that traps charge carriers.

6. **Performance Enhancement**: The improved dielectric constant translates to higher generated stress (up to 1.9 MPa) and actuated strain (5.2% at 12.5 kV/mm) at lower operating voltages, demonstrating the practical significance of the enhancement principles.

References

[1] Matsuno, R., Kokubo, Y., Takamatsu, S., & Takahara, A. (2021). Actuator Performance of Dielectric Elastomers Comprising Hydrogenated Carboxylated Acrylonitrile-Butadiene Rubber/Nitrile Group-Modified Titanium Oxide Particles. *ACS Omega*.

[2] Chueangchayaphan, W., Luangchuang, P., & Chueangchayaphan, N. (2022). High Performance of Titanium Dioxide Reinforced Acrylonitrile Butadiene Rubber Composites. *Polymers*, 14(23), 5267.

[3] Chueangchayaphan et al. (2022). Dielectric constant vs. frequency for different TiO_2 loadings in NBR composites.

[4] El-Refaie, E. M., Nasrat, L. S., Mohamed, M. K., & Ibrahim, I. A. (2023). Investigation the dielectric strength and mechanical features of nitrile butadiene rubber enhanced by different nanoparticles. *Egyptian Journal of Petroleum*.

[5] El-Refaie et al. (2023). Dielectric constant values: TiO_2 nanoparticles ≈ 48, MgO nanoparticles ≈ 9.7.

[6] Yang, D., Huang, S., Wu, Y., et al. (2015). Enhanced actuated strain of titanium dioxide/nitrile-butadiene rubber composite by the biomimetic method. *RSC Advances*, 5, 65385-65394.

[7] Supplementary data for TiO_2/NBR composites. Breakdown strength and dielectric constant values.

[8] Chen, Q.-G., et al. (2024). Photo-Curable Stretchable High-κ Polymer/TiO_2 Nanosheet Hybrid Dielectrics for Field-Effect Transistors. *Small Science*.

[9] Study tracking and erosion properties of modified NBR with nanoparticles. (2024).