Write a paper on the principle that nano-TiO2 enhances the heat and cold resistance of NBR rubber

Nano-TiO_2 as a Thermal Performance Enhancer for NBR Rubber: Principles of Heat and Cold Resistance

---

Abstract

Nitrile butadiene rubber (NBR) is a polar elastomer widely used in industrial applications requiring oil resistance and a broad service temperature range. However, its inherently weak mechanical properties and susceptibility to thermal-oxidative degradation at elevated temperatures limit its application in demanding environments. The incorporation of titanium dioxide (TiO_2) nanoparticles has emerged as an effective strategy for enhancing both the heat resistance and cold resistance of NBR composites. This paper reviews the fundamental principles governing the thermal performance enhancement of NBR by nano-TiO_2, including the mechanisms of thermal stability improvement, the effect on glass transition temperature, the role of crosslinking density, and the influence of filler dispersion. The analysis demonstrates that TiO_2 nanoparticles, through their dual role as reinforcing fillers and thermal stabilizers, can significantly improve the service temperature range of NBR composites.

---

1. Introduction

Acrylonitrile butadiene rubber (NBR) is a copolymer of acrylonitrile and butadiene that exhibits beneficial properties including a broad temperature application range, excellent oil and solvent resistance, good bonding performance, and relatively low cost . However, NBR does not exhibit self-reinforcing behaviors due to the absence of strain-induced crystallization, resulting in comparatively weak mechanical properties . Furthermore, like most diene rubbers, NBR is susceptible to thermal-oxidative degradation at elevated temperatures, which limits its service life in high-temperature applications.

The incorporation of inorganic fillers into NBR matrices has been extensively explored to improve mechanical, thermal, and electrical properties. Among various fillers, titanium dioxide (TiO_2) nanoparticles have attracted considerable attention due to their unique characteristics, including chemical stability, non-toxicity, high reactivity, biocompatibility, and low cost . TiO_2 has been widely employed as a white pigment in rubber industries, but recent research has demonstrated its potential as an effective reinforcing filler and thermal stabilizer that can significantly improve both the heat resistance and cold resistance of NBR composites.

This paper examines the fundamental principles by which nano-TiO_2 enhances the thermal performance of NBR rubber, focusing on the mechanisms of heat resistance improvement, the influence on glass transition temperature and low-temperature performance, and the critical role of filler dispersion and interfacial interactions.

---

2. Heat Resistance Enhancement Mechanisms

2.1 The Challenge of Thermal-Oxidative Degradation in NBR

NBR, due to its butadiene content, is susceptible to thermal-oxidative degradation at elevated temperatures. The degradation mechanism involves the formation of free radicals through C-H bond homolytic cleavage, particularly at the secondary allylic positions of the butadiene units . These free radicals react with molecular oxygen to form peroxy radicals, which subsequently abstract hydrogen atoms from the polymer chain, accumulating hydroperoxides. Thermal decomposition of these hydroperoxides initiates autoxidation, leading to chain scission, crosslinking, and ultimately, deterioration of mechanical properties .

The onset decomposition temperature (Td) of unfilled NBR has been reported at approximately 388.9°C, with significant weight loss occurring between 300°C and 500°C . For NBR, the temperature at which 5% weight loss occurs (T95) is a key indicator of thermal stability.

2.2 Physical Barrier Effect

One of the primary mechanisms by which nano-TiO_2 enhances heat resistance is through a physical barrier effect. When well-dispersed TiO_2 nanoparticles are incorporated into the NBR matrix, they act as obstacles that impede the diffusion of oxygen into the polymer bulk and the escape of volatile degradation products . This barrier effect slows the rate of thermal-oxidative degradation, increasing the onset temperature of decomposition.

Studies on TiO_2-filled polymer systems have demonstrated that the presence of nanoparticles increases the mean free path for oxygen entry and volatile exit, resulting in slower gas diffusion inside the polymer matrix . This behavior is particularly pronounced when good filler-polymer interactions exist, as the interfacial adhesion creates a more effective barrier.

For NBR/GE (graphene) composites, it was observed that adding filler reduced decomposition and contributed to thermal stability, with the onset decomposition temperature (Td) increasing from 388.9°C for pure NBR to 426.6–428.8°C for GE-filled composites . This principle applies similarly to TiO_2-filled systems.

2.3 Free Radical Scavenging and Stabilization

TiO_2 nanoparticles can act as free radical scavengers, intercepting the reactive species generated during thermal-oxidative degradation. The surface hydroxyl groups on TiO_2 can react with free radicals, terminating the propagation steps of the degradation chain reaction. This mechanism is particularly effective at low filler concentrations, where the nanoparticles are well-dispersed and present a high surface area for interaction with reactive species .

Research on ABS/TiO_2 composites has shown that TiO_2 particles can influence oxidative stability, with low concentrations of commercial TiO_2 exhibiting an increase in thermal stability . The modified TiO_2 with peroxy groups, however, showed a catalytic effect at higher concentrations, demonstrating the importance of surface chemistry in determining the ultimate effect on thermal stability .

2.4 Enhanced Crosslinking Density

The incorporation of TiO_2 into NBR significantly influences the vulcanization behavior, which in turn affects thermal stability. Studies have demonstrated that TiO_2 acts as a co-activator in sulfur curing systems, stimulating crosslinking reactions .

Key observations regarding cure characteristics include:

- **Scorch time (ts1)**: Decreased with TiO_2 addition, indicating faster initiation of crosslinking
- **Optimum cure time (tc90)**: Decreased, showing accelerated overall curing process
- **Cure rate index (CRI)**: Increased up to 30 phr, indicating enhanced cure kinetics
- **Minimum torque (ML)**: Increased, reflecting higher compound viscosity and restricted molecular mobility
- **Maximum torque (MH)**: Increased, indicating higher crosslink density and composite stiffness
- **Torque difference (MH-ML)**: Increased, reflecting higher crosslink density

The increased crosslink density is particularly significant for heat resistance. Higher crosslink density restricts segmental mobility of polymer chains, reducing the number of reactive sites available for oxidative attack and enhancing the overall thermal stability of the composite.

2.5 Interfacial Interactions

The polar nature of NBR, imparted by the acrylonitrile content, creates favorable conditions for interaction with the surface of TiO_2 nanoparticles. The surface of TiO_2 particles contains hydroxyl groups (-OH) that can form physical interactions with the polar -C≡N groups of NBR . This interaction contributes to:

- **Improved filler dispersion**: Well-dispersed TiO_2 particles with aggregate sizes predominantly less than 100 nm provide maximum surface area for thermal stabilization

- **Strong filler-rubber adhesion**: Strong interfacial interactions enable effective transfer of stress and heat from the rubber matrix to the TiO_2 particles

- **Reduced chain mobility**: The bound rubber layers formed around TiO_2 particles restrict segmental motion, enhancing thermal stability

2.6 Thermal Stability Performance Data

The thermal stability enhancement of TiO_2/NBR composites is supported by evidence from related rubber systems. In NBR/PVC hollow fibers loaded with TiO_2, results showed increased storage modulus, stiffness, and glass transition temperature, while breaking elongation decreased . The shift in glass transition temperature to higher values confirms the restricted chain mobility and enhanced thermal stability.

For natural rubber/TiO_2 composites, dynamic mechanical analysis (DMA) revealed that the glass transition temperature and activation energy of the composites were higher than those of pure natural rubber . The thermal decomposition activation energies for TiO_2-filled NR composites ranged from 201.7 to 231.1 kJ/mol, demonstrating the influence of TiO_2 on the energy barrier for thermal degradation .

---

3. Cold Resistance Enhancement Mechanisms

3.1 The Challenge of Low-Temperature Performance in NBR

The cold resistance of NBR is governed by its glass transition temperature (Tg), which is determined by the acrylonitrile content. Higher acrylonitrile content increases polarity and Tg but improves oil resistance; lower acrylonitrile content reduces Tg but compromises oil resistance. The butadiene segments in NBR, however, provide some inherent flexibility that contributes to low-temperature performance.

3.2 Influence of TiO_2 on Glass Transition Temperature

The incorporation of TiO_2 nanoparticles into NBR generally results in a shift in glass transition temperature (Tg) to a higher temperature . This shift is attributed to several factors:

Restricted Segmental Motion: The physical interactions between TiO_2 nanoparticles and NBR chains create bound rubber layers, effectively immobilizing polymer segments and increasing the temperature at which segmental motion becomes possible.

Increased Crosslink Density: The enhanced crosslink density resulting from TiO_2 incorporation restricts the mobility of polymer chains, contributing to the elevation of Tg.

Filler Volume Effect: The presence of rigid TiO_2 particles reduces the free volume available for chain motion, increasing the energy required for the glass transition.

In TiO_2/NBR composites, the shift in Tg to higher temperatures confirms the reinforcing effect and restricted chain mobility . The magnitude of the shift depends on filler content, dispersion quality, and the nature of filler-matrix interactions.

3.3 Balancing Heat and Cold Resistance

While the elevation of Tg indicates improved heat resistance, it also suggests potential trade-offs in cold resistance. However, studies on modified TiO_2 systems have shown that careful filler design can mitigate this effect. Research on Talc@TiO_2/XNBR composites demonstrated that using organic modifiers such as PAAS (polyacrylate sodium) can actually decrease the glass transition temperature while maintaining the beneficial effects of filler reinforcement .

Specifically, modified Talc@TiO_2 groups exhibited a reduction in Tg from 8.4°C to 0°C, indicating increased chain flexibility and improved low-temperature performance . This phenomenon was attributed to the modified filler reducing the adsorption of rubber molecules onto the filler network, allowing greater chain mobility at lower temperatures. Furthermore, secondary relaxation phenomena were observed in the range of -40°C to 10°C, which can contribute to improved toughness and impact resistance at low temperatures .

3.4 Mechanisms of Cold Resistance Preservation

Surface Modification: The use of surface modifiers can adjust filler-polymer interactions to preserve low-temperature performance. Modifiers such as KH550, NDZ201, and PAAS have been shown to improve filler dispersion and reduce the restrictive effect on polymer chain mobility, allowing for wider service temperature ranges .

Optimized Filler Loading: The amount of TiO_2 loading is critical for balancing heat and cold resistance. While higher loadings generally improve heat resistance through increased crosslink density and barrier effects, excessive loading can lead to excessive stiffening and Tg elevation, compromising cold resistance.

Filler Morphology: The size, shape, and surface characteristics of TiO_2 particles influence their effect on low-temperature performance. Nano-scale particles with high surface area can create more efficient reinforcement while potentially offering better control over Tg shifts.

---

4. Synergistic Effects on Thermal Performance

4.1 Combined Heat and Cold Resistance

The unique advantage of TiO_2/NBR composites is the potential for simultaneous improvement in both heat and cold resistance when optimized. The physical barrier effect, free radical scavenging, and enhanced crosslink density contribute to heat resistance, while careful surface modification and loading optimization allow for preservation or even improvement of cold resistance.

The broad temperature application range of NBR can be extended through TiO_2 reinforcement, making the composites suitable for applications requiring performance under diverse thermal conditions.

4.2 Influence of Filler Dispersion

The quality of TiO_2 dispersion in the NBR matrix is critical for achieving optimal thermal performance. Studies on nano-TiO_2 filled rubber composites have shown that B-TiO_2 (20-40 nm) exhibits good dispersion in NBR, with aggregate sizes predominantly less than 100 nm . Good dispersion ensures:

- Maximum surface area for thermal stabilization
- Uniform distribution of barrier effects
- Consistent crosslink density throughout the composite
- Optimal balance of heat and cold resistance

4.3 Role of Surface Chemistry

The surface chemistry of TiO_2 nanoparticles plays a crucial role in determining their effect on thermal performance. The presence of hydroxyl groups on the TiO_2 surface enables interactions with NBR chains and curing agents, influencing crosslink density and chain mobility . Surface modification can tailor these interactions to achieve specific thermal performance characteristics.

---

5. Practical Implications and Applications

The enhanced heat and cold resistance of TiO_2/NBR composites have significant practical implications:

Automotive Applications: Improved thermal stability extends the service life of NBR seals, hoses, and gaskets in high-temperature engine compartments.

Industrial Components: Enhanced heat resistance enables use in applications requiring exposure to elevated temperatures, such as oil field equipment and chemical processing components.

Cold Climate Applications: Preserved or improved cold resistance extends the service temperature range, making the composites suitable for applications in cold environments.

Dielectric Elastomer Actuators: The combination of enhanced dielectric properties and improved thermal performance makes TiO_2/NBR composites promising materials for soft robotics and sensor applications .

---

6. Conclusions

The enhancement of heat and cold resistance in NBR rubber by nano-TiO_2 is governed by several interrelated mechanisms:

1. **Physical Barrier Effect**: Well-dispersed TiO_2 nanoparticles impede oxygen diffusion and volatile escape, slowing thermal-oxidative degradation and increasing the onset temperature of decomposition.

2. **Free Radical Scavenging**: The surface hydroxyl groups on TiO_2 can intercept reactive free radicals generated during thermal degradation, terminating the propagation steps of the degradation chain reaction.

3. **Enhanced Crosslink Density**: TiO_2 acts as a co-activator in sulfur curing systems, accelerating crosslinking and increasing crosslink density, which restricts chain mobility and enhances thermal stability.

4. **Interfacial Interactions**: The polar interactions between TiO_2 surface hydroxyl groups and NBR nitrile groups create strong filler-matrix adhesion, contributing to improved thermal performance.

5. **Glass Transition Temperature Control**: The shift in Tg to higher temperatures confirms restricted chain mobility, while surface modification and optimized loading can preserve cold resistance.

The dual role of TiO_2 as both a reinforcing filler and a thermal stabilizer provides a synergistic enhancement of thermal performance, extending the service temperature range of NBR composites for demanding applications.

References

[1] Chueangchayaphan, W., Luangchuang, P., & Chueangchayaphan, N. (2022). High Performance of Titanium Dioxide Reinforced Acrylonitrile Butadiene Rubber Composites. *Polymers*, 14(23), 5267.

[2] Recycled ABS/TiO_2 Composites: Thermal Degradation Properties. Research Square.

[3] Li, F.-Z., et al. (2018). Investigation of Ageing Behaviour of Nitrile–Butadiene Rubber with Added GE. *Kem. Ind.*, 67(1-2), 29–37.

[4] Dispersion Morphology and Mechanical Properties of Nano-Titanium Dioxide Filled Rubber Composites. *China Synthetic Rubber Industry*, 2005(2), 98-104.

[5] Modified Talc@TiO_2 Filled XNBR Composites: Thermal and Dynamic Mechanical Properties. Southwest Jiaotong University Master's Thesis.

[6] TiO_2/NBR-PVC Hollow Fibers: Damping and Mechanical Properties. *Fibers and Polymers*, 2013, 14(4), 616-622.

[7] TiO_2/Natural Rubber Composites: Thermal Decomposition Kinetics. *Journal of Anhui Agricultural Sciences*, 2009, 33.