Write a thesis about the effect of the amount of nano TiO2 on the mechanical behavior of TiO2/PTFE

The Effect of Nano-TiO_2 Content on the Mechanical Behavior of TiO_2/PTFE Composites

Abstract

This thesis investigates the influence of nano-titanium dioxide (TiO_2) content on the mechanical properties of polytetrafluoroethylene (PTFE)-based composites. TiO_2 nanoparticles serve as effective reinforcing fillers that can significantly enhance the mechanical and tribological performance of PTFE through mechanisms including dispersion strengthening, transfer film reinforcement, and interfacial bonding. A critical analysis of experimental studies reveals that the relationship between TiO_2 content and mechanical behavior follows a non-monotonic pattern, with an optimal loading range typically between 1.5–5 wt% or volume fraction depending on the composite system and testing conditions. Below the optimal content, insufficient reinforcement occurs; above it, particle agglomeration leads to property degradation. The nano-scale nature of the TiO_2 filler is essential for achieving superior performance compared to micrometer-scale particles, as the increased surface area enables stronger matrix-filler interactions and more effective transfer film reinforcement during wear. This thesis provides a comprehensive review of the mechanical behavior across different loading levels, underlying mechanisms, and practical implications for composite design.

---

1. Introduction

1.1 Background

Polytetrafluoroethylene (PTFE) is a high-performance polymer renowned for its exceptional chemical resistance, thermal stability, and low coefficient of friction . These properties make PTFE an attractive material for applications ranging from self-lubricating bearings and seals to microwave substrates and protective coatings . However, pure PTFE suffers from inherent limitations that restrict its broader

engineering applications: low wear resistance, poor creep resistance, low hardness, and susceptibility to severe adhesive wear .

The incorporation of inorganic fillers into PTFE matrices has emerged as an effective strategy to overcome these limitations . Among various fillers, titanium dioxide (TiO_2) nanoparticles have attracted considerable attention due to their high hardness, chemical stability, strong adhesion to polymer matrices, and ability to improve both mechanical and tribological properties simultaneously .

1.2 Significance of Nano-TiO_2 Loading

The amount of nano-TiO_2 incorporated into the PTFE matrix is a critical design parameter that fundamentally influences the resulting composite's mechanical behavior. Unlike micrometer-scale fillers, nanoparticles exhibit a much higher surface area-to-volume ratio, which enhances bonding to the polymer matrix and enables more effective load transfer . However, excessive filler content leads to particle agglomeration, creating stress concentrations and defect sites that degrade mechanical performance . Understanding the relationship between filler loading and mechanical properties is therefore essential for optimizing composite formulation.

This thesis examines the effect of nano-TiO_2 content on the mechanical behavior of TiO_2/PTFE composites, including hardness, tensile strength, wear resistance, and friction coefficient. The analysis draws upon experimental studies investigating various TiO_2 loading levels and composite systems, ranging from PTFE/PI blends to epoxy-PTFE coatings and PTFE-based microwave substrates.

---

2. Mechanical Properties of PTFE and TiO_2/PTFE Composites

2.1 Baseline Mechanical Properties of Unfilled PTFE

Unfilled PTFE exhibits relatively low mechanical strength and hardness. Studies using quasi-static tensile experiments report that pure PTFE demonstrates significant viscoelastic behavior with no obvious yield

point and moderate tensile strength . The low hardness of PTFE (approximately 56.5% lower than reinforced composites) limits its load-bearing capacity in tribological applications . The hardness of PTFE can be increased by up to 56.5% through filler incorporation .

2.2 Reinforcing Mechanisms of Nano-TiO_2

Nano-TiO_2 particles enhance the mechanical properties of PTFE through several mechanisms:

Dispersion Strengthening: Well-dispersed TiO_2 nanoparticles within the PTFE matrix act as effective dispersion reinforcing elements. The hard ceramic particles impede crack propagation and increase the energy required for fracture, resulting in improved toughness and hardness .

Transfer Film Reinforcement: During sliding wear, PTFE forms a thin lubricating transfer film on the counterface. TiO_2 particles embedded within this transfer film serve as high-hardness fillers that reinforce the film, enhancing its load-bearing capacity and durability . This mechanism significantly extends the wear life of the composite .

Interfacial Bonding: The surface hydroxyl groups on TiO_2 nanoparticles enable chemical bonding with PTFE or coupling agents, improving interfacial adhesion and load transfer efficiency . Surface modification of TiO_2 with silane coupling agents (e.g., KH570) enhances dispersion and interfacial compatibility .

"Micro-bearing" Effect: Hard nanoparticles act as micro-bearings during friction, supporting the applied load and reducing direct contact between the polymer matrix and the counterface . This reduces wear and stabilizes the friction coefficient.

---

3. Effect of TiO_2 Content on Mechanical Properties

3.1 Hardness

The addition of nano-TiO_2 to PTFE significantly increases composite hardness. The hardness enhancement is attributed to the rigid nature of TiO_2 particles, which increases resistance to indentation and surface deformation . In PTFE/nano-EG ternary composites reinforced with different nanoparticles, composites containing nano-TiO_2 showed significant improvement in hardness compared to pure PTFE .

3.2 Tensile Strength and Elastic Modulus

Tensile strength and elastic modulus generally increase with nano-TiO_2 content up to an optimum loading level. PTFE-based composites reinforced with nanoparticles exhibit higher mechanical properties than pure PTFE . The improvements are attributed to:

- Effective load transfer from the matrix to the rigid TiO_2 particles

- Dispersion strengthening effects

- Reduced free volume and constrained polymer chain mobility

However, at excessive filler loadings, particle agglomeration compromises these improvements .

3.3 Wear Resistance

The effect of nano-TiO_2 content on wear resistance is particularly well-documented, with a clear optimum loading level. In PTFE/PI composites filled with nanometer TiO_2, the anti-wear properties improved significantly, with the **lowest wear rate observed at 1.5 vol% nano-TiO_2**, which was approximately 52% lower than that of the unfilled PTFE/PI composite . The wear rate increased beyond this optimum loading level, indicating the presence of an optimal filler concentration.

The superior wear resistance at optimal nano-TiO_2 loading is attributed to:

- More effective formation of transfer films

- Enhanced bonding between nanoparticles and the polymer matrix

- Increased surface area-to-volume ratio compared to micrometer particles

In contrast, **micrometer TiO_2 particles** showed a different trend: the friction coefficient and wear rates increased with increasing filler volume fraction, and the wear mechanism was dominated by severe adhesion and abrasive wear .

3.4 Friction Coefficient

The friction coefficient of TiO_2/PTFE composites also exhibits content-dependent behavior. In nanometer TiO_2 particle-filled PTFE/PI composites, the friction coefficient **first decreases with increasing filler content and then increases** as the filler volume fraction continues to rise . The optimal friction reduction occurs at approximately 1% nano-TiO_2 content.

In epoxy-PTFE composite coatings, the addition of modified TiO_2 nanoparticles (in combination with PTFE) reduced the dry friction coefficient by more than 73% . The synergistic effect of PTFE's friction reduction and TiO_2's dispersion enhancement was crucial for achieving this improvement.

---

4. Influence of Particle Size: Nano vs. Micro

A critical distinction exists between the effects of nanometer and micrometer TiO_2 particles on mechanical behavior. Studies comparing the two scales reveal fundamentally different behaviors:

Nano-TiO_2:

- Decreases wear rate and friction coefficient up to an optimal loading
- Forms more effective transfer films due to higher surface area
- Enhances interfacial bonding with polymer matrix
- Wear mechanism: slight abrasive wear

Micro-TiO_2:

- Increases friction coefficient and wear rate with increasing content

- Limited reinforcement due to lower surface-to-volume ratio

- Greater tendency for stress concentration

- Wear mechanism: severe adhesion and abrasive wear

The superior performance of nano-TiO_2 is attributed to its ability to blend well with the polymer matrix, strengthening the transfer film and improving interfacial bonding .

---

5. Optimal Nano-TiO_2 Content

5.1 Content Range by Composite System

Based on available experimental studies, the optimal nano-TiO_2 content varies depending on the composite system and application:

Composite System	Optimal Content	Property Optimized	Reference
PTFE/PI	1.5 vol%	Wear resistance	
PTFE/PI	~1.0 vol%	Friction coefficient	
PTFE/SiO_2 (microwave)	5 wt% TiO_2 (+50 wt% SiO_2)	Dielectric + tensile (7.32 MPa)	
Epoxy-PTFE coating	1-5 wt% (modified)	Hardness, toughness, corrosion	
PTFE/nano-EG	Not specified	Hardness (+56.5%)	

5.2 General Pattern

A consistent pattern emerges across studies: mechanical and tribological properties improve with increasing nano-TiO_2 content up to an optimal level, beyond which performance degrades. The degradation at high loading is attributed to:

- Particle agglomeration creating stress concentrations

- Reduced interfacial bonding due to incomplete wetting

- Increased composite brittleness

- Disruption of transfer film formation

---

6. Mechanisms of Property Enhancement

6.1 Surface Modification and Dispersion

Dispersion quality is critical to achieving optimal mechanical properties. Surface modification of nano-TiO_2 with silane coupling agents (e.g., KH550, KH570) improves dispersion and interfacial compatibility . The silane molecules graft onto the TiO_2 surface through Ti-O-Si bonds, reducing surface energy and preventing agglomeration .

The fracture surface morphology of epoxy-PTFE/TiO_2 composites with modified nanoparticles shows significantly greater roughness than composites with unmodified particles, indicating improved interfacial bonding and tougher fracture behavior .

6.2 Transfer Film Formation and Reinforcement

During sliding wear, PTFE forms a transfer film on the counterface. The presence of nano-TiO_2 particles within this film reinforces it, enhancing its load-bearing capacity and durability . Studies on PI/TiO_2/PTFE composite fibers demonstrated that TiO_2 particles act as anchors for PTFE, promoting uniform coating and better binding on the fiber surface . The composite achieved 1782 cycles to failure, approximately 300 times greater than the original fiber .

6.3 Synergistic Effects with Other Fillers

Nano-TiO_2 can work synergistically with other reinforcing components. In hybrid composites containing multiple fillers, mechanical properties are enhanced through combined mechanisms:

- Nano-EG (expanded graphite) increases hardness through its lamellar structure

- TiO_2 provides rigid particle reinforcement

- Synergistic effects produce property improvements exceeding those of individual fillers

---

7. Applications and Practical Implications

7.1 Microwave Substrates

TiO_2/PTFE composites are used in microwave circuit applications. A study on TiO_2 and SiO_2 filled PTFE composites showed that the tensile strength reaches 7.32 MPa at 5 wt% TiO_2 and 50 wt% SiO_2 loading, with acceptable CTE (17 ppm/°C) and moisture absorption (0.2%) .

7.2 Self-Lubricating Coatings

Epoxy-PTFE composite coatings modified with nano-TiO_2 demonstrate excellent tribological and anticorrosion properties. The modified TiO_2 improves section toughness, hardness, and binding force, with the dry friction coefficient decreasing by more than 73% .

7.3 Wear-Resistant Fibers

PI fibers coated with TiO_2/PTFE composite shells exhibit dramatically improved wear resistance, with cycles to failure increased approximately 300 times compared to original fibers . These fibers are suitable for aerospace cables, marine mooring lines, and climbing ropes.

7.4 High-Performance Sealings and Bearings

PTFE-based composites with optimized nano-TiO_2 content offer improved wear resistance and reduced friction for bearing and sealing applications in demanding environments.

---

8. Conclusion

This thesis has examined the effect of nano-TiO_2 content on the mechanical behavior of TiO_2/PTFE composites. The following conclusions can be drawn:

1. **Nano-TiO_2 incorporation significantly enhances mechanical properties** of PTFE composites, including hardness, tensile strength, wear resistance, and friction performance, through mechanisms of dispersion strengthening, transfer film reinforcement, and interfacial bonding.

2. **The relationship between TiO_2 content and mechanical behavior is non-monotonic.** An optimal filler loading range exists—typically between 1.5–5 wt% or volume fraction depending on the composite system—where properties are maximized. Below this level, insufficient reinforcement occurs; above it, particle agglomeration causes property degradation.

3. **Nano-scale TiO_2 particles are superior to micrometer-scale particles** for PTFE reinforcement. The higher surface area-to-volume ratio of nanoparticles enhances matrix bonding, transfer film formation, and load transfer efficiency. Micrometer TiO_2 actually increases wear rate with increasing content, while nano-TiO_2 decreases it up to the optimum.

4. **The optimal TiO_2 content depends on the composite system and target property.** For tribological applications, approximately 1.5 vol% nano-TiO_2 provides maximum wear resistance in PTFE/PI composites. For microwave substrates, 5 wt% TiO_2 in combination with SiO_2 yields a balanced property profile.

5. **Surface modification is critical** for achieving optimal reinforcement. Silane coupling agents improve TiO_2 dispersion and interfacial compatibility, significantly enhancing mechanical properties and corrosion resistance.

6. **Future research should focus on** understanding the interactions between nano-TiO_2 and different PTFE matrix types, developing advanced dispersion techniques, and exploring synergistic filler combinations to further enhance composite performance.

References

[1] Ryu, C., Ri, J.-G., Kim, Y.-S., Rim, C.-H., Kim, C.-I., & Yu, C.-J. (2024). Interfacial properties of a ZnO/PTFE composite from density functional tight-binding simulations. *RSC Advances*, 14, 35097-35103.

[2] Yuan, Y., Cui, Y. R., Wu, K. T., Huang, Q. Q., & Zhang, S. R. (2014). TiO2 and SiO2 filled PTFE composites for microwave substrate applications. *Journal of Polymer Research*, 21(2), 1-6.

[3] Jin, Y., Wang, L., Cai, T., Xu, H., Zhan, J., Qi, S., Tian, G., & Wu, D. (2026). Improving the friction and wear performance of polyimide fiber by constructing a TiO2/PTFE composite shell on the fiber surface. *Polymer*, 344, 129542.

[4] Surface modified nano-La2O3 and nano-TiO2 filled PTFE nanocomposites. In *Different Nano-Fillers on the Tribological Properties of PTFE Nanocomposites*. Springer.

[5] Mechanical and tribological behavior of nanometer and micrometer TiO2 particle-filled PTFE/PI composites. *Materials & Design*, 32(2), 964-970.

[6] Mechanical and Tribological Behavior of Nanometer and Micrometer TiO2 Particle-Filled PTFE/PI Composites. *Proceedings of the 7th Asian-Australasian Conference on Composite Materials*.

[7] Average hardness values of PTFE and PTFE-based composites. ResearchGate.

[8] Improvement of the Tribological Properties and Corrosion Resistance of Epoxy–PTFE Composite Coating by Nanoparticle Modification. *Coatings*, 11(1), 10.

[9] Assessing the Influence of Inorganic Nanoparticles on the Mechanical and Tribological Performance of PPS-Based Composites. *Polymers*, 17(19), 2573.

[10] Tribological and Thermal properties of Hybrid Kevlar/PTFE Fabric Composite Filled With Nano-TiO2. *Proceedings of the 2nd International Conference on Multi-functional Materials and Structures*.